

---

---

**Fine ceramics (advanced ceramics,  
advanced technical ceramics) — Test  
method for determining thermal  
expansion coefficient and residual  
stress of CVD ceramic coatings**

iTeh Standards  
(<https://standards.itih.ai>)  
Document Preview

ISO 23458:2020

<https://standards.itih.ai/catalog/standards/iso/3606b038-f591-4928-841d-a1a13ae5a81d/iso-23458-2020>



iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

ISO 23458:2020

<https://standards.iteh.ai/catalog/standards/iso/3606b038-f591-4928-841d-a1a13ae5a81d/iso-23458-2020>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>2</b>
<b>5 Apparatus</b> .....	<b>2</b>
5.1 General.....	2
5.2 Heating and cooling device.....	3
5.3 Temperature measurement.....	3
5.4 Test piece mounting.....	3
5.5 Data recording system.....	4
5.6 Dimensional measuring devices.....	4
<b>6 Specimens</b> .....	<b>4</b>
6.1 Test piece.....	4
6.2 Dimensions.....	5
6.3 Test piece preparation.....	6
6.3.1 General.....	6
6.3.2 Test piece handling and storage.....	6
6.3.3 Number of test pieces.....	6
<b>7 Test procedure</b> .....	<b>6</b>
7.1 Measurement of the test piece dimensions.....	6
7.2 Measurement of the elastic modulus.....	6
7.3 Measurement of the thermal expansion coefficient of CVD coatings.....	6
7.4 Calculation of the residual stress in CVD coatings.....	7
<b>8 Calculation</b> .....	<b>7</b>
8.1 Thermal expansion coefficient of the CVD ceramic coatings, $\alpha_c$ .....	7
8.2 Residual stress in CVD coatings, $\sigma_c$ .....	7
<b>9 Test report</b> .....	<b>8</b>
<b>Bibliography</b> .....	<b>9</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 206, *Fine ceramics*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

ISO 23458:2020

<https://standards.iteh.ai/catalog/standards/iso/3606b038-f591-4928-841d-a1a13ae5a81d/iso-23458-2020>

# Fine ceramics (advanced ceramics, advanced technical ceramics) — Test method for determining thermal expansion coefficient and residual stress of CVD ceramic coatings

## 1 Scope

This document specifies a test method for determining thermal expansion coefficient up to 2 300 K and the residual stress of chemical vapour deposition (CVD) ceramic coatings (thickness > 0,03 mm) at room temperature. Procedures for test piece preparation, test modes, heat rate, data collection, property calculations and reporting procedures are given.

This document applies to CVD ceramic coatings on metal or ceramic substrates. This test method can be used for material research, quality control, characterization and design data-generation purposes.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3611, *Geometrical product specifications (GPS) — Dimensional measuring equipment: Micrometers for external measurements — Design and metrological characteristics*

ISO 17139, *Fine ceramics (advanced ceramics, advanced technical ceramics) — Thermophysical properties of ceramic composites — Determination of thermal expansion*

ISO 19603, *Fine ceramics (advanced ceramics, advanced technical ceramics) — Test method for determining elastic modulus and bending strength of thick ceramic coatings*

IEC 60584-1, *Thermocouples — Part 1: EMF specifications and tolerances*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

### 3.1

#### relative method

indirect test method to obtain the measured parameter

Note 1 to entry: The expected parameter A is usually difficult to measure directly, but parameters B and C are known parameters or easy to obtain. If the analytical relationship of  $A = f(B, C)$  is established, the parameter A can be calculated.

### 3.2

#### linear thermal expansion

positive or negative change in one dimension that occurs when a material is subjected to a change in temperature

## 4 Principle

The deformation of a coated bar during heating or cooling involves two effect factors, i.e. thermal expansion coefficient and residual stress in the coating and the substrate. The thermal expansion coefficient is a material characteristic. However, the residual stresses in the coating are not only due to a material property but depend also on the size of the component and the cross-sectional area ratio of the coating and substrate.

The thermal expansion coefficient of CVD ceramic coatings is deduced by the relative method, i.e. it is related with the expansion coefficient of the substrate and the coefficient of the coated bar. Two types of test piece, a bar with CVD ceramic coating (composite) and a bar without coating (substrate), shall be used to measure the thermal expansion coefficient according to ISO 17139. After determining the elastic modulus of the substrate and coating, the thermal expansion coefficient of both the composite and the substrate are obtained. The thermal expansion coefficient of CVD ceramic coating shall then be calculated.

The sample length change and environment temperature are measured continuously at regular, frequent intervals during the imposed cycle. The residual stress of CVD ceramic coatings is usually generated due to the mismatch of thermal expansion coefficient between the coating and the substrate. Based on the uniform strain model, geometric compatibility analysis and internal stress equilibrium, the residual stress calculation formula of CVD ceramic coatings is deduced by the relative method, which is a function of many factors including elastic modulus, expansion coefficient, configurations and temperature. After getting the thermal expansion coefficient of the coating, the residual stress of CVD ceramic coatings shall be calculated from elastic modulus, expansion coefficient, cross-sectional area ratio of the coating to substrate and the temperature during coating preparation.

## 5 Apparatus

### 5.1 General

Recommended testing equipment is shown in [Figure 1](#). This can be used to measure the thermal expansion coefficient of two testing pieces in the same environment. If not, the two testing pieces shall be tested respectively in the same environment using the normal thermal expansion equipment in accordance with ISO 17139.

**NOTE** The two test pieces can be of the same materials or different materials. In this document, one is the composite with CVD coating and the other is the substrate.