

FINAL
DRAFT

INTERNATIONAL
STANDARD

ISO/FDIS
23475-1

ISO/TC 17/SC 17

Secretariat: SAC

Voting begins on:
2020-11-03

Voting terminates on:
2020-12-29

Testing method for steel tyre cord — Part 1: General requirements

*Méthode d'essai pour les câbles de pneumatiques en acier —
Partie 1: Exigences générales*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO/FDIS 23475-1](https://standards.iteh.ai/catalog/standards/sist/8d8e9bc5-14bd-4f30-b530-08ee8161ac93/iso-fdis-23475-1)

<https://standards.iteh.ai/catalog/standards/sist/8d8e9bc5-14bd-4f30-b530-08ee8161ac93/iso-fdis-23475-1>

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.



Reference number
ISO/FDIS 23475-1:2020(E)

© ISO 2020

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/FDIS 23475-1
<https://standards.iteh.ai/catalog/standards/sist/8d8e9bc5-14bd-4f30-b530-08ee8161ac93/iso-fdis-23475-1>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Dimension	1
4.1 Cord diameter	1
4.1.1 Measure with micrometer	1
4.1.2 Measure with profile projector	3
4.2 Unravell'd Filament diameter	4
4.2.1 Principle	4
4.2.2 Apparatus	4
4.2.3 Procedure	5
4.2.4 Expression of results	5
4.2.5 Test report	5
4.3 Linear density	5
4.3.1 Principle	5
4.3.2 Apparatus	5
4.3.3 Procedure	6
4.3.4 Test report	6
4.4 Lay direction and lay length	6
4.4.1 Lay direction/direction of lay	6
4.4.2 Trace method for lay length	6
4.4.3 Untwisting method for lay length	8
5 Process property	9
5.1 Straightness	9
5.1.1 Principle	9
5.1.2 Apparatus	9
5.1.3 Procedure	9
5.1.4 Test Report	9
5.2 Arc height	9
5.2.1 Principle	9
5.2.2 Apparatus	10
5.2.3 Procedure	10
5.2.4 Test report	10
5.3 Flare	10
5.3.1 Principle	10
5.3.2 Apparatus	10
5.3.3 Procedure	10
5.3.4 Test report	11
5.4 Residual torsion	11
5.4.1 Principle	11
5.4.2 Apparatus	11
5.4.3 Procedure	11
5.4.4 Test report	11
6 Mechanical property	12
6.1 Breaking load and elongation at fracture	12
6.1.1 Principle	12
6.1.2 Apparatus	12
6.1.3 Procedure	12
6.1.4 Test report	13
6.2 Elongation between defined forces (EDF)	13
6.2.1 Principle	13

	6.2.2	Apparatus.....	14
	6.2.3	Procedure.....	15
	6.2.4	Test report.....	15
6.3		Loop test (Elasticity).....	15
	6.3.1	Principle.....	15
	6.3.2	Apparatus.....	15
	6.3.3	Procedure.....	16
	6.3.4	Test report.....	17
7		Determination of mass and composition of coating.....	17
	7.1	X-Ray fluorescence spectroscopy.....	17
	7.1.1	Principle.....	17
	7.1.2	Apparatus.....	17
	7.1.3	Reagents.....	17
	7.1.4	Preparation of test samples.....	18
	7.1.5	Procedure.....	18
	7.1.6	Expression of results.....	18
	7.1.7	Test report.....	19

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO/FDIS 23475-1](https://standards.iteh.ai/catalog/standards/sist/8d8e9bc5-14bd-4f30-b530-08ee8161ac93/iso-fdis-23475-1)
<https://standards.iteh.ai/catalog/standards/sist/8d8e9bc5-14bd-4f30-b530-08ee8161ac93/iso-fdis-23475-1>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC17, *Steel*, Subcommittee SC 17, *Steel wire rod and wire products*.

<https://standards.iteh.ai/catalog/standards/sist/8d8e9bc5-14bd-4f30-b530-0f18161e02/iso-23475-1>

A list of all parts in the ISO 23475 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/FDIS 23475-1

<https://standards.iteh.ai/catalog/standards/sist/8d8e9bc5-14bd-4f30-b530-08ee8161ac93/iso-fdis-23475-1>

Testing method for steel tyre cord —

Part 1: General requirements

1 Scope

This document specifies test methods of steel cords which are used for tyre reinforcement. Dimension, process properties, mechanical properties and coating test method are all included.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 17832, *Non-parallel steel wire and cords for tyre reinforcement*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 17832 apply.

4 Dimension <https://standards.iteh.ai/catalog/standards/sist/8d8e9bc5-14bd-4f30-b530-08ee8161ac93/iso-fdis-23475-1>

4.1 Cord diameter

4.1.1 Measure with micrometer

4.1.1.1 Principle

Hold the sample between two parallel circular faced anvils of a micrometer. Close the movable anvil gradually and gently until it is in contact with the specimen. Read the value on the micrometer.

4.1.1.2 Apparatus

4.1.1.2.1 Micrometer

A precision disk micrometer with non-rotate spindle is suggested. This micrometer may have a hole (maximum 8 mm) in the center of the anvils. (see [Figure 1](#))

Measuring range is from 0 mm to 25 mm. Resolution is 0,001 mm

Anvil type: the diameter of the anvils shall be greater than one lay length (min. 20 mm in diameter).
Measuring force range: < 10 N. It is suggested from 3 N - 5 N.

The anvils shall be plane within 0,002 mm and parallel within 0,005 mm.




Figure 1 — Disk micrometer

4.1.1.2.2 Fusing machine

4.1.1.3 Procedure

- a) Clean the surface of the anvils with clean paper. Verify whether the micrometer reads 0,000 when the anvils are closed for each measurement.
- b) Fuse a specimen to a length about 150 mm and ensure that cord end is well secured with no unravelling. Place the sample in the centre of the anvils.
- c) Close the movable anvil gradually and gently until it is in contact with the specimen. For normal cords, stop rotating the spindle when 3 ‘click’ are heard and for HE, HI and OC constructions only 1 “click” is heard.
- d) Axially rotate the sample between repeated measurements in order to find the maximum diameter (D_1) and minimum diameter (D_2)




Figure 2 — Diameter test diagram

4.1.1.4 Expression of results

Calculate average diameter (D) with [Formula 1](#) below:

$$D = \frac{D_1 + D_2}{2} \tag{1}$$

where

D_1 is the maximum diameter, expressed in millimetres (mm)

D_2 is the minimum diameter, expressed in millimetres (mm)

D is the average diameter, expressed in millimetres (mm)

4.1.1.5 Test report

Report the average diameter to nearest 0,001 mm

4.1.2 Measure with profile projector

4.1.2.1 Principle

Specimens of a cord sample are successively put on the optical microscope. A silhouette of the cord is projected on the screen. The thickness of the specimen is measured by moving the abscissa axis of the projector.

4.1.2.2 Apparatus

4.1.2.2.1 Profile projector, with

- Magnification possibility : x 10 or x 20
- Micrometer stage table: resolution 0,001 mm

4.1.2.2.2 Sample holder, A frame on which two magnets are fixed in order to position the test specimen.

[ISO/FDIS 23475-1](https://standards.iteh.ai/catalog/standards/sist/8d8e9bc5-14bd-4f30-b530-08ee8161ac93/iso-fdis-23475-1)

4.1.2.2.3 Fusing machine

<https://standards.iteh.ai/catalog/standards/sist/8d8e9bc5-14bd-4f30-b530-08ee8161ac93/iso-fdis-23475-1>

4.1.2.3 Procedure

- a) Fuse a specimen to a length about 100 mm, ensure that fuse is securely tied in order to prevent the cord ends from any unravelling. Put the specimen on the sample holder and ensure that is fixed by magnets.
- b) Bring the sample into sample holder and adjust the focal distance. Make the sample being projected on the screen.
- c) Rotate the sample until the maximum profile is being projected on the screen. Move the micrometer table until the horizontal reference line contacts two consecutive waves (see [Figure 3](#)).




Figure 3 — X axis contacts the two consecutive waves

- d) Reset the micrometer. Move the stage until X axis contacts the opposite wave ([Figure 4](#)). Record the reading as maximum diameter (D_1). If there are two waves on the opposite side, measure the bigger one.




Figure 4 — X axis contacts the other side wave

- e) Turn the specimen through 90 degrees until a minimum diameter is obtained, record the minimum diameter D_2 . Repeat the step c and d and record the reading as minimum diameter (D_2). If there are two waves on the opposite side, measure the bigger one (Figure 5).




Figure 5 — the minimum diameter
 iTeh STANDARD PREVIEW
 (standards.iteh.ai)

4.1.2.4 Expression of results

Calculate average diameter (D) of the two readings with [Formula \(1\)](https://standards.iteh.ai/catalog/standards/sist/8d8e9bc5-14bd-4f30-b530-08ee8161ac93/iso-ids-23475-1).
ISO/FDIS 23475-1

4.1.2.5 Test Report

Report the average diameter to the nearest 0,001 mm.

NOTE This test method is generally used for open cords and HI cords or for other cord types that are sensitive to radial compression when using micrometer.

4.2 Unravalled Filament diameter

4.2.1 Principle

A sample is held between two parallel blade anvils of a micrometer. The movable anvil is closed gradually and gently until it is in contact with the specimen. Read the value on the micrometer.

4.2.2 Apparatus

4.2.2.1 Blade micrometre (see Figure 6)

- Measuring range is from 0 mm to 25 mm. Resolution is 0,001 mm.
- Anvil type: blade
- Measuring force: <10 N. It is suggested from 3 N - 5 N.




Figure 6 — Blade micrometre

4.2.2.2 Nipper pliers

4.2.3 Procedure

- Clean the surface of the anvils with clean paper. Verify whether the micrometre reads 0,000 when the anvils are closed for each measurement.
- Cut the wire approximately 100 mm in length. Position the specimen in the centre of the anvils.
- The movable anvil is closed gradually and gently until it is in contact with the specimen. Read the value after 3 'click' are heard.
- Measure on the same section of the specimen until maximum diameter (D_1) and minimum diameters (D_2) are found.

4.2.4 Expression of results

Calculate average diameter (d) of the two readings with [Formula 2](#) below.

$$D = \frac{(D_1 + D_2)}{2}$$

<https://standards.iteh.ai/catalog/standards/sist/8d8e9bc5-14bd-4f30-b530-08ee8161ac93/iso-fdis-23475-1>

(2)

where

D_1 is the maximum diameter, expressed in millimetres (mm)

D_2 is the minimum diameter, expressed in millimetres (mm)

D is average diameter, expressed in millimetres (mm).

4.2.5 Test report

Report the average diameter to the nearest 0,001 mm.

4.3 Linear density

4.3.1 Principle

A straight section of the cord of a predefined length, generally 1 m, is weighted using an analytical balance.

4.3.2 Apparatus

4.3.2.1 Analytical balance, which can be read to the nearest 0,001 g