



# Standard Test Method for Modulus of Rupture in Bending of Electrode Graphite<sup>1</sup>

This standard is issued under the fixed designation C1025; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

<sup>ε1</sup> NOTE—Updated units of measurement throughout editorially in May 2010.

## 1. Scope

1.1 This test method covers determination of the modulus of rupture in bending of specimens cut from graphite electrodes using a simple square cross section beam in four-point loading at room temperature.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

**C651** Test Method for Flexural Strength of Manufactured Carbon and Graphite Articles Using Four-Point Loading at Room Temperature

**C709** Terminology Relating to Manufactured Carbon and Graphite

**C783** Practice for Core Sampling of Graphite Electrodes

**E4** Practices for Force Verification of Testing Machines

**E691** Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

## 3. Terminology

3.1 *Definitions*—For definitions of terms relating to manufactured carbon and graphite, see Terminology **C709**.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee **D02** on Petroleum Products and Lubricants and is the direct responsibility of Subcommittee **D02.F0** on Manufactured Carbon and Graphite Products.

Current edition approved May 1, 2010. Published December 2010. Originally approved in 1984. Last previous edition approved in 2005 as C1025–91(2005). DOI: 10.1520/C1025-91R10E01.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

## 3.2 Definitions of Terms Specific to This Standard:

3.2.1 *modulus of rupture in bending*— the value of maximum stress in the extreme fiber of a specified beam loaded to failure in bending computed from the calculations in Section **9**.

## 4. Significance and Use

4.1 This test method provides a means for determining the modulus of rupture of a square cross section graphite specimen machined from the electrode core sample obtained according to Practice **C783**, with a minimum core diameter of 57 mm. This test method is recommended for quality control or quality assurance purposes, but should not be relied upon to compare materials of radically different particle sizes or orientational characteristics. For these reasons as well as those discussed in **4.2** an absolute value of flexural strength may not be obtained.

4.2 *Specimen Size*—The maximum particle size and maximum pore size vary greatly for manufactured graphite electrodes, generally increasing with electrode diameter. The test is on a rather short stubby beam, therefore the shear stress is not insignificant compared to the flexural stress, and the test results may not agree when a different ratio or specimen size is used.

## 5. Apparatus

5.1 The testing machine shall conform to the requirements of Sections 14 and 17 of Practices **E4**.

5.2 The four-point loading fixture shall consist of bearing blocks which ensure that forces applied to the beam are normal only and without eccentricity. (See Test Method **C651**.) The directions of loads and reactions may be maintained parallel by judicious use of linkages, rocker bearings, and flexure plates. Eccentricity of loading can be avoided by the use of spherical bearings. Provision must be made in fixture design for relief of torsional loading to less than 5 % of the nominal specimen strength. Refer to **Fig. 1** for a suggested four-point fixture.

5.3 The bearing block diameter shall be between  $\frac{1}{10}$  and  $\frac{1}{20}$  of the specimen support span, 12 mm to 6 mm. A hardened steel bearing block or its equivalent is necessary to prevent distortion of the loading member.