



Standard Test Method for Oxidation Characteristics of Inhibited Mineral Oils¹

This standard is issued under the fixed designation D943; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

^{e1} NOTE—Updated Scope with regard to SI units and added mercury caveat editorially in October 2010.

1. Scope

1.1 This test method covers the evaluation of the oxidation stability of inhibited steam-turbine oils in the presence of oxygen, water, and copper and iron metals at an elevated temperature. This test method is limited to a maximum testing time of 10 000 h. This test method is also used for testing other oils, such as hydraulic oils and circulating oils having a specific gravity less than that of water and containing rust and oxidation inhibitors.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.2.1 *Exception*—The values in parentheses in the figures are provided for information for those using old equipment based on non-SI units.

1.3 **WARNING**—Mercury has been designated by many regulatory agencies as a hazardous material that can cause central nervous system, kidney and liver damage. Mercury, or its vapor, may be hazardous to health and corrosive to materials. Caution should be taken when handling mercury and mercury containing products. See the applicable product Material Safety Data Sheet (MSDS) for details and EPA's website—<http://www.epa.gov/mercury/faq.htm>—for additional information. Users should be aware that selling mercury and/or mercury containing products into your state or country may be prohibited by law.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For specific warning statements, see Section 6.

¹ This test method is under the jurisdiction of ASTM Committee D02 on Petroleum Products, Liquid Fuels, and Lubricants and is the direct responsibility of Subcommittee D02.09.0C on Oxidation of Turbine Oils.

Current edition approved Oct. 1, 2010. Published December 2010. Originally approved in 1947. Last previous edition approved in 2004 as D943-04a.

In 1976, this test method ceased to be a joint ASTM-IP standard. DOI: 10.1520/D0943-10.

2. Referenced Documents

2.1 *ASTM Standards*:²

A510 Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel

B1 Specification for Hard-Drawn Copper Wire

D664 Test Method for Acid Number of Petroleum Products by Potentiometric Titration

D1193 Specification for Reagent Water

D3244 Practice for Utilization of Test Data to Determine Conformance with Specifications

D3339 Test Method for Acid Number of Petroleum Products by Semi-Micro Color Indicator Titration

D4057 Practice for Manual Sampling of Petroleum and Petroleum Products

D4310 Test Method for Determination of Sludging and Corrosion Tendencies of Inhibited Mineral Oils

D5770 Test Method for Semiquantitative Micro Determination of Acid Number of Lubricating Oils During Oxidation Testing

E1 Specification for ASTM Liquid-in-Glass Thermometers

2.2 *Energy Institute Standards*:³

Specifications for IP Standard Thermometers

2.3 *British Standard*:⁴

BS 1829

3. Summary of Test Method

3.1 The oil sample is contacted with oxygen in the presence of water and an iron-copper catalyst at 95°C. The test continues until the measured acid number of the oil is 2.0 mg KOH/g or above. The number of test hours required for the oil to reach 2.0 mg KOH/g is the “oxidation lifetime.”

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Energy Institute, 61 New Cavendish St., London, W1G 7AR, United Kingdom.

⁴ Available from British Standards Institute, 389 Chiswick High Rd., London, W4 4AL, United Kingdom.

The test tube has a calibration line at 300 mL (maximum error 1 mL). This calibration applies to the test tube alone at 20°C.

5.2 *Heating Bath*, thermostatically controlled, capable of maintaining the oil sample in the oxidation cell at a temperature of $95 \pm 0.2^\circ\text{C}$, fitted with a suitable stirring device to provide a uniform temperature throughout the bath, and large enough to hold the desired number of oxidation cells immersed in the heating bath to a depth of 390 ± 10 mm and in the heating liquid itself to a depth of 355 ± 10 mm.

NOTE 2—Metal block heaters meeting the test method requirements may also be used. It is not known what types of heating baths were used in developing the precision statement.

5.2.1 Studies have suggested that direct sunlight or artificial light may adversely influence the results of this test.⁵ To minimize effects of light exposure on the lubricant being tested, light shall be excluded from the lubricant by one or more of the following ways:

5.2.1.1 Use of heated liquid baths that are designed and constructed of metal, or combinations of metals and other suitable opaque materials, that prevent light from entering the test cell from the sides is preferred. If a *viewing window* is included in the design, this *viewing window* shall be fitted with a suitable opaque cover and be kept closed when no observation is being made.

5.2.1.2 If glass heating baths are used, the bath shall be wrapped with aluminum foil or other opaque material.

5.2.1.3 Bright light entering the test cell from directly overhead can be eliminated by use of an opaque shield.

5.3 *Flowmeter*, with a capacity of at least 3 L of oxygen/h, and an accuracy of ± 0.1 L/h.

5.4 *Heating Bath Thermometer*—ASTM Solvents Distillation Thermometer having a range from 72 to 126°C, and conforming to the requirements for Thermometer 40C as prescribed in Specification E1, or for Thermometer 70C as prescribed in Specifications for IP Standard Thermometers. Alternatively, temperature-measuring devices of equal or better accuracy may be used.

5.5 *Oxidation Cell Thermometer*,³ having a range from 80 to 100°C, graduated in 0.1°C, total length—250 mm, stem diameter—6.0 to 7.0 mm, calibrated for 76-mm immersion.^{6,7} Alternatively, temperature-measuring devices of equal or better accuracy may be used.

5.6 *Thermometer Bracket*, for holding the oxidation cell thermometer, of 18-8 stainless steel, having the dimensions shown in Fig. 2. The thermometer is held in the bracket by two fluoroelastomer O-rings of approximately 5 mm inside diameter. Alternatively, thin stainless steel wire may be used.

5.7 *Wire Coiling Mandrel*, as shown in Fig. 3.

5.8 *Abrasive Cloth*, silicon carbide, 100-grit with cloth backing.

5.9 *Syringes*, glass, with Luer-Lok locking connectors, 10 and 50-mL capacities for sampling, and water additions, respectively.

5.10 *Syringe Sampling Tube*, Grade 304 stainless steel tubing, 2.11 mm in outside diameter, 1.60 mm in inside diameter, 559 ± 2 mm long, with one end finished at 90° and the other end fitted with a Luer-Lok female connector. The Luer-Lok connector is preferably of elastomeric material, such as polyfluorovinylchloride to provide a good seal with the syringe.^{7,8}

5.11 *Stopper*, for Luer fitting of syringe sampling tube, made of polytetrafluoroethylene or polyfluorovinylchloride.⁹

5.12 *Sampling Tube Holder*, for supporting the syringe sampling tube, made of methyl methacrylate resin, having the dimensions shown in Fig. 4.

5.13 *Sampling Tube Spacer*, for positioning the end of the sampling tube above the sampling tube holder, made of a length of plastic tubing polyvinyl chloride, polyethylene, polypropylene, or polytetrafluoroethylene having an inside diameter of approximately 3 mm and 51 ± 1 mm length.

5.14 *Flexible Tubing*, polyvinyl chloride approximately 6.4 mm in inside diameter with a wall for delivery of oxygen to the oxidation cell.

6. Reagents and Materials

6.1 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water as defined by Type II of Specification D1193.

6.2 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society where such specifications are available.¹⁰ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

6.3 *Acetone*, reagent grade. (**Warning**—Health hazard; flammable.)

6.4 *Catalyst Wires*:

6.4.1 *Low-Metalloid Steel Wire*,¹¹ 1.59 mm in diameter (No. 16 Washburn and Moen Gage).

⁸ The sole source of supply of syringe needles with polychloro-trifluoroethylene hub known to the committee at this time is Hamilton Co., catalog number KF-714.

⁹ Suitable stoppers are available from suppliers of infrared spectrometer sample cells.


¹⁰ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For Suggestions on the testing of reagents not listed by the American Chemical Society, see *Annual Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

¹¹ Carbon steel wire, soft bright annealed and free from rust, of Grade 1008 as described in Specification A510 is satisfactory. Similar wire conforming to BS 1829 is also satisfactory. If these steels are not available, other equivalent steels may be used, provided they are found to be satisfactory in comparative tests using Test Method D943.

⁵ Supporting data (a summary of these results) have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:D02-1365.

⁶ The sole source of supply of the Brooklyn thermometer No. 21276-RM known to the committee at this time is the Brooklyn Thermometer Co., Farmingdale, NY.

⁷ If you are aware of alternative suppliers, please provide this information to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee,¹ which you may attend.



NOTE 1—All dimensions are in millimetres (inches).

NOTE 2—Material: 18-8 Stainless Steel, 22 Gage (0.792 mm).

FIG. 2 Thermometer Bracket

6.4.2 *Electrolytic Copper Wire*, 1.63 mm in diameter (No. 16 Imperial Standard Wire Gage or No. 14 American Wire Gage), 99.9 % purity, conforming to Specification B1. Soft copper wire of an equivalent grade may also be used.

NOTE 3—Alternatively, suitably prepared catalyst coils may be purchased from a supplier.

6.5 *Detergent*, water-soluble.

6.6 *n-Heptane*, reagent grade. (Warning—Flammable. Harmful if inhaled.)

6.7 *Hydrochloric Acid*, concentrated [36 mass % (relative density 1.19)]. (Warning—Toxic and corrosive.)

6.8 *Isopropyl Alcohol*, reagent grade. (Warning—Flammable.)

6.9 *Oxygen*, 99.5 % minimum purity, with pressure regulation adequate to maintain a constant flow of gas through the

apparatus. The use of a two-stage pressure regulator on tank oxygen is recommended. (Warning—Vigorously accelerates combustion.)

6.10 *Cleaning Reagent*, cleaning by a 24-h soak at room temperature either in Nochromix^{7,12} (Warning—Corrosive. Health Hazard.) or in Micro^{7,13} solution.


7. Sampling

7.1 Samples for this test can come from tanks, drums, small containers, or even operating equipment. Therefore, use the applicable apparatus and techniques described in Practice D4057.

¹² The sole source of supply of Nochromix known to the committee at this time is Godax Laboratories, Inc., 720-B Erie Ave., Takoma Park, MD 20912.

¹³ The sole source of supply of the Micro solution known to the committee at this time is International Products Corp., P.O. Box 70, Burlington, NJ 08016.

ASTM D943 - 04a (2010) ε1



NOTE 1—Dimensions are in millimetres (inches).

FIG. 3 Mandrel for Winding Catalyst Coils




Table of Dimensions

Dimension	mm		in.	
	Dimension	Tolerance	Dimension	Tolerance
A	2.4	0.1	0.09375	0.005
B	7.5	0.1	0.296875	0.005
C	12.7	0.25	0.50	0.01
D	38.1	0.50	1.50	0.02
E	6.4	0.50	0.25	0.02
F	25.4	0.25	1.00	0.01
G	38.1	0.50	1.50	0.02
H	9.5	0.50	0.375	0.02
I	76.2	0.50	3.00	0.02

FIG. 4 Sampling Tube Holder

7.2 For one single determination the minimum required sample size is 300 mL.

8. Preparation of Apparatus

8.1 *Cleaning Catalyst*—Immediately prior to winding a catalyst coil, clean a 3.00 ± 0.01 -m length of iron wire and an equal length of copper wire with wads of absorbent cotton wet with *n*-Heptane and follow by abrasion with abrasive cloth until a fresh metal surface is exposed. Then wipe with dry absorbent cotton until all loose particles of metal and abrasive have been removed. In subsequent operations handle the catalyst wires with clean gloves (cotton, rubber, or plastic) to prevent contact with the skin.

8.2 *Preparation of Catalyst Coil*—Twist the iron and copper wires tightly together at one end for three turns and then wind them simultaneously alongside each other on a threaded mandrel (Fig. 3), inserting the iron wire in the deeper thread.

Remove the coil from the mandrel, twist the free ends of the iron and copper wires together for three turns, and bend the twisted ends to conform to the shape of the spiral coil. The overall length of the finished coil should be 225 ± 5 mm. If necessary, the coil may be stretched to give the required length (Note 3 and Note 4.)

NOTE 4—The finished catalyst coil is a double spiral of copper and iron wire, 225 ± 5 mm overall length and 15.9 to 16.5 mm inside diameter. The turns of wire are evenly spaced, and two consecutive turns of the same wire are 3.96 to 4.22 mm apart, center to center. The mandrel shown in Fig. 3 is designed to produce such a coil. Using this mandrel, the iron wire is wound on a thread of 14.98-mm diameter, while the copper wire is wound on a thread of 15.9-mm diameter. The smaller diameter is to allow for *springback* of the steel wire after winding, so as to give 15.9-mm consistent inside diameter. Use of a very soft annealed steel wire may allow use of identical thread diameters for the two wires. Any arrangement that leads to the coil configuration described above is satisfactory.

8.3 *Catalyst Storage*—The catalyst coil may be stored in a dry, inert atmosphere prior to use. A suitable procedure for catalyst storage is given in Appendix X1. Before use it should be inspected to ensure that no corrosion products or contaminating materials are present. For overnight storage (less than 24 h) the coil may be stored in *n*-Heptane.

8.3.1 *n*-Heptane used for catalyst storage must be free of traces of water and corrosive materials. Redistilled *n*-Heptane conforming to 6.6 and stored in a tightly sealed bottle is suitable.

8.4 *Cleaning New Glassware*—Wash new oxygen delivery tubes, condensers, and test tubes with a hot detergent solution and rinse thoroughly with tap water. Clean the interiors of the test tubes, exteriors of the condensers, and both interiors and exteriors of the oxygen delivery tubes with cleaning reagent. Rinse thoroughly with tap water until all cleaning solution is removed. Rinse all parts with reagent water and allow to dry at room temperature or in an oven. The final reagent water rinse may be followed by an isopropyl alcohol rinse, or acetone rinse, optionally followed by dry air blowing, to hasten drying at room temperature.

8.5 *Cleaning Used Glassware*—Immediately following termination of a test, drain the oil completely from the test tube. Rinse all the glassware with *n*-Heptane to remove traces of oil, wash with a hot detergent solution using a long-handled brush, and rinse thoroughly with tap water. If deposits still adhere to the glassware, a method that has been found useful is to fill the test tubes with detergent solution, insert the oxygen delivery tubes and condensers, and place the tubes in the bath at test temperature. Several hours soaking in this manner often serves to loosen all adhering deposits except iron oxide. Subsequent rinsing with hot (50°C) hydrochloric acid will serve to remove iron oxide. After all deposits are removed, rinse all glassware with a cleaning reagent. Rinse thoroughly with tap water until all acid is removed. Rinse all parts with reagent water and allow to dry at room temperature or in an oven. The final reagent water rinse may be followed by an isopropyl alcohol rinse, or acetone rinse, optionally followed by dry air blowing, to hasten drying at room temperature. Store glassware in a dry dust-free condition until ready to use.

8.6 *Cleaning Used Sampling Tube*—Immediately following termination of a test, drain the oil completely from the