



SLOVENSKI STANDARD
SIST EN 384:2016+A2:2022

01-september-2022

Konstruktivski les - Ugotavljanje karakterističnih vrednosti mehanskih lastnosti in gostote (vključno z dopnilom A2)

Structural timber - Determination of characteristic values of mechanical properties and density

Bauholz für tragende Zwecke - Bestimmung charakteristischer Werte für mechanische Eigenschaften und Rohdichte

Bois de structure - Détermination des valeurs caractéristiques des propriétés mécaniques et de la masse volumique

Ta slovenski standard je istoveten z: EN 384:2016+A2:2022

ICS:

79.040	Les, hlodovina in žagan les	Wood, sawlogs and sawn timber
91.080.20	Lesene konstrukcije	Timber structures

SIST EN 384:2016+A2:2022 **en,fr,de**

EUROPEAN STANDARD

EN 384:2016+A2

NORME EUROPÉENNE

EUROPÄISCHE NORM

June 2022

ICS 79.040

Supersedes EN 384:2016+A1:2018

English Version

Structural timber - Determination of characteristic values of mechanical properties and density

Bois de structure - Détermination des valeurs
caractéristiques des propriétés mécaniques et de la
masse volumique

Bauholz für tragende Zwecke - Bestimmung
charakteristischer Werte für mechanische
Eigenschaften und Rohdichte

This European Standard was approved by CEN on 8 October 2018 and includes Amendment 2 approved by CEN on 13 March 2022.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Symbols and abbreviations	7
5 Mechanical properties determined from full-size specimens	8
5.1 Sampling.....	8
5.2 Testing.....	8
5.3 Reference conditions	9
5.3.1 Moisture content	9
5.3.2 Bending strength.....	9
5.3.3 Tension strength	9
5.3.4 Density	9
5.4 Adjustment factors	9
5.4.1 General.....	9
5.4.2 Moisture content	9
5.4.3 Timber size and test length	10
5.4.4 Modulus of elasticity	11
5.4.5 Other adjustments	12
5.5 Analysis of data	12
5.5.1 Sub-sample analysis.....	12
5.5.2 Characteristic values.....	12
6 Bending strength and modulus of elasticity determined from small, clear hardwood specimens	14
7 Other mechanical properties for hardwoods and softwoods	14
8 Report	16
Annex A (normative) Requirements for reports for visual grading assignment	17
Bibliography	20

European foreword

This document (EN 384:2016+A2:2022) has been prepared by Technical Committee CEN/TC 124 “Timber structures”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2022, and conflicting national standards shall be withdrawn at the latest by December 2022.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document includes Amendment 1 approved by CEN on 8 October 2018 and Amendment 2 approved by CEN on 13 March 2022.

This document supersedes A1 EN 384:2016+A1:2018 A1.

The start and finish of text introduced or altered by amendment is indicated in the text by tags A1 A1 and A2 A2.

A1 Deleted text A1

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Introduction

Structural design codes can only function effectively if standard methods of determining the mechanical and physical properties exist. The aim of the procedures given in this standard is to derive characteristic values that are comparable in terms of the populations they represent. The standard permits the use of as much existing test data as possible from various sampling and testing techniques.

Where methods are given to permit characteristic values to be determined from a less than ideal amount of structural size test data, reduction factors to reflect a lower degree of confidence are employed.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 384:2016+A2:2022

<https://standards.iteh.ai/catalog/standards/sist/89ec6d74-23ee-47fa-a14b-c1067e2335bc/sist-en-384-2016a2-2022>

1 Scope

This European Standard gives a method for determining characteristic values of mechanical properties and density, for defined populations of visual grades and/or strength classes of machine graded structural timber. Additionally, it covers the stages of sampling, testing, analysis and presentation of the data.

The standard provides methods to derive strength, stiffness and density properties for structural timber from tests with defect-free specimen.

The values determined in accordance with this standard for mechanical properties and density are suitable for assigning grades and species to the strength classes of EN 338.

NOTE 1 For assigning grades and species to the strength classes in EN 338 only three properties, i.e. bending or tension strength, modulus of elasticity parallel to grain in bending or tension and density need to be determined from test data, other properties can be calculated according to Table 2.

NOTE 2 EN 1912 gives examples of established visual grades assigned to strength classes.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 338, *Structural timber — Strength classes*

EN 408, *Timber structures — Structural timber and glued laminated timber — Determination of some physical and mechanical properties*

EN 13183-2, *Moisture content of a piece of sawn timber — Part 2: Estimation by electrical resistance method*

EN 13183-3, *Moisture content of a piece of sawn timber — Part 3: Estimation by capacitance method*

EN 14081-1:2016, *Timber structures — Strength graded structural timber with rectangular cross section — Part 1: General requirements*

EN 14081-2, *Timber structures — Strength graded structural timber with rectangular cross section — Part 2: Machine grading; additional requirements for initial type testing*

EN 14081-3, *Timber structures — Strength graded structural timber with rectangular cross section — Part 3: Machine grading; additional requirements for factory production control*

EN 14358:2016, *Timber structures — Calculation and verification of characteristic values*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

EN 384:2016+A2:2022 (E)

- 3.1 characteristic value**
representative value of a material property used for design, which is based either on 5-percentile values (e.g. strength properties and density) or mean values (e.g. modulus of elasticity)
- 3.2 *p*-percentile**
value for which the probability of getting lower values is p %
- 3.3 population**
timber for which the characteristic values are relevant
- 3.4 timber source**
identifiable geographical origin of a species or species combination from which timber is, or is intended to be, strength graded
- 3.5 sample**
a number of ungraded specimens of one timber species or species combination, one source, with sizes and quality representative of the timber population (see 5.1)
- 3.6 sub-sample**
part of one or more samples consisting of specimens of one grade
- 3.7 small clear test**
test to determine mechanical properties of small defect-free specimens
- 3.8 specimen**
piece of timber from which the test piece is taken
- 3.9 thickness**
lesser dimension perpendicular to the longitudinal axis of a piece of timber
- 3.10 width**
larger dimension perpendicular to the longitudinal axis of a piece of timber
- 3.11 depth**
in the case of bending, cross-sectional dimension parallel to the direction of loading; in the case of tension, the width

4 Symbols and abbreviations

a_f	distance between the inner load points of the bending test (in mm)
E_0	modulus of elasticity parallel to grain (in N/mm ²)
$E_{0,\text{mean}}$	mean characteristic value of modulus of elasticity parallel to grain (in N/mm ²)
$E_{0,k}$	5-percentile characteristic value of modulus of elasticity parallel to grain (in N/mm ²)
$E_{90,\text{mean}}$	mean characteristic value of modulus of elasticity perpendicular to grain (in N/mm ²)
\bar{E}_i	mean modulus of elasticity for one sub-sample (in N/mm ²)
$\bar{E}_{i,\text{min}}$	lowest mean modulus of elasticity of all sub-samples (in N/mm ²)
$E_{m,\text{global}}$	global modulus of elasticity in bending (in N/mm ²)
$E_{m,\text{local}}$	local modulus of elasticity in bending (in N/mm ²)
f	strength property
$f_{c,0,k}$	5- percentile characteristic value of compression strength parallel to grain (in N/mm ²)
$f_{c,90,k}$	5- percentile characteristic value of compression strength perpendicular to grain (in N/mm ²)
f_k	5- percentile characteristic value of strength (in N/mm ²)
$f_{m,k}$	5- percentile characteristic value of bending strength (in N/mm ²)
$f_{t,0,k}$	5- percentile characteristic value of tension strength parallel to grain (in N/mm ²)
$f_{t,90,k}$	5- percentile characteristic value of tension strength perpendicular to grain (in N/mm ²)
$f_{05,i}$	5-percentile value for each sub-sample (in N/mm ²)
$f_{05,i,\text{min}}$	lowest 5-percentile value of all sub-samples (in N/mm ²)
$f_{v,k}$	5- percentile characteristic value of shear strength (in N/mm ²)
G_{mean}	mean characteristic value of shear modulus (in N/mm ²)
h	depth (in mm)
k_h	factor for adjusting f when h is not 150 mm
k_l	factor for adjusting f when test span is not 18 h
k_n	factor to adjust for the number of sub-samples
k_v	factor to allow for the lower variability of f_{05} values between sub-samples for machine grades in comparison with visual grades
ℓ	span (in mm)
ℓ_{et}	effective length for the test (in mm)
n	total number of specimens

EN 384:2016+A2:2022 (E)

n_i	number of specimens in a sub-sample
n_s	number of sub-samples
u	moisture content (in %)
u_{ref}	reference moisture content, normally at 12 %
ρ	density (in kg/m ³)
ρ_{mean}	mean density (in kg/m ³)
ρ_k	characteristic density (5-percentile) (in kg/m ³)
$\rho_{05,i}$	5-percentile density for a sub-sample (in kg/m ³)
$\rho_{05,i,\text{min}}$	lowest 5-percentile density of all sub-samples (in kg/m ³)

5 Mechanical properties determined from full-size specimens**5.1 Sampling**

The sampling shall be representative of the population, A2 including commercial practices A2 .

Any known or suspected difference in the mechanical properties of the population due to e.g. sawmills, tree size, countries or silviculture shall be represented within the sampling by a similar proportion to their frequency in the population. This shall be the major influence in determining the number and size of samples.

Samples shall be selected from one source of timber and shall be graded visually or by machine to sub-samples according to the requirements given in EN 14081-1.

For visual grading, each sub-sample shall consist of at least 40 specimens and be of one source.

For bending and tension parallel to grain tests, specimens shall have a sufficient length so that critical defects can be located in the critical test zone (see 5.2). A2 However, care should be taken to avoid biasing the sample through selection of unusually long lengths compared to industrial practice.

NOTE 1 For bending specimens, a length of at least 30 times the depth or 3,6 m, whichever is the lesser, meets this requirement. Shorter lengths are accepted if they are justified in the report (see Clause 8) and meet the requirements of EN 408.

NOTE 2 For tension specimens, a length of at least 2 m plus the length required for the grips meets this requirement. Shorter lengths are accepted if they are justified in the report (see Clause 8) and meet the requirements of EN 408. A2

For the determination of strengths perpendicular to the grain and shear strength clear specimens shall be sampled.

5.2 Testing

Testing shall be carried out in accordance with EN 408 for strength, modulus of elasticity, density and moisture content. For bending parallel to grain, tension parallel to grain or modulus of elasticity, a critical section shall be selected in each piece of timber. This section is the position at which failure is expected to occur and therefore determines the grade for that piece. For bending the tension edge shall be selected at random. Whenever possible the critical section shall be placed inside the inner load points in a bending test or between the jaws in a tension test (centrally if possible). If this is not possible, the second most critical section shall be tested and determines the grade for that piece.

Existing historical data (before 1995) from different test methods or moisture conditions are acceptable provided sufficient information exists to adjust the results to the reference conditions given in 5.3.

5.3 Reference conditions

5.3.1 Moisture content

The reference moisture content shall be consistent with a temperature of 20 °C and 65 % relative humidity.

NOTE For most timber species this corresponds to a moisture content of about 12 %.

For specimens not tested to failure, the moisture content of each specimen is permitted to be determined from EN 13183-2 or EN 13183-3.

5.3.2 Bending strength

The reference condition corresponds to bending to a depth of 150 mm and to the standard test set-up proportions of third point loading with an overall span of 18 times the specimen depth.

5.3.3 Tension strength

The reference condition corresponds to a depth of 150 mm.

5.3.4 Density

Density is determined on small defect-free prisms according EN 408.

For specimens not tested to failure, the density of each specimen is permitted to be determined from the mass and volume of the test piece and adjusted to the density of the small defect-free prisms, by dividing by 1,05 in case of softwood. For hardwood no adjustment is necessary.

Adjustment for moisture content may also be necessary.

5.4 Adjustment factors

5.4.1 General

Test results shall be adjusted, piece by piece, to the standard reference conditions as given in 5.3.

If historical data (before 1995) is being used and records for individual specimen are incomplete, sub-sample 5-percentile or mean value shall be adjusted.

5.4.2 Moisture content

5.4.2.1 General

Test values for density, stiffness and strength shall be adjusted to reference conditions using the best available information that is based on previous test data. These adjustments shall be justified in the report.

Testing at reference conditions is advised, but for some species or end uses this could not be achieved. The purpose of this clause is to provide guidance for these situations.

NOTE 1 The following sub clauses provide simplified adjustments to be used in the absence of better information.

NOTE 2 The simplified adjustment for bending strength and tension strength is no adjustment when the moisture content is in the range 8 % to 18 %.

If the moisture content u is lower than 8 %, special consideration is required for the adjustment of strength properties, modulus of elasticity and density.