INTERNATIONAL STANDARD

ISO 5178

Second edition 2019-01

Destructive tests on welds in metallic materials — Longitudinal tensile test on weld metal in fusion welded joints

Essais destructifs des soudures sur matériaux métalliques — Essai de traction longitudinale du métal fondu des assemblages soudés par fusion

iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 5178:2019

https://standards.iteh.ai/catalog/standards/iso/58928f67-c3f7-4076-b346-85175a943cc0/iso-5178-2019



iTeh Standards (https://standards.iteh.ai) Document Preview

ISO 5178:2019

https://standards.iteh.ai/catalog/standards/iso/58928t67-c3t7-4076-b346-85175a943cc0/iso-5178-2019



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Fax: +41 22 749 09 47 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

Foreword			Page
			iv
1	Scop	oe	1
2	Normative references		1
3	Terms and definitions		1
4	Symbols and abbreviated terms		1
5	=	ciple	
6	Removal of test specimens		2
	6.1	Location	
	6.2	Marking	
	6.3	Heat treatment and/or ageing	
	6.4	Extraction	
		6.4.1 General	2
		6.4.2 Steel	2
		6.4.3 Other metallic material	
	6.5	Machining of test specimens	
	6.6	Dimensions	
	6.7	Surface quality	4
7	Conditions of testing		4
8	Test results I Teh Standards		4
	8.1	General	
	8.2	Examination of fracture surfaces	
9	Test report Preview		
Δnn	ov A (in	oformative) Evample of a test report	5

ISO 5178-2010

https://standards.iteh.ai/catalog/standards/iso/58928f67-c3f7-4076-b346-85175a943cc0/iso-5178-2019

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 5, *Testing and inspection of welds*.

Any feedback, question or request for official interpretation related to any aspect of this document should be directed to the Secretariat of ISO/TC 44/SC 5 via your national standards body. A complete listing of these bodies can be found at www.iso.org/members.html. Official interpretations, where they exist, are available from this page: https://committee.iso.org/sites/tc44/home/interpretation.html.

This second edition cancels and replaces the first edition (ISO 5178:2001), which has been technically revised. The main changes compared to the previous edition are as follows:

- the normative reference has been revised from ISO 6892 to ISO 6892-1:
- new mandatory <u>Clause 3</u> has been added;
- Clauses 5 and 9 have been improved.

Destructive tests on welds in metallic materials — Longitudinal tensile test on weld metal in fusion welded joints

1 Scope

This document specifies the sizes of test specimens and the test procedure for carrying out longitudinal tensile tests on cylindrical test specimens in order to determine the mechanical properties of weld metal in a fusion welded joint.

This document applies to metallic materials in all forms of product with joints made by any fusion welding process, having joint sizes that are sufficient to obtain cylindrical test specimens with dimensions in accordance with ISO 6892-1.

Unless specified otherwise for specific points in this document, the general principles of ISO 6892-1 apply.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6892-1, Metallic materials — Tensile testing — Part 1: Method of test at room temperature

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at http://www.electropedia.org/

4 Symbols and abbreviated terms

The symbols and abbreviated terms to be used for the longitudinal tensile tests shall be as specified in ISO 6892-1.

5 Principle

An increasing tensile load is continuously applied until rupture occurs in a cylindrical test specimen taken longitudinally from the weld metal in a welded joint.

The test shall be carried out at room temperature between 10 °C and 35 °C, unless otherwise specified.

Tests carried out under controlled conditions shall be made at a temperature of 23 °C ± 5 °C.

6 Removal of test specimens

6.1 Location

The test specimen shall be taken longitudinally from the welded joint of the manufactured product or from the test piece. After machining, the parallel length of the test specimen shall consist only of weld metal (see Figures 1 and 2).

To enable correct positioning of the test specimen in the joint, the joint cross-section at both ends of the test specimen can be macroetched.

6.2 Marking

Each test piece shall be marked in order to identify its exact location in the manufactured product or in the joint from which it has been removed.

Each test specimen shall be marked in order to identify its exact location in the test piece from which it has been taken.

When removed from the test piece, each test specimen shall be marked.

6.3 Heat treatment and/or ageing

No heat treatment shall be applied to the welded joint or to the test specimen unless it is specified or permitted by the relevant application standard dealing with the welded joint to be tested. Details of any heat treatment shall be recorded in the test report. If natural ageing of aluminium alloys takes place, the time between welding and testing shall be recorded.

NOTE The presence of hydrogen in ferrous weld metals can adversely affect the test results and suitable hydrogen release treatment.

6.4 Extraction

ISO 5178:2019

6.4.1 General

The mechanical or thermal processes used to extract the test specimen shall not change the properties of the test specimen in any way.

6.4.2 Steel

Shearing is excluded for thicknesses greater than 8 mm. If thermal cutting or other cutting methods which can affect the cut surfaces are used to cut the test specimen from the welded plate, or from the test piece, the cuts shall be made at a distance greater than or equal to 8 mm from the surfaces of the final parallel length of the test specimen. Thermal cutting shall not be used parallel to the original surface of the welded plate or of the test piece.

6.4.3 Other metallic material

Shearing and thermal cutting are excluded and only machining (e.g. sawing and turning) shall be used.

6.5 Machining of test specimens

Unless otherwise specified in the particular application standard dealing with the welded joint under examination, the test specimens shall be taken from the centre of the weld metal as shown in Figure 1 and the cross-section as shown in Figure 2. In the case where the test specimen is not taken from midthickness, the distance from the surfaces, t_1 , shall be recorded [see Figures 2 a) and b)]. In the case of very thick or double-sided welded joints, more than one test specimen may be taken at different