



Designation: B622 – 10

Standard Specification for Seamless Nickel and Nickel-Cobalt Alloy Pipe and Tube¹

This standard is issued under the fixed designation B622; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification² covers seamless pipe and tube of nickel and nickel-cobalt alloys (UNS N10001, UNS N10242, UNS N10665, UNS N12160, UNS N10675, UNS N10276, UNS N06455, UNS N06007, UNS N08320, UNS N06975, UNS N06002, UNS N06985, UNS N06022, UNS N06035, UNS N08135, UNS N06255, UNS N06058, UNS N06059, UNS N06200, UNS N10362, UNS N06030, UNS N08031, UNS R30556, UNS N08535, UNS N06250, UNS N06060, UNS N06230, UNS N06686, UNS N10629, UNS N06210, UNS N10624, and UNS R20033)* as shown in [Table 1](#).

1.2 Pipe and tube shall be supplied in the solution annealed and descaled condition. When atmosphere control is used, descaling is not necessary.

1.3 This specification is limited to tubes up to and including 3.5 in. (88.9 mm) outside diameter.

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet (MSDS) for this product/material as provided by the manufacturer; to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved Dec. 15, 2010. Published December 2010. Originally approved in 1977. Last previous edition approved in 2006 as B622 – 06. DOI: 10.1520/B0622-10.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SB-622 in Section II of that Code.

* New designation established in accordance with Practice E527 and SAE J1086, Practice for Numbering Metals and Alloys (UNS).

2. Referenced Documents

2.1 *ASTM Standards*:³

[B829 Specification for General Requirements for Nickel and Nickel Alloys Seamless Pipe and Tube](#)

[E8 Test Methods for Tension Testing of Metallic Materials](#)

[E527 Practice for Numbering Metals and Alloys in the Unified Numbering System \(UNS\)](#)

3. Terminology

3.1 *Definitions*:

3.1.1 *average diameter, n*—the average of the maximum and minimum outside diameters, or the maximum and minimum inside diameters, as determined at any cross section of the tube.

3.1.2 *pipe, n*—seamless tube conforming to the particular dimensions commercially known as standard pipe sizes ([Appendix X2](#)).

3.1.3 *tube, n*—a hollow product of round or any other cross section having a continuous periphery.

4. General Requirements

4.1 Material furnished under this specification shall conform to the applicable requirements of Specification [B829](#) unless otherwise provided herein. [9/astm-b622-10](#)

5. Ordering Information

5.1 It is the responsibility of the purchaser to specify all requirements that are necessary for the material ordered under this specification. Examples of such requirements include, but are not limited to the following:

5.1.1 *Alloy* ([Table 1](#)).

5.1.2 *Dimensions*:

5.1.2.1 *Tube*—Outside diameter, minimum or average wall thickness, and length.

5.1.2.2 *Pipe*—Standard pipe size and schedule ([Appendix X2](#)).

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

TABLE 1 Chemical Requirements

	Composition Limits, %																								
	Ni	Cr	Mo	Fe	W	C	Si	Co	Mn	V	P	S	Ti	Cu	Cb (Nb) + Ta	Al	Zr	La	N	B	Cb (Nb)	Ta	Ni+ Mo	Mg	
Ni-Mo Alloys N10001	remainder ^A	1.0	26.0-30.0	4.0-6.0	...	0.05	1.0	2.5	1.0	0.2-0.4	0.04	0.03
N10665	remainder ^A	1.0	26.0-30.0	2.0 max	...	0.02	0.10	1.0	1.0	...	0.04	0.03
N10675	65.0 min	1.0-3.0	27.0-32.0	1.0-3.0	3.0	0.01	0.10	3.0	3.0	0.20	0.030	0.010	0.20	0.20	0.20	0.50	0.10	0.20	0.20	94.0-98.0	...	
N10629	remainder ^A	0.5-3.0	26.0-30.0	1.0-6.0	...	0.01	0.05	2.5	1.5	...	0.04	0.01	...	0.5	0.1-	0.5	
N10624	remainder ^A	6.0-10.0	21.0-25.0	5.0-8.0	...	0.01	0.10	1.0	1.0	...	0.025	0.01	...	0.5	
Ni-Mo-Cr-Fe Alloy N10242	remainder ^A	7.0-9.0	24.0-26.0	2.0 max	...	0.03	0.80	1.00	0.80	...	0.030	0.015	...	0.50	0.006	0.50	
Low C Ni-Cr-Mo Alloys N10276	remainder ^A	14.5-16.5	15.0-17.0	4.0-7.0	3.0-4.5	0.010	0.08	2.5	1.0	0.35	0.04	0.03	
N06022	remainder ^A	20.0-22.5	12.5-14.5	2.0-6.0	2.5-3.5	0.015	0.08	2.5	0.50	0.35	0.02	0.02	
N06035	remainder ^A	32.25-34.25	7.60-9.00	2.00 max	0.60	0.050	0.60	1.00	0.50	0.20	0.030	0.015	...	0.30	...	0.40	
N06455	remainder ^A	14.0-18.0	14.0-17.0	3.0 max	...	0.015	0.08	2.0	1.0	...	0.04	0.03	0.70	0.30	...	0.40	
Ni-Cr-Fe-Mo-Cu Alloys N06007	remainder ^A	21.0-23.5	5.5-7.5	18.0-21.0	1.0	0.05	1.0	2.5	1.0-	...	0.04	0.03	...	1.5-	1.75-	
N06975	47.0-52.0	23.0-26.0	5.0-7.0	remainder ^A	...	0.03	1.0	...	1.0	...	0.03	0.03	0.70-	0.70-	2.5	
N06985	remainder ^A	21.0-23.5	6.0-8.0	18.0-21.0	1.5	0.015	1.0	5.0	1.0	...	0.04	0.03	1.50	1.5-	0.50	
N06030	remainder ^A	28.0-31.5	4.0-6.0	13.0-17.0	1.5-	0.03	0.8	5.0	1.5	...	0.04	0.02	...	1.0-	0.30-	
N06255	47.0-52.0	23.0-26.0	6.0-8.0	remainder ^A	4.0	max	1.0	...	1.0	...	0.03	0.03	0.69	2.4	1.50	
N06250	50.0-54.0	20.0-23.0	10.1-12.0	remainder ^A	max	0.020	0.09	...	1.00	...	0.030	0.005	max	max	
Ni-Fe-Cr-Mo Alloys N08320	25.0-27.0	21.0-23.0	4.0-6.0	remainder ^A	...	0.05	1.0	...	2.5	...	0.04	0.03	4xC	
N08135	33.0-38.0	20.5-23.5	4.0-5.0	remainder ^A	0.20-0.80	0.030	0.75	...	1.00	...	0.03	0.03	
N06002	remainder ^A	20.5-23.0	8.0-10.0	17.0-20.0	0.20-	0.05-	1.0	0.5-	1.0	...	0.04	0.03	
N06060	54.0-60.0	19.0-22.0	12.0-14.0	remainder ^A	0.25-	0.03	0.50	...	1.50	...	0.030	0.005	...	0.25-	0.50-	
Ni-Fe-Cr-Co Alloy R30556	19.0-22.5	21.0-23.0	2.5-4.0	remainder ^A	2.0-3.5	0.05-	0.20-	16.0-	0.50-	...	0.04	0.015	0.10-	0.001-	0.005-	0.10-	0.02	0.30	0.3-	0.3-	1.25	

TABLE 1 Continued

		Composition Limits, %																							
		Ni	Cr	Mo	Fe	W	C	Si max	Co	Mn	V	P max	S max	Ti	Cu	Cb (Nb) +Ta	Al	Zr	La	N	B	Cb (Nb)	Ta	Ni+ Mo	Mg
Ni-Cr-W-Mo Alloys N06230	1.0- 3.0	remainder A	20.0- 24.0	1.0- 3.0	3.0 max	13.0- 15.0	0.05- 0.15	0.25- 0.75	5.0 max	0.30- 1.00	...	0.03	0.015	0.50 max	...	0.005- 0.050	...	0.015 max
Low C-Ni- Cr-Mo N06058	19.0- 21.0	balance	20.0- 23.0	1.5 max	0.3 max	0.3	0.10 max	0.3 max	0.50 max	0.50 max	...	0.015	0.005	...	0.50 max	...	0.40 max	0.02- 0.15
N06059	15.0- 16.5	balance	22.0- 24.0	1.5 max	0.010 max	0.10 max	0.3 max	0.5 max	...	0.015	0.010	...	0.50 max	...	0.1- 0.4
Low C-Ni- Cr-Mo-Cu Alloy N06200	15.0- 17.0	remainder A	22.0- 24.0	3.0 max	0.010 max	0.08 max	2.0 max	0.50 max	...	0.025	0.010	...	1.3- 1.9	...	0.50 max
Low C-Ni- Mo-Cr Alloy N10362	21.5- 23.0	remainder A	13.8- 15.6	1.25 max	0.010 max	0.08 max	0.60 max	0.60 max	...	0.025	0.010	0.50 max
Low C-Ni- Fe-Cr- Mo-Cu Alloys N08031	6.0- 7.0	30.0-32.0	26.0- 28.0	balance	0.015 max	0.3 max	2.0 max	2.0 max	...	0.020	0.010	...	1.0- 1.4	0.15- 0.25
N08535	2.5- 4.0	29.0-36.5	24.0- 27.0	remainder A	0.03 max	0.50 max	1.0 max	1.0 max	...	0.03	0.03	...	1.50 max
Low C-Ni- Cr-Mo-W Alloy N06686	15.0- 17.0	remainder A	19.0- 23.0	5.0 max	3.0- 4.4	...	0.010 max	0.08 max	0.75 max	0.75 max	...	0.04	0.02	0.02- 0.25
Ni-Co-Cr-Si Alloy N12160	1.0 max	remainder A	26.0- 30.0	3.5 max	1.0 max	...	0.15 max	2.4- 3.0	27.0- 33.0	1.5 max	...	0.030	0.015	0.20- 0.80	1.0 max
Cr-Ni-Fe-N Alloy R20033	0.50- 2.0	30.0-33.0	31.0- 35.0	balance	0.015 max	0.05 max	...	2.0 max	...	0.02	0.01	...	0.3- 1.20	0.35- 0.60
Low C-Ni- Mo-Cr-Ta Alloy N06210	18.0- 20.0	remainder A	18.0- 20.0	1.0 max	0.015 max	0.08 max	1.0 max	0.5 max	0.35 max	0.02	0.02	1.5- 2.2

A See 12.1.