



SLOVENSKI STANDARD
oSIST prEN ISO 23216:2022
01-september-2022

Ogljikove plasti - Določanje optičnih lastnosti amorfnih ogljikovih plasti s spektroskopsko elipsometrijo (ISO 23216:2021)

Carbon based films - Determination of optical properties of amorphous carbon films by spectroscopic ellipsometry (ISO 23216:2021)

Kohlenstoffschichten - Bestimmung der optischen Eigenschaften von amorphen Kohlenstoffschichten mittels spektroskopischer Ellipsometrie (ISO 23216:2021)

Films à base de carbone - Détermination des propriétés optiques des films de carbone amorphe par ellipsométrie spectroscopique (ISO 23216:2021)

Ta slovenski standard je istoveten z: prEN ISO 23216

ICS:

25.220.99 Druge obdelave in prevleke Other treatments and coatings

oSIST prEN ISO 23216:2022

en,fr,de

INTERNATIONAL
STANDARD

ISO
23216

First edition
2021-05

**Carbon based films — Determination
of optical properties of amorphous
carbon films by spectroscopic
ellipsometry**

*Films à base de carbone — Détermination des propriétés optiques des
films de carbone amorphe par ellipsométrie spectroscopique*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 23216:2022](https://standards.iteh.ai/catalog/standards/sist/66d2c31e-df95-4985-bf65-bb0e5fc62956/osist-pren-iso-23216-2022)

[https://standards.iteh.ai/catalog/standards/sist/66d2c31e-df95-4985-bf65-
bb0e5fc62956/osist-pren-iso-23216-2022](https://standards.iteh.ai/catalog/standards/sist/66d2c31e-df95-4985-bf65-bb0e5fc62956/osist-pren-iso-23216-2022)



Reference number
ISO 23216:2021(E)

© ISO 2021

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 23216:2022](https://standards.iteh.ai/catalog/standards/sist/66d2c31e-df95-4985-bf65-bb0e5fc62956/osist-pren-iso-23216-2022)

<https://standards.iteh.ai/catalog/standards/sist/66d2c31e-df95-4985-bf65-bb0e5fc62956/osist-pren-iso-23216-2022>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Test specimen preparation	1
5 Apparatus	2
6 Procedure	2
6.1 Treatment of specimen before test.....	2
6.2 Preparation for test.....	2
6.3 Testing conditions for test.....	2
6.4 Optical model for analysis.....	3
6.5 Number of test repeats.....	3
7 Classification of test results	3
8 Test report	3
Annex A (normative) Classification method for amorphous carbon films by optical properties	5
Bibliography	7

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 23216:2022](https://standards.iteh.ai/catalog/standards/sist/66d2c31e-df95-4985-bf65-bb0e5fc62956/osist-pren-iso-23216-2022)

<https://standards.iteh.ai/catalog/standards/sist/66d2c31e-df95-4985-bf65-bb0e5fc62956/osist-pren-iso-23216-2022>

ISO 23216:2021(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

This document provides a determination method and a classification for optical properties of amorphous carbon films by spectroscopic ellipsometry.

Amorphous carbon films have a structure, containing both sp^2 and sp^3 bonded carbon atoms and in several cases also hydrogen. There are graphite-like, polymer-like, glass-like and diamond-like carbon films. Because of their outstanding mechanical properties, amorphous carbon films are used in various hard coating applications on hard metals, e.g. as protective coatings against wear and corrosion in automotive parts. Biomedical and optical applications on alternative substrate materials such as silicon and glass have become more and more important. Currently, amorphous carbon films are classified into several types with regard to their chemical structures, and each type is selectively used according to its appropriate application. For an easy classification of amorphous carbon films, an optically quantified phase fingerprint with high accuracy is provided as a result of an international interlaboratory comparison.

The optical properties of refractive index n and extinction coefficient k determined by spectroscopic ellipsometry are the key quantities for the proposed classification of amorphous carbon films. The interlaboratory comparison demonstrated that a classification within the n - k plane is feasible for all types of amorphous carbon films. This will be beneficial for the identification of the coating type on alternative substrate materials (such as silicon and glass) and additional industrial applications. Spectroscopic ellipsometry as a fast and non-destructive analytical method can also be applied to quality control and development in industrial applications, given that smooth and well-defined substrate materials are used and appropriate modelling is applied.

This document is intended to implement recommended ellipsometric test conditions and the n - k plane classification scheme of amorphous carbon films on silicon wafers.

This document is useful for the complementary optical property classification and quality control of amorphous carbon films.

As amorphous carbon films show a huge diversity of structure and properties, it is crucial to select the appropriate type of amorphous carbon film to exploit their excellent properties in practical use. Therefore, carbon films are characterized by spectroscopic ellipsometry under reasonable conditions. This enables the classification of amorphous carbon films on silicon wafers within the n - k plane acting as a process fingerprint.

Carbon based films — Determination of optical properties of amorphous carbon films by spectroscopic ellipsometry

1 Scope

This document specifies spectroscopic ellipsometry for the determination of optical properties (refractive index n and extinction coefficient k) and the optical classification of different types of amorphous carbon films within the n - k plane.

It is applicable to amorphous carbon films deposited by ionized evaporation, sputtering, arc deposition, plasma-assisted chemical vapour deposition, hot filament techniques and others.

It does not apply to carbon films modified with metals or silicon, amorphous carbon films that have a gradient of composition/property in the thickness, paints and varnishes.

2 Normative references

There are no normative references in this document.

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1

refractive index

n

ratio of the velocity of propagation of electromagnetic radiation in a vacuum to the velocity of propagation of electromagnetic radiation in a medium

3.2

extinction coefficient

k

amount of absorption of electromagnetic radiation in a medium (substance)

4 Test specimen preparation

Amorphous carbon films on various substrates can be tested if the substrates are optically isotropic and optical models are available for them. The recommended test substrate is a Si wafer with a mirror surface. It can be used as substrates of the amorphous carbon films for testing depending on the requirements. Specimens shall be homogeneous amorphous carbon films. The thickness of the amorphous carbon films shall be 0,02 μm to 5 μm .

Any pertinent details of the specimens such as their dimensions, surface finish, material type, composition, microstructure and processing treatments shall be supplied.

ISO 23216:2021(E)

5 Apparatus

5.1 Halogen lamp and blue LED for a light source, which shall have a spectral range of more than 450 nm to 950 nm.

5.2 Detector, for the acquisition of ellipsometric measurement data, which shall have a spectral range of more than 450 nm to 950 nm.

5.3 Spectrometer combined with photomultiplier tube (PMT)/charge coupled device (CCD)/photodiode array (PDA), for detecting data.

5.4 Software, for obtaining optical constants and film thickness from ellipsometric measurement data.

5.5 Stage, for putting a sample.

5.6 Goniometer, to establish the angle of incidence to 70° or to a multi-angle.

5.7 Camera, for observation of the sample surface and positioning of the flat surface.

6 Procedure

6.1 Treatment of specimen before test

Wash the specimens ultrasonically in a high purity organic solvent for 10 min or longer, with the testing surface downward in the case of the disc specimen. Without allowing them to dry, the specimens should be rinsed with high purity organic solvent and then dried for 30 min or longer in an oven set at 120 °C. Organic solvent can be replaced with other solvents or deionized water as long as clean specimen surfaces are produced at the end of the procedure. The specimens shall be stored, in the same atmosphere as that used for the testing apparatus, until required.

6.2 Preparation for test

Place the specimen for measurement on the stand and set it in place to be irradiated with the light. Adjust the stand height to allow the signal to be as strong as possible for detection.

6.3 Testing conditions for test

Recommended test conditions are listed below, but these may be changed to suit the particular needs of the measuring process. All test conditions shall be described in the test report.

- a) Wavelength in measurement: 450 nm to 950 nm.
- b) Angle of incidence: 70°.
- c) Spot size: over 500 μm \times 500 μm .
- d) Duration of measurement: 5 s.

The test provides data for the angle of the ratio for the amplitudes of reflected p and s polarized lights, and the phase difference.

From the refractive index and extinction coefficient spectra, the values at or as close as possible to 550 nm should be used for amorphous carbon classification.