



Designation: ~~D6210-08~~ Designation: D6210 - 10

## Standard Specification for Fully-Formulated Glycol Base Engine Coolant for Heavy-Duty Engines<sup>1, 2</sup>

This standard is issued under the fixed designation D6210; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope\*

1.1 This specification covers the requirements for fully-formulated glycol base coolants for cooling systems of heavy-duty engines. When concentrates are used at 40 to 60 % glycol concentration by volume in water of suitable quality, (see Appendix X1), or when prediluted glycol base engine coolants (50 volume % minimum) are used without further dilution, they will function effectively during both winter and summer to provide protection against corrosion, cavitation, freezing, and boiling.

1.2 This specification is intended to cover the requirements for engine coolants prepared from virgin or recycled ethylene or propylene glycol.

NOTE 1—Committee D15 has not substantially studied the impact of using recycled glycols from sources such as:

- glycol bottoms
- polyester manufacturing waste
- aircraft and runway deicers
- medical waste

to prepare engine coolants. However, several serious cases of very poor performance have been reported and substantiated in heavy duty fleets when recycled glycols from sources such as above have been used to prepare engine coolants. Efforts are underway to more clearly define the purity requirements for glycols used to prepare engine coolants meeting this specification, whether from recycled engine coolants or other sources.

1.3 The coolants governed by this specification are categorized as follows:

Coolant Type	Description
I-FF	Ethylene glycol base concentrate
II-FF	Propylene glycol base concentrate
III-FF	Ethylene glycol predilute (50 vol %)
IV-FF	Propylene glycol predilute (50 vol %)

1.4 Coolant concentrates meeting this specification do not require any addition of Supplemental Coolant Additive (SCA) until the first maintenance interval when a maintenance dose of SCA is required to continue protection in certain heavy duty engine cooling systems, particularly those of the wet cylinder liner-in-block design. The SCA additions are defined by and are the primary responsibility of the engine manufacturer or vehicle manufacturer. If they provide no instructions, follow the SCA supplier's instructions.

1.5 The values stated in SI units are to be regarded as standard. The values given in parentheses are for information only.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>3</sup>

D1126 [Test Method for Hardness in Water](#)

D1293 [Test Methods for pH of Water](#)

D3306 [Specification for Glycol Base Engine Coolant for Automobile and Light-Duty Service](#)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D15 on Engine Coolants and is the direct responsibility of Subcommittee D15.07 on Specifications. Current edition approved Oct. 1, 2008. Published November 2008. Originally approved in 1998. Last previous edition approved in 2006 as D6210-06. DOI: 10.1520/D6210-08.

Current edition approved Dec. 1, 2010. Published January 2011. Originally approved in 1998. Last previous edition approved in 2008 as D6210-08. DOI: 10.1520/D6210-10.

<sup>2</sup> A research report is available from ASTM International Headquarters. Request RR:D15-1023.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard.

D4327 [Test Method for Anions in Water by Chemically Suppressed Ion Chromatography](#)

D5828 [Test Method for Compatibility of Supplemental Coolant Additives \(SCAs\) and Engine Coolant Concentrates](#)—~~Test Method for Compatibility of Supplemental Coolant Additives (SCAs) and Engine Coolant Concentrates~~

D7583 [Test Method for John Deere Coolant Cavitation Test](#)

2.2 *Other Standards:*<sup>4</sup>

Federal Method 2540B Total Dissolved Solids Dried at 103–105°C

### 3. General Requirements

~~3.1 Concentrated~~ **3.1 Concentrated** and prediluted coolants shall meet all of the physical, chemical and performance requirements of Specification D3306., Tables 1, 2, and 3.

3.2 The coolant concentrate mixed with water or the prediluted coolant, when maintained with maintenance doses of SCA in accordance with the engine manufacturer’s recommendations, and those on the product label, shall be suitable for use in a properly maintained cooling system in normal service for a minimum of two years (see Appendix X1).

### 4. Additional Requirements

4.1 The coolant concentrate or prediluted coolant additionally shall provide protection in operating engines against cavitation corrosion (also termed liner pitting) and against scaling of internal engine hot surfaces. Hot surfaces typically are within the engine head, head spacer, upper cylinder liner, or liquid cooled exhaust manifold. ASTM has test methods under development for both cavitation corrosion and hot surface scaling. Until these procedures are approved as ASTM standards, the mandatory requirements of Annex A1 shall apply.

~~4.2 Lack~~ **4.2 Lack** of compatibility between the coolant and SCA product’s chemistry may cause the solute to precipitate out of solution, with potential adverse effects in the vehicle or engine cooling system. A test procedure for compatibility (Test Method D5828) has been developed and approved. The compatibility of SCA and coolant concentrate solutions meeting this specification shall be determined using D5828 and the results reported.

~~4.3 Both~~ **4.3 Both** the concentrated and prediluted coolants shall contain less than 50 µg/g sulfate ion.

### 5. Keywords

5.1 cavitation; fully-formulated heavy-duty engine coolant; supplemental coolant additive maintenance dose

## ANNEX

### (Mandatory Information)

#### ~~A1. CHEMICAL REQUIREMENTS~~ **A1. REQUIREMENTS FOR FULLY FORMULATED HEAVY DUTY ENGINE COOLANT**

A1.1 Laboratory data or in-service experience demonstrating a positive influence on reducing cavitation corrosion in an operating engine is required. See Table A1.1.

A1.1.1 In-service qualification tests may consist of single- or multiple-cylinder engine tests. At the option of the engine or vehicle manufacturer, such testing may be conducted in “loose engines” or in engines fully integrated into an application, such as a vehicle, a power boat, or a stationary power source. One such test has been developed. ~~A1.2 Several chemical compositions have been tested extensively by producers and users and satisfactorily minimize cylinder liner cavitation in actual test engines. Coolants meeting either of the following compositions are regarded as passing the requirements of <sup>5</sup>~~

A1.1.2 Coolants that have completed the Test Method D7583 (laboratory test method to demonstrate coolant cavitation performance) test with a maximum pit count of 200 are regarded as passing the requirements of A1.1.

A1.1.3 Several chemical compositions have been tested extensively by producers and users and satisfactorily minimize cylinder liner cavitation in actual test engines. Coolants meeting either of the following compositions are regarded as passing the requirements of A1.1:

~~A1.2.1~~ A1.1.3.1 A minimum concentration of nitrite (as NO<sub>2</sub><sup>-</sup>) of 1200 µg/g (ppm) in the 50 volume % predilute coolant, or  
~~A1.2.2~~ A1.1.3.2 A minimum combined concentration of nitrite (as NO<sub>2</sub><sup>-</sup>) plus molybdate (as MoO<sub>4</sub><sup>-2</sup>) in the 50 volume % predilute coolant of 780 µg/g (ppm). At least 300 µg/g (ppm) each of NO<sub>2</sub><sup>-</sup> and MoO<sub>4</sub><sup>-2</sup> must be present.

A1.2.1.3.3 The above concentrations are doubled for coolant concentrates.

~~A1.3 Chemical composition requirements for cavitation corrosion protection will be removed from this specification and replaced with an ASTM test method when a test method is developed and adopted.~~

<sup>4</sup> Standard Method for the Examination of Water and Wastewater, American Public Health Association, et al, 1015 15th Street, N.W. Washington, DC 20005

<sup>5</sup> “A Comparison of Engine Coolant in an Accelerated Heavy-Duty Engine Cavitation Test,” SAE Technical Paper 960883, SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001.