



Designation: ~~D5057-90 (Reapproved 2006)~~ Designation: D5057 - 10

Standard Test Method for Screening Apparent Specific Gravity and Bulk Density of Waste¹

This standard is issued under the fixed designation D5057; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of apparent specific gravity and bulk density in waste. For the purpose of this test method, materials to be measured will be classified into three groups:

1.1.1 *Group A*—Free-flowing liquids; apparent specific gravity (ASG),

1.1.2 *Group B*—Granules, powders and water reactive liquids, solids or sludges; bulk density (BD), and

1.1.3 *Group C*—Bulk solids (such as gravel, paper or wood, etc.); apparent specific gravity (ASG).

1.2 This test method is designed and intended as a preliminary test to complement the more sophisticated quantitative analytical techniques that may be used to determine specific gravity. This test method offers to the user the option and the ability to screen waste for apparent specific gravity or bulk density when the more sophisticated techniques are not available and the total waste composition is unknown.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For a specific hazard statement, see Section 9.

2. Referenced Documents

2.1 *ASTM Standards:*²

D1192 [Guide for Equipment for Sampling Water and Steam in Closed Conduits](#)

D1193 [Specification for Reagent Water](#)

D3370 [Practices for Sampling Water from Closed Conduits](#)

D4057 [Practice for Manual Sampling of Petroleum and Petroleum Products](#) ~~Practice for Manual Sampling of Petroleum and Petroleum Products~~

D5681 [Terminology for Waste and Waste Management](#)

3. Terminology

3.1

3.1 For definitions of terms used in this test method refer to Terminology D5681.

3.2 Definition of Term Specific to This Standard:

3.2.1

3.2.1 *screening*—a preliminary qualitative or semi-quantitative test, developed from classical qualitative and quantitative techniques, that is designed to efficiently give the user specific information about a waste that will aid in determining waste identification, process compatibility, and safety in handling.

4. Summary of Test Method

4.1 The specific gravity of a material is the ratio of the masses of equal volumes of a waste and reagent water. The apparent specific gravity of materials in Groups A and C is determined by comparing the mass of a sample to the mass of the same volume of reagent water. The bulk density of wastes in Group B is determined as a direct mass/volume ratio of the sample alone and should be used for determinations on water reactive materials. The weights are used in determining mass.

¹ This test method is under the jurisdiction of ASTM Committee D34 on Waste Management and is the direct responsibility of Subcommittee D34.01.05 on Screening Methods.

Current edition approved May/Dec. 1, 2006-2010. Published May-2006-January 2011. Originally approved in 1990. Last previous edition approved in 2004-2006 as D5057-90(2004). DOI: 10.1520/D5057-90R06-10.1520/D5057-10.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

5. Significance and Use

5.1 This test method is intended for use by those in the waste management industries for the determination of apparent specific gravity and bulk density of waste.

5.2 The apparent specific gravity and bulk density determined by this test method can be used for the conversion of measured volumes to weights.

5.3 The apparent specific gravity and bulk density, when correlated with other properties, can be used to indicate the character of the waste.

6. Interferences

6.1 Excessive temperatures causing loss of sample components due to vaporization could result in erroneous readings.

6.2 Large, obvious void spaces interfere in this test method and will give inaccurate results because of the false volume measured.

7. Apparatus

7.1 *Weighing Bottle*—Specific gravity bottle or equivalent container is needed.

7.2 *Spatulas*.

7.3 *Top Loader Balance*, with a sensitivity of 0.01 g is required.

8. Reagents and Materials

8.1 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean reagent water as defined by Type IV of Specification D1193.

9. Hazards

9.1 **Warning**—Avoid inhalation of and skin and eye contact with all hazardous materials.

10. Sampling

10.1 Collect the sample in accordance with Specification D1192 and Practices D3370 and D4057.

NOTE 1—Extreme temperature variations between the sample and reagent water should be avoided.

11. Procedure

11.1 Make all weight measurements to nearest 0.01 g.

11.2 Weigh the empty container (weighing bottle or specific gravity bottle) with lid on, and record weight as *W*.

11.3 Fill the container with water and place lid on container. Wipe off excess water and weigh. Record weight of water-filled container as *R*.

11.4 For free-flowing liquids (Group A):

11.4.1 Fill the empty container (see 7.1) with sample.

11.4.2 Place the lid on the container, pushing out excess sample through the hole.

11.4.3 Wipe off excess sample.

11.4.4 Weigh the sample-filled container with lid on, and record weight as *S*.

11.5 For granules, powders, and water reactive materials (Group B):

11.5.1 Add as much of the sample to the weighed container (see 7.1) as possible without exerting pressure, filling the container with sample but not allowing large void spaces (see 6.2). The container may be tapped or lightly tamped.

11.5.2 Place the lid on the container and weigh the sample and bottle and record weight as *S*.

11.6 For bulk solids such as gravel, paper or wood (Group C):

11.6.1 Add as much of the sample to the weighed container (see 7.1) as possible without exerting pressure. Place the lid on the container and weigh and record weight as *S*.

11.6.2 Fill remaining space in the container with water and place the lid on the container, taking care that air bubbles are not trapped in the material or the container.

11.6.3 Weigh and record weight of sample and water, in container with the lid on. Record weight as *Q*.

NOTE 2—The quantity *Q-S* may be erroneously high due to the water absorbed by the solid sample.

12. Calculation

12.1 Calculate the apparent specific gravity (ASG) or bulk density from the following equations, matching the appropriate equation with the procedure of choice for each group.

12.1.1 For Group A materials:

$$\text{ASG} = \frac{(S-W)}{(R-W)} \quad (1)$$