### FINAL DRAFT

## INTERNATIONAL STANDARD

# ISO/FDIS 23523

ISO/TC **71**/SC **6** 

Secretariat: JISC

Voting begins on: 2021-01-22

Voting terminates on: 2021-02-16

### Test methods for discrete polymer fibre for fibre-reinforced cementitious composites

## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/FDIS 23523 https://standards.iteh.ai/catalog/standards/sist/0fl 5bfc4-df42-4762-9cf8-6a59910389a0/iso-fdis-23523

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNO-LOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STAN-DARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.



Reference number ISO/FDIS 23523:2021(E)

### iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/FDIS 23523 https://standards.iteh.ai/catalog/standards/sist/0f15bfc4-df42-4762-9cf8-6a59910389a0/iso-fdis-23523



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org

Published in Switzerland

### Contents

Page
------

Fore	word		iv			
Intro	ductio	n	v			
1	Scop	e				
2	Normative references					
2	Torm	is and definitions	1			
3						
4	Symbols and abbreviated terms					
5	Test methods for determining fibre diameter					
	5.1 Consecutive fibre method					
	53	Test renort				
6	Test	nothed for determining fibre length				
0	6.1	Procedure				
	6.2	Test report				
7	Tost	method for determining tensile strength and initial modulus of elasticity	5			
/	7.1	Testing machine	<b>5</b>			
	7.2	Sampling of specimens.	5			
	7.3	Procedure	5			
	7.4	Tensile strength.	6			
	7.5	Initial modulus of elasticity <b>DAND I NEVIEW</b>	6			
	7.6	Test report (standards.iteh.ai)	7			
8	Test	Test method for determining fibre density				
	8.1	Procedure <u>ISO/FDIS-23523</u>	7			
	8.2	Test report standards: itelr:ai/catalog/standards/sist/0fl 5bfc4-df42-4762-9cf8-	7			
9	Test	Test method for determining thermal properties of fibre				
	9.1	Melting point				
	9.2	Test report	8			
10	Test	method for determining moisture content of fibre	8			
	10.1	Procedure				
	10.2	Test report	9			
11	Test	method for determining alkaline durability	9			
	11.1	General	9			
	11.Z	Apparatus and reagents	9			
	11.5	Propagation of alkaling solution	10 10			
	11.4	Exposure of alkaline condition	10 10			
	11.5	Tensile test procedure				
	11.7	Calculations				
	11.8	Test report				
Bibli	ograph	y				

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see <a href="https://www.iso.org/directives">www.iso.org/directives</a>).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see <a href="https://www.iso.org/patents">www.iso.org/patents</a>).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see <a href="https://www.iso.org/iso/foreword.html">www.iso.org/iso/foreword.html</a>.

This document was prepared by Technical Committee ISO/TC 71, Concrete, reinforced concrete and prestressed concrete, Subcommittee SC 6, Non-traditional reinforcing materials for concrete structures. https://standards.iteh.ai/catalog/standards/sist/0f15bfc4-df42-4762-9cf8-

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <u>www.iso.org/members.html</u>.

### Introduction

Polymer fibre in this document means a fibre made with macromolecule substances as raw material such as aramid fibre, polyamide fibre, polyester fibre, polyethylene fibre, polypropylene fibre, polyvinylalcohol fibre. For fibre-reinforced cementitious composites (FRCC), many kinds of and types of polymer fibres are designed and produced on various demands. However, standards of discrete polymer fibres for FRCC in the civil engineering field are not specified yet despite the need for it.

If the fibre suppliers can show the principal fibre properties such as geometry and standardized basic mechanical properties, the engineer can design, manufacture and practice more effectively. Therefore, although the standard of the fibre itself is useful for users, construction engineers and others, it is expected to be used primarily by more fibre suppliers than those.

The status of the existing standards is as follows;

- 1) Test methods for composites exist, i.e. ISO 19044, ISO 21022 and ISO 21914. However, they are not for polymer fibre itself. Breaking force and elongation at break for the fibre itself are specified in ISO 2062, but other material properties of fibres, such as initial modulus of elasticity and thermal properties, are not specified.
- 2) Existing standards for fibres are intended for clothing textiles, ropes or strips. Test methods and unit system are different from those in the civil engineering field. The traditional unit system for textile is the Tex system, in which sectional size of fibre is expressed by weight per length. The unit system is different from that used in the civil engineering field. It would be very convenient to express them in SI units such as Newtons millimetres. R V IR W

The purpose of each testing item is described belowiteh.ai)

For a fibre design, the fibre shape and mechanical properties are important for selection. The fibre length is selected upon the matrix composition. For example, a 4 mm to 12 mm length fibre is suitable for a uniform matrix such as cement mortar, and 20 mm oblonger is required for concrete that includes coarse aggregates. The fibre diameter is also important because it influences the fibre dispersion through the fibre aspect (length/diameter) ratio. The tensile strength and initial modulus of elasticity are key parameters that influence the reinforcing performance of the fibre through the fibre, in spite of their importance, are not included in this document as they are strongly related to the matrix properties and are generally difficult to estimate. In addition, creep and fatigue properties are not included in this document either because the needs of these properties depend on the application situations of the FRCC.

In terms of fibre usage, the fibre reinforcement performance in the FRCC is related to the fibre volume fraction, which is calculated from the fibre weight according to the fibre density. In the use of moisturized fibre products for a uniform fibre dispersion, the existence of water can have a significant effect on the hydration of the cementitious matrix. Thus, the fibre moisture content needs to be accurately estimated.

For the operation stage of the FRCC, their thermal properties and durability against chemicals are of particular concern. For instance, in case of high strength cementitious composites, the polymer fibre can melt during a fire to introduce small cavity so as to release the high internal pressure and consequently reduce the risk of an explosive failure of the cement matrix. Therefore, for fire protection applications, a relatively low melting point of the fibre is considered as apriority. In addition, fibres for the FRCC need to have high durability against alkaline conditions. Thus, the melting point and alkaline durability are two important parameters of the fibres.

The fibre properties are defined in this document as the properties of the smallest fibre unit that disperses in the FRCC. In actual application, fibres can also exist in the form of bundle even within the FRCC.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO/FDIS 23523 https://standards.iteh.ai/catalog/standards/sist/0f15bfc4-df42-4762-9cf8-6a59910389a0/iso-fdis-23523

### Test methods for discrete polymer fibre for fibrereinforced cementitious composites

### 1 Scope

This document specifies the test methods for discrete polymer fibre for fibre-reinforced cementitious composites (FRCC).

This document defines the test methods for discrete polymer fibre, such as diameter, length, tensile strength, initial modulus of elasticity, density, melting point, moisture content and alkaline durability as basic items. These are test methods intended for certification of a fibre and not for quality control or field acceptance.

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1183-1, Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method

ISO 1183-2, Plastics — Methods for determining the density of non-cellular plastics — Part 2: Density gradient column method

ISO/FDIS 23523 ISO 1183-3, Plasticshtps://**Methodst-fori/determining**sthe@defnsity1@f-non-cellular plastics — Part 3: Gas pyknometer method 6a59910389a0/iso-fdis-23523

ISO 11357-3, Plastics — Differential scanning calorimetry (DSC) — Part 3: Determination of temperature and enthalpy of melting and crystallization

#### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <u>https://www.iso.org/obp</u>

— IEC Electropedia: available at http://www.electropedia.org/

3.1

#### fibre-reinforced cementitious composite

FRCC

concrete or mortar containing short discrete fibres that are distributed in the matrix

#### 3.2

#### standard atmosphere

condition of an atmosphere with temperature of (20  $\pm$  2) °C and relative humidity of (65  $\pm$  4) %

#### 3.3

#### standard condition

condition in *standard atmosphere* (3.2) for a period of at least 24 h

#### 3.4

tenacity

tensile strength of fibre in cN/dtex

#### 3.5

#### filament yarn

long and continuous fibre which has not been cut for fibre diameter determination or cut to the product length

#### 3.6

#### consecutive fibre

long and continuous fibre for fibre diameter determination which is longer than the *chopped fibre* (3.7) products

#### 3.7

#### chopped fibre

short fibre which is cut to the product length

3.8

#### individual fibre

smallest unit of fibre structure in fibre-reinforced cementitious composite

Note 1 to entry: to entry: "tex" expresses the unit that shows the sectional size of the individual fibre in weight (grams) per 1 000 metres of fibre.

# 4 Symbols and abbreviated terms ANDARD PREVIEW

		<u> </u>	
С	cN/dtex	tenacity (Standard S. tten.al)	5.4
d	mm	nominal value of individual fibre diameter	<u>5.1</u>
$d_{\mathrm{f}}$	mm http	measuredivalue.ofindividual fibresdiameter1762-9cf8-	<u>5.1, 5.2, 7.4, 7.5</u>
E <sub>ini</sub>	N/mm <sup>2</sup>	initial modulus of elasticity fdis-23523	<u>7.5</u>
$\overline{f_{\rm f0}}$	N/mm <sup>2</sup>	average value of tensile strength of non-exposure specimen	<u>11.7</u>
$\overline{f_{f1}}$	N/mm <sup>2</sup>	average value of tensile strength of alkaline exposed specimen	<u>11.7</u>
$f_{\mathrm{f}}$	N/mm <sup>2</sup>	tensile strength	5.4
1	m	length of specimen	<u>5.1</u>
$L_{\rm f}$	mm	measured value of fibre length	<u>5.2</u>
$L_{\rm F}$	mm	winding frame length in Figure 2	<u>11.2</u>
lg	mm	grip length in tensile test	<u>11.2</u>
l <sub>test</sub>	mm	gauge length in tensile test	<u>7.5, 11.2</u>
т	g	mass of specimen	<u>5.1, 5.2, 10.1</u>
<i>m</i> ′	g	sample mass in standard condition	<u>10.1</u>
M <sub>w</sub>	%	moisture content	<u>10.1</u>
n <sub>f</sub>		number of fibres in yarn	<u>5.1, 7.4, 7.5</u>
P <sub>A</sub>	N	load at point A	<u>7.5</u>
P <sub>max</sub>	N	maximum tensile load	<u>7.4</u>
R <sub>et</sub>	%	tensile strength retention	11.7
T <sub>m</sub>	°C	melting point	<u>9.1</u>
$\delta_{ m ini}$	mm	elongation at initial slope in tensile load – elonga- tion curve	7.5
ρ	g/cm <sup>3</sup>	density	<u>7.1</u> , 9.4

#### 5 Test methods for determining fibre diameter

#### 5.1 Consecutive fibre method

a) Cut out filament yarns to make specimen referring to <u>Table 2</u>. Specimens are prepared by cutting out from each package without first layer. Take five specimens per package, each with a length according to <u>Table 2</u> with an accuracy of 0,1 %. Use an appropriate metering device under a tension of 0,05 cN/dtex, with a tolerance of ±10 %. For fibres with diameters less than 0,5 mm, use a wrap reel. For diameters 0,5 mm and above, use a scale.

Nominal diameter, d	Length, l	
mm	m	
<i>d</i> < 0,08	250	
0,08 ≤ <i>d</i> < 0,30	100	
0,3 ≤ <i>d</i> < 0,5	10	
0,5 ≤ <i>d</i>	5	

Table	2 —	Specimen	length
-------	-----	----------	--------

- b) Condition the specimens before testing in the standard condition.
- c) Measure the mass of the conditioned specimens, *m*, with an accuracy of 0,1 % in a standard **iTeh STANDARD PREVIEW**
- d) Calculate the fibre diameter with Formula (1):

$$d_{\rm f} = 2 \sqrt{\frac{m}{\pi \times l \times \rho \times n_{\rm f}}}$$

$$\frac{\rm ISO/FDIS \ 23523}{\rm https://standards.iteh.ai/catalog/standards/sist/0fl \ 5bfc4-df42-4762-9cf8-Formula (2) is derived from that for determining m 3523}$$

$$m = \pi \left(\frac{d_{\rm f}}{2}\right)^2 \times 1000 \times l \times \frac{\rho}{1000} \times n_{\rm f} \tag{2}$$

Calculate the average value of the five or more results. The results shall be rounded off with a precision of three significant digits. If required, calculate the standard deviation and a 95 % confidence interval.

#### 5.2 Chopped fibre method

- a) Pick up 200 chopped fibre specimens for five or more times from the same package.
- b) Condition the specimens before testing in the standard condition.
- c) Measure the mass of the conditioned specimens, m, with an accuracy of 0,1 % in the standard atmosphere.
- d) Calculate the fibre diameter with <u>Formula (3)</u>

$$d_{\rm f} = 2\sqrt{\frac{5 \times m}{\pi \times L_{\rm f} \times \rho}} \tag{3}$$

Formula (4) is derived from that for determining *m*,

$$m = \pi \left(\frac{d_{\rm f}}{2}\right)^2 \times L_{\rm f} \times \frac{\rho}{1\,000} \times 200 \tag{4}$$

(1)

Calculate the average value of the five or more results. The results shall be rounded off with a precision of three significant digits. If required, calculate the standard deviation and a 95 %confidence interval.

NOTE The vibroscope method in ISO 1973 can be used under the agreement of the parties concerned.

#### 5.3 Test report

The test report shall include the following items:

- fibre profile (type of fibre, nominal value of fibre diameter, nominal value of fibre length, and a) supplier);
- conditioning status; b)
- number of specimens (consecutive fibre method) or number of specimens set (chopped fibre C) method);
- length of specimen (consecutive fibre method) or measured value of fibre length (chopped fibre d) method);
- mass of specimen; e)
- density used in calculation; f)
- measured value of fibre diameter; **IIeh STANDARD PREVIEW** g)
- any deviations from the procedure; h)
- any unusual features observed; i)
- the date of the test: j)
- **ISO/FDIS 23523**

(standards.iteh.ai)

- https://standards.iteh.ai/catalog/standards/sist/0f15bfc4-df42-4762-9cf8-
- a reference to this document (i.e. ISO 23528:4)389a0/iso-fdis-23523 k)

#### Test method for determining fibre length 6

#### 6.1 Procedure

- Pick up 200 or more chopped fibre specimens from the same package. a)
- b) Condition the specimens before testing in the standard condition.
- Measure the length of the specimen by a scale in millimetres. c)
- Calculate the average value of the length, *L*<sub>f</sub>. The results shall be rounded off with a precision of 1 mm; d)

#### 6.2 Test report

The test report shall include the following items:

- fibre profile (type of fibre, nominal value of fibre diameter, nominal value of fibre length, supplier); a)
- conditioning status; b)
- number of specimens; c)
- measured value of fibre length; d)
- any deviations from the procedure; e)
- f) any unusual features observed;

- g) the date of the test;
- h) a reference to this document (i.e. ISO 23523:-).

#### 7 Test method for determining tensile strength and initial modulus of elasticity

#### 7.1 Testing machine

Testing machine that can provide the extension to an individual fibre specimen at a constant rate shall be used. The testing machine is for consecutive fibre before cutting. It shall be capable of being set at test lengths of 200 mm to 500 mm using clamps to grip the specimen.

The clamps for gripping the specimens shall prevent slippage and fracture of specimen at the jaws. Flatfaced unlined jaws shall be the normal type but, if these cannot prevent slippage, then other types of clamps may be used, such as lined jaws, bollard clamps or other types of snubbing devices.

The pinching type clamps are generally used in a tensile test and can be used for a relatively short specimen. But if the pressure or frictional force for pinching the specimen is increased, the specimen is easily damaged at the gripping portion. Therefore, it is preferable to use lined jaws such as thin rubber sheet, man-made leather or other deformable and gripping thin materials.

The bollard-type clamps are also used in a tensile test of fibre. These are a type in which a specimen is wound to be fixed, and then it requires a long specimen.

As the type of clamp can influence the reading of the elongation, all interested parties shall use the same type.

The testing machine shall be equipped with an automatic load/elongation recording devices of sufficiently fast response, or with a system directly recording the breaking load and elongation at break.

The testing machine shall be capable of setting a pretension feither by means of a set of pre-tensioning weights or by using the load-measuring device. O/iso-fdis-23523

#### 7.2 Sampling of specimens

In principle, specimens shall be a consecutive individual fibre. Specimens are prepared by cutting out from each package without first layer in consideration of the test length and grip length. The number of specimens shall be no fewer than 10.

If fibres of sufficient length cannot be obtained, the test length shall be at least 20 mm. In this case, the number of specimens shall be no fewer than 30.

In the case of bundled fibre products decomposed in FRCC, specimens with at least 8 turn bundles per 10 cm shall be used.

#### 7.3 Procedure

- a) Condition the specimens before testing in a standard condition.
- b) Elongation rate shall be set in the range from 50 % of test length to 100 % of a test length per minute. Lower rate can be applied if agreed by all interested parties according to elongation capacity of fibre or facileness of initial modulus of elasticity calculation.
- c) Set the specimen on the clamp. Move the crosshead until the specimen is taut, then start testing. Record tensile load and displacement during testing. Stop testing after the rupture of the specimen.
- d) Omit the results obtained from the specimens as follows, and additional tests shall be carried out using the specimens from the same package:
  - specimen slipped out from clamp;