



~~Designation: D3159-06~~ Designation: D3159 – 10

## Standard Specification for Modified ETFE-Fluoropolymer Molding and Extrusion Materials<sup>1</sup>

This standard is issued under the fixed designation D3159; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope\*

1.1 This specification covers melt processible molding and extrusion materials of modified ETFE-fluoropolymer. The ETFE resin is a copolymer of ethylene containing approximately 75 mass % of tetrafluoroethylene.

1.2 The values stated in SI units as detailed in ~~IEEE/ASTM SI-10~~ IEEE/ASTM SI-10 are to be regarded as standard. The values given in parentheses are for information only.

NOTE 1—Although this specification and ISO 12086-1 (1994) and ISO 12086-2 (1994) differ in approach or detail, data obtained using either are technically equivalent.

1.3 The following safety hazards caveat pertains only to the test method portion, Section 11, of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.4 Recycled material is not appropriate for this specification because performance requirements cannot be met with recycled material. Therefore, this specification is for virgin material only.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

D150 Test Methods for AC Loss Characteristics and Permittivity (Dielectric Constant) of Solid Electrical Insulation

D618 Practice for Conditioning Plastics for Testing

D638 Test Method for Tensile Properties of Plastics

D792 Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement

D883 Terminology Relating to Plastics

D1238 Test Method for Melt Flow Rates of Thermoplastics by Extrusion Plastometer

D1600 Terminology for Abbreviated Terms Relating to Plastics

D3418 Test Method for Transition Temperatures and Enthalpies of Fusion and Crystallization of Polymers by Differential Scanning Calorimetry

D3892 Practice for Packaging/Packing of Plastics

E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods

~~IEEE/ASTM SI-10~~ IEEE/ASTM SI-10 Use of the International System of Units (SI): The Modern Metric System

#### 2.2 ISO Standards:

ISO 12086-1 (1994) Plastics—Fluoropolymer Dispersions and Moulding and Extrusion Materials—Part 1

ISO 12086-2 (1994) Plastics—Fluoropolymer Dispersions and Moulding and Extrusion Materials—Part 2

### 3. Terminology

#### 3.1 Definitions:

3.1.1 *General*—The terminology given in Terminology D883 is applicable to this specification.

3.1.2 *lot, n*—one production run or a uniform blend of two or more production runs.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials (Section D20.15.12).

~~Current edition approved March 15, 2006. Published April 2006. Originally approved in 1973. Last previous edition approved in 2004 as D3159-04. DOI: 10.1520/D3159-06.~~

Current edition approved Nov. 1, 2010. Published January 2011. Originally approved in 1973. Last previous edition approved in 2006 as D3159-06. DOI: 10.1520/D3159-10.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard.

3.1.3 *Abbreviated Terms:*

3.1.4 *General*—The abbreviated terms given in Terminology D1600 are applicable to this specification.

#### 4. Classification

4.1 This specification covers five types of modified ETFE-fluoropolymer supplied in pellet form classified according to their specific gravity. The resins of each type are divided into one to three grades according to their melt flow rate.

4.2 A one-line system shall be used to specify materials covered by this specification. The system uses predefined cells to refer to specific aspects of this specification, as illustrated as follows:

**iTeh Standards**  
**(<https://standards.iteh.ai>)**  
**Document Preview**

[ASTM D3159-10](#)

<https://standards.iteh.ai/catalog/standards/sist/b85bd000-de4c-4857-a9e1-f2e5962ea073/astm-d3159-10>

Standard Number : Type : Grade : Special  
Block : : : Notes

: : : , :

Example: Specification D3159 – 95, I 2

For this example, the line callout ~~would~~shall be, Specification D3159 – 95,I2 and ~~would~~shall specify a modified ETFE-fluoropolymer that has all of the properties listed for that type and grade in the appropriate specified properties, or tables, or both, in the specification identified. A comma is used as the separator between the standard number and the type. Separators are not needed between the type and grade.<sup>3</sup> ~~Provision for special notes is included so that other information can be provided when required. An example would be in Specification D3295 where dimensions and tolerances are specified for each AWG size within the type and class. When special notes are used, they shall be preceded by a comma.~~

**5. General Requirements**

- 5.1 The material shall be of uniform composition and so prepared as to conform to the requirements of this specification.
- 5.2 The material described in this specification shall be free of foreign matter to such a contamination level as shall be agreed upon between the purchaser and the seller.

**6. Performance Requirements**

- 6.1 The average test result of the lot shall conform to the requirements prescribed in Tables 1 and 2 when tested by the procedures specified herein. Table 2 lists those tests requiring a specimen molded as described in Section 8.

**7. Sampling**

- 7.1 The materials shall be sampled in accordance with an adequate statistical sampling program.

**8. Specimen Preparation**

- 8.1 Prepare a molded sheet 1.5 ± 0.3 mm (0.06 ± 0.01 in.) thick. Use a picture-frame-type chase having a suitable blanked-out section and thickness to produce the desired sheet. Use clean aluminum foil, 0.13 to 0.18 mm (0.005 to 0.007 in.) thick, in contact with the resin. A high-temperature mold release agent may be sprayed on the aluminum foil to help prevent the foil from sticking to the sheet. Use steel molding plates at least 1.0 mm (0.040 in.) thick and of an area adequate to cover the chase.
- 8.2 Lay down and smoothly cover one plate with a sheet of aluminum foil. Place the mold chase on top of this assembly. Place within the mold chase sufficient molding material to produce the required sheet in such manner that the polymer charge is a mound in the middle of the chase. Place a second sheet of aluminum foil on top of the granules and add the top mold plate. Place the assembly in a compression molding press having platens that have been heated to 300 ± 5°C (572 ± 10°F).
- 8.3 Bring the press platens to incipient contact with the mold assembly. Hold for 2 to 4 min without pressure. Apply approximately 1 MPa (145 psi) and hold for 1 to 1.5 min. Then apply 2 to 4 MPa (290 to 580 psi) and hold for 1 to 1.5 min. Maintain the press at 300 ± 5°C (572 ± 10°F) during these steps. Remove the assembly from the press and place between two 20 ± 7-mm (0.75 ± 0.25-in.) steel plates whose temperature is less than 40°C (104°F).
- 8.4 When the sheet is cool enough to touch (about 50 to 60°C (122 to 140°F)), remove aluminum foil from the sheet. (If the sheet is allowed to cool to room temperature, the aluminum foil cannot be pulled free.)

**9. Conditioning**

- 9.1 For tests of specific gravity, tensile properties, and electrical properties, condition the molded test specimen in accordance

<sup>3</sup> See the ASTM *Form and Style Manual*, available from ASTM Headquarters.

**TABLE 1 Specific Gravity, Melting Point, and Flow Rate Requirements**

Type Grade	I			II			III		IV	V
	1	2	3	1	2	3	1	2	1	1
Specific gravity,										
min:	1.69	1.69	1.69	1.75	1.75	1.75	1.83	1.83	1.74	1.74
max:	1.76	1.76	1.76	1.84	1.84	1.84	1.88	1.88	1.78	1.80
Melting point, °C,										
min:	255	255	250	220	220	220	218	218	220	250
max:	<del>280</del>	<del>280</del>	<del>280</del>	<del>255</del>	<del>255</del>	<del>255</del>	<del>230</del>	<del>230</del>	<del>240</del>	<del>260</del>
max:	<u>280</u>	<u>280</u>	<u>280</u>	<u>259</u>	<u>259</u>	<u>259</u>	<u>230</u>	<u>230</u>	<u>240</u>	<u>260</u>
Flow rate, g/10 min,										
min:	2.0	8.0	25	2.0	10.1	25	9.0	25.0	10	15
max:	<del>16.0</del>	<del>28.0</del> <sup>A</sup>	45	<del>10.0</del>	<del>19.0</del>	35	<del>18.0</del>	<del>35.0</del>	40	30
max:	16.0	28.0 <sup>A</sup>	45	10.0	19.0	40	18.0	35.0	40	30

<sup>A</sup> Measured with 1.588-mm (0.0625-in.) orifice; other values measured with 2.095-mm (0.0825-in.) orifice.