INTERNATIONAL STANDARD

ISO 9854-2

Second edition 2023-09

Thermoplastics pipes for the transport of fluids — Determination of Charpy impact properties —

Part 2:

Test conditions for pipes of various materials

Tubes thermoplastiques pour le transport des fluides — Détermination des caractéristiques au choc Charpy —

Partie 2: Conditions d'essai pour différentes matières constitutives de tubes 0 9854-2:2023

https://standards.iteh.ai/catalog/standards/sist/749288fe-e6f9-4b23-a302-a79f04907dd6/iso-9854-2-2023



iTeh STANDARD PREVIEW (standards.iteh.ai)

18O 9854-2:2023 https://standards.iteh.ai/catalog/standards/sist/749288fe-e6f9-4b23-a302-a79f04907dd6/iso-9854-2-2023



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office CP 401 • Ch. de Blandonnet 8 CH-1214 Vernier, Geneva Phone: +41 22 749 01 11 Email: copyright@iso.org Website: www.iso.org Published in Switzerland

Co	ntent	S		Page
Intr	oductio)n		vi
1	Scop	e		1
2	Nori	native 1	references	1
3	Terr	ns and o	definitions	1
4	Spec 4.1	Meth 4.1.1 4.1.2 4.1.3 4.1.4	PVC-U, PVC-HI and PVC-O pipes PVC-C pipes ABS and ASA pipes	
	4.2	4.1.5 Meth 4.2.1 4.2.2 4.2.3 4.2.4 4.2.5 4.2.6	PP-H, PP-B, PP-R and PP-RCT pipes od B General PVC-U, PVC-HI and PVC-O pipes PVC-C pipes ABS and ASA pipes PP-H, PP-B, PP-R and PP-RCT pipes PE pipes	4

(standards.iteh.ai)

ISO 9854-2:2023

https://standards.iteh.ai/catalog/standards/sist/749288fe-e6f9-4b23-a302-a79f04907dd6/iso-9854-2-2023

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at www.iso.org/patents. ISO shall not be held responsible for identifying any or all such patent rights.

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves* for the transport of fluids, Subcommittee SC 5, *General properties of pipes, fittings and valves of plastic materials and their accessories -- Test methods and basic specifications.*

This second edition cancels and replaces the first edition (ISO 9854-2:1994), which has been technically revised.

The main changes are as follows:

- the title has been revised;
- throughout the document, unplasticized poly(vinyl chloride), for extrusion, impact modified (PVC-U, EP) has been replaced by high-impact poly(vinyl chloride) (PVC-HI);
- throughout the document, polypropylene (PP) and propylene-copolymer have been replaced by propylene homopolymer (PP-H), propylene impact polymer (PP-B) and propylene random copolymer (PP-R);
- propylene random copolymer with modified crystallinity (PP-RCT), oriented unplasticized poly(vinyl chloride) (PVC-O), and polyethylene (PE) have been added in the Scope;
- the normative references listed in <u>Clause 2</u> have been updated;
- <u>Clause 3</u>, Terms and definitions, has been added;
- the title of <u>Table 1</u>, PVC-U and PVC-U, EP pipes, has been replaced by PVC-U, PVC-HI and PVC-O pipes;
- PVC-O has been added in Table 1;

- the terms "external diameter" and "wall thickness" have been replaced by "nominal outside diameter, d_n " and "nominal wall thickness, e_n " in Tables 1, 2, 3 and 4;
- the title of <u>Table 4</u>, Polypropylene (PP) and propylene-copolymer pipes, has been replaced by PP-H, PP-B, PP-R and PP-RCT pipes;
- PP-RCT has been added in Table 4;
- Subclause 4.2 has been added specifying method B, and including specifications on PE pipes (4.2.6);
- Tables 5, 6, 7, 8 and 9 have been added, including details for notched specimen. Table 9 also specifies PE pipes.

A list of all parts in the ISO 9854 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

iTeh STANDARD PREVIEW (standards.iteh.ai)

18O 9854-2:2023 https://standards.iteh.ai/catalog/standards/sist/749288fe-e6f9-4b23-a302-a79f04907dd6/iso

Introduction

This document specifies the test parameters for determining the impact properties of thermoplastics pipes.

The test can be carried out at -20 °C, 0 °C or 23 °C, depending on the pipe material and/or size.

Data obtained from specimens of different dimensions are not directly comparable.

iTeh STANDARD PREVIEW (standards.iteh.ai)

18O 9854-2:2023 https://standards.iteh.ai/catalog/standards/sist/749288fe-e6f9-4b23-a302-a79f04907dd6/iso 9854-2-2023

Thermoplastics pipes for the transport of fluids — Determination of Charpy impact properties —

Part 2:

Test conditions for pipes of various materials

1 Scope

This document specifies the values or options chosen for the test parameters (i.e. the impact energy, specimen dimensions, specimen type, specimen supports and test temperature) for both unnotched and notched specimens, for testing the impact resistance (pendulum method) of thermoplastics pipes of the following materials, in accordance with ISO 9854-1.

It applies to pipes made of unplasticized poly(vinyl chloride) (PVC-U), high-impact poly(vinyl chloride) (PVC-HI), oriented unplasticized poly(vinyl chloride) (PVC-O), chlorinated poly(vinyl chloride) (PVC-C), acrylonitrile/butadiene/styrene (ABS), acrylonitrile/styrene/acrylate (ASA), propylene homopolymer (PP-H), propylene impact polymer (PP-B), propylene random copolymer (PP-R), propylene random copolymer with modified crystallinity (PP-RCT), and polyethylene (PE).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 9854-1:2023, Thermoplastics pipes for the transport of fluids — Determination of Charpy impact properties — Part 1: General test method

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 9854-1 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at https://www.iso.org/obp
- IEC Electropedia: available at https://www.electropedia.org/

4 Specific test conditions

4.1 Method A

4.1.1 General

For testing in accordance with ISO 9854-1, the values or options for the test parameters shall conform to those specified in <u>Tables 1</u>, <u>2</u>, <u>3</u>, or <u>4</u>, and with <u>4.1.2</u>, <u>4.1.3</u>, <u>4.1.4</u> or <u>4.1.5</u>, as appropriate, depending on the material from which the pipe is made, and its size.

4.1.2 PVC-U, PVC-HI and PVC-O pipes

See <u>Table 1</u>.

4.1.3 PVC-C pipes

See <u>Table 2</u>.

4.1.4 ABS and ASA pipes

See <u>Table 3</u>.

4.1.5 PP-H, PP-B, PP-R and PP-RCT pipes

See <u>Table 4</u>.

Table 1 — PVC-U, PVC-HI and PVC-O pipes

Pip	e dimensi	ons		Specimen	Impact	Test temperature			
d_{n}	$e_{\rm n}$	Sample cut			energy		°C		
mm	mm	direction	ty pe	supports	J	PVC-U	PVC-HI	PVC-O	
<25	All		1	ISO 9854- 1:2023, Figure 1	15				
≥25 but <75	All		2	ISO 9854- 1:2023, Figure 2	15	23 ± 2	0 ± 2	0 ± 2	
≥75	≤9,5	longitudinal	ANDA 2 anda	ISO 9854- 1:2023, Figure 2	15				
≥75	>9,5	(50	3 ISO 9	ISO 9854- 1:2023, Figure 2	50				
≥75 but <160	starAllards	iteh.ai/catalog/	stand <mark>4</mark> rds/si	ISO 9854-	-e6f 15 4b2	3-a302-a	79f04907	ld6/iso-	
≥160	≤9,5	circumferential	4 985	1:2023, 3	15				
≥160	>9,5		5	Figure 3	50				
^a See ISO 9854	-1:2023, Tab	le 1.						·	

Table 2 — PVC-C pipes

	Pipe dimension	ıs			Impact	Test temper-
$d_{ m n}$ mm	$e_{ m n}$ mm	Sample cut di- rection	Specimen type a supports		energy J	ature °C
<25	All		1	ISO 9854- 1:2023, Figure 1		
≥25 but <75	≤4,2		2	ISO 9854- 1:2023, Figure 2		
≥25 but <75	>4,2 but ≤9,5	longitudinal	3	ISO 9854- 1:2023, Figure 2	15	23 ± 2
≥75	≤9,5		2	ISO 9854- 1:2023, Figure 2		
≥75	>9,5		3	ISO 9854- 1:2023, Figure 2		
a See ISO 9854	-1:2023, Table 1.					

Table 2 (continued)

	Pipe dimension	C		Impact	Test temper-				
d _n	e _n	Sample cut di- rection	Specimen type ^a	Specimen supports	energy [ature °C			
111111	111111	<u> </u>			,				
≥75	All	circumferential	4	ISO 9854- 1:2023, Figure 3					
a See ISO 9854	See ISO 9854-1:2023, Table 1.								

Table 3 — ABS and ASA pipes

	Pipe dimension	ns			Impact	Test temper- ature	
d_{n}	e_{n}	Sample cut di-	Specimen type ^a	Specimen supports	energy		
mm	mm	rection	сурс	Supports	J	°C	
<75	<3		2	ISO 9854- 1:2023, Figure 2			
<75	≥3	longitudinal	3	ISO 9854- 1:2023, Figure 2			
≥75	iTen S	longitudinal	RD 2PR	ISO 9854- 1:2023, Figure 2	15	23 ± 2	
≥75	≥3	standard	ls.it₃eh.:	ISO 9854- 1:2023, Figure 2			
≥75 but <160	All	ISO 9854	-2:202 4	ISO 9854-			
http≥160tanda	rds.ite \3 i/catal	circumferential	749288 4 e-e6f9	1:2023, 302-8	79f04907da		
≥160	≥3	9854-2	-2023 5	Figure 3			
a See ISO 9854	4-1:2023, Table 1.		-				

Table 4 — PP-H, PP-B, PP-R and PP-RCT pipes

]	Pipe dimension				Test temperature			
$d_{ m n}$	0		Specimen	Specimen	Impact energy	°C		
	$e_{\rm n}$	Sample cut direction	type ^a	supports	I	PP-H	PP-B, PP-R	
mm	mm				,	РР-П	and PP-RCT	
<25	All		1	ISO 9854- 1:2023, Figure 1		23 ± 2		
≥25 ^b but <75	≤4,2	longitudinal	2	ISO 9854- 1:2023, Figure 2	15			
≥25 ^b but <75	>4,2 but ≤10,5		3	ISO 9854- 1:2023, Figure 2			0 ± 2	
≥75	>4,2 but ≤10,5		3	ISO 9854- 1:2023, Figure 2				

NOTE When the wall thickness of the pipe is greater than 10,5 mm, Method B is preferred.

^a See ISO 9854-1:2023, Table 1.

For d_n 25 pipes, product standards can define different specimen type for pipe impact test based on application.

Table 4 (continued)

]	Pipe dimension				Test temperature		
d	0		Specimen	Specimen	Impact energy	°C	
$d_{\rm n}$	$e_{ m n}$	Sample cut direction	type ^a	supports	ī	DD II	PP-B, PP-R
mm	mm	uncetion			J	PP-H	and PP-RCT
≥75 but <160	>4,2 but ≤10,5		4	ISO 9854-			
≥160	>9,5 but ≤10,5	circumferential	5	1:2023, Figure 3			

NOTE When the wall thickness of the pipe is greater than 10,5 mm, Method B is preferred.

4.2 Method B

4.2.1 General

For testing in accordance with ISO 9854-1, the values or options for the test parameters shall conform to those specified in Tables 5, 6, 7, 8 or 9, and with 4.2.2, 4.2.3, 4.2.4, 4.2.5 or 4.2.6, as appropriate, depending on the material from which the pipe is made, and its size.

PVC-U, PVC-HI and PVC-O pipes PREVIEW 4.2.2

See Table 5.

4.2.3 PVC-C pipes

See <u>Table 6</u>.

4.2.4 **ABS** and **ASA** pipes

See Table 7.

4.2.5 PP-H, PP-B, PP-R and PP-RCT pipes

See <u>Table 8</u>.

4.2.6 PE pipes

See Table 9.

Table 5 — PVC-U and PVC-HI and PVC-O pipes

_	Pipe di	mensions			Te	est temperatu	re
Impact direction	$d_{\rm n}$	$e_{\rm n}$	Specimen type ^a	Specimen sup- ports		°C	
uncetion	mm	mm	type	ports	PVC-U	PVC-HI	PVC-O
Flatwise		≤6	6	ISO 9854-			
riatwise	A 11	>6	7	1:2023, Figure 4	23 ± 2 , or	0 ± 2 , or	0 ± 2, or
Edgazziaa	All	≤6	8	ISO 9854-	0 ± 2	-20 ± 2	-20 ± 2
Edgewise		>6	9	1:2023, Figure 4			
a See ISO 98	54-1:2023,	Table 1.					

See ISO 9854-1:2023, Table 1.

For d_n 25 pipes, product standards can define different specimen type for pipe impact test based on application.