



Designation: D3350 – 10a

Standard Specification for Polyethylene Plastics Pipe and Fittings Materials¹

This standard is issued under the fixed designation D3350; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers the identification of polyethylene plastic pipe and fittings materials in accordance with a cell classification system. It is not the function of this specification to provide specific engineering data for design purposes, to specify manufacturing tolerances, or to determine suitability for use for a specific application.

1.2 Polyethylene plastic materials, being thermoplastic, are reprocessible and recyclable (Note 2). This specification allows for the use of those polyethylene materials, provided that all specific requirements of this specification are met.

NOTE 1—The notes in this specification are for information only and shall not be considered part of this specification.

NOTE 2—See Guide D5033 for information and definitions related to recycled plastics.

1.3 The values stated in SI units are to be regarded as standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 3—There is no known ISO equivalent to this standard.

1.5 For information regarding molding and extrusion materials see Specification D4976. For information regarding wire and cable materials see Specification D1248.

2. Referenced Documents

2.1 ASTM Standards:²

- D618 Practice for Conditioning Plastics for Testing
- D638 Test Method for Tensile Properties of Plastics
- D746 Test Method for Brittleness Temperature of Plastics and Elastomers by Impact
- D790 Test Methods for Flexural Properties of Unreinforced

¹ This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials.

Current edition approved Nov. 15, 2010. Published January 2011. Originally approved in 1974. Last previous edition approved in 2010 as D3350 - 10. DOI: 10.1520/D3350-10A.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- and Reinforced Plastics and Electrical Insulating Materials
 - D792 Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement
 - D883 Terminology Relating to Plastics
 - D1238 Test Method for Melt Flow Rates of Thermoplastics by Extrusion Plastometer
 - D1248 Specification for Polyethylene Plastics Extrusion Materials for Wire and Cable
 - D1505 Test Method for Density of Plastics by the Density-Gradient Technique
 - D1603 Test Method for Carbon Black Content in Olefin Plastics
 - D1693 Test Method for Environmental Stress-Cracking of Ethylene Plastics
 - D1898 Practice for Sampling of Plastics³
 - D2837 Test Method for Obtaining Hydrostatic Design Basis for Thermoplastic Pipe Materials or Pressure Design Basis for Thermoplastic Pipe Products
 - D2839 Practice for Use of a Melt Index Strand for Determining Density of Polyethylene
 - D3892 Practice for Packaging/Packing of Plastics
 - D4218 Test Method for Determination of Carbon Black Content in Polyethylene Compounds By the Muffle-Furnace Technique
 - D4703 Practice for Compression Molding Thermoplastic Materials into Test Specimens, Plaques, or Sheets
 - D4883 Test Method for Density of Polyethylene by the Ultrasound Technique
 - D4976 Specification for Polyethylene Plastics Molding and Extrusion Materials
 - D5033 Guide for Development of ASTM Standards Relating to Recycling and Use of Recycled Plastics³
 - F1473 Test Method for Notch Tensile Test to Measure the Resistance to Slow Crack Growth of Polyethylene Pipes and Resins
- 2.2 ISO Standard:
- ISO 12162 Thermoplastic Materials for Pipes and Fittings for Pressure Applications—Classification and Designation—Overall Service (Design) Coefficient

3. Terminology

3.1 Definitions:

³ Withdrawn. The last approved version of this historical standard is referenced on www.astm.org.

*A Summary of Changes section appears at the end of this standard.

3.1.1 Terms as described in Terminology **D883** shall apply in this specification.

3.1.2 *polyethylene plastics*—as defined by this specification, plastics or resins prepared by the polymerization of no less than 85 % ethylene and no less than 95 % of total olefins with additional compounding ingredients.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *materials*—polyethylene (PE) resins with the added compounding ingredients.

3.2.2 *PE compounds*—has the same meaning as PE plastics materials, compounds, and plastics.

3.3 Historical usage and user group conventions have resulted in inconsistent terminology used to categorize and describe polyethylene resins and compounds. The following terminology is in use in ASTM specifications pertaining to polyethylene:

3.3.1 *Specification D1248:*

3.3.1.1 Type (0, I, II, III, IV) = density ranges (same, respectively, as Class in Specification **D4976**).

3.3.1.2 Class (A, B, C, D) = composition and use.

3.3.1.3 Category (1, 2, 3, 4, 5) = melt index ranges (same as Grade in Specification **D4976**).

3.3.1.4 Grade (E, J, D, or W followed by one or two digits) = specific requirements from tables.

3.3.2 *Specification D3350:*

3.3.2.1 Type (I, II, III) = density ranges (same as Types I, II, and III in Specification **D1248** and Classes 1, 2, and 3 in Specification **D4976**).

3.3.2.2 Class = a line callout system consisting of “PE” followed by six cell numbers from Table 1 plus a letter (A, B, C, D, E) denoting color and UV stabilizer.

3.3.2.3 Grade = simplified line callout system using “PE” followed by density and slow crack growth cell numbers from Table 1.

3.3.3 *Specification D4976:*

3.3.3.1 Group (1, 2) = branched or linear polyethylene.

3.3.3.2 Class (0, 1, 2, 3, 4) = density ranges (same, respectively, as Type in Specification **D1248**).

3.3.3.3 Grade (1, 2, 3, 4, 5) = melt index ranges (same as Category in Specification **D1248**).

4. Classification

4.1 Polyethylene plastic pipe and fittings compounds are classified in accordance with density, melt index, flexural modulus, tensile strength at yield, slow crack growth resistance, and hydrostatic strength classification in **Table 1**.

NOTE 4—It has been a long-standing practice to use the following terms in describing polyethylene plastics:

Type I (0.910 to 0.925) = Low Density

Type II (0.926 to 0.940) = Medium Density

TABLE 1 Primary Properties^A—Cell Classification Limits

Property	Test Method	0	1	2	3	4	5	6	7	8
1. Density, g/cm ³	D1505	Unspecified	0.925 or lower	>0.925-0.940	>0.940-0.947	>0.947-0.955	>0.955	Specify Value
2. Melt index	D1238	Unspecified	>1.0	1.0 to 0.4	<0.4 to 0.15	<0.15	^B	Specify Value
3. Flexural modulus, MPa (psi)	D790	Unspecified	<138 (<20 000)	138-276 (20 000 to <40 000)	276-552 (40 000 to 80 000)	552-758 (80 000 to 110 000)	758-1103 (<1103 to <160 000)	>1103 (>160 000)	...	Specify Value
4. Tensile strength at yield, MPa (psi)	D638	Unspecified	<15 (<2200)	15-<18 (2200-<2600)	18-<21 (2600-<3000)	21-<24 (3000-<3500)	24-<28 (3500-<4000)	>28 (>4000)	...	Specify Value
5. Slow Crack Growth Resistance										
I. ESCR	D1693	Unspecified	A	B	C	C	Specify Value
a. Test condition (100% Igepal.)			48	24	192	600				
b. Test duration, h			50	50	20	20				
c. Failure, max, %	F1473	Unspecified	10	30	100	500	Specify Value
II. PENT (hours)		Unspecified	10	30	100	500	Specify Value
Molded plaque, 80°C, 2.4 MPa		Unspecified	10	30	100	500	Specify Value
Notch depth, F1473 , Table 1		Unspecified	10	30	100	500	Specify Value
6. Hydrostatic Strength Classification										
I. Hydrostatic design basis, MPa (psi), (23°C)	D2837	NPR ^C	5.52 (800)	6.89 (1000)	8.62 (1250)	11.03 (1600)	Specify Value
II. Minimum required strength, MPa (psi), (20°C)	ISO 12162	8 (1160)	10 (1450)	...	Specify Value


^ACompliance with physical properties in accordance with Section 8 is required including requirements for cell classification, color, and ultraviolet (UV) stabilizer, thermal stability, brittleness temperature, density, tensile strength at yield, and elongation at break.

^B Refer to 10.1.4.1.

^C NPR = Not Pressure Rated.

Type III (0.941 to 0.965) = High Density

NOTE 5—The manner in which materials are identified in the cell classification is illustrated for Class PE233424B as follows (refer also to Table 1 and 6.2):



4.2 Materials used in polyethylene plastic pipe and fittings shall use a cell-type format for the identification, close characterization, and specification of material properties. The information from the format is to be used alone or in combination.

NOTE 6—This type format, however, is subject to possible misapplication since unobtainable property combinations can be selected if the user is not familiar with commercially available materials. The manufacturer should be consulted. Additionally, the appropriate ASTM standard specification should be reviewed to assure materials utilized will meet all the material and piping requirements as specified in the standard.

4.3 Grade—A code for polyethylene pipe and fittings materials that consists of the two letter abbreviation for polyethylene (PE) followed by two numbers that designate the density cell (Property 1) and the slow crack growth resistance cell (Property 5), as defined by either Test Method F1473 or Test Method D1693, of the thermoplastic, as specified in Table 1. For the requirements of Property 5 (slow crack growth resistance), consult the materials section of the appropriate ASTM standard specification for the end-use application.

NOTE 7—Grade designations were adapted from Specification D1248 - 84 prior to the removal of pipe material from D1248 - 84. Former Specification D1248 - 84 grades for PE pipe materials were P14, P23, P24, P33, and P34. Equivalent Specification D3350 grade designations for these materials are PE11, PE20, PE23, PE30, and PE33, respectively.

5. Materials and Manufacture

5.1 The molding and extrusion material shall be polyethylene plastic in the form of powder, granules, or pellets.

5.2 The molding and extrusion materials shall be as uniform in composition and size and as free of contamination as is achieved by good manufacturing practice. If necessary, the level of contamination may be agreed upon between the manufacturer and the purchaser.

5.3 When specified, the color and translucence of molded or extruded pieces formed, under the conditions specified by the manufacturer of the materials, shall be comparable within commercial match tolerances to the color and translucence of standard samples supplied in advance by the manufacturer of the material.

6. Physical Properties

6.1 Cell Classification—Test values for specimens of the PE material prepared as specified in Section 9 and tested in accordance with Section 10 shall conform to the requirements given in Table 1. A typical property value for a PE material is to be the average value from testing numerous lots or batches and determines the cell number. When, due to manufacturing tolerances and testing bias, individual lot or batch values fall into the adjoining cell, the individual value shall not be considered acceptable unless the user, or both the user and the producer, determine that the individual lot or batch is suitable for its intended purpose.

6.2 Color and Ultraviolet (UV) Stabilizer—The color and UV stabilization shall be indicated at the end of the cell classification by means of a letter designation in accordance with the following code:

Code Letter	Color and UV Stabilizer
A	Natural
B	Colored
C	Black with 2 % minimum carbon black
D	Natural with UV stabilizer
E	Colored with UV stabilizer

6.3 Thermal Stability—The PE material shall contain sufficient antioxidant so that the minimum induction temperature shall be 220°C when tested in accordance with 10.1.9.

6.4 Brittleness Temperature—The brittleness temperature shall not be warmer than -60°C when tested in accordance with Test Method D746.

6.5 Density—The density used to classify the material shall be the density of the PE base resin (uncolored PE) determined in accordance with 10.1.3. When the average density of any lot or shipment falls within ±0.002 g/cm³ of the nominal value, it shall be considered as conforming to the nominal value and to all classifications based on the nominal value.

6.5.1 For black compounds, containing carbon black, determine the density, *Dp*, and calculate the resin density, *Dr*, as follows:

$$Dr = Dp - 0.0044C$$

where:

C = weight percent of carbon black.

6.5.2 For colored compounds, the nominal density of the base resin shall be provided by the manufacturer, on request.

6.6 Tensile Strength at Yield—The tensile strength at yield used to classify the material shall be the tensile strength at yield of the PE resin determined in accordance with 10.1.6. When the average tensile strength at yield of any lot or shipment falls within ±3.45 MPa (±500 psi) of the nominal value, it shall be considered as conforming to the nominal value and to all classifications based on the nominal value.

6.7 Elongation at Break—As tested in accordance with 10.1.6, all pressure rated materials shall have a minimum extension at break of 400 %.

7. Sampling

7.1 A batch or lot shall be considered as a unit of manufacture and shall consist of one production run or as a blend of two or more production runs of material.