



Designation: ~~C979-05~~ Designation: C979/C979M - 10

## Standard Specification for Pigments for Integrally Colored Concrete<sup>1</sup>

This standard is issued under the fixed designation C979/C979M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This specification covers the basic requirement for colored and white pigments in powder form to be used as admixtures in concrete for the purpose of producing integrally colored concrete. Where the pigments are a constituent of a multicomponent admixture, this specification applies to the pigment constituent of the admixture. This specification is not intended to establish compatibility of pigments with any other concrete admixtures unless they are tested in combination in accordance with 3.74.7.

1.2 This specification does not include the determination of pigment stability when elevated temperature using low-pressure (atmospheric) or high-pressure (autoclave) steam is used to accelerate the curing process.

1.3 In addition to tests defining the pigments themselves, a limited number of tests on concrete are included to define the effects on setting times, air content, and compressive strength. If more extensive information is required for a particular job, additional testing criteria and procedures should be agreed upon between the seller and user.

1.4 The maximum prescribed dosage rate of a pigment, established in accordance with 3.74.7, shall be equal to or less than 10 mass % of cement. When a combination of pigments is used to produce the desired color and color intensity, the total dosage rate of all pigments combined shall not exceed any of the individual maximum dosage rates of the component pigments.

~~1.5 The values stated in SI units are to be regarded as the standard. The inch-pound units in parentheses are for information purposes only.~~

~~1.5 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard. Some values have only SI units because inch-pound equivalents are not used in practice.~~

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

C33 Specification for Concrete Aggregates

C39/C39M Test Method for Compressive Strength of Cylindrical Concrete Specimens

C125 Terminology Relating to Concrete and Concrete Aggregates

C143/C143M Test Method for Slump of Hydraulic-Cement Concrete

C150 Specification for Portland Cement

C173/C173M Test Method for Air Content of Freshly Mixed Concrete by the Volumetric Method

C192/C192M Practice for Making and Curing Concrete Test Specimens in the Laboratory

C231 Test Method for Air Content of Freshly Mixed Concrete by the Pressure Method

C260 Specification for Air-Entraining Admixtures for Concrete

C403/C403M Test Method for Time of Setting of Concrete Mixtures by Penetration Resistance

D50 Test Methods for Chemical Analysis of Yellow, Orange, Red, and Brown Pigments Containing Iron and Manganese

D1208 Test Methods for Common Properties of Certain Pigments

D1535 Practice for Specifying Color by the Munsell System

G23 Practice for Operating Light-Exposure Apparatus (Carbon-Arc Type) With and Without Water for Exposure of Nonmetallic Materials<sup>3</sup>

#### 2.2 ACI Standards:

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.23 on Chemical Admixtures.

Current edition approved Jan-Dec. 1, 2005-2010. Published January 2005-2011. Originally approved in 1982. Last previous edition approved in 2004-2005 as C979 - 045. DOI: 10.1520/C0979\_C0979M-105.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Withdrawn. The last approved version of this historical standard is referenced on www.astm.org.

211.1 Recommended Practice for Selecting Proportions for Normal and Heavyweight Concrete<sup>4</sup>**3. Terminology****3.1 Definitions:**

3.2 For definitions of terms used in this specification, refer to Terminology C125.

**4. General Requirements**

3.1

4.1 *Water Wettability*—The pigment shall be water wettable when tested in accordance with 7.48.1.

3.2

4.2 *Alkali Resistance*—The pigment treated with sodium hydroxide shall not show any significant (Note 1) change of color when tested in accordance with 7.28.2.

3.3

4.3 *Total Sulfates*—Calculated as SO<sub>3</sub>, the sulfates shall not exceed 5.0 mass % of the original pigment sample when tested in accordance with 7.38.3.

3.4

4.4 *Water Solubility*—The total matter soluble in water shall not exceed 2.0 mass % of the original pigment sample when tested in accordance with 7.48.4.

3.5

4.5 *Atmospheric Curing Stability*—The magnitude of color differences between pigmented concrete specimens cured in dry air and those cured at high relative humidity when tested in accordance with 7.58.5 shall not be greater than the magnitude of the color difference between two unpigmented specimens cured under the same conditions.

3.6

4.6 *Light Resistance*—The exposed portions of the specimens shall show no significant differences (Note 1) in color from the unexposed portions when tested in accordance with 7.68.6. While a pigment that fails this test shall not be considered light resistant, a pigment that passes this test may still be subject to fading when exposed to natural weathering conditions.

NOTE 1—A significant difference is defined as one that is readily perceptible by visual observation without close examination. Lighting and viewing conditions as described in Practice D1535, 6.1, may be used.

3.7

**4.7 Effects on Concrete:**

34.7.1 When compared with the control mixture, the concrete that is pigmented at the maximum prescribed dosage rate shall have a 28-day compressive strength of not less than 90 % and a water-cement ratio of not greater than 110 % of that of the control mixture when prepared and tested in accordance with 7.78.7 (Note 2).

34.7.2 The pigment, when added to a concrete mixture at the maximum prescribed dosage rate, shall neither accelerate the initial or final set by more than 1 h nor retard the initial or final set by more than 1½ h, as compared to the uncolored concrete control mixture when tested in accordance with 7.78.7 (Note 2).

34.7.3 Using the same quantity of air-entraining admixture, the pigments, when added to a concrete mixture at the maximum prescribed dosage rate, shall not change the air content by more than 1.0 %, as compared to the uncolored control mixture when tested in accordance with 7.78.7.

NOTE 2—These values include allowance for normal variations in test results. The object of the 90 % compressive-strength requirement is to require a level of performance of the pigmented concrete comparable to that of the reference concrete when tested in accordance with 7.78.7.

3.8

4.8 *Color Match of Shipment*—The color produced by the shipment of pigment shall not be significantly different (Note 1) from the color produced by the standard supplied by the pigment manufacturer when samples of both the shipment and the standard are tested in accordance with 7.88.8. New concrete specimens containing the standard sample of the particular pigment must be prepared whenever a new shipment is evaluated. This is necessary to eliminate color variations caused by any of the other mortar ingredients, specimen preparation, or curing.

**4. Rejection**

4.1 The purchaser has the right to reject material that does not conform to the requirements of this specification. Rejection shall be reported to the producer or supplier in writing.

4.2 Individual packages or containers varying more than 5% from the stated mass may be rejected. If the average weight of 50 packages taken at random is less than that stated, the entire shipment may be rejected.

**5. Packaging**

5.1 Packages or containers shall be clearly marked as to color designation and the net mass.

<sup>4</sup> Available from American Concrete Institute (ACI), P.O. Box 9094, Farmington Hills, MI 48333-9094, <http://www.concrete.org>.

~~5.2 The package or container for the pigment, only when so designated by the manufacturer, shall be added to the concrete batch, provided that it is composed of disintegrating paper or soluble material which, when tested as a unit (pigment and packaging), conforms to all requirements of this specification. Rejection~~

~~5.1 The purchaser has the right to reject material that does not conform to the requirements of this specification. Rejection shall be reported to the producer or supplier in writing.~~

~~5.2 Individual packages or containers varying more than 5 % from the stated mass may be rejected. If the average weight of 50 packages taken at random is less than that stated, the entire shipment may be rejected.~~

## **6. Packaging**

~~6.1 Packages or containers shall be clearly marked as to color designation and the net mass.~~

~~6.2 The package or container for the pigment, only when so designated by the manufacturer, shall be added to the concrete batch, provided that it is composed of disintegrating paper or soluble material which, when tested as a unit (pigment and packaging), conforms to all requirements of this specification.~~

## **7. Materials for Tests**

~~6.1~~

~~7.1 *Cement*—For the atmospheric curing stability and the light resistance tests, using white cement is suggested. The cement used in all other tests shall be either a Type I or Type II cement conforming to Specification C150 or the cement proposed for specific work.~~

~~6.2~~

~~7.2 *Aggregates*—The aggregates used in all tests shall conform to Specification C33 or shall be the aggregates proposed for specific work. For the atmospheric curing stability and the light resistance tests, clean silica sand shall be used. For both the reference and the pigmented mixtures, the aggregate grading shall be controlled by determining the mass of separate fractions.~~

~~6.3~~

~~7.3 *Admixtures*—If any of the test mixtures contain any admixtures in addition to pigment other than an air-entraining admixture complying with Specification C260, the pigment shall be considered to comply with this specification only when used in conjunction with such other admixture(s).~~

~~7.~~

## **8. Test Methods**

~~7.1~~

~~8.1 *Water Wettability*—Add 10.0 g of the pigment to 150 mL of deionized water in a 250-mL beaker. If the pigment does not readily mix with the water when stirred with a spatula, but instead a substantial portion of the pigment floats on the surface of the water, the pigment is repellent and not water wettable.~~

~~7.28.2 *Alkali Resistance*—Add two 10.0 g-portions of the pigment to separate 250-mL beakers, each containing 150 mL of deionized water. Stir until thoroughly mixed. Add 10 mL of 10 mass % sodium hydroxide solution to one beaker, and stir thoroughly once more. Let the slurries stand 1 h, then remix and filter on separate Buchner funnels. Wash the filter cake with three replacement washes of hot deionized water. Dry the cake on the filter paper in an oven at  $110 \pm 3$  °C ( $230 \pm 5$  °F) for  $4 \pm 0.5$  h. Remove from the oven, cool, and crush the pigment into a fine powder in a mortar. Make two small adjacent piles of the pigment powders and press them flat with a spatula. Compare the color of the control and treated pigment powders.~~

~~7.38.3 *Percentage of SO<sub>3</sub>*—Perform the sulfates soluble in hydrochloric acid test and determine the percentage in accordance with Test Methods D50.~~

~~7.4~~

~~8.4 *Water Solubility*—Perform the matter soluble in water test in accordance with Test Methods D1208.~~

~~7.5~~

~~8.5 *Atmospheric Curing Stability*—The composition and method of preparation of the test specimens shall be in accordance with Annex A1. Pigments shall be tested at both ½ % and 6 % levels (based on the cement mass). Two sets of specimens (designated as control specimens and test specimens) shall be prepared at the same time under identical conditions except for curing. Each set shall consist of two pigmented mortar specimens, one at each of the two levels of pigmentation, and one unpigmented specimen. If, for a particular pigment being tested, the specimens that contain the pigment at a dosage rate of ½ % of the cement mass do not provide a significant difference (Note 1) in color when compared to the corresponding unpigmented specimen, the pigment dosage rate shall be increased until but not beyond the rate at which the difference in color becomes significant. In addition, tests using the higher dosage rate of 6 % of the cement mass shall continue to be performed as specified. Compare for color the specimens that were cured under different conditions. For evaluating the color stability of the pigment tested, also compare the uncolored mortar specimens for color variations. Differences in the curing conditions or efflorescence, or both, can affect the color shade of any finished mortar or concrete, either colored or uncolored.~~

~~7.6~~

~~8.6 *Light Resistance*—The test shall be conducted in a Type E or EH exposure apparatus as described in Practice G23. Type EH apparatus shall be operated without automatic humidity control. The exposure apparatus shall be operated in accordance with~~