

DRAFT INTERNATIONAL STANDARD

ISO/DIS 2810

ISO/TC 35/SC 9

Secretariat: BSI

Voting begins on:
2019-11-18

Voting terminates on:
2020-02-10

Paints and varnishes — Natural weathering of coatings — Exposure and assessment

Peintures et vernis — Vieillissement naturel des revêtements — Exposition et évaluation

ICS: 87.040

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/a175498d-febc-4ec2-bab2-bcb853a24b3b/iso-fdis-2810>

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 2810:2019(E)

© ISO 2019

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Full standard:
<https://standards.iteh.ai/catalog/standards/sist/a175498d-febc-4ec2-bab2-bcb853a24b3b/iso-fdis-2810>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 General	2
5 Exposure racks	3
6 Apparatus for measurement of climatic factors	4
6.1 Measurement of solar radiation	4
6.1.1 Pyranometers	4
6.1.2 Pyrheliometers	4
6.1.3 Total-ultraviolet radiometers	4
6.1.4 Narrow-band ultraviolet radiometers	4
6.2 Other climate-measuring instruments	5
7 Test specimens	5
8 Procedure	6
9 Supplementary test conditions	6
10 Evaluation of properties	7
11 Precision	7
12 Test report	7
Annex A (normative) Environment and climate	9
Annex B (informative) Classification of climates	11
Bibliography	12

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

This third edition cancels and replaces the second edition (ISO 2810:2004). The main changes compared to the previous edition are as follows:

- The list in 4b) has been amended by radiant exposure and temperature;
- The time of wetness has been deleted from the list of additional observations on climate in [A.2](#) and replaced by a note with the reference to ASTM Practice G84;
- The text has been editorially revised and the normative references have been updated.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Paints and varnishes — Natural weathering of coatings — Exposure and assessment

1 Scope

This document specifies the conditions which need to be taken into consideration in the selection of the type of natural weathering and the natural weathering procedure to be used to determine the resistance of coatings or coating systems (direct weathering or weathering behind window glass).

Natural weathering is used to determine the resistance of coatings or coating systems (denoted in the following text simply by coatings) to the sun's radiation and the atmosphere.

Special atmospheric influences, e.g. industrial pollution, are not taken into account in this document.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1514, *Paints and varnishes — Standard panels for testing*

ISO 2808, *Paints and varnishes — Determination of film thickness*

ISO 2813, *Paints and varnishes — Determination of gloss value at 20 degrees, 60 degrees and 85 degrees*

ISO 3668, *Paints and varnishes — Visual comparison of colour of paints*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 4618, *Paints and varnishes — Terms and definitions*

ISO 4628-1, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 1: General introduction and designation system*

ISO 4628-2, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 2: Assessment of degree of blistering*

ISO 4628-3, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 3: Assessment of degree of rusting*

ISO 4628-4, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 4: Assessment of degree of cracking*

ISO 4628-5, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 5: Assessment of degree of flaking*

ISO 4628-6, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 6: Assessment of degree of chalking by tape method*

ISO 4628-8, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 8: Assessment of degree of delamination and corrosion around a scribe or other artificial defect*

ISO 4628-10, *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance — Part 10: Assessment of degree of filiform corrosion*

ISO 18314-1, *Analytical colorimetry — Part 1: Practical colour measurement*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 4618 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <http://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 durability

ability of a specimen to resist the deleterious effect of its environment

3.2 time of wetness

period during which an exposed coating has surface moisture present on it

4 General

The durability of a coating during natural weathering depends on how, where and when the coating is weathered. Therefore, these parameters and the intended use of the coating shall be taken into account when exposures are carried out.

In particular, the following parameters shall be considered:

- a) the location of the exposure site, for example industrial, marine, rural. In choosing sites, those which differ markedly in the type or level of pollution from the normal shall be avoided, unless they are appropriate to the intended end use of the coating under test;
- b) the height, angle and orientation of the exposure rack. These parameters will govern the extent to which the specimens are affected, for example by radiant exposure, temperature, dew, frost and atmospheric pollutants;
- c) the nature of the terrain on which the rack is constructed (for example concrete, grass, gravel). The terrain may affect the climatic conditions around the specimen under test. It would rarely be feasible to select an ideal terrain in practice, but the effect of such variations in climatic conditions will be minimized by ensuring that all specimens are situated sufficiently high above the ground (see [Clause 5](#));
- d) whether the performance of the coating on the front and/or the back of the specimen is of interest. Certain types of degradation, for example rust formation and/or mould growth, are frequently more severe on the shaded parts of the specimen;
- e) the intended use of the coating, including its substrate, and whether the coating is to be washed or polished in service.

The results of tests on an exposure rack will apply precisely only to the environment in which they were obtained.

Provided that the test conditions are reasonably appropriate to the intended end use, the relative performance of a number of coatings tested at the same time will enable valid deductions to be drawn. It is recommended that each series of specimens under evaluation include coatings of known performance to act as reference standards.

The results of natural weathering may vary according to the time of year during which the tests are carried out. The influence of these variations will be reduced if the exposure period is sufficiently long. The exposure period should be at least one year, or a multiple of one year. The reproducibility of the results will be improved if the exposure period always starts at the same time of year, preferably in spring.

Natural weathering tests are normally carried out for a fixed period of time. However, in many cases it is preferable to define the test period in terms of a certain degree of degradation or by the radiant exposure (dosage) of solar radiation to which the specimen is to be subjected (see [Clause 6](#)). The latter procedure may reduce the influence of seasonal variations but does not eliminate it.

Radiant exposure may be determined by measurement of irradiance, and integration of the measurements over the period of natural weathering.

The climatic conditions shall be monitored and a complete record reported, together with the other conditions of weathering.

Care is required in the selection of test specimens of substrates with variable (anisotropic) properties, for example wood or steel. In these cases, replication of the tests is essential if misleading results are to be avoided.

Washing and polishing during exposure will affect the durability of the coating. It shall therefore be mentioned in the test report.

5 Exposure racks

Unless otherwise specified or agreed, use exposure racks on which the specimens are facing towards the equator. The specimens shall be firmly held on the racks by attachments made of stainless steel or other corrosion-resistant material, in such a manner that they are mechanically stressed as little as possible.

The exposure racks shall be constructed so that the atmosphere has free access to the specimens and that water that drains from one specimen does not drain onto another. In addition, the racks may be designed so that a portion of the specimens can be covered to allow evaluation between an exposed and a masked area. By using special devices, particular conditions may be simulated, for example by using a "black box" in accordance with SAE J 1976 to simulate automotive conditions, or backing the test panel with plywood or other insulation material to simulate building side wall or roof area conditions.

Metal substrates for corrosion tests shall not be in electrical contact with metals during the exposure period or, as far as possible, in direct contact with wood or other porous materials. If specimens are supported in grooves, suitable drainage holes shall be provided to prevent accumulation of water.

Unless otherwise stated, the racks shall be constructed so that all specimens are supported either at a minimum height of 0,45 m above the ground or at a height sufficient to avoid contact with vegetation and to prevent damage.

The area beneath and in the vicinity of the racks shall be characterized by low reflectance and by ground cover typical of that climatological area. In desert areas, the racks shall be located on gravel, in most temperate areas on low-cut grass.

Usually the panels are supported at an angle of 45° to the horizontal. Depending on the intended end use of the coating, other angles may be agreed, for example 5° for automotive finishes or roof coatings, or vertical exposure for textured wall finishes. When testing corrosion performance, it is appropriate to expose specimens vertically facing away from the equator as well as inclined at 45° and 5° facing towards the equator (see EN 13523-19). Specimens facing away from the equator will remain wet for

longer periods since they dry less rapidly than those exposed facing towards the equator. This will lead to a higher tendency to corrode.

The racks shall be situated so that, at a sun height of 20° and more, no shadow falls on to the specimens.

When testing the durability of coatings for interior use which are exposed to radiation which has passed through window glass, racks that are covered by a window pane are used. Since, depending on the quality, the transmission of window glass in the UV range is different, the type of window glass shall be agreed upon between the interested parties for each particular case (see [Clause 9](#)).

6 Apparatus for measurement of climatic factors

6.1 Measurement of solar radiation

6.1.1 Pyranometers

Pyranometers are radiometers used to measure the total solar radiant energy incident upon a surface per unit time per unit area.

The energy measured includes direct and diffuse radiant energy as well as radiant energy reflected from the background.

Pyranometers shall meet at least the requirements for a Second Class instrument as defined by the World Meteorological Organization (WMO). In addition, pyranometers shall be calibrated at least annually, and their calibration factor shall be traceable to the World Radiometric Reference (WRR) (see WMO Publication No. 8, Chapter 9).

6.1.2 Pyrhemimeters

Pyrhemimeters are radiometers used to measure the direct (beam) solar irradiance incident on a surface normal to the sun's rays.

The energy measured excludes diffuse radiant energy as well as radiant energy reflected from the background.

Pyrhemimeters shall meet at least the requirements for a First Class instrument as defined by the World Meteorological Organization (WMO). In addition, pyrhemimeters shall be calibrated at least annually, and their calibration factor shall be traceable to the World Radiometric Reference (WRR) (see WMO Publication No. 8).

6.1.3 Total-ultraviolet radiometers

When used to define exposure stages, total-ultraviolet radiometers shall have a passband that maximizes the acceptance of radiation in the 300 nm to 400 nm, 295 nm to 385 nm, or any other commonly used total-ultraviolet wavelength region, and they shall be cosine-corrected to include ultraviolet sky radiation. Commercially available total-ultraviolet radiometers require annual calibration checks if they are deployed between latitudes 40° north and 40° south. Outside these latitudes, annual calibration is not a requirement, but it is considered satisfactory.

6.1.4 Narrow-band ultraviolet radiometers

When used to define exposure stages, narrow-band ultraviolet radiometers shall be cosine-corrected if used in conjunction with either natural fixed-angle or glass-filtered exposures. They shall be calibrated following the manufacturer's instructions.

6.2 Other climate-measuring instruments

Instrumentation required for the measurement of air temperature, specimen surface temperature, relative humidity, rainfall, time of wetness, and sunshine hours shall be appropriate to the exposure method used, and shall be agreed upon between the interested parties.

7 Test specimens

The simplest and most widely used test specimen is a flat panel of the appropriate substrate, but much useful additional information may be obtained by carrying out exposure tests on structures. This is particularly true of wooden assemblies such as window frames, where coating performance at the joints is of interest. Design features which allow accumulation and entrapment of water may also lead to premature coating degradation. Therefore, test specimens should preferably be included which show the characteristics of such structures.

Unless otherwise agreed, use standard test panels complying with ISO 1514, with the area of the panels at least 0,03 m² and no side less than 100 mm long.

Coat the panels with the product(s) under test by the appropriate method and dry (or stove) each coat in the specified manner for the specified time, followed (if appropriate) by conditioning or ageing. Coat both faces and the edges of the panels with the product under test, unless the panel would not be so used in practice. Alternatively, the back and edges may be coated with a good-quality protective paint [see [Clause 4 d](#)].

If specified or agreed, particularly in the case of corrosion tests, provide uncoated areas on the specimen, preferably by one or more of the following methods:

- a) After the specified drying time and immediately before placing the specimens on the exposure rack, make a straight scratch or scribe mark through the coating to the substrate. To make the scratch, use an instrument with a hard tip. The scratch shall have a width of 0,2 mm to 1,0 mm, unless otherwise agreed. As the result of the test depends on e.g. the depth of the scratch and the scratching tool used, the details of how the scratch was made shall be stated in the test report.

NOTE Normally, vertical and/or horizontal lines are used. By agreement, diagonal criss-cross lines (a St. Andrew's cross) can be employed. However, in this case the coating may flake where the lines cross which makes evaluation, e.g. by image analysis, difficult.

- b) Before applying the product(s) under test, attach to the prepared specimen a strip of pressure-sensitive adhesive tape of agreed size at an agreed location. Coat the specimen in the normal way. Either directly after coating or immediately before placing on the exposure rack, carefully remove the tape. Clean off any residues of adhesive with a suitable solvent which does not affect the coating.

Determine the thickness, in micrometres, of the coating by using one of the non-destructive methods specified in ISO 2808. Provide the specimens with a suitable marking which is resistant to natural weathering.

The number of test specimens depends on

- the number of different properties to be investigated and the number of specimens required for each test method;
- the number of times each test method is to be carried out before, during and after weathering.

If not otherwise specified or agreed, the number of test specimens shall be not less than three.

The use of reference specimens of known durability and of composition similar to that of the test specimen is recommended.