

FINAL
DRAFT

INTERNATIONAL
STANDARD

ISO/FDIS
7711-1

ISO/TC 106/SC 4

Secretariat: DIN

Voting begins on:
2021-07-23

Voting terminates on:
2021-09-17

Dentistry — Diamond rotary instruments —

Part 1: General requirements

Médecine bucco-dentaire — Instruments rotatifs diamantés —

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Partie 1: Exigences générales

[ISO/FDIS 7711-1](#)

<https://standards.iteh.ai/catalog/standards/sist/e72876b5-a49-4c6c-b4d1-5083d0ae3040/iso-fdis-7711-1>

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/FDIS 7711-1:2021(E)

© ISO 2021

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO/FDIS 7711-1](https://standards.iteh.ai/catalog/standards/sist/e72876b5-a49-4c6c-b4d1-5083d0ae3040/iso-fdis-7711-1)

<https://standards.iteh.ai/catalog/standards/sist/e72876b5-a49-4c6c-b4d1-5083d0ae3040/iso-fdis-7711-1>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms, definitions and symbols	1
4 Symbols	2
5 Requirements	3
5.1 Material	3
5.1.1 Blank	3
5.1.2 Shank hardness	3
5.1.3 Working part	3
5.2 Designation, colour code, grit sizes	3
5.2.1 Designation	3
5.2.2 Colour code	3
5.2.3 Grit size distribution	4
5.2.4 Grit sizes	4
5.3 Dimensions	4
5.3.1 Designated dimensions of overall length	4
5.3.2 Designated dimensions of the shank	6
5.3.3 Dimensions of working part	6
5.4 Bending test to verify the instrument strength	7
5.4.1 Effect on run-out	7
5.4.2 Breaking test	7
5.5 Resistance to processing and reprocessing	8
6 Measurement and test methods	8
6.1 Sampling	8
6.2 Testing of the dimensions	8
6.3 Testing of the run-out	9
6.4 Testing of resistance to processing and reprocessing	9
6.4.1 Sampling	9
6.4.2 Equipment	9
6.4.3 Reagent	9
6.4.4 Preparation of the test piece	9
6.4.5 Procedure	9
6.5 Visual inspection	9
7 Marking and packaging	9
7.1 Marking on diamond rotary instruments	9
7.2 Labelling on the package	10
7.3 Instructions for use, processing and reprocessing	10
Bibliography	11

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 106, *Dentistry*, Subcommittee SC 4, *Dental instruments*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 55, *Dentistry*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition of ISO 7711-1 cancels and replaces the first edition (ISO 7711:1997) and the second edition (ISO 7711-3:2004), which have been technically revised.

The main changes compared to the previous edition are as follows:

- the references ISO 7711-3 in 7711-1 have been included;
- definitions have been added to [Clause 3](#);
- blank materials have been added in 4.1;
- tables for force values were removed.

A list of all parts in the ISO 7711 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Dentistry — Diamond rotary instruments —

Part 1: General requirements

1 Scope

This document specifies the general requirements and test methods for diamond rotary instruments used in dentistry, including designation, colour code and grit sizes and a quality control for these instruments.

It applies to all types of diamond rotary instruments independent of type and shape with exception to diamond discs, which are specified in ISO 7711-2.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1797:2017, *Dentistry — Shanks for rotary and oscillating instruments*

ISO 1942, *Dentistry — Vocabulary*

ISO 2157, *Dentistry — Nominal diameters and designation code numbers for rotary instruments*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 8325:2004, *Dentistry — Test methods for rotary instruments*

ISO 6106, *Abrasive products — Checking the grain size of superabrasives*

ISO 14457, *Dentistry — Handpieces and motors*

ISO 21850-1, *Dentistry — Materials for dental instruments — Part 1: Stainless steel*

3 Terms, definitions and symbols

For the purposes of this document, the following terms and definitions given in ISO 1942 and ISO 14457 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <https://www.electropedia.org/>

3.1

blank

supporting material for a rotary instrument consisting of a *shank* (3.5), neck (optional) and an uncoated *working part* (3.6)

Note 1 to entry: See [Figure 1](#).



Key

- 1 working part
- 2 neck
- 3 shank

Figure 1 — Blank

3.2 diamond rotary instrument

rotary instrument consisting of a *blank* (3.1) and a *working part* (3.6) coated with diamond grit

Note 1 to entry: See [Figure 2](#).



Key

- 1 working part
- 2 neck
- 3 shank

iTeh STANDARD PREVIEW
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/e72876b5-af49-4c6c-b4d1-5083d0ae3940/iso-fdis-7711-1>

Figure 2 — Diamond rotary instrument

3.3 macrogrit

grit with grit size distribution which is determined by sieving

3.4 microgrit

grit with grit size distribution which is determined by sedimentation

3.5 shank

part of the diamond instrument to be connected to a dental handpiece

3.6 working part

part of the diamond instrument with an active grinding surface

4 Symbols

The following symbols are used in this document:

d_1	diameter of the working part
d_2	diameter of the head diameter;
d_3	
D	minimum of neck diameter
F_1	test force for run-out
F_2	test force for breaking test
L	length from the tip to the minimum of neck diameter
L_2	overall length of the instrument
	NOTE The overall length of the instrument, L_2 , is the sum of the fitting length of the shank, the length of the neck and the length of the working part.

5 Requirements

5.1 Material

5.1.1 Blank

The stainless steel material for the blank of the diamond rotary instrument shall be in accordance with ISO 21850-1.

5.1.2 Shank hardness

ISO/FDIS 7711-1

The hardness of the shank shall comply with ISO 1797.

5.1.3 Working part

The working part shall be coated with diamond grit, bound in either metal or other suitable material at the discretion of the manufacturer.

The diamond grit may consist of natural or synthetic origin.

5.2 Designation, colour code, grit sizes

5.2.1 Designation

The fineness of the diamond grit used shall comply with the requirements in [Table 1](#).

5.2.2 Colour code

The colour code complements the designation. Usage of the colour code for mean grit size is optional and at the discretion of the manufacturer. If colour coding is used, the colours shall be those specified in [Table 1](#).

The location on the diamond instrument where the colour is applied may be on the shank or neck and is left at the discretion of the manufacturer.

5.2.3 Grit size distribution

5.2.3.1 Macrogrits

The method for determining or verifying the grit size distribution of macrogrits for diamonds used in the manufacture of industrial products (e.g. grinding wheels, saws) as specified in ISO 6106, for grit sizes between 1 180 µm and 41 µm, shall be used.

The series of diamond grit sizes is designated as D series (D 1 181 to D 46), where “D” denotes diamond.

NOTE Further information is given in References [13] and [15].

5.2.3.2 Microgrits

Currently no internationally accepted method for determining or verifying the grit size distribution of microgrits diamonds is available. Therefore, methods from regional standards or national standards are used.

The series of diamond grit sizes is designated as M series, where “M” denotes microgrit.

NOTE Further information is given in References [12] and [14].

5.2.4 Grit sizes

The grit sizes as specified in Table 1 shall be used for all types of diamond instruments.

The grit sizes and their classification in regard to their fineness are selected according to Table 1.

Because of the difficulty in separating grit sizes, overlapping areas are unavoidable and commonly accepted.

Columns 3 and 4 indicate colour codes and their equivalent grit size ranges, respectively.

Table 1 — Designation, colour code, grit sizes for diamond grits

Designation	Abbreviation	Colour code	Grit designation	Mean grit size ^a µm
ultra-fine	UF	white	M 4 to M 14	8
extra fine	EF	yellow	M 10 to M 36	25
fine	F	red	M 27 to D 76	46
medium	M	blue	D 64 to D 126	107
coarse	C	green	D 107 to D 181	151
very coarse	VC	black	D 151 to D 213	181

^a Mean grit size, in µm, is used for information in the communication to the dentist or dental technician.

NOTE Grit sizes >D 213 are acceptable in extraoral or laboratory use. Designation 'very coarse' can be also be designated as 'extra coarse' or 'super coarse'.

Overlapping of grit sizes may be allowed as dictated by the intended use of the instruments.

5.3 Dimensions

5.3.1 Designated dimensions of overall length

The overall length of the diamond rotary instrument, L_2 , is the sum of the fitting length of the shank, the neck and the length of the working part. "Standard" refers to instruments with standard fitting lengths of shank. For instruments with longer or shorter shank lengths, the overall length, L_2 , will vary accordingly. See ISO 1797 for fitting lengths of shanks.

The dimensions for Type 1 shall be according to ISO 1797:2017, Table 1.

If the manufacturer deviates from the overall length specified in Tables 2 to 5, it shall be ensured that the minimum fitting length of ISO 1797 is observed.

Table 2 — Overall length L_2 for instruments with length of working part up to 5 mm

Dimensions in millimetres

Designation	Overall length L_2		
Shank type	Type 1	Type 2	Type 3
Tolerance	$\pm 0,5$	$L_2 \leq 50: \pm 0,5$ $L_2 > 50: \pm 1$	$\pm 0,5$
short	$L_2 \leq 18,5$	—	$L_2 \leq 16,5$
standard	$18,5 < L_2 \leq 22,0$	$L_2 \leq 44,5$	$16,5 < L_2 \leq 19,0$
long	$22,0 < L_2 \leq 26,0$	$44,5 < L_2 \leq 64,5$	$19,0 < L_2 \leq 21,0$
extra long	$26,0 < L_2 \leq 34,0$	$64,5 < L_2 \leq 70,0$	$21,0 < L_2 \leq 25,0$

Table 3 — Overall length L_2 for instruments with working part length exceeding 5 mm and up to 7,5 mm

Dimensions in millimetres

Designation	Overall length L_2		
Shank type	Type 1	Type 2	Type 3
Tolerance	$\pm 0,5$	$L_2 \leq 50: \pm 0,5$ $L_2 > 50: \pm 1$	$\pm 0,5$
short	$L_2 \leq 18,5$	—	$L_2 \leq 18,5$
standard	$18,5 < L_2 \leq 22,0$	$L_2 \leq 44,5$	$18,5 < L_2 \leq 21,0$
long	$22,0 < L_2 \leq 26,0$	$44,5 < L_2 \leq 64,5$	$21,0 < L_2 \leq 23,0$
extra long	$26,0 < L_2 \leq 34,0$	$64,5 < L_2 \leq 70,0$	$23,0 < L_2 \leq 25,0$

Table 4 — Overall length L_2 for instruments with working part length exceeding 7,5 mm and up to 9 mm

Dimensions in millimetres

Designation	Overall length L_2		
Shank type	Type 1	Type 2	Type 3
Tolerance	$\pm 0,5$	$L_2 \leq 50: \pm 0,5$ $L_2 > 50: \pm 1$	$\pm 0,5$
short	$L_2 \leq 19,5$	—	$L_2 \leq 19,5$
standard	$19,5 < L_2 \leq 24,0$	$L_2 \leq 44,5$	$19,5 < L_2 \leq 22,0$
long	$24,0 < L_2 \leq 28,0$	$44,5 < L_2 \leq 64,5$	$22,0 < L_2 \leq 24,0$
extra long	$28,0 < L_2 \leq 34,0$	$64,5 < L_2 \leq 70,0$	$24,0 < L_2 \leq 25,0$

Table 5 — Overall length L_2 for instruments with working part length exceeding 9 mm and up to 12 mm

Dimensions in millimetres

Designation	Overall length L_2		
Shank type	Type 1	Type 2	Type 3
Tolerance	$\pm 0,5$	$L_2 \leq 50: \pm 0,5$ $L_2 > 50: \pm 1$	$\pm 0,5$
short	$L_2 \leq 23,5$	—	$L_2 \leq 21,5$

Table 5 (continued)

Designation	Overall length L_2		
	Type 1	Type 2	Type 3
Tolerance	$\pm 0,5$	$L_2 \leq 50: \pm 0,5$ $L_2 > 50: \pm 1$	$\pm 0,5$
standard	$23,5 < L_2 \leq 27,0$	$L_2 \leq 46,0$	$21,5 < L_2 \leq 24,0$
long	$27,0 < L_2 \leq 31,0$	$46,0 < L_2 \leq 64,5$	$24,0 < L_2 \leq 26,0$
extra long	$31,0 < L_2 \leq 34,0$	$64,5 < L_2 \leq 70,0$	$26,0 < L_2 \leq 30,0$

5.3.2 Designated dimensions of the shank

The shank shall be Type 1, 2 or 3 of ISO 1797:2017.

5.3.3 Dimensions of working part

5.3.3.1 Tolerances of nominal diameter

The nominal diameter is the largest diameter of the working part. The designation shall be in accordance with ISO 2157.

Tolerances of nominal diameter of working parts are shown in [Table 6](#).

Table 6 — Tolerances of nominal diameter of working part

Grit size	Ultra-fine to fine	Medium to very coarse
Tolerance	$\pm 0,08$ mm	$\pm 0,10$ mm

Testing shall be carried out in accordance with [ISO 8325](#).
<https://standards.iso.org/standards/sist/e72876b5-a49-4c6c-b4d1-5083d0ae3040/iso-fdis-7711-1>

5.3.3.2 Tolerances of length of working part

If the manufacturer designates the length of the working part (coated length) the tolerance shall be $\pm 0,5$ mm.

5.3.3.3 Run-out of working part

The maximum total indicated run-out shall be as given in [Table 7](#).

Table 7 — Run-out of working part

Designation	Maximum run-out mm
ultra-fine	0,07
extra fine	0,07
fine	0,08
medium	0,10
coarse	0,12
very coarse	0,14

The measurement location shall be as given in [Table 8](#).