
**Paper, board and pulp —
Determination of water-soluble
sulfates**

Papier, carton et pâte — Détermination des sulfates solubles dans l'eau

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 9198:2020

<https://standards.iteh.ai/catalog/standards/iso/3fb449b6-3a60-41a8-b8c1-896c3e79b251/iso-9198-2020>



iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 9198:2020

<https://standards.iteh.ai/catalog/standards/iso/3fb449b6-3a60-41a8-b8c1-896c3e79b251/iso-9198-2020>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	1
5 Reagents	1
6 Apparatus	2
7 Sampling and preparation of sample	2
8 Procedure	2
9 Calculation	3
10 Precision	3
11 Test report	4

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

ISO 9198:2020

<https://standards.iteh.ai/catalog/standards/iso/3fb449b6-3a60-41a8-b8c1-896c3e79b251/iso-9198-2020>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*.

This third edition cancels and replaces the second edition (ISO 9198:2001), which has been technically revised. The main changes compared to the previous edition are as follows:

- In 6.4, the addition of the option of filtering the suspension through a medium coarseness filter paper prior to withdrawing an aliquot with a syringe.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Paper, board and pulp — Determination of water-soluble sulfates

1 Scope

This document specifies a method for the determination of water-soluble sulfates in all types of pulp, paper and board. The lower limit of the determination is 20 mg of sulfate ion per kilogram of dry sample.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 186, *Paper and board — Sampling to determine average quality*

ISO 287, *Paper and board — Determination of moisture content of a lot — Oven-drying method*

ISO 638, *Paper, board and pulps — Determination of dry matter content — Oven-drying method*

ISO 7213, *Pulps — Sampling for testing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

— ISO Online browsing platform: available at <https://www.iso.org/obp>

— IEC Electropedia: available at <http://www.electropedia.org/>

3.1

water-soluble sulfates

in pulp, paper and board, the amount of sulfate ion that is extracted with water at 23 °C and determined under the conditions specified

4 Principle

Pieces of the sample are extracted with water at 23 °C in a disintegrator. An aliquot of the resulting suspension is used for determination of the sulfate ion content by ion chromatography.

5 Reagents

Use only reagents of recognized analytical quality and only water as specified in 5.1.

5.1 Distilled water or deionized water, of conductivity less than 0,1 mS/m at 25 °C.

5.2 Sulfate stock solution, $r(\text{SO}_4^{-2}) = 1\,000 \text{ mg/l}$.

Dry a portion of potassium sulfate (K_2SO_4) at 140 °C. Transfer $181,5 \text{ mg} \pm 2 \text{ mg}$ thereof to a 100 ml volumetric flask, dissolve the salt and make up to the mark with water (5.1).

Commercially available standard solutions can be used.

5.3 Sulfate intermediate solution

Dilute the sulfate stock solution (5.2) with water (5.1) to a sulfate ion concentration of, for example, $r(\text{SO}_4^{-2}) = 10 \text{ mg/l}$. Do not use sulfate intermediate solutions that are more than 1 week old.

5.4 Other solutions, as specified in the instructions for the ion chromatograph.

6 Apparatus

6.1 **Wet disintegrator**, a high-speed mixer, capable of disintegrating the sample completely.

6.2 **Ion chromatograph**, having a pump, an injector loop of known volume, a column system suitable for the determination of sulfates and a conductivity detector.

6.3 **Syringe**, of a quality suitable for ion chromatography, of capacity 5 ml and having a filter of about $0,2 \mu\text{m}$ pore diameter.

6.4 **Tea strainer or similar device with a fine mesh screen**, of stainless steel, to prevent fibres from clogging the syringe. Alternatively, the suspension can be filtered through a medium coarseness filter paper prior to withdrawing an aliquot with a syringe.

7 Sampling and preparation of sample

The procedure to be followed when sampling depends on the particular circumstances in each case. If the analysis is being made to evaluate a lot or a consignment of pulp, paper or board, the sample shall be taken in accordance with ISO 7213 or ISO 186, as relevant. If the analysis is made on another type of sample, report the origin of the sample and, if possible, the sampling procedure.

Since the amount of sulfates in the sample can be very low, take care not to contaminate it during sampling. Wear clean gloves at all times when handling the sample.

Keep the sample protected, wrapped in aluminium foil or in plastic bags, until required for analysis.

Select the sample portion for the analysis so that it is representative of the sample received.

8 Procedure

Carry out the procedure in duplicate. A blank shall also be carried through the entire procedure.

Weigh, to the nearest 0,01 g, a test portion, generally of between 2 g and 5 g. Split thick board and pulp sheets into thinner pieces to facilitate soaking.

The size of the test portion should be selected so that the sulfate ion content of the extract is within the optimum range of the ion chromatograph.

At the same time, determine the dry matter content on a separate portion using the procedure specified in ISO 287 or ISO 638, as relevant.

Transfer the weighed test portion to the disintegrator (6.1) and add $250 \text{ ml} \pm 2 \text{ ml}$ of water (5.1) at $23 \text{ }^\circ\text{C} \pm 2 \text{ }^\circ\text{C}$. Disintegrate the sample portion until it is completely disintegrated, but no longer. After disintegration, let the sample portion soak for about 2 h.

Withdraw an aliquot for analysis of the suspension, using the syringe (6.3). If this operation is hampered by the presence of fibres or fibre bundles, use the tea strainer or similar device (6.4) to prevent fibrous