



Designation: ~~C873/C873M-10~~ Designation: C873/C873M - 10a

Standard Test Method for Compressive Strength of Concrete Cylinders Cast in Place in Cylindrical Molds¹

This standard is issued under the fixed designation C873/C873M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This test method covers the determination of strength of cylindrical concrete specimens that have been molded in place using special molds attached to formwork. This test method is limited to use in slabs where the depth of concrete is from 125 to 300 mm [5 to 12 in.].

1.2 *Units*—The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to consult and establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. (Warning—Fresh hydraulic cementitious mixtures are caustic and may cause chemical burns to skin and tissue upon prolonged exposure.²)*

2. Referenced Documents

2.1 ASTM Standards:³

C39/C39M Test Method for Compressive Strength of Cylindrical Concrete Specimens

C42/C42M Test Method for Obtaining and Testing Drilled Cores and Sawed Beams of Concrete

C470/C470M Specification for Molds for Forming Concrete Test Cylinders Vertically

C617 Practice for Capping Cylindrical Concrete Specimens

C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials

C1231/C1231M Practice for Use of Unbonded Caps in Determination of Compressive Strength of Hardened Concrete Cylinders

3. Summary of Test Method

3.1 A concrete cylinder mold assembly consisting of a mold and a tubular support member is fastened within the concrete formwork prior to placement of the concrete as shown in Fig. 1. The elevation of the mold upper edge is adjusted to correspond to the level of the finished slab surface. The mold support prevents direct contact of the slab concrete with the outside of the mold and permits easy removal of the mold from the slab. The mold is filled at the time its location is reached in the normal course of concrete placement. The specimen in the “cured-in-place” condition is removed from its in-place location immediately prior to de-molding, capping, and testing. The reported compressive strength is corrected on the basis of specimen length-diameter ratio using correction factors provided in the section on calculation of Test Method C42/C42M.

4. Significance and Use

4.1 Cast-in-place cylinder strength relates to the strength of concrete in the structure due to the similarity of curing conditions because the cylinder is cured within the slab. However, due to differences in moisture condition, degree of consolidation, specimen size, and length-diameter ratio, there is not a unique relationship between the strength of cast-in-place cylinders and cores of the

¹ This test method is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.61 on Testing for Strength.


Current edition approved June 15, 2010. Published July 2010. Originally approved in 1977. Last previous edition approved in 2004 as C873/C873M-04 ^{ε1}. DOI: 10.1520/C0873_C0873M-10.

Current edition approved Dec. 15, 2010. Published January 2011. Originally approved in 1977. Last previous edition approved in 2010 as C873/C873M-10. DOI: 10.1520/C0873_C0873M-10a.

² Section on Safety Precautions, Manual of Aggregate and Concrete Testing, *Annual Book of ASTM Standards*, Vol 04.02.


³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.



(a) Plan of support member

(b) Plan of mold



(c) Elevation of support member and mold

FIG. 1 Schematic of Cast-in-Place Cylinder Mold Assembly

same age. When cores can be drilled undamaged and tested in the same moisture condition as the cast-in-place cylinders, the strength of the cylinders can be expected to be on average 10 % higher than the cores at ages up to 91 days for specimens of the same size and length-diameter ratio.⁴

4.2 Strength of cast-in-place cylinders may be used for various purposes, such as estimating the load-bearing capacity of slabs, determining the time of form and shore removal, and determining the effectiveness of curing and protection.

5. Apparatus

5.1 Cast-in-place molds shall have a diameter at least three times the nominal maximum aggregate size. The length-diameter

⁴ Bloem, D. L., "Concrete Strength in Structures," *Journal of the American Concrete Institute*, JACIA, March 1968, or *ACI Proceedings*, PACIA, Vol. 65, No. 3, pp. 169-248.