



Designation: ~~C1074-10~~ Designation: C1074 – 10a

Standard Practice for Estimating Concrete Strength by the Maturity Method¹

This standard is issued under the fixed designation C1074; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This practice provides a procedure for estimating concrete strength by means of the maturity method. The maturity index is expressed either in terms of the temperature-time factor or in terms of the equivalent age at a specified temperature.

1.2 This practice requires establishing the strength-maturity relationship of the concrete mixture in the laboratory and recording the temperature history of the concrete for which strength is to be estimated.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. (Warning—Fresh hydraulic cementitious mixtures are caustic and may cause chemical burns to skin and tissue upon prolonged exposure.²)*

2. Referenced Documents

2.1 ASTM Standards:³

C39/C39M Test Method for Compressive Strength of Cylindrical Concrete Specimens

C78 Test Method for Flexural Strength of Concrete (Using Simple Beam with Third-Point Loading)

C109/C109M Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or [50-mm] Cube Specimens)

C192/C192M Practice for Making and Curing Concrete Test Specimens in the Laboratory

C403/C403M Test Method for Time of Setting of Concrete Mixtures by Penetration Resistance

C511 Specification for Mixing Rooms, Moist Cabinets, Moist Rooms, and Water Storage Tanks Used in the Testing of Hydraulic Cements and Concretes

C684 Test Method for Making, Accelerated Curing, and Testing Concrete Compression Test Specimens

C803/C803M Test Method for Penetration Resistance of Hardened Concrete

C873/C873M Test Method for Compressive Strength of Concrete Cylinders Cast in Place in Cylindrical Molds

C900 Test Method for Pullout Strength of Hardened Concrete

C918/C918M Test Method for Measuring Early-Age Compressive Strength and Projecting Later-Age Strength

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *datum temperature*—the temperature that is subtracted from the measured concrete temperature for calculating the temperature-time factor according to Eq 1.

3.1.2 *equivalent age*—the number of days or hours at a specified temperature required to produce a maturity equal to the maturity achieved by a curing period at temperatures different from the specified temperature.

3.1.3 *maturity*—the extent of the development of a property of a cementitious mixture.

3.1.3.1 *Discussion*—While the term is used usually to describe the extent of relative strength development, it can also be applied to the evolution of other properties that are dependent on the chemical reactions that occur in a cementitious mixture. At any age, maturity depends on the curing history.

3.1.4 *maturity function*—a mathematical expression that uses the measured temperature history of a cementitious mixture

¹ This practice is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.64 on Nondestructive and In-Place Testing.

Current edition approved ~~June~~ Dec. 15, 2010. Published ~~July 2010~~ January 2011. Originally approved in 1987. Last previous edition approved in ~~2004~~ 2010 as ~~C1074-04~~ C1074-10. DOI: 10.1520/C1074-10a.

² Section on Safety Precautions, Manual of Aggregate and Concrete Testing, *Annual Book of ASTM Standards*, Vol 04.02.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

during the curing period to calculate an index that is indicative of the maturity at the end of that period. Refer to Appendix X1 for additional discussion of this term.

3.1.5 *maturity index*—an indicator of maturity that is calculated from the temperature history of the cementitious mixture by using a maturity function.

3.1.5.1 *Discussion*—The computed index is indicative of maturity provided there has been a sufficient supply of water for hydration or pozzolanic reaction of the cementitious materials during the time used in the calculation. Two widely used maturity indexes are the *temperature-time factor* and the *equivalent age*.

3.1.6 *maturity method*—a technique for estimating concrete strength that is based on the assumption that samples of a given concrete mixture attain equal strengths if they attain equal values of the maturity index **(1, 2, 3)**.⁴

3.1.7 *strength-maturity relationship*—an empirical relationship between compressive strength and maturity index that is obtained by testing specimens whose temperature history up to the time of test has been recorded.

3.1.8 *temperature-time factor*—the maturity index computed according to Eq 1.

4. Summary of Practice

4.1 A strength-maturity relationship is developed by laboratory tests on the concrete mixture to be used.

4.2 The temperature history of the field concrete, for which strength is to be estimated, is recorded from the time of concrete placement to the time when the strength estimation is desired.

4.3 The recorded temperature history is used to calculate the maturity index of the field concrete.

4.4 Using the calculated maturity index and the strength-maturity relationship, the strength of the field concrete is estimated.

5. Significance and Use

5.1 This practice can be used to estimate the in-place strength of concrete to allow the start of critical construction activities such as: (1) removal of formwork and reshoring; (2) post-tensioning of tendons; (3) termination of cold weather protection; and (4) opening of roadways to traffic.

5.2 This practice can be used to estimate strength of laboratory specimens cured under non-standard temperature conditions.

5.3 The major limitations of the maturity method are: (1) the concrete must be maintained in a condition that permits cement hydration; (2) the method does not take into account the effects of early-age concrete temperature on the long-term strength; and (3) the method needs to be supplemented by other indications of the potential strength of the concrete mixture.

5.4 The accuracy of the estimated strength depends, in part, on using the appropriate maturity function for the particular concrete mixture. Annex A1 provides a procedure for determining experimentally the best parameters (datum temperature or value of Q) for the maturity functions described in Section 6.

6. Maturity Functions

6.1 There are two alternative functions for computing the maturity index from the measured temperature history of the concrete.

6.2 One maturity function is used to compute the *temperature-time factor* as follows: [63dfl58f9a41/astm-c1074-10a](https://doi.org/10.1520/C1074-10a)

$$M(t) = \Sigma(T_a - T_o) \Delta t \quad (1)$$

where:

$M(t)$ = the temperature-time factor at age t , degree-days or degree-hours,

Δt = a time interval, days or hours,

T_a = average concrete temperature during time interval, Δt , °C, and

T_o = datum temperature, °C.

6.3 The other maturity function is used to compute *equivalent age* at a specified temperature as follows **(4)**:

$$t_e = \Sigma e^{-Q\left(\frac{1}{T_s} - \frac{1}{T_i}\right)} \Delta t \quad (2)$$

where:

t_e = equivalent age at a specified temperature T_s , days or h,

Q = activation energy divided by the gas constant, K,

T_a = average temperature of concrete during time interval Δt , K,

T_s = specified temperature, K, and

Δt = time interval, days or h.

NOTE 1—Temperature in kelvin (K) equals approximately temperature °C + 273 °C.

6.4 Approximate values of the datum temperature, T_o , and the activation energy divided by the gas constant, Q , are given in Appendix X1. Where maximum accuracy of strength estimation is desired, the appropriate values of T_o or Q for a specific concrete mixture are determined according to the procedures given in Annex A1.

⁴ The boldface numbers in parentheses refer to the list of references at the end of this practice.

7. Apparatus

~~7.1A device is required to monitor and record the concrete temperature as a function of time. Acceptable devices include thermocouples or thermistors connected to strip-chart recorders, or digital data-loggers, or embedded digital devices that measure temperature and record and store the data. The recording time interval shall be ½ h or less for the first 48 h and 1 h or less thereafter. The temperature recording device shall be accurate to within ± 1 °C.~~

~~7.2 Alternative devices include commercial maturity instruments that automatically compute and display either temperature-time factor or equivalent age.~~ Apparatus

7.1 A device is required to monitor and record the concrete temperature as a function of time and compute the maturity index in accordance with Eq 1 or Eq 2.

~~NOTE 2—Commercial maturity instruments use specific values of datum temperature or activation energy in evaluating the maturity index; thus the displayed maturity index may not be indicative of the true value for the concrete mixture being used. Refer to 2—Acceptable devices include commercial maturity instruments that monitor temperature and compute and display either temperature-time factor or equivalent age. Some commercial maturity instruments use fixed values of datum temperature or activation energy in evaluating the maturity index; thus the displayed maturity index may not be indicative of the true value for the concrete mixture being used. Refer to Appendix X1 for information on correcting the displayed values. For information on correcting displayed time-temperature values for another value of datum temperature. Equivalent-age values displayed by a maturity instrument cannot be adjusted for another activation energy value.~~

7.2 Alternative devices include temperature sensors connected to data-loggers, or embedded digital devices that measure, record, and store temperature data as a function of time. The temperature data are used to calculate the maturity index according to Eq 1 or Eq 2.

7.3 The time interval between temperature measurements shall be ½ h or less for the first 48 h and 1 h or less thereafter. The temperature recording device shall be accurate to within ± 1 °C.

8. Procedure to Develop Strength-Maturity Relationship

8.1 Prepare at least 15 cylindrical specimens according to Practice C192/C192M . The mixture proportions and constituents of the concrete shall be similar to those of the concrete whose strength will be estimated using this practice. If two batches are needed to prepare the required number of cylinders, cast an equal number of cylinders from each batch, and test one cylinder from each batch at the test ages given in 8.4.

8.2 Embed temperature sensors to within ± 15 mm of the centers of at least two specimens. Immediately connect the sensors to maturity instruments or to temperature-recording devices such as data-loggers or strip-chart recorders.

NOTE 3—A method to assist in the proper positioning of the sensor is to insert a small diameter rigid rod into the center of the freshly made cylinder. The rod will push aside any interfering aggregate particles. The rod is removed and the sensor is inserted into the cylinder. The side of the cylinder mold should be tapped with a rubber mallet or the tamping rod to ensure that the concrete comes into contact with the sensor.

8.3 Moist cure the specimens in a water bath or in a moist room meeting the requirements of Specification C511.

8.4 Unless specified otherwise, perform compression tests at ages of 1, 3, 7, 14, and 28 days in accordance with Test Method C39/C39M. Test two specimens at each age and compute the average strength. If the range of compressive strength of the two specimens exceeds 10 % of their average strength, test another cylinder and compute the average of the three tests. If a low test result is due to an obviously defective specimen, discard the low test result.

NOTE 4—For concrete mixtures with rapid strength development, or when strength estimates are to be made at low values of maturity index, tests should begin as soon as practicable. Subsequent tests should be scheduled to result in approximately equal increments of strength gain between test ages. At least five test ages should be used.

8.5 At each test age, record the average maturity index for the instrumented specimens.

8.5.1 If maturity instruments are used, record the average of the displayed values.

8.5.2 If temperature recorders are used, evaluate the maturity index according to Eq 1 or Eq 2. Unless specified otherwise, use a time interval (Δt) of ½ h or less for the first 48 h of the temperature record. Longer time intervals are permitted for the relatively constant portion of the subsequent temperature record.

NOTE 5—Judgement should be used in selecting the initial time intervals to record temperature in mixtures that result in rapid changes in early-age temperature due to rapid hydration. Appendix X2 gives an example of how to evaluate the temperature-time factor or equivalent age from the recorded temperature history of the concrete.

8.6 Plot the average compressive strength as a function of the average value of the maturity index. Draw a best-fit curve through the data. The resulting curve is the strength-maturity relationship to be used for estimating the strength of the concrete mixture cured under other temperature conditions. Fig. 1 is an example of a relationship between compressive strength and temperature-time factor, and Fig. 2 is an example of a relationship between compressive strength and equivalent age at 20 °C.

NOTE 6—The strength-maturity relationship can also be established by using regression analysis to determine a best-fit equation to the data. Possible equations that have been found to be suitable for this purpose may be found in Ref. (3). A popular equation is to express strength as a linear function of the logarithm of the maturity index (see Fig. 3).

8.7 When specified, a flexural strength versus maturity index relationship is permitted. Prepare at least 15 beam specimens in accordance with Practice C192/C192M. If two batches are needed to prepare the required number of specimens, cast an equal




FIG. 1 Example of a Relationship Between Compressive Strength and Temperature-Time Factor




FIG. 2 Example of a Relationship Between Compressive Strength and Equivalent Age at 20 °C




FIG. 3 Example of Compressive Strength as a Function of Logarithm of Equivalent Age

number of beams from each batch, and test one beam from each batch at the test ages given in 8.4. Embed temperature sensors in two specimens, one from each batch if two batches are made. Connect the sensors to maturity instruments or temperature recording devices, and moist cure the specimens in a water bath or in a moist room meeting the requirements of Specification C511.

Measure flexural strength in accordance with Test Method C78 at time intervals of 1, 3, 7, 14 and 28 days, or as specified otherwise (See Note 4). Test two specimens at each age and compute the average strength. If the range of flexural strength of the two specimens exceeds 15 % of their average strength, test another beam and compute the average of the three tests. If a low test result is due to an obviously defective specimen, discard the low test result. Use the same procedures as in 8.5 and 8.6 to develop the flexural strength-maturity relationship.

8.8 It is also permitted to develop a relationship between cube strength of concrete and the maturity index. Follow the procedure as given for cylinders except that the cubes should be prepared and tested in accordance with the applicable test method. Insert temperature sensors at the centers of at least two cubes. Test two cubes at each test age. In deciding whether to discard a low cube strength result, use the precision statement of the standard test method for cube strength as guidance.

9. Procedure to Estimate In-Place Strength

9.1 As soon as is practicable after concrete placement, embed temperature sensors into the fresh concrete. When using this practice to allow critical construction operations to begin, install sensors at locations in the structure that are critical in terms of exposure conditions and structural requirements.

NOTE 7—In building construction, exposed portions of slabs and slab-column connections are typically critical locations. The advice of the Engineer should be sought for critical locations in the particular structure under construction.

9.2 Connect the sensors to maturity instruments or temperature-recording devices and activate the recording devices as soon as is practicable. Use the same value of datum temperature or activation energy, whichever is applicable, as was used in computing the maturity index during development of the strength-maturity relationship (See Section 8).

9.3 When the strength at the location of a sensor is to be estimated, read the value of the maturity index from the maturity instrument or evaluate the maturity index from the temperature record.

9.4 Using the strength-maturity relationship developed in Section 8, read off the value of compressive (or flexural) strength corresponding to the measured maturity index.

9.5 Prior to performing critical operations, such as formwork removal or post-tensioning, supplement determination of the concrete maturity with other tests to ensure that the concrete in the structure has a potential strength that is similar to that of the concrete used to develop the strength-maturity relationship. Appropriate techniques include:

9.5.1 In-place tests that give indications of strength, such as Test Method C803/C803M, Test Method C873/C873M, or Test Method C900.

9.5.2 Early-age compressive strength tests in accordance with Test Method C918/C918M of standard-cured specimens molded from samples of the concrete as-delivered.

9.5.3 Compressive strength tests on specimens molded from samples of the concrete as-delivered and subjected to accelerated curing in accordance with Test Method C684.

9.5.4 Early-age tests of field-molded cylinders instrumented with maturity instruments. The measured strengths are compared with the strengths estimated from the established strength-maturity relationship. If the difference consistently exceeds 10 %, a new strength-maturity relationship is to be developed.

10. Precision and Bias

10.1 This practice is used to estimate the in-place strength of concrete based on the measured thermal history at a point in the structure and a previously established strength-maturity relationship. The accuracy of the estimated strength depends on several factors, such as the appropriateness of the maturity function for the specific mixture, the early-age temperature history, and the actual mixture proportions. For this reason, it is not possible to write statements about the precision and bias of the estimated strength.

11. Keywords

11.1 in-place strength; maturity method; nondestructive testing; temperature

ANNEX

(Mandatory Information)

A1. DETERMINATION OF DATUM TEMPERATURE OR ACTIVATION ENERGY

A1.1 Procedure

A1.1.1 The testing required to determine experimentally the datum temperature or the activation energy can be performed using mortar specimens, and the results are applicable to the concrete under investigation (5, 6, 7). The basic approach is to establish the compressive strength versus age relationships for mortar specimens cured in water baths maintained at three different temperatures. Two baths are at the maximum and minimum concrete temperatures expected for the in-place concrete during the period when strengths are to be estimated. The third bath temperature is midway between the extremes. Depending on the data analysis procedure that is used, the final setting times of the mortar at the three temperatures may also have to be measured.

A1.1.2 Proportion a mortar mixture having a fine aggregate-to-cement ratio (by mass) that is the same as the coarse aggregate-to-cement ratio of the concrete mixture under investigation (6). The paste shall have the same water-cementitious materials ratio and the same amounts of admixtures that will be used in the concrete.

A1.1.3 If the strength data will be analyzed using the reciprocal plotting procedure in A1.1.7, final setting times must be measured. Prepare three mortar specimens using containers specified in Test Method C403/C403M. Carefully submerge each specimen into its corresponding temperature bath. Determine the time of final setting for each temperature in accordance with Test Method C403/C403M. The specimens are removed from the water baths and excess water is removed prior to making penetration measurements. If the data will be analyzed using the regression procedures in A1.1.8, it is not necessary to measure times of final setting.

A1.1.4 Prepare three sets of 50-mm mortar cubes, with 18 cubes per set. Mold the cubes in accordance with Test Method C109/C109M and carefully submerge each set into one of the temperature baths. For each set, remove the molds and return the specimens to their respective baths approximately 1 h before the first series of compression tests.

A1.1.5 For each set of cubes, determine the compressive strength of three cubes in accordance with Test Method C109/C109M at an age that is approximately twice the time of final setting. If final setting times were not measured, perform the first test when the compressive strength is approximately 4 MPa. Perform subsequent tests on three cubes from each set at ages that are approximately twice the age of the previous tests. For example, if the time of the first test was 12 h, successive compressive strength tests would be performed at 1, 2, 4, 8, 16, and 32 days.

A1.1.6 The strength versus age data obtained at the three curing temperatures are analyzed to determine the relationship between the rate constant for strength development (*k*-value) and the curing temperature. Different procedures can be used depending on the available computational tools. If the user has the capability to perform only linear regression analysis, use the procedure in A1.1.7 or A1.1.8.2. If the user has a computer program that can perform regression analyses with a general function, use the procedure in A1.1.8.1.

A1.1.7 To use this procedure, the final setting times at the three temperatures must be measured. Prepare a graph with the reciprocal of strength as the *y*-axis and the reciprocal of age as the *x*-axis. For each curing temperature, plot the reciprocal of the average cube strength along the *y*-axis and the reciprocal of the age beyond the time of final setting along the *x*-axis. An example of such a plot is shown in Fig. A1.1. Determine the slope and the intercept of the best-fitting straight line through the data for each curing temperature. For each straight-line, divide the value of the intercept by the value of the slope. These quotients are the *k*-values that are used to calculate the datum temperature or the activation energy.

A1.1.8 As an alternative to the procedure in A1.1.7, the *k*-values can be estimated by either of the following methods. In these cases, the final setting times do not have to be measured.

A1.1.8.1 If the user has access to a computer program that will permit the fitting of a general equation to a set of data, determine the *k*-values by fitting the following equation to the strength-age data for each curing temperature:

$$S = S_{u1} \frac{k(t - t_o)}{1 + k(t - t_o)} \tag{A1.1}$$




FIG. A1.1 Reciprocal of Strength Versus Reciprocal of Age Beyond Time of Final Setting