



Designation: C836/C836M – 11

Standard Specification for High Solids Content, Cold Liquid-Applied Elastomeric Waterproofing Membrane for Use with Separate Wearing Course¹

This standard is issued under the fixed designation C836/C836M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification describes the required properties and test methods for a cold liquid-applied elastomeric-type membrane, one- or two-component, for waterproofing building decks and walls subject to hydrostatic pressure in building areas to be occupied by personnel, vehicles, or equipment. This specification applies only to a membrane system that will be covered with a separate wearing course, traffic course, or backfill.

NOTE 1—See Guide C898 and Guide C1471 for proper application of membrane.

1.2 There are no ISO standards similar or equivalent to this ASTM standard.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

C717 Terminology of Building Seals and Sealants

¹ This specification is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.22 on Waterproofing and Dampproofing Systems.

Current edition approved Jan. 1, 2011. Published February 2011. Originally approved in 1976. Last previous edition approved in 2010 as C836/C836M – 10. DOI: 10.1520/C0836_C0836M-11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

C794 Test Method for Adhesion-in-Peel of Elastomeric Joint Sealants

C898 Guide for Use of High Solids Content, Cold Liquid-Applied Elastomeric Waterproofing Membrane with Separate Wearing Course

C1250 Test Method for Nonvolatile Content of Cold Liquid-Applied Elastomeric Waterproofing Membranes

C1305 Test Method for Crack Bridging Ability of Liquid-Applied Waterproofing Membrane

C1375 Guide for Substrates Used in Testing Building Seals and Sealants

C1471 Guide for the Use of High Solids Content Cold Liquid-Applied Elastomeric Waterproofing Membrane on Vertical Surfaces

C1522 Test Method for Extensibility After Heat Aging of Cold Liquid-Applied Elastomeric Waterproofing Membranes

D2240 Test Method for Rubber Property—Durometer Hardness

3. Terminology

3.1 *Definitions*—Refer to Terminology C717 for definitions of the terms used in this specification.

4. Classification

4.1 Types:

4.1.1 *Type I*—A one-component, cold liquid-applied waterproofing material suitable for immediate application after mixing. Type I products may be used with an accelerator that is beneficial but not essential for curing of the membrane.

4.1.2 *Type II*—A two-component, cold liquid-applied waterproofing material. Combining two components is essential for curing of the membrane.

5. Physical Requirements

5.1 *Material*—Membrane materials shall cure, after application by spreading or spraying, to form an elastomeric film capable of maintaining a seal against liquid water.



5.2 The physical, mechanical, and performance properties of the membrane shall conform to the requirements described in [Table 1](#).

6. Test Methods

6.1 *Standard Conditions*—Standard conditions for all tests shall be $23 \pm 2^\circ\text{C}$ [$73.4 \pm 3.6^\circ\text{F}$] and $50 \pm 5\%$ relative humidity.

6.2 Conditioning/Mixing:

6.2.1 Store all membrane materials to be tested in an unopened container at standard conditions for at least 24 h before any test specimens are prepared.

6.2.2 Follow the manufacturer's instructions for mixing and preparing membrane materials for testing. Thoroughly mix one-component samples before using. Mix two-component compounds in the ratio recommended by the manufacturer.

6.3 *Test Surfaces*—In addition to the mortar test surfaces specified, use other test surfaces when required by the specifier.

6.4 *Primer*—When required by the manufacturer, use a primer as directed by the manufacturer on all substrate materials in test assemblies.

6.5 Hardness:

6.5.1 Following the manufacturer's instructions, apply a film of membrane, $1.5 \pm 0.1\text{ mm}$ [$60 \pm 5\text{ mils}$] thick, on a 100 by 150-mm [4 by 6-in.] piece of polyethylene film-coated paper and allow the membrane to cure for 14 days at standard conditions. If more than one application is required, the total time for film application shall not exceed 48 h.

6.5.2 After curing, strip the film from the coated paper, cut into pieces, and lay the pieces one upon another to provide a test specimen meeting the requirements of Test Method [D2240](#).

6.5.3 Using a Type 00 hardness gauge, obtain an instantaneous reading of the film hardness as specified in Test Method [D2240](#).

6.6 Weight Loss:

6.6.1 Test in compliance with the requirements of Test Method [C1250](#).

6.7 Low-Temperature Crack Bridging:

6.7.1 Test in compliance with the requirements of Test Method [C1305](#).

6.8 Film Thickness on Vertical Surface:

6.8.1 Prepare mortar test blocks 152 by 76 by 25 mm [6 by 3 by 1 in.] as described in Guide [C1375](#).

6.8.2 Prepare the test assembly by covering one cut face of a mortar slab with a film of membrane material $1.5 \pm 0.1\text{ mm}$ [$60 \pm 5\text{ mils}$] in thickness, mixed and applied in accordance with the manufacturer's directions. Install the film in one application unless manufacturer's application instructions require application in several coats. If applied in several coats, the test substrate shall be set in a vertical position between applications, and the complete film thickness shall be accomplished in 48 h in accordance with the manufacturer's instructions.

6.8.3 Immediately after applying the film, place the coated slab on its end, in a vertical position, and let remain in this position for 24 h at standard conditions.

6.8.4 Using a vernier caliper, measure the thickness of the total assembly at five points within 25 mm [1 in.] of the top end of the slab. Cover the film at each point of measurement with a 25-mm [1 in.] square piece of aluminum, 0.5 mm [0.002 in.] thick, to prevent point indentation on the film.

6.8.5 Cut a 25-mm [1-in.] wide band of film from across the top of the mortar strip. Measure the thickness of the test mortar in approximately the same five locations that measurements were made in [6.8.4](#). Determine the average.

6.8.6 Determine the film thickness by subtracting the average test mortar thickness from the average total assembly thickness (test mortar and film).

6.9 Adhesion-in-Peel After Water Immersion:

6.9.1 Perform the test as specified in Test Method [C794](#) with the following qualifications:

6.9.1.1 Mortar shall be the test substrate. Other substrates may be tested when specified.

6.9.1.2 The cure conditions shall be 14 days at standard conditions, followed by 7 days at $70 \pm 2^\circ\text{C}$ [$158 \pm 3.6^\circ\text{F}$].

6.9.1.3 After the specimen has cured for about 7 days, coat the cloth with a layer of the compound about 2.5 mm [0.1 in.] thick to help minimize cloth failure.

6.10 *Optional Test for Adhesion in Peel*—An optional method for running the adhesion test after the assemblies have been completely cured is to attach a 0.45-kg [1-lb] weight to the end of the strip of cloth, and let hang for a period of 2 min. If no separation occurs at the interface during this period, the film has met the minimum adhesion requirements.

6.11 Extensibility After Heat Aging:

TABLE 1 High Solids Content, Cold Liquid-Applied Elastomeric Waterproofing Membrane Physical Requirements

Property	Requirement	Test Method
Hardness, Type 00, min	50	D2240 as modified in section 6.5 of this specification
Weight loss, max, %	20	C1250
Nonvolatile, min, %	80	
Low temperature crack bridging	no cracking	C1305
Film thickness (vertical surface), min, mm [mils]	1.5 ± 0.1 [60 ± 5]	See section 6.8 of this specification ^A
Adhesion-in-Peel after water immersion, N [lbf]	4.4 [1]	C794 as modified in section 6.9 of this specification
Optional test for adhesion-in-peel	No separation at interface	See section 6.10 of this specification
Extensibility after heat aging, min, mm [in.]	6.4 [$\frac{1}{4}$], no cracking	C1522
Stability, min, months	6	See section 6.12 of this specification.

^A Numbers refer to portions of the Test Methods section, Section [6](#), of this specification.