



## Standard Test Method for Behavior of Materials in a Vertical Tube Furnace at 750°C<sup>1</sup>

This standard is issued under the fixed designation E136; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This fire-test-response test method covers the determination under specified laboratory conditions of combustion characteristics of building materials.

1.2 Limitations of this fire-test response test method are shown below.

1.2.1 This test method does not apply to laminated or coated materials.

1.2.2 This test method is not suitable or satisfactory for materials that soften, flow, melt, intumesce or otherwise separate from the measuring thermocouple.

1.2.3 This test method does not provide a measure of an intrinsic property.

1.2.4 This test method does not provide a quantitative measure of heat generation or combustibility; it simply serves as a test method with selected (end point) measures of combustibility.

1.2.5 The test method does not measure the self-heating tendencies of materials.

1.2.6 In this test method materials are not being tested in the nature and form used in building applications. The test specimen consists of a small, specified volume that is either (1) cut from a thick sheet; (2) assembled from multiple thicknesses of thin sheets; or (3) placed in a container if composed of granular powder or loose-fiber materials.

1.2.7 Results from this test method apply to the specific test apparatus and test conditions and are likely to vary when changes are made to one or more of the following: (1) the size, shape, and arrangement of the specimen; (2) the distribution of organic content; (3) the exposure temperature; (4) the air supply; (5) the location of thermocouples.

1.3 This test method references notes and footnotes that provide explanatory information. These notes and footnotes, excluding those in tables and figures, shall not be considered as requirements of this test method.

1.4 The values stated in SI units are to be regarded as standard. The values given in parentheses are for information only.

1.5 This standard is used to measure and describe the response of materials, products, or assemblies to heat and flame under controlled conditions, but does not by itself incorporate all factors required for fire-hazard or fire-risk assessment of the materials, products, or assemblies under actual fire conditions.

1.3 This test method includes two options, both of which use a furnace to expose test specimens of building materials to a temperature of 750°C (1382°F).

1.3.1 The furnace for the apparatus for Option A consists of a ceramic tube containing an electric heating coil, and two concentric vertical refractory tubes.

1.3.2 The furnace for the apparatus for Option B (Test Method E2652) consists of an enclosed refractory tube surrounded by a heating coil with a cone-shaped airflow stabilizer.

1.4 This test method references notes and footnotes that provide explanatory information. These notes and footnotes, excluding those in tables and figures, shall not be considered as requirements of this test method.

1.5 The values stated in SI units are to be regarded as standard. The values given in parentheses are for information only.

1.6 This standard is used to measure and describe the response of materials, products, or assemblies to heat and flame under controlled conditions, but does not by itself incorporate all factors required for fire-hazard or fire-risk assessment of the materials, products, or assemblies under actual fire conditions.

1.7 Fire testing is inherently hazardous. Adequate safeguards for personnel and property shall be employed in conducting these tests.

1.7

1.8 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee E05 on Fire Standards and is the direct responsibility of Subcommittee E05.23 on Combustibility. Current edition approved Dec. 15, 2009-2011. Published January 2010-February 2011. Originally approved in 1958. Last previous edition approved in 2009 as E136 – 09ab. DOI: 10.1520/E0136-09B-10.1520/E0136-11.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

- D1929 [Test Method for Determining Ignition Temperature of Plastics](#)
- D3174 [Test Method for Ash in the Analysis Sample of Coal and Coke from Coal](#)
- E84 [Test Method for Surface Burning Characteristics of Building Materials](#)
- E176 [Terminology of Fire Standards](#)
- E2652 [Test Method for Behavior of Materials in a Tube Furnace with a Cone-shaped Airflow Stabilizer, at 750C](#)

### 2.2 ISO Standard:<sup>3</sup>

- ISO 1182 Noncombustibility Test for Building Materials
- ISO 13943 Fire Safety-Vocabulary

### 2.3 Other Standard:

- BS 476 Combustibility Test of Materials<sup>3</sup>

## 3. Terminology

3.1 Definitions—For definitions of terms found in this test method, refer to Terminology E176 and ISO 13943. In case of conflict, the definitions given in Terminology E176 shall prevail.

## 4. Summary of Test Method

4.1 This test method uses a furnace consisting of a ceramic tube containing an electric heating coil to expose building materials to a temperature of 750°C (1382°F) until failure occurs or for at least 30 min.

4.2 The furnace consists of two concentric vertical refractory tubes.

4.3 Thermocouples are used to assess the temperature increases resulting from combustion of the building material.

4.4 Visual observation is used to assess the occurrence of flaming.

4.1 This test method uses a furnace to expose building materials to a temperature of 750°C (1382°F) until failure occurs or for at least 30 min.

4.2 This test method offers the choice of two options: Option A (Sections 6 through 9) and Option B (Test Method E2652).

4.3 The furnace for Option A consists of two concentric vertical refractory tubes.

4.4 The furnace for Option B (Test Method E2652) consists of an enclosed refractory tube surrounded by a heating coil with a cone-shaped airflow stabilizer.

4.5 Thermocouples are used to assess the temperature increases resulting from combustion of the building material.

4.6 Visual observation is used to assess the occurrence of flaming.

4.7 Section 15 is the report and acceptance criteria section for this test method (both options).

## 5. Significance and Use

5.1 While actual building fire exposure conditions are not duplicated, this test method will assist in indicating those materials which do not act to aid combustion or add appreciable heat to an ambient fire.

5.2 Materials passing the test are permitted limited flaming and other indications of combustion.

## 6. Apparatus

6.1 The test apparatus, as shown in Apparatus for Option A

6.1 The test apparatus shown in Fig. 1, shall consist primarily of the following: , shall be used for Option A and shall consist primarily of the following:

6.1.1 *Refractory Tubes*—Two concentric, refractory tubes, 76 and 102 mm (3 and 4 in.) in inside diameter and 210 to 250 mm (8½ to 10 in.) in length, with axes vertical, and with heat applied by electric heating coils outside of the larger tube. A controlled flow of air is admitted tangentially near the top of the annular space between the tubes and passes to the bottom of the inner tube. The outer tube rests on a refractory bottom and the inner tube rests on three spacer blocks so as to afford a total opening under the inner tube equal to or greater than that of the annular space. The refractory bottom plate has a removable plug for cleaning.

6.1.2 *Transparent Cover*—A transparent cover of heat-resistant glass or other transparent material shall be provided over the top of the inner tubes. The cover shall have a circular opening  $28.7 \pm 0.8$  mm ( $1\frac{1}{8} \pm \frac{1}{32}$  in.) centered over the axis of the tubes. This opening has an area of 645 mm<sup>2</sup> (1.0 in.<sup>2</sup>). The cover shall be in two equally-sized, movable parts.


6.1.3 *Thermocouples* and an automatically recording device shall be provided. The thermocouples shall be located as follows:

6.1.3.1 Thermocouple  $T_1$  is located in the center of the air space between the two concentric, refractory tubes; approximately 204 mm (8 in.) down from the top of the 102-mm (4-in.) diameter tube (Note 1).

6.1.3.2 Thermocouple  $T_3$  is located at the approximate geometric center of the specimen.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.



NOTE—Inch-Pound Equivalents

in.	3	4	6	10	10 <sup>3</sup> / <sub>4</sub>	1 in. <sup>2</sup>	No. 16 Awg
mm	76	102	152	254	273	6.4 cm <sup>2</sup>	1.29

FIG. 1 Cross Section of Furnace Assembly

6.1.3.3 Thermocouple  $T_4$  is located on the surface, in contact with the test specimen; in the same horizontal plane as  $T_3$ .

6.1.3.4 Thermocouples  $T_1$ ,  $T_3$  and  $T_4$  shall have a time constant (time to reach 63.2 % of the furnace air temperature of 750°C (1382°F)) of 5 to 10 s (Note 2).

NOTE 1—Thermocouple  $T_1$  is used for better regulation of the temperature of the air in the furnace space.

NOTE 2—Ungrounded, metallic-sheathed thermocouples of 1-mm diameter have been found to meet the time constant requirements.

6.2 *Specimen Holder*—The specimen holder for solid test specimens shall be as shown in Fig. 2.

6.2.1 Test specimens in granular or powder form shall be contained in thin-wall, open-top vessels of inert materials whose outside dimensions conform to the test specimen shape and maximum size specified in 7.4.2.2. These vessels shall have walls of either solid or mesh construction.

6.3 *Test Specimen Location*—During the test, the geometric center of the test specimen shall be located at the geometric center  $\pm 3$  mm ( $\pm 1/8$  in.) of the 76-mm (3-in.) diameter tube.

## 7. Test Specimens

### 7.1 Test Specimens for Option A

7.1 The test specimens for Option A shall comply with 7.2 through 7.5.

7.2 All test specimens shall be 38 by 38 by 51  $\pm$  2.5 mm (1.5 by 1.5 by 2.0  $\pm$  0.1 in.).

7.3 The test specimens shall be dried at 60  $\pm$  3°C (140  $\pm$  5°F) for not less than 24 h but no more than 48 h.

7.4 Test specimens shall then be placed in a desiccator to cool at least 1 h before testing.

7.5 Not less than four identical specimens shall be tested.

## 8. Procedure

### 8.1 Procedure for Option A

8.1 The procedure for Option A shall comply with 8.2 through 8.11.

#### 8.2 Test Room Setup:

8.2.1

8.2.1.1 Conduct the test at room conditions of 21  $\pm$  3°C (70  $\pm$  5°F).




FIG. 2 Specimen Holder for Solid Specimens

8.1.2 The test apparatus shall not be exposed to drafts or any other form of direct sunlight or artificial illumination which would adversely affect the observation of flaming inside the furnace.

8.1.3 8.2.3 The room temperature shall not change by more than 3°C (5°F) during a test.

8.2

8.3 Air Flow—Provide an external air source to supply clean air through a metal tube located near the top of the test apparatus, tangentially between the annular spaced ceramic tubes. The air shall be supplied at a steady and controllable rate of 0.0027 m<sup>3</sup>/min (0.10 ft<sup>3</sup>/min) ± 20 %, which will give an air flow of 3 m (10 ft)/min past a loaded test specimen in the furnace at 750°C (1382°F).

Measure the air at room temperature, as specified in 8.1.1 8.2.1 and meter by a rotameter or other metering device in line with the metal tube.

8.3

8.4 Stabilized Furnace Temperature—Prior to the initial heating period insert a thermocouple,  $T_2$ , into the furnace from the top and place it where the geometric center of the test specimen will be during the test. Use this thermocouple to establish the stabilized furnace temperature.

8.4

8.5 Test Furnace Setup—Prepare the furnace by bringing the temperature of thermocouple  $T_2$ , located in the furnace at the position to be occupied by the geometric center of the specimen, to a temperature of 750 ± 5.5°C (1382 ± 10°F). Maintain the temperature in the unloaded furnace for at least 15 min to ensure stability.

8.5 Once the operating temperature has been established by thermocouple,  $T_2$ , note the temperature on thermocouple  $T_1$  and control the test chamber during the test to the observed  $T_1$  temperature reading. It is acceptable to use  $T_3$  as  $T_2$ .

8.6

8.7 Test Procedure—As rapidly as possible, insert the test specimen into the furnace with thermocouple  $T_3$  inserted from the top of the test specimen to its geometric center and thermocouple  $T_4$  attached to the side surface of the test specimen.

8.67.1 Close the top cover to the 6.4-cm<sup>2</sup> (1-in.<sup>2</sup>) opening immediately after insertion of the test specimen. Readings for thermocouples  $T_3$  and  $T_4$  shall be made at intervals (Note 3) not to exceed 10 s during the first 5 min, and as often as necessary afterwards to produce a smooth curve. Do not change the regulation of the current through the heating coils and the air flow during the test.

NOTE 3—A continuous read-out recording is preferred since it is possible for the maximum temperature to occur between the 10-s intervals.

8.67.2 Continue the test until the temperatures at thermocouples  $T_3$  and  $T_4$  have reached maxima, or until it is evident that the specimen does not pass this test.

8.67.3 After 30 min of testing have elapsed, or at any time subsequent to that, testing shall be discontinued if, over the previous

10 minutes, the temperature measured at the center thermocouple  $T_3$  has risen by no more than 1°C in any one minute. The final temperature reading shall be recorded as the maximum temperature.

8.78 Throughout the test make and record visual observations on the test specimens, noting quality, quantity, or intensity and duration of flaming or smoking, or both, and change of state.

8.8 ~~Note~~ 8.9 Note and record the time of occurrence of any flaming and the duration of such flaming in seconds.

NOTE 4—Flaming is sometimes difficult to identify. Some specimens exhibit only flame as a steady blue-colored luminous gas zone. Do not ignore this and note it under “observations during test” in the test report.

8.9 ~~Weigh~~ 8.10 Weigh each test specimen before and after testing and record the weight, in g, before and after the test for each test specimen.

8.10 1 Record the temperatures (initial, maximum and final), in °C, as measured by the appropriate thermocouples.

## 9. Calculation for Option A

9.1 The calculations for Option A shall be conducted in accordance with 9.2 through 9.3.

9.2 Calculate and record the weight loss for each of the test specimens, expressed as a percentage of the initial weight of the test specimen, to the nearest 1 %.

9.23 Calculate and record the temperature rise, in °C, for each of the test specimens.

9.23.1 Calculate the temperature rise as the difference between the maximum temperature and the initial temperature, as measured by thermocouple,  $T_3$ .

## 10. Report

~~10.1 Report the material as passing the test if at least three of the four test specimens tested meet the individual test specimen criteria detailed in 10.2.~~ Apparatus for Option B

10.1 The apparatus used for Option B shall be in accordance with Section 6 of Test Method E2652.

## 11. Test Specimens for Option B

11.1 The test specimens used for Option B shall be in accordance with Section 7 of Test Method E2652.

## 12. Test Setup and Calibration for Option B

12.1 The test specimens for Option B shall be in accordance with Section 8 of Test Method E2652.

## 13. Test Procedure for Option B

13.1 The test procedure for Option B shall be in accordance with Section 9 of Test Method E2652.

## 14. Calculations for Option B

14.1 The calculations for Option B shall be in accordance with Section 10 of E2652.

## 15. Report

15.1 ~~Report the material as passing the test if at least three of the four test specimens tested meet the individual test specimen criteria detailed in 15.2 or 10.3.~~ 15.3. The three test specimens do not need to meet the same individual test specimen criteria.

~~10.2~~

15.2 If the weight loss of the test specimen is 50 % or less, the material passes the test when the criteria in ~~10.2.1~~ 15.2.1 and in ~~10.2.2~~ 15.2.2 are met:

~~10.2.1~~

15.2.1 The recorded temperatures of the surface and interior thermocouples do not at anytime during the test rise more than 30°C (54°F) above the stabilized furnace temperature measured at  $T_2$  prior to the test.

~~10.2.2~~

15.2.2 There is no flaming from the test specimen after the first 30 s.

~~10.3~~

15.3 If the weight loss of the specimen exceeds 50 %, the material passes the test when the criteria in ~~10.3.1~~ 15.3.1 and in ~~10.3.2~~ 15.3.2 are met:

~~10.3.1~~

15.3.1 The recorded temperature of the surface and interior thermocouples do not, at any time during the test, rise above the stabilized furnace temperature measured at  $T_2$  prior to the test.

~~10.3.2~~

15.3.2 No flaming from the test specimen is observed at any time during the test.

## 11.

15.4 Report the option that was used.

## 16. Precision and Bias

11.1.1 ~~16.1~~ No information is presented about the precision and bias of this test method for measuring combustion characteristics since the test results are nonquantitative and are reported as pass or fail. (See X1.6.)

14.2 There have been attempts to determine precision and bias for some of the numerical results for this test method but the results have not been made public.

## 12.17. Keywords

127.1 building materials; combustion; heated tube; limited combustion; Setchkin furnace; tube furnace; vertical tube furnace

## APPENDIX

### (Nonmandatory Information)

## X1. COMMENTARY

### X1.1 Introduction

X1.1.1 The difference in fire risk between a combustible building material and a noncombustible (or incombustible) one is generally obvious. However, some materials may contain only a limited amount of combustible content and may not contribute appreciably to an ambient fire. The term noncombustible, while in recognized use as indicating a material that will not ignite or burn, is indefinite in its application unless referenced to a well defined testing procedure.

### X1.2 Definition

X1.2.1 Most dictionaries have defined noncombustible in simple terms, such as that used in the 1920 edition of the National Building Code promulgated by the National Board of Fire Underwriters (NBFU): Incombustible materials or construction are those that “will not ignite or burn when subjected to fire.” In 1943 the same code redefined incombustible construction as “assemblies which do not involve materials of such kind or quantity or so contained as to burn during exposure in a test fire or continue flaming or ignite after the furnace is shut off.”

X1.2.2 About this same time Committee C05 (now E05) and the New York City Building Code suggested adding a reference of 649°C (1200°F) as the fire exposure temperature. By 1949 the term incombustible was changed to noncombustible in the National Building Code without definition. The first edition of the BOCA Basic Building Code (1950) defined a noncombustible material as “any material which will neither ignite or actively support combustion in air at a temperature of 649°C [1200°F] during an exposure of five minutes in a vented tube or vented crucible furnace.”

X1.2.3 The 1955 edition of the NBFU National Building Code established a definition for noncombustible material **(1)**<sup>4</sup> that was subsequently adopted by other model codes, the Life Safety Code **(2)**, and most local codes. The adopted definition was as follows:

Noncombustible as applied to a building construction material means a material that, in the form in which it is used, falls in one of the following groups (a) through (c). It does not apply to surface finish materials nor to the determination of whether a material is noncombustible from the standpoint of clearances to heating appliances, flues or other sources of high temperature. No material shall be classed as noncombustible which is subject to increase in combustibility or flame spread rating beyond the limits herein established, through the effects of age, moisture or other atmospheric condition. Flame spread rating as used herein refers to ratings obtained in accordance with Test Method E84.

a) Materials no part of which will ignite and burn when subjected to fire. Any material that liberates flammable gas when heated to a temperature of 750°C (1382°F), for 5 min shall not be considered noncombustible within the meaning of this paragraph.

b) Materials having a structural base of noncombustible material, as defined in (a), with a surfacing not over 1/8-in. thick that has a flame spread rating not higher than 50.

c) Materials, other than as described in (a) or (b), having a surface flame spread rating not higher than 25 without evidence of continued progressive combustion and of such composition that surfaces that would be exposed by cutting through the material in any way would not have a flame spread rating higher than 25 without evidence of continued progressive combustion.

X1.2.4 In adopting this definition, NBFU stated that it was based on a determination of which materials “could be properly classed as noncombustible and then fixing the qualifying conditions in the definition to include these materials.” The definition was considered to apply to materials used for the walls, roofs, or other structural parts of buildings, but not to surface finish materials and not to the determination of whether a material is noncombustible from the standpoint of clearances to heating appliances, flues, or other sources of high temperature.

X1.2.5 After Test Method E136 was promulgated, (initially as a tentative in 1958, then as a full standard in 1965), many building codes replaced either part (a) of the NBFU definition or the entire definition with the specification that materials shall have been successfully tested in accordance with Test Method E136. In 1973, the American Insurance Association (successor to NBFU)

<sup>4</sup> The boldface numbers in parentheses refer to the list of references appended to this method.