



SLOVENSKI STANDARD
oSIST prEN 18007-4:2023
01-november-2023

Elektromagnetno utripno varjenje - 4. del: Popis in kvalifikacija varilnih postopkov

Electromagnetic pulse welding - Part 4: Specification and qualification of welding procedures

Schweißen und verwandte Verfahren - Elektromagnetisches Pulsschweißen - Teil 4: Spezifikation und Qualifizierung von Schweißverfahren

Soudage par impulsion électromagnétique - Partie 4 : Descriptif et qualification des modes opératoires de soudage

Ta slovenski standard je istoveten z: prEN 18007-4

oSIST prEN 18007-4:2023

<https://standards.iteh.ai/catalog/standards/sist/047bbc02-a15d-4b0d-ad00-5cbe240096af/osist-pren-18007-4-2023>

ICS:

25.160.10 Varilni postopki in varjenje Welding processes

oSIST prEN 18007-4:2023

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 18007-4

August 2023

ICS 25.160.10

English Version

Welding and allied processes - Electromagnetic pulse welding - Part 4: Specification and qualification of welding procedures

Schweißen und verwandte Verfahren -
Elektromagnetisches Pulsschweißen - Teil 4:
Spezifikation und Qualifizierung von Schweißverfahren

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 121.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	4
Introduction	5
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions, symbols and abbreviated terms.....	6
3.1 Terms and definitions	6
3.2 Symbols and abbreviated terms.....	7
4 Development and qualification of welding procedures.....	7
4.1 General.....	7
4.2 Technical content of a pWPS.....	8
4.2.1 General.....	8
4.2.2 Manufacturer information	8
4.2.3 Base material type(s), temper(s), and reference standard(s)	8
4.2.4 Base material dimensions and geometry.....	8
4.2.5 Equipment identification	8
4.2.6 Tool coil identification.....	8
4.2.7 Clamping arrangement.....	8
4.2.8 Joint design.....	8
4.2.9 Joint preparation and cleaning methods.....	9
4.2.10 Welding details.....	9
5 Qualification based on a welding procedure test.....	9
5.1 General.....	9
5.2 Shape and dimensions of test specimens.....	9
5.2.1 General.....	9
5.2.2 Overlap joint of tubular parts.....	9
5.2.3 Overlap joint of a tubular part with a solid cylindrical part	10
5.2.4 Overlap joint of sheets	10
5.3 Welding of test specimens	11
5.4 Examination and testing of test specimens	11
5.4.1 Extent of testing.....	11
5.4.2 Location and extraction of test specimens	12
5.4.3 Non-destructive examination.....	14
5.4.4 Destructive testing	15
5.4.5 Alternative tests	17
5.4.6 Re-testing.....	17
6 Qualification based on pre-production welding test.....	17
6.1 General.....	17
6.2 Test specimens	17
6.3 Examination and testing of test specimens	17
6.4 Range of qualification.....	17
7 Range of qualification.....	17
7.1 General.....	17
7.2 Related to the manufacturer.....	18
7.3 Related to the base material	18

7.4	Common to all welding procedures	18
7.4.1	Welding process	18
7.4.2	Type of control method	18
7.4.3	Type of welding equipment	18
7.4.4	Welding tools	18
7.4.5	Joint configuration and joint design	18
7.4.6	Other variables	18
8	Welding procedure qualification record (WPQR)	19
	Annex A (informative) Examination and testing	20
A.1	Examination and testing	20
A.2	Non-destructive testing	20
A.2.1	General	20
A.2.2	Visual examination	20
A.2.3	Dimensional measurements	20
A.2.4	Surface crack inspection	21
A.2.5	Dye penetrant testing	21
A.2.6	Leak testing	21
A.2.7	Laser ultrasound testing	21
A.2.8	Tomography	22
A.3	Destructive testing	23
A.3.1	General	23
A.3.2	Bend testing	23
A.3.3	Peel testing	24
A.3.4	Compression testing	25
A.3.5	Torsion testing	25
A.3.6	Lap shear tensile testing	25
A.3.7	Fatigue testing	26
A.3.8	Metallographic examination	26
A.3.9	Hardness measurements	26
A.4	Electrical conductivity measurements	26
A.5	Proof testing	27
	Annex B (informative) Welding Procedure Specifications	28
	Bibliography	30

prEN 18007-4:2023 (E)**European foreword**

This document (prEN 18007-4:2023) has been prepared by Technical Committee CEN/TC 121 “Welding and allied processes”, the secretariat of which is held by DIN.

This document is currently submitted to the CEN Enquiry.

The EN 18007 series of standards consists of the following parts:

- *Part 1: Welding knowledge, terminology and vocabulary,*
- *Part 2: Design of welded joints,*
- *Part 3: Qualification of welding operators and weld setters,*
- *Part 4: Specification and qualification of welding procedures,*
- *Part 5: Quality and inspection requirements.*

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[oSIST prEN 18007-4:2023](https://standards.iteh.ai/catalog/standards/sist/047bbc02-a15d-4b0d-ad00-5cbe240096af/osist-pren-18007-4-2023)

<https://standards.iteh.ai/catalog/standards/sist/047bbc02-a15d-4b0d-ad00-5cbe240096af/osist-pren-18007-4-2023>

Introduction

Electromagnetic pulse welding is an innovative solid-state welding technology that belongs to the group of pressure welding processes and is based on the use of electromagnetic forces to deform, accelerate and weld workpieces. No external heat source is used, the connection is only created by a high-velocity impact.

The increasing use of the electromagnetic pulse welding process has created the need for a standard, to ensure that the welding operations are carried out in the most effective manner and that appropriate controls are performed on all aspects of the implementation.

To be effective, welded products need to be free from problems in production and in service. To achieve this goal, it is necessary to provide controls from the design phase through material selection, choice of parameters, the fabrication itself, and inspection. For example, poor design can create serious and costly difficulties in the workshop or in service. Incorrect process parameters and/or material selection can result in welding defects. Welding procedures need to be correctly formulated and approved to avoid weld discontinuities. To ensure the manufacture of a quality product, management needs to understand the causes of potential problems and implement appropriate inspection procedures and subsequent quality measures. Supervision should be implemented to ensure that the specified quality is achieved.

iTeh Standards (<https://standards.iteh.ai>) Document Preview

[oSIST prEN 18007-4:2023](https://standards.iteh.ai/catalog/standards/sist/047bbc02-a15d-4b0d-ad00-5cbe240096af/osist-pren-18007-4-2023)

<https://standards.iteh.ai/catalog/standards/sist/047bbc02-a15d-4b0d-ad00-5cbe240096af/osist-pren-18007-4-2023>

prEN 18007-4:2023 (E)

1 Scope

This document specifies the requirements for the specification and qualification of welding procedures for electromagnetic pulse welding.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4063, *Welding, brazing, soldering and cutting — Nomenclature of processes and reference numbers*

ISO 14270, *Resistance welding — Destructive testing of welds — Specimen dimensions and procedure for mechanized peel testing resistance spot, seam and embossed projection welds*

ISO 14273:2016, *Resistance welding — Destructive testing of welds — Specimen dimensions and procedure for tensile shear testing resistance spot and embossed projection welds*

ISO 15607:2019, *Specification and qualification of welding procedures for metallic materials — General rules*

ISO 17637, *Non-destructive testing of welds — Visual testing of fusion-welded joints*

ISO 17639, *Destructive tests on welds in metallic materials — Macroscopic and microscopic examination of welds*

prEN 18007-1, *Welding and allied processes - Electromagnetic pulse welding - Part 1: Welding knowledge, terminology and vocabulary*

prEN 18007-3:—, *Electromagnetic pulse welding - Part 3: Qualification of welding operators and weld setters*

3 Terms and definitions, symbols and abbreviated terms

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in prEN 18007-1 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.2 Symbols and abbreviated terms

For the purposes of qualification of welding procedures, the abbreviations listed in ISO 15607:2019, Table 1 apply.

Symbol	Term	Unit
b	width of the parallel length	mm
b_1	width of the shoulder	mm
L_c	parallel length	mm
L_0	original gauge length	mm
L_s	maximum width of the weld after machining	mm
L_t	total length of the test specimen	mm
r	radius of shoulder	mm
t_s	thickness of the test specimen	mm

4 Development and qualification of welding procedures

4.1 General

A Welding Procedure Specification (WPS) is of extreme importance to industry, since it is the document that describes how a weld should be carried out. It is a document that has been qualified by a specific method and provides the required variables of the welding procedure to ensure repeatability during production welding. The document should contain welding parameters, materials used, configuration of the joint, equipment characteristics and weld configuration. For more information see EN ISO 15607.

Qualification of welding procedures shall be performed prior to production welding. The manufacturer shall prepare a preliminary welding procedure specification (pWPS) and shall ensure that it is applicable for production using experience from previous production jobs and the general knowledge of the welding technology.

A pWPS shall be used as the basis for the establishment of a welding procedure qualification record (WPQR). The pWPS shall be tested in accordance with one of the methods listed in 5 (welding procedure test) or 6 (pre-production test). Five shall be used when the production part or joint geometry is accurately represented by a standardized test piece or pieces, as shown in 5.2. However, 6 shall be used when the production part or joint geometry is not accurately represented by standardized test specimens.

The minimum information required in a pWPS is given in 4.2. For some applications, it may be necessary to supplement or reduce the list.

A WPS covers a certain range of base materials, joint configurations and thicknesses. Ranges and tolerances in accordance with the relevant standard and the manufacturer's experience shall be specified when appropriate.

Annex B shows an example of a pWPS form. Two different types of joints are possible; joints of overlapping sheets and joints of overlapping tubes. The first one presents a preliminary WPS for electromagnetic pulse welding of sheets regarding the parameters found. The second one is based on the first, but adapted to overlapping tubes.

prEN 18007-4:2023 (E)

4.2 Technical content of a pWPS

4.2.1 General

The following information, as a minimum, shall be included in a pWPS.

4.2.2 Manufacturer information

- identification of the manufacturer,
- identification of the pWPS.

4.2.3 Base material type(s), temper(s), and reference standard(s)

- designation of the material(s) and referenced standard(s).

4.2.4 Base material dimensions and geometry

Dimensions and geometry of the parts comprising the welded joint:

- general geometry of the parts to be welded,
- outer diameter and wall thickness of tubes,
- dimensions of the sheets (length, width, thicknesses),
- geometrical specifics like chamfers, if applicable.

4.2.5 Equipment identification

- type of machine used and appropriate identification (model, serial number, manufacturer),
- ...

4.2.6 Tool coil identification

- materials, <https://standards.iteh.ai/catalog/standards/sist/047bbc02-a15d-4b0d-ad00-5cbe240096af/osist-pren-18007-4-2023>
- drawing or drawing number,
- description.

4.2.7 Clamping arrangement

- method and type of clamps and fixtures (dimensions and material).

4.2.8 Joint design

- sketch of the joint design including dimensions (overlap distance, distance between flyer and stationary part, ...),
- joint configuration.

4.2.9 Joint preparation and cleaning methods

For example:

- degreasing,
- removal of edge burrs,
- grinding and polishing, if needed,
- ...

4.2.10 Welding details

- the welding process shall be designated as listed in ISO 4063,
- welding method; welding of sheets or tubular parts,
- process parameters:
 - charging voltage,
 - energy,
 - geometrical process parameters like position in the tool coil,
 - ...

5 Qualification based on a welding procedure test

5.1 General

This method specifies how a welding procedure can be qualified by welding and testing of standardized test specimens.

<https://www.itesh.com/standards/prEN-18007-4-2023> The welded assembly, to which the welding procedure will relate to in production, shall be represented by actual components or by preparing a standardized test piece in accordance with 5.2.

The welding operator who undertakes the welding procedure test satisfactorily in accordance with this document is qualified according to prEN 18007-5.

Test specimens shall be cut from the actual components, subscale test component or welded separately according to 5.3.

5.2 Shape and dimensions of test specimens

5.2.1 General

The test pieces shall be designed to represent, as far as possible, the component and joint geometry.

The length or number of test specimens shall be sufficient to allow for all required tests to be performed. Test specimens longer than the minimum size may be used, to allow for additional specimens, for re-testing of specimens, or both (see 5.4.6). If relevant, the rolling direction or extrusion direction shall be marked on the test specimens.

5.2.2 Overlap joint of tubular parts

The test piece shall be prepared in accordance with Figure 1.