



Standard Specification for “Fiberglass” (Glass-Fiber-Reinforced Thermosetting-Resin) Pressure Pipe Fittings¹

This standard is issued under the fixed designation D5685; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers “fiberglass” (glass-fiber-reinforced thermosetting-resin) fittings for use with filament wound or centrifugally cast fiberglass pipe, or both, in sizes 1 in. through 24 in. for pipe manufactured to Specification D2996 or D2997, or both.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 The following safety hazard caveat pertains only to the test method portion, Section 7, of this specification:

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—The term “fiberglass pipe” as described in Section 3 of this specification applies to both reinforced thermosetting resin pipe (RTRP) and reinforced polymer mortar pipe (RPMP).

NOTE 2—For the purposes of this standard, ploymer does not include natural polymers.

NOTE 3—There is no known ISO equivalent to this standard.

2. Referenced Documents

2.1 ASTM Standards:²

- D618 Practice for Conditioning Plastics for Testing
- D883 Terminology Relating to Plastics
- D1598 Test Method for Time-to-Failure of Plastic Pipe Under Constant Internal Pressure
- D1599 Test Method for Resistance to Short-Time Hydraulic Pressure of Plastic Pipe, Tubing, and Fittings

¹ This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.23 on Reinforced Plastic Piping Systems and Chemical Equipment.

Current edition approved Feb. 1, 2011. Published March 2011. Originally approved in 1995. Last previous edition approved in 2005 as D5685 - 05. DOI: 10.1520/D5685-11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

- D1600 Terminology for Abbreviated Terms Relating to Plastics
 - D2143 Test Method for Cyclic Pressure Strength of Reinforced, Thermosetting Plastic Pipe
 - D2310 Classification for Machine-Made “Fiberglass” (Glass-Fiber-Reinforced Thermosetting-Resin) Pipe
 - D2992 Practice for Obtaining Hydrostatic or Pressure Design Basis for “Fiberglass” (Glass-Fiber-Reinforced Thermosetting-Resin) Pipe and Fittings
 - D2996 Specification for Filament-Wound “Fiberglass” (Glass-Fiber-Reinforced Thermosetting-Resin) Pipe
 - D2997 Specification for Centrifugally Cast “Fiberglass” (Glass-Fiber-Reinforced Thermosetting-Resin) Pipe
 - D3567 Practice for Determining Dimensions of “Fiberglass” (Glass-Fiber-Reinforced Thermosetting Resin) Pipe and Fittings
 - D4024 Specification for Machine Made “Fiberglass” (Glass-Fiber-Reinforced Thermosetting Resin) Flanges
 - F412 Terminology Relating to Plastic Piping Systems
 - F477 Specification for Elastomeric Seals (Gaskets) for Joining Plastic Pipe
- ### 2.2 ANSI Standard:
- B16.5 Steel Pipe Flanges, Flanged Valves and Fittings³

3. Terminology

3.1 Definitions:

3.1.1 *General*—Definitions are in accordance with Terminology D883 or F412. Abbreviations are in accordance with Terminology D1600, unless otherwise indicated. The abbreviation for fiberglass pipe is RTRP and the abbreviation for fiberglass fittings is RTRF.

3.1.2 *“fiberglass” pipe*—tubular product containing glass fiber reinforcements embedded in or surrounded by cured thermosetting resin. The composite structure may contain aggregate, granular or platelet fillers, thixotropic agents, pigments, or dyes. Thermoplastic or thermosetting liners or coatings may be included.

3.1.3 *reinforced thermosetting resin pipe*—fiberglass pipe without aggregate (RTRP).

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

*A Summary of Changes section appears at the end of this standard

3.1.4 *reinforced polymer mortar pipe*—fiberglass pipe with aggregate (RPMP).

3.1.5 *reinforced thermosetting resin fitting*—fiberglass fitting without aggregate (RTRF).

3.1.6 *reinforced polymer mortar fitting*—fiberglass fitting with aggregate (RPMF).

4. Classification

4.1 This specification covers fiberglass fittings defined by type (method of manufacture), grade (general resin type), class (general liner type), category (configuration of joining system), and pressure rating (a single letter designating the pressure class and method of manufacture).

4.2 Types:

4.2.1 *Type 1*—Filament-wound fittings manufactured by winding continuous fibrous-glass strand roving or roving tape, either preimpregnated or impregnated during winding, onto a mandrel, or a liner corresponding to the fitting shape.

4.2.2 *Type 2*—Compression molded fittings made by applying external pressure and heat to a molding compound that is confined within a closed mold.

4.2.3 *Type 3*—Resin transfer molded fittings manufactured by pumping a thermosetting resin into glass reinforcements that have been cut to size and clamped between matched molds.

4.2.4 *Type 4*—Centrifugally cast fittings made by applying resin and reinforcement to the inside of a mold that is rotating and heated, subsequently polymerizing the resin system.

4.2.5 *Type 5*—Contact molded fittings made by applying resin and reinforcement to a mold or to mitered filamentwound stock or centrifugally cast pipe stock. This procedure shall also cover “spray-up” fittings which are made by spraying resin and reinforcement on a mold or over mitered pipe wound stock. “Contact molding” includes both hand lay-up and spray-up manufacturing processes.

4.2.6 Fittings of Type 1 through Type 5 which require thrust blocking or external axial restraint when installed shall have the letter “R” appended to the type of designation. (For instance, a contact molded fitting requiring thrust blocking when installed would be designated a type “5R”.)

4.3 Grades:

4.3.1 *Grade 1*—Epoxy-resin.

4.3.2 *Grade 2*—Polyester-resin.

4.3.3 *Grade 3*—Phenolic-resin.

4.3.4 *Grade 4*—Vinylester resin.

4.3.5 *Grade 7*—Furan resin.

4.4 Classes:

4.4.1 *Class A*—No liner.

4.4.2 *Class B*—Polyester-resin liner (nonreinforced).

4.4.3 *Class C*—Epoxy-resin liner (nonreinforced).

4.4.4 *Class D*—Phenolic resin liner (nonreinforced).

4.4.5 *Class E*—Polyester-resin liner (reinforced).

4.4.6 *Class F*—Epoxy-resin liner (reinforced).

4.4.7 *Class G*—Phenolic resin liner (reinforced).

4.4.8 *Class H*—Thermoplastic-resin liner (specify).

4.4.9 *Class I*—Furan-resin liner (reinforced).

4.4.10 *Class J*—Vinylester resin liner (nonreinforced).

4.4.11 *Class K*—Vinylester resin liner (reinforced).

4.5 Joint Categories (Method of Joining):

4.5.1 *Category 1*—Taper-to-taper adhesive-bonded joint fittings manufactured with a tapered socket to be used in conjunction with a pipe or fitting with a matching spigot section and a suitable adhesive. This joining method provides an interference fit over the entire length of the bond line.

4.5.2 *Category 2*—Straight-taper adhesive-bonded joint fitting manufactured with a tapered socket to be used with a pipe or fitting with an untapered spigot section and a suitable adhesive. This joining method provides an interference fit at the bottom of the socket.

4.5.3 *Category 3*—Straight adhesive bonded joint fitting manufactured with an untapered socket for use with a pipe or fitting with an untapered spigot and a suitable adhesive. This joining provides no interference fit.

4.5.4 *Category 4*—Butt and strap joint made by a contact molding process which involves hand lay-up with glass-woven roving or chopped strand mat, or both, which is saturated with resin.

4.5.5 *Category 5*—Flanged fittings are available as all outlets flanged or as flange-by-joint specified in this specification. Flanges are in compliance with Specification **D4024**.

4.5.6 *Category 6*—Elastomeric (gasket) sealed joints with sealant manufactured in compliance with Specification **F477** for joints which have integral longitudinal restraint and do not require thrust blocking or external longitudinal restraint.

4.5.7 *Category 7*—Elastomeric (gasket) sealed joints with seals manufactured in compliance with Specification **F477** for joints which require thrust blocking or external longitudinal restraint.

4.6 *Pressure Rating*—Pressure rating shall be categorized by a single letter designation. Pressure designations are shown in **Table 1**. The pressure ratings are applicable for the temperature at which the fittings were tested and for lower temperatures down to -50°F (-46°C). When agreed upon between purchaser and manufacturer, pressure ratings determined by tests conducted following Practice **D2992** are acceptable.

4.7 *Designation Code*—The fitting designation code shall consist of the abbreviation RTRF or RPMF followed by the type, grade, and class in Arabic numerals and the pressure rating category as a capital letter.

NOTE 4—An example is RTRF 21A2E. This designation describes a

TABLE 1 Pressure Categories

| Designation | Pressure Rating ^A , psig (kPa) |
|-------------|---|
| A | 25 (172) |
| B | 50 (345) |
| C | 100 (690) |
| D | 150 (1034) |
| E | 200 (1380) |
| F | 250 (1724) |
| G | 300 (2068) |
| H | 400 (2759) |
| I | 500 (3448) |
| J | 1000 (6896) |

^A Pressure ratings are applicable only for the temperature at which the fittings were tested and for lower temperatures.