



**SLOVENSKI STANDARD**  
**oSIST prEN ISO 21207:2024**  
**01-julij-2024**

---

**Korozijski preskusi v umetnih atmosferah - Pospešeni korozijski preskusi, ki vključujejo izmenično izpostavljenost plinom, ki spodbujajo korozijo, nevtralnemu razprševanju soli in sušenju (ISO/DIS 21207:2024)**

Corrosion tests in artificial atmospheres - Accelerated corrosion tests involving alternate exposure to corrosion-promoting gases, neutral salt-spray and drying (ISO/DIS 21207:2024)

Korrosionsprüfungen in künstlichen Atmosphären - Beschleunigte Korrosionstests mit alternativer Einwirkung von korrosionsfördernden Gasen, neutraler Salzsprühung und Trocknung (ISO/DIS 21207:2024)

Essais de corrosion en atmosphères artificielles - Essais de corrosion accélérée par expositions alternées à des gaz favorisant la corrosion ou au brouillard salin neutre et à un séchage (ISO/DIS 21207:2024)

<https://standards.iteh.ai/catalog/standards/sist/e7a5eb57-8f27-42a0-8f9f-fb031a05e9e0/osist-pren-iso-21207-2024>

**Ta slovenski standard je istoveten z: prEN ISO 21207**

---

**ICS:**

77.060

Korozija kovin

Corrosion of metals

**oSIST prEN ISO 21207:2024**

**en,fr,de**





# DRAFT International Standard

## ISO/DIS 21207

### Corrosion tests in artificial atmospheres — Accelerated corrosion tests involving alternate exposure to corrosion-promoting gases, neutral salt-spray and drying

*Essais de corrosion en atmosphères artificielles — Essais de corrosion accélérée par expositions alternées à des gaz oxydants ou au brouillard salin neutre et à un séchage*

ICS: 77.060

ISO/TC 156

Secretariat: **SAC**

Voting begins on:  
**2024-06-05**

Voting terminates on:  
**2024-08-28**

Document Preview

[oSIST prEN ISO 21207:2024](https://standards.iteh.ai/catalog/standards/sist/e7a5eb57-8f27-42a0-8f9f-fb031a05e9e0/osist-pren-iso-21207-2024)

<https://standards.iteh.ai/catalog/standards/sist/e7a5eb57-8f27-42a0-8f9f-fb031a05e9e0/osist-pren-iso-21207-2024>

This document is circulated as received from the committee secretariat.

**ISO/CEN PARALLEL PROCESSING**

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENTS AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

## ISO/DIS 21207:2024(en)

# iTeh Standards (<https://standards.iteh.ai>) Document Preview

[oSIST prEN ISO 21207:2024](https://standards.iteh.ai/catalog/standards/sist/e7a5eb57-8f27-42a0-8f9f-fb031a05c9e0/osist-pren-iso-21207-2024)

<https://standards.iteh.ai/catalog/standards/sist/e7a5eb57-8f27-42a0-8f9f-fb031a05c9e0/osist-pren-iso-21207-2024>



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

## ISO/DIS 21207:2024(en)

## Contents

Page

|   |           |
|---|-----------|
| <b>Foreword</b> .....   | <b>iv</b> |
| <b>Introduction</b> .....   | <b>v</b>  |
| <b>1 Scope</b> .....  | <b>1</b>  |
| <b>2 Normative references</b> .....   | <b>1</b>  |
| <b>3 Terms and definitions</b> .....  | <b>1</b>  |
| <b>4 Apparatus and reagents</b> .....   | <b>1</b>  |
| 4.1 Exposure of test objects to mixtures of NO <sub>2</sub> and SO <sub>2</sub> ..... | 2         |
| 4.2 Salt spray testing in accordance with ISO 9227.....                               | 3         |
| 4.3 Drying in standard atmosphere.....  | 3         |
| <b>5 Evaluation of the corrosivity of the tests</b> .....                             | <b>3</b>  |
| 5.1 Reference test panels.....  | 3         |
| 5.2 Arrangement of the reference panels during testing.....                           | 3         |
| 5.3 Determination of mass loss after testing.....                                     | 3         |
| 5.4 Satisfactory performance of test.....   | 4         |
| <b>6 Test objects</b> .....   | <b>4</b>  |
| <b>7 Procedure</b> .....  | <b>5</b>  |
| 7.1 Test method A.....  | 5         |
| 7.1.1 Test cycle.....   | 5         |
| 7.1.2 Salt spray testing followed by drying (step a).....                             | 5         |
| 7.1.3 Exposure to corrosive gases followed by drying (step b).....                    | 5         |
| 7.1.4 Test duration.....  | 6         |
| 7.2 Test method B.....  | 6         |
| 7.2.1 Test cycle.....   | 6         |
| 7.2.2 Salt spray testing followed by drying (step a or step c).....                   | 6         |
| 7.2.3 Exposure to corrosive gases (step b or step d).....                             | 6         |
| 7.2.4 Test duration.....  | 7         |
| <b>8 Evaluation of results</b> .....  | <b>7</b>  |
| <b>9 Test report</b> .....  | <b>7</b>  |
| <b>Annex A (informative) Recommended test periods</b> .....                           | <b>9</b>  |
| <b>Annex B (informative) Results from Interlaboratory comparison</b> .....            | <b>10</b> |
| <b>Bibliography</b> .....   | <b>11</b> |

## ISO/DIS 21207:2024(en)

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the WTO principles in the Technical Barriers to Trade (TBT) see the following URL: [Foreword - Supplementary information](#)

This document was prepared by Technical Committee ISO/TC 156 Corrosion of metals and alloys.

This third edition cancels and replaces the second edition (ISO 21207:2015).

The main changes compared to the previous edition are as follows:

- Table A2 has been withdrawn.
- [Annex B](#) has been added. This annex includes an interlaboratory comparison, comprising three laboratories.
- The dispersion limits of Cu mass loss have been increased to 30 % in [Table 1](#).

These methods (A and B) are not intended to be used for comparative testing as a means of ranking different materials relative to each other with respect to corrosion resistance.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).