

Designation: D2041-03a Designation: D2041/D2041M - 11

# Standard Test Method for Theoretical Maximum Specific Gravity and Density of Bituminous Paving Mixtures<sup>1</sup>

This standard is issued under the fixed designation D2041/D2041M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\varepsilon$ ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

## 1. Scope

1.1This test method covers the determination of the theoretical maximum specific gravity and density of uncompacted bituminous paving mixtures at 25°C (77°F).

1.2The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

- 1.1 This test method covers the determination of the theoretical maximum specific gravity and density of uncompacted bituminous paving mixtures at 25°C [77°F].
- 1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.
- 1.2.1 Residual pressure measurements are shown in both the SI unit of kPa and the commonly used non-standard equivalent unit of "mm of Hg".
- 1.2.2 Measurements of volume and mass are only given in SI units because they are the only units typically used in practice when performing this test method.
- 1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

## 2. Referenced Documents

2.1 ASTM Standards:<sup>2</sup>

C670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials

D979 Practice for Sampling Bituminous Paving Mixtures

D3666 Specification for Minimum Requirements for Agencies Testing and Inspecting Road and Paving Materials

D4753 Guide for Evaluating, Selecting, and Specifying Balances and Standard Masses for Use in Soil, Rock, and Construction Materials Testing

- E1 Specification for ASTM Liquid-in-Glass Thermometers
- E12 Terminology Relating to Density and Specific Gravity of Solids, Liquids, and Gases<sup>3</sup>

## 3. Terminology

- 3.1 The terms "specific gravity" and "density" used in this test method are in accordance with Terminology E12.
- 3.2 Definitions of Terms Specific to This Standard:
- 3.2.1 density, as determined by this test method—the mass of a cubic metremeter of the material at 25°C (77°F)[77°F] in SI units.
  - 3.2.2 residual pressure, as employed by this test method—the pressure in a vacuum vessel when vacuum is applied.
- 3.2.3 specific gravity, as determined by this test method—the ratio of a given mass of material at 25°C (77°F)[77°F] to the mass of an equal volume of water at the same temperature.

<sup>&</sup>lt;sup>1</sup> This test method is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.21 on Specific Gravity and Density of Bituminous Mixtures.

Current edition approved  $\underline{\text{Dec.Jan.}}$  1,  $\underline{2003.2011.}$  Published  $\underline{\text{December 2003.March 2011.}}$  Originally approved in 1964. Last previous edition approved in 2003 as D2041 – 03 $\underline{\text{A}}$ . DOI:  $\underline{\text{10.1520/D2041-03A.}}$ 10.1520/D2041 $\underline{\text{D2041M-11.}}$ 

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>&</sup>lt;sup>3</sup> Withdrawn.

# 4. Summary of Test Method

4.1 A weighed sample of oven-dry paving mixture in the loose condition is placed in a tared vacuum vessel. Sufficient water at a temperature of 25°C  $(77^{\circ}F)[77^{\circ}F]$  is added to completely submerge the sample. Vacuum is gradually applied to reduce the residual pressure in the vacuum vessel to 4 kPa (30[30 mm of Hg)Hg] or less and then held for 15  $\pm$  2 min. At the end of the vacuum period, the vacuum is gradually released. The volume of the sample of paving mixture is obtained by immersing the vacuum container with the sample in a water bath and weighing or by filling the vacuum container level full of water and weighing in air. Both the temperature and mass are measured at this time. From these mass and volume measurements, the specific gravity or density at  $25^{\circ}C$  [77 °F] is calculated.

#### 5. Significance and Use

- 5.1 The theoretical maximum specific gravities and densities of bituminous paving mixtures are fundamental properties whose values are influenced by the composition of the mixture in terms of types and amounts of aggregates and bituminous materials.
- 5.1.1 Maximum specific gravity is used (1) in the calculation of air voids in the compacted bituminous paving mixture, (2) in calculating the amount of bitumen absorbed by the aggregate, and (3) to provide target values for the compaction of paving mixtures.

Note 1—The quality of the results produced by this standard are dependent on the competence of the personnel performing the procedure and the capability, calibration, and maintenance of the equipment used. Agencies that meet the criteria of Standard Practice D3666 are generally considered capable of competent and objective testing/sampling/inspection/etc. Users of this standard are cautioned that compliance with Practice D3666 alone does not completely assure reliable results. Reliable results depend on many factors; following the suggestions of Practice D3666 or some similar acceptable guideline provides a means of evaluating and controlling some of those factors

#### 6. Apparatus

- 6.1 Containers:
- 6.1.1 Vacuum Bowls—Either a metal or plastic bowl with a diameter of approximately 180 to 260 mm (7[7] to 10.25 in.) 10 in.] and a bowl height of at least 160 mm (6.3 in.) [6 in.] shall be equipped with a transparent cover fitted with a rubber gasket and a connection for the vacuum line. Both the bowl and cover should be sufficiently stiff to withstand the applied vacuum pressure without visibly deforming. The hose connection shall be covered with a small piece of fine wire mesh to minimize the loss of any fine material.
- Note—The 2—The transparent cover allows observation of the release of air bubbles.
  - 6.1.2 Vacuum Flask for Weighing in Air Only, a thick-walled volumetric glass flask with a capacity of approximately 4000 mL, fitted with a rubber stopper with a connection for the vacuum line. The hose connection in the flask should be covered with a small piece of fine wire mesh to minimize the loss of any fine material
  - 6.2 *Balance*, capable of being read to the nearest 0.1 g and conforming to the requirements of Specification D4753, Class GP2. If underwater measurements will be taken, then the balance shall be equipped with a suitable suspension apparatus and holder to permit weighing the sample while suspended from the center of the scale.
- 6.3 Vacuum Pump or Water Aspirator, capable of evacuating air from the vacuum container to a residual pressure of 4.0 kPa (30[30 mm of Hg)Hg] or less.
  - 6.3.1 When a vacuum pump is used, a suitable trap shall be installed between the vacuum vessel and vacuum source to reduce the amount of water vapor entering the vacuum pump.
  - 6.4 Residual Pressure Manometer or Calibrated Absolute Pressure Gage—This manometer or calibrated absolute pressure gage shall be used to confirm the specified pressure is applied to the container and shall be capable of measuring residual pressure to 4.0 kPa (30[30] mm of Hg)Hg] or less. It is to be connected at the end of the vacuum line using an appropriate tube and either a "T" connector on the top of the container or by using a separate opening (from the vacuum line) in the top of the container to attach the hose. To avoid damage, the manometer or gage itself is not to be situated on top of the vessel but adjacent to it.
- Note 23—Residual pressure in the vacuum vessel in millimet<del>re</del>rs of mercury is the difference in the height of mercury.
  - 6.5 *Manometer or Vacuum Gage*, suitable for measuring the vacuum being applied at the source of the vacuum. This device can be connected directly to the vacuum source or be in the vacuum line close to the source.
- Note3—The 4—The vacuum leg of a residual pressure manometer occasionally acquires one or more air bubbles that introduce error into the residual pressure reading. The additional vacuum gage or manometer provides a means to quickly detect differences between the two vacuum measurements.
  - 6.6 Thermometers—Calibrated liquid-in-glass thermometers of suitable range with subdivisions and maximum scale error of 0.5°C (0.9°F), or any other thermometric device of equal accuracy, precision, and sensitivity shall be used. Thermometers shall conform to the requirements of Specification—Calibrated liquid-in-glass thermometers of suitable range with subdivisions and maximum scale error of 0.5°C [1°F], conforming to the requirements of Specification E1—or any other thermometric device of equal accuracy, precision, and sensitivity shall be used.
  - 6.7 Water Bath, capable of maintaining, by any means, a constant temperature of  $25 \pm 1^{\circ}\text{C}$  (77[77  $\pm 1.8^{\circ}\text{F}).2^{\circ}\text{F}$ ]. The water bath must be suitable for immersion of the suspended container with its deaerated sample.
- 6.8 Bleeder Valve, attached to the vacuum trainline to facilitate both the adjustment of the vacuum being applied to the vacuum