

---

---

**Plastics — Abrasion test method for  
artificial turfs using combined UV  
exposure and mechanical wear**

*Plastiques — Méthode d'essai d'abrasion pour gazons artificiels  
combinant exposition UV et usure mécanique*

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

ISO 19721:2022

<https://standards.iteh.ai/catalog/standards/sist/7e1be67c-59d4-420c-a2ee-c4c671c0f1d6/iso-19721-2022>



iTeh STANDARD PREVIEW  
(standards.iteh.ai)

ISO 19721:2022

<https://standards.iteh.ai/catalog/standards/sist/7e1be67c-59d4-420c-a2ee-c4c671c0f1d6/iso-19721-2022>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2022

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>2</b>
<b>5 Apparatus</b> .....	<b>2</b>
<b>6 Test specimens</b> .....	<b>2</b>
<b>7 Test conditions</b> .....	<b>3</b>
7.1 Radiation.....	3
7.2 Relative humidity.....	3
7.3 Spray cycle.....	3
7.4 Exposure conditions.....	3
<b>8 Procedure</b> .....	<b>4</b>
8.1 Conditioning.....	4
8.2 Mounting and handling of the test specimen.....	4
8.3 Combined exposure.....	5
8.3.1 General.....	5
8.3.2 Simultaneous exposure.....	5
8.3.3 Sequential exposure.....	5
8.4 Radiant exposure measurement.....	5
<b>9 Determination of the changes</b> .....	<b>5</b>
9.1 Change of appearance.....	5
9.2 Test of sports functional characteristics.....	6
<b>10 Test report</b> .....	<b>6</b>
<b>Annex A (informative) Artificial turf</b> .....	<b>7</b>
<b>Annex B (informative) Examples of test results</b> .....	<b>9</b>
<b>Annex C (informative) Typical test apparatus</b> .....	<b>14</b>
<b>Bibliography</b> .....	<b>16</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 6, *Ageing, chemical and environmental resistance*.

ISO 19721:2022

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## Introduction

The radiant exposure, combined with simultaneous or sequential mechanical stud wear test, can assess the abrasion resistance of artificial turf used outdoors. The test method developed considers exposure that provides UV radiant exposure and stud wear. This accelerated test method is to be used as a screening or qualifying test for artificial turfs for public sports facilities. The test method may not necessarily correlate to results from exposure to actual use conditions.

The International Organization for Standardization (ISO) draws attention to the fact that it is claimed that compliance with this document may involve the use of a patent.

ISO takes no position concerning the evidence, validity and scope of this patent right.

The holder of this patent right has assured ISO that he/she is willing to negotiate licenses under reasonable and non-discriminatory terms and conditions with applicants throughout the world. In this respect, the statement of the holder of this patent right is registered with ISO. Information may be obtained from the patent database available at [www.iso.org/patents](http://www.iso.org/patents).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights other than those in the patent database. ISO shall not be held responsible for identifying any or all such patent rights.

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

ISO 19721:2022

<https://standards.iteh.ai/catalog/standards/sist/7e1be67c-59d4-420c-a2ee-c4c671c0f1d6/iso-19721-2022>



# Plastics — Abrasion test method for artificial turfs using combined UV exposure and mechanical wear

## 1 Scope

This document specifies an abrasion test method for accelerated testing of artificial turfs for use in sports facilities.

Combined exposure to simulated solar UV radiation and mechanical wear in simultaneous or sequential modes is the method used. The details of radiation, temperature, and moisture exposure, as well as to mechanical abrasion using soccer shoe studs on rotating drum assembly, are given in this document.

NOTE It was determined that simultaneous exposure was more effective than sequential exposure.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 4892-1, *Plastics — Methods of exposure to laboratory light sources — Part 1: General guidance*

ISO 4892-2, *Plastics — Methods of exposure to laboratory light sources — Part 2: Xenon-arc lamps*

ISO 4892-3, *Plastics — Methods of exposure to laboratory light sources — Part 3: Fluorescent UV lamps*

EN 15306, *Surfaces for outdoor sports areas — Exposure of synthetic turf to simulated wear*

DIN 75220, *Ageing of automobile components in solar simulation units*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org>

### 3.1

#### **artificial turf**

synthetic fibres made to mimic the natural grass

Note 1 to entry: It is a carpet-like mat consisting of *piles* (3.2), backing sheet, silica sand, rubber chips and shock absorption pad.

Note 2 to entry: See [Annex A](#) for the details on the construction of artificial turf.

### 3.2

#### **pile**

directional treads or fibres affixed to the backing layer sheet

### 3.3

#### **abrasion**

process of rubbing away *pile* (3.2) material under contact with stud under load

**3.4  
simultaneous exposure**

exposure to UV radiation and *abrasion* (3.3) occurring at the same time

**3.5  
sequential exposure**

exposure to UV radiation and *abrasion* (3.3) occurring one after the other

## 4 Principle

The specimen is exposed to both UV radiation and mechanical wear, either simultaneous or sequential. To create such a test, an apparatus consisting of an abrasion device, test specimen support and an artificial radiation source is used. The artificial turf specimen is placed on the specimen support and is made to come in contact with an abrasion device for cyclic frictional force application at the same time or in sequence with being subjected to predetermined exposure to radiation, heat and humidity conditions.

## 5 Apparatus

For the simultaneous exposure, the test device shall include a stud-cylinder abrasion device, test specimen support and radiation source; all assembled in an environmental test chamber or room with temperature and humidity control. A water spray nozzle can also be added.

For sequential exposure, a stud-cylinder abrasion device, and a test chamber meeting the irradiance, temperature, humidity and wetting, and other requirements for exposure devices in ISO 4892-1 are required.

A typical test apparatus is given in [Annex C](#).

**5.1 Laboratory radiation source**, an UVA-340 fluorescent lamp, Xenon arc lamp or metal halide lamp shall be used. If other radiation source is used, the radiation source shall be reported.

**5.1.1 Fluorescent UVA-340 lamp**, in accordance with ISO 4892-3, type 1A(UVA-340).

**5.1.2 Metal halide lamp** in accordance with DIN 75220.

**5.1.3 Xenon arc lamp**, in accordance with ISO 4892-2, method A (Xenon arc with simulated direct solar radiation filters).

**5.2 Abrasion device**, in accordance with EN 15306.

**5.3 Spraying system**, in accordance with ISO 4892-1.

## 6 Test specimens

The test specimen shall be at least 800 mm × 400 mm. The uniform abraded surface shall be at least 500 mm × 300 mm. Other sizes may be used upon agreement between the parties involved.

The dimension is changeable only if the irradiance uniformity is satisfied. Different specimen dimensions may be used provided that the irradiance uniformity on the specimen is assured.



## 7 Test conditions

### 7.1 Radiation

Unless otherwise specified, the irradiance shall be controlled at the levels specified in [Tables 1, 2](#) and [3](#). Other exposure levels may be used if agreed between the parties involved.

### 7.2 Relative humidity

Unless otherwise specified, the relative humidity or condensation cycle shall be controlled at the levels specified in [Tables 1, 2](#) and [3](#). Other exposure levels may be used if agreed between the parties involved.

### 7.3 Spray cycle

The spray cycles given in [Table 3](#) shall be used.

NOTE Spray cycle can be added to conditions given in [Table 1](#) and [Table 2](#), upon agreement by the parties involved.

### 7.4 Exposure conditions

The exposure conditions specified in [Tables 1, 2](#) and [3](#), providing various exposure conditions and cycle conditions for UVA-340, metal halide and Xenon devices, respectively, shall be followed.

Examples of test results using the conditions given in [Table 2](#) are shown in [Annex B](#).

NOTE Each type of radiation source has its own spectral irradiation distribution, and so can lead to different test results irrespective of the test materials. Therefore, the test result comparison of different test materials is effective only when obtained under the same light source, same cycles, and same test period. The light source can be selected upon agreement between the parties involved.

**Table 1 — Test conditions for UVA-340 and stud wear exposure**

Step	Parameter	Test condition		
UV exposure <sup>a</sup>	Irradiance setpoint	0,80 W/m <sup>2</sup> ·nm at 340 nm	—	
	Cycle	UV exposure (240 ± 4) min	Condensation (120 ± 2) min	
	BPT	(60 ± 3) °C	(45 ± 3) °C	
Stud wear	Linear speed (to and from)	(0,25 ± 0,05) m/s		
	Transverse movement (20 ± 1) mm	(0,015 ± 0,005) m/s		
	Temperature and relative humidity	Simultaneous exposure	Same as those in exposure step	
		Sequential exposure	(23 ± 2) °C, (50 ± 10) % R.H.	

<sup>a</sup> Detailed test conditions may be redesigned upon agreement between the parties involved. If the detailed test conditions are changed, they shall be stated in the test report.

**Table 2 — Test conditions for metal halide and stud wear exposure**

Step	Parameter		Test condition <sup>a</sup>
UV exposure <sup>b</sup>	Irradiance setpoint <sup>c</sup>		(1 000 ± 100) W/m <sup>2</sup> at (300 to 3 000) nm
	Chamber temperature		(32 ± 3) °C
	BPT		(48 ± 3) °C
	Relative humidity		(60 ± 10) %
Stud wear	Linear speed (to and from)		(0,25 ± 0,05) m/s
	Transverse movement (20 ± 1) mm		(0,015 ± 0,005) m/s
	Temperature and relative humidity	Simultaneous exposure	Same as those in exposure step
		Sequential exposure	(23 ± 2) °C, (50 ± 10) % R.H.

<sup>a</sup> Either open or closed system can be used to obtain the required test conditions and shall be reported.

<sup>b</sup> Detailed test conditions may be redesigned upon agreement between the parties involved. If the detailed test conditions are changed, they shall be stated in the test report.

<sup>c</sup> The tolerance of radiation is generally used among 10 % (±100), 5 % (±50), 2 % (±20) of the required irradiance, and can be chosen upon agreement between the parties involved.

**Table 3 — Test conditions for Xenon and stud wear exposure**

Step	Parameter		Test condition <sup>a</sup>
UV exposure <sup>b</sup>	Irradiance setpoint	(300 to 400) nm	(60 ± 2) W/m <sup>2</sup>
		340 nm	(0,51 ± 0,02) W/m <sup>2</sup> ·nm
	Spray		(102 ± 0,5) min, No spray Water sprayed
	Chamber temperature		(38 ± 3) °C
	BPT		(63 ± 3) °C
Relative humidity		(50 ± 10) %	—
Stud wear	Linear speed (to and from)		(0,25 ± 0,05) m/s
	Transverse movement (20 ± 1) mm		(0,015 ± 0,005) m/s
	Temperature and relative humidity	Simultaneous exposure	Same as those in exposure step
		Sequential exposure	(23 ± 2) °C, (50 ± 10) % R.H.

<sup>a</sup> Either open or closed system can be used to obtain the required test conditions, and shall be reported.

<sup>b</sup> Detailed test conditions may be redesigned upon agreement between the parties involved. If the detailed test conditions are changed, they shall be stated in the test report.

## 8 Procedure

### 8.1 Conditioning

The test specimen shall be stored for 24 h at (23 ± 2) °C, (50 ± 10) % R.H. before conducting the test.

### 8.2 Mounting and handling of the test specimen

The test specimen shall be constructed in accordance with the method provided by the manufacturer. The conditioned test specimen shall be mounted on the tray and the height of the cylinder shall be adjusted until all studs make contact with the test specimen.

NOTE Some common artificial turf constructions are given in [Table A.1](#).

### 8.3 Combined exposure

#### 8.3.1 General

The test specimens are subjected to both UV exposure and stud wear mechanical exposure. Two procedures are allowed: simultaneous exposure (8.3.2) and sequential exposure (8.3.3).

UV exposure and stud wear test shall be carried out following the procedure specified in Tables 1, 2, and 3, depending on the laboratory radiation source. Any changes to the specified conditions shall be stated in the test report.

Stud wear should be performed in accordance with EN 15306.

Stud-wear cycle should always begin at the end of the dry phase in the UV exposure cycle. This condition can be achieved by drying the turf for a period of at least 1 h under UV exposure.

#### 8.3.2 Simultaneous exposure

UV exposure and stud wear mechanical exposure shall be performed within one device, in simultaneous manner as specified in Table 4.

NOTE UV radiant exposure is limited by the ratio of the stud wear device to the specimen's surface. Stud abrasion is performed with the same climatic parameters as the UV exposure.

**Table 4 — UV-Stud cycles in a simultaneous manner**

Step	UV exposure	Stud wear
1	Initial UV exposure (h)	—
2	UV exposure (h)	Stud wear (cycle)
3	Final UV exposure (h)	—

#### 8.3.3 Sequential exposure

UV exposure and stud wear mechanical exposure shall be performed in the same or a separate device, in continual alternations as specified in Table 5.

Stud wear shall be performed at  $(23 \pm 2) ^\circ\text{C}$ ,  $(50 \pm 10) \% \text{R.H.}$

Sequential UV and stud wear test parameters (the total number of cycles and the duration of exposure/abrasion period, etc.) are to be decided upon agreement between the parties involved because of the difference in the environmental conditions of each country and the frequency of use<sup>[1],[2]</sup>.

**Table 5 — Sequential UV and stud wear test**

Step	UV exposure	Stud wear
1	Initial UV exposure (h)	—
2	—	Stud wear (cycle)

### 8.4 Radiant exposure measurement

Radiation exposure measurement shall be performed in accordance with ISO 4892-1.

## 9 Determination of the changes

### 9.1 Change of appearance

Report the visual change in fibrillation, flattening, breaking of fibres, abrasion, etc., using photographs.