



Designation: ~~B68-02~~ Designation: B68/B68M - 11

Standard Specification for Seamless Copper Tube, Bright Annealed ¹

This standard is issued under the fixed designation B68/B68M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification establishes the requirements for bright annealed seamless copper tube suitable for use in refrigeration, oil lines, gasoline lines, and so forth, where tube with an interior surface essentially free from scale and dirt is required.

1.1.1 Tubes made from any of the following Copper UNS No. designations shall be supplied, unless otherwise specified in the contract or purchase order:

Copper UNS No. ²	Type of Copper
C10200	Oxygen-free without residual deoxidants
C10300	Oxygen-free, extra low phosphorus
C10800	Oxygen-free, low phosphorus
C12000	Phosphorus deoxidized, low residual phosphorus
C12200	Phosphorus deoxidized, high residual phosphorus

~~1.2 Values stated in inch-pound units are the standard except for grain size, which is given in SI units.~~

~~1.3 This specification is the companion to SI Specification B68M; therefore, no SI equivalents are presented in this specification.~~

~~1.4 The following hazard statement pertains only to the test method described in Sections 20.5 and 21.2.6 of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*~~

1.2 Units—The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

- ~~2.1 ASTM Standards:³ B68M Specification for Seamless Copper Tube, Bright Annealed (Metric)~~
- B153 Test Method for Expansion (Pin Test) of Copper and Copper-Alloy Pipe and Tubing
- B251 Specification for General Requirements for Wrought Seamless Copper and Copper-Alloy Tube
- B251M Specification for General Requirements for Wrought Seamless Copper and Copper-Alloy Tube (Metric)
- B577 Test Methods for Detection of Cuprous Oxide (Hydrogen Embrittlement Susceptibility) in Copper
- B601 Classification for Temper Designations for Copper and Copper Alloys Wrought and Cast
- B846 Terminology for Copper and Copper Alloys
- B968/B968M Test Method for Flattening of Copper and Copper-Alloy Pipe and Tube
- E3 Guide for Preparation of Metallographic Specimens
- E88/E8M Test Methods for Tension Testing of Metallic Materials
- E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
- E53 Test Method for Determination of Copper in Unalloyed Copper by Gravimetry

¹ This specification is under the jurisdiction of ASTM Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.04 on Pipe and Tube.

Current edition approved Oct. 10, 2002. Published November 2002. Originally published as B68-22T. Last previous edition B68-99. DOI: 10.1520/B0068-02.

Current edition approved Feb. 15, 2011. Published March 2011. Originally approved in 1922. Last previous edition approved in 2002 as B68-02. DOI: 10.1520/B0068_B0068M-11.

² Refer to Practice E527 for explanation of unified numbering system (UNS).

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

- E62 Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods)
- E112 Test Methods for Determining Average Grain Size
- E243 Practice for Electromagnetic (Eddy-Current) Examination of Copper and Copper-Alloy Tubes
- E255 Practice for Sampling Copper and Copper Alloys for the Determination of Chemical Composition
- E527 ~~Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)~~ Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)
- E2575 Test Method for Determination of Oxygen in Copper and Copper Alloys

3. General Requirements

3.1 The following sections of Specification B251 or B251M are a part of this specification.

- 3.1.1 Terminology, General,
- 3.1.2 Material and Manufacture,
- 3.1.3 Workmanship, Finish, and Appearance,
- 3.1.4 Significance of Numerical Limits,
- 3.1.5 Inspection,
- 3.1.6 Rejection and Rehearing,
- 3.1.7 Certification,
- 3.1.8 Test Reports,
- 3.1.9 Packaging and Package Marking, and
- 3.1.10 Supplementary Requirements.

3.2 In addition, when a section with an identical title to those referenced in 3.1 appears in this specification, such section may contain requirements which supersede those appearing in Specification B251 or B251M. In case of conflict, this specification prevails.

4. Terminology

3-1

4.1 Definitions:

3-1.1 See Terminology

4.1.1 See Terminology B846 for definitions of terms related to copper and copper alloys.

3-1.2

4.1.2 *bright anneal, n*—a thermal treatment carried out in a controlled atmosphere so that surface oxidation is reduced to a minimum and the surface remains relatively bright.

3-2 Definitions of Terms Specific to This Standard:

3-2.1 *capable of*—the test need not be performed by the producer of the material. However, if subsequent testing by the purchaser establishes that the material does not meet these requirements, the material shall be subject to rejection. *stm-b68-b68m-11*

4.—the surface obtained by annealing under conditions of controlled atmosphere to prevent oxidation and to retain the original luster of the product.

5. Ordering Information

4-1 Include the following information in orders for products:

- 4-1.1 ASTM designation and year of issue (for example, B68-95);
- 4-1.2 UNS copper number (for example, C10200);
- 4-1.3 Temper (Section

5-1 Include the following information when placing orders for products under this specification, as applicable:

- 5-1.1 ASTM designation and year of issue (for example, B68/B68M – 11),
- 5-1.2 UNS copper number (for example, C10200),
- 5-1.3 Temper (Section 8),

4-1.4 Dimensions, diameter, and wall thickness (Section 16),

- 4-1.5 How furnished: straight lengths or coils;
- 4-1.6 Total length, or number of pieces, of each size;
- 4-1.7 Total weight, each size, and

4-1.8 When product is purchased for agencies of the U.S. Government:

4-2 The following options are available and shall be specified at the time of placing the order, when required:

- 4-2.1 Electromagnetic (eddy-current) test;
- 4-2.2 Embrittlement test;
- 4-2.3 Expansion test;
- 4-2.4 Flattening test;
- 4-2.5 Certification, and

4.2.6 Mill test report.

5. General Requirements

5.1 The following sections of Specification B251 are a part of this specification.

- 5.1.1 Terminology, General;
- 5.1.2 Material and Manufacture;
- 5.1.3 Workmanship, Finish, and Appearance;
- 5.1.4 Significance of Numerical Limits;
- 5.1.5 Inspection;
- 5.1.6 Rejection and Rehearing;
- 5.1.7 Certification;
- 5.1.8 Test Reports;
- 5.1.9 Packaging and Package Marking, and
- 5.1.10 Supplementary Requirements.

5.2 In addition, when a section with an identical title to those referenced in 5.1 appears in this specification, such section may contain requirements which supersede those appearing in Specification B251. In case of conflict, this specification prevails.

5.1.5 How furnished: straight lengths or coils,

5.1.6 Total length, or number of pieces, of each size,

5.1.7 Total weight, each size, and

5.1.8 When product is purchased for agencies of the U.S. Government.

5.2 The following options are available and shall be specified at the time of placing the order, when required:

5.2.1 Electromagnetic (eddy-current) test,

5.2.2 Embrittlement test,

5.2.3 Expansion test,

5.2.4 Flattening test,

5.2.5 Certification, and

5.2.6 Mill test report.

6. Materials and Manufacture

6.1 *Materials:*

6.1.1 The material of manufacture shall be billets, bars, or tube of the Copper UNS No. C10200, C10300, C10800, C12000, or C12200 and shall be of such soundness as to be suitable for processing into the tubular products described.

6.2 *Manufacture:*

6.2.1 The tube shall be manufactured by such hot- or cold-working processes as to produce a homogeneous uniform wrought structure in the finished product. The tube shall be cold drawn to the finished sizediameter and wall thickness, and shall be bright annealed to meet the specified temper.

7. Chemical Composition

7.1 The material shall conform to the chemical composition requirements prescribed in Table 1 for the specified copper.

7.2 ~~These specification limits do not preclude the presence of other elements. It is not prohibited to establish limits for unnamed elements and to require analysis by agreement between the manufacturer or supplier and the purchaser for the specified copper [alloy] UNS No. designation specified in the ordering information.~~

7.2 These composition limits do not preclude the presence of other elements. By agreement between the manufacturer and the purchaser, limits may be established and analysis required for unnamed elements.

8. Temper

8.1 The tube shall be furnished in either of two annealed tempers as follows:

TABLE 1 Chemical Composition

Element	Composition, %				
	Copper UNS No.				
	C10200 ^A	C10300	C10800	C12000	C12200
Copper, ^B min	99.95	99.90	99.9
Copper ^B + phosphorus, min	...	99.95	99.95
Phosphorus	...	0.001–0.005	0.005–0.012	0.004–0.012	0.015–0.040

^A Oxygen in C10200 shall be 10 ppm max. in accordance with E2575.

^B Silver counting as copper.

Annealed (O)

Temper Designation

 O50
 O60

 (Light annealed)
 (Soft annealed)

8.1.1 Tempers are defined in Classification B601.

9. Grain Size

9.1 Tube in the tempers O50 (light annealed) and O60 (soft annealed) shall conform to the requirements of Table 2.

10. Mechanical Property Requirements

10.1 *Tensile Strength:*

10.1.1 The tube shall have a minimum tensile strength of 30 ksi (210 MPa) when tested in accordance with Test Methods E8/E8M.

10.2 *Elongation:*

10.2.1 The tensile elongation of the tube shall be a minimum 40 % (2-in. or 50 mm gage length) when tested in accordance with Test Methods E8/E8M.

11. Performance Requirements

11.1 *Expansion Test:*

11.1.1 When specified in the contract or purchase order, the outside diameter of the tube furnished shall be capable of being expanded as follows when tested in accordance with Test Method B153.

Outside Diameter, in. Outside Diameter, in. (mm)	Expansion, % Expansion, %
— $\frac{3}{4}$ and under	40
— $\frac{3}{4}$ (19) and under	40
— over $\frac{3}{4}$	30
— over $\frac{3}{4}$ (19)	30

11.1.1.1 The expanded tube shall show no cracks or ruptures seen through visual inspection without the use of special equipment or enhancement excepting the use of corrective lenses.

11.1.2 A flattening test is an optional alternative to the expansion test for annealed tube over 4 in. (100 mm) in diameter.

11.2 *Flattening Test:*

11.2.1 ~~When specified in the contract or purchase order, the tube shall be capable of being flattened in accordance with the method described in 21.2.6.1 and shall contain no cracks or flaws visible to the unaided eye in the flattened section.~~

11.2.1 When specified in the contract or purchase order, the tube shall be capable of being flattened in accordance with the test method described in B968/B968M.

12. Microscopical Examination

12.1 Samples of Copper UNS Nos. C10200, C10300, and C12000 shall be free of cuprous oxide as determined by Procedure A of Test Methods B577. When Copper UNS Nos. C10800 or C12200 are supplied, examination is not required. In case of a dispute, a referee method shall be used in accordance with Procedure C of Test Methods B577.

13. Hydrogen Embrittlement

13.1 Samples of Copper UNS Nos. C10200, C12000, and C12200 shall be capable of passing the embrittlement test of Procedure B of Test Methods B577. The actual performance of this test is not mandatory under the terms of this specification unless definitely specified in the ordering information. In case of a dispute, a referee method shall be used in accordance with Procedure C of Test Methods B577.

14. Nondestructive Testing

14.1 Upon agreement between the manufacturer and the purchaser, each tube up to $3\frac{1}{8}$ in. (80 mm) in outside diameter shall be subjected to electromagnetic (eddy-current) test. For this test, the tube shall be examined in the final drawn or annealed temper, before coiling or in straight ~~lengths before final anneal lengths.~~

14.2 *Electromagnetic (Eddy-Current) Test:*

14.2.1 When examined in accordance with Practice E243, tubes that do not actuate the signaling device of the testing unit shall be considered as conforming to the requirements of the test.

TABLE 2 Average Grain Size Requirements

Temper	Grain Size, mm
O50	0.015 to 0.040
O60	0.040, min

15. Purchases for U.S. Government Agencies

15.1 When the contract or purchase order stipulates the purchase is for an agency of the U.S. Government, the tubes furnished shall conform to the conditions specified in the Supplementary Requirements of Specification B251 or B251M.

16. Dimensions and Permissible Variations

16.1 The dimensions and tolerances for product covered by this specification shall be as specified in the following tables and related paragraphs of Specification B251 or B251M:

16.1.1 *Wall Thickness Tolerance*—Table 1.

16.1.2 *Diameter Tolerances*—Table 3.

16.1.3 *Length Tolerances*—Tables 5 and 6.

16.1.4 *Squareness of Cut*—Refer to Squareness of Cut section 5.6.

16.2 *Coils, Length Tolerances*—Refer to Table 2, —Refer to Table 3, Table 4, and Table 5 of this specification.

17. Workmanship, Finish, and Appearance

17.1 *Workmanship*:

17.1.1 The tube furnished shall be clean, free of dirt, scale, and other defects, but blemishes of a nature that do not interfere with the intended application are acceptable.

17.1.2 The tube shall be bright annealed after the last drawing operation or, when required, after coiling.

17.2 *Finish and Appearance*:

17.2.1 The interior and exterior surfaces of the tube shall be typical in appearance to that of bright annealed copper.

18. Sampling

18.1 The lot size, portion size, and selection of sample portions shall be as follows:

18.1.1 *Lot Size*—The lot size shall be 10 000 lb (5000 kg) or fraction thereof.

18.1.2 *Portion Size*—Sample portions shall be selected as to be representative of the lot according to the following schedule:

Number of Pieces in Lot	Number of Sample Portions to Be Taken ^A
1 to 50	1
51 to 200	2
201 to 1500	3
Over 1500	0.2 % of the total number of pieces in the lot, but not to exceed 10 pieces

^AEach sample portion shall be taken from a separate tube.

18.1.2.1 In case of tube furnished in coils, a length sufficient for all necessary tests shall be cut from each coil selected for testing. The remaining portion of the selected coils shall be included in the shipment and the permissible variation in length on such coils shall be waived.

18.2 *Chemical Composition*:

18.2.1 The composite sample shall be prepared from approximate equal weights taken from the sample portions and prepared in accordance with Practice E255. The minimum weight of the composite sample shall be 150 g.

18.2.2 The manufacturer shall have the option of sampling at the time castings are poured or from the semifinished product. When composition has been determined during the manufacturing process, sampling of the finished product is not required.

18.2.3 When sampled at the time castings are poured, at least two samples shall be taken, one after the start and one near the end of the pour, for each group of castings poured simultaneously from the same source of molten metal.

18.2.4 When samples are taken from the semifinished product, a sample shall be taken to represent each 10 000 lb (5000 kg) or fraction thereof, except that not more than one sample per piece shall be required.

19. Number of Tests and Retests

19.1 *Tests*:

TABLE 3 Coil Length Tolerances (Specific Lengths)

Tube Outside Diameter, in.	Tolerances, in., All Plus, for Nominal Lengths in Feet	
	Up to 50, incl	Over 50 to 100, incl
Up to 2, incl	12	24
Tube Outside Diameter, mm	Tolerances, mm, All Plus, for Nominal Lengths, mm	
	Up to 15 000, incl.	Over 15 000 to 30 000, incl.
Up to 50, incl	300	610

TABLE 4 Coil Length Tolerances (Mill Lengths)
(Applicable only full-length pieces)

Tube Outside Diameter, in.	Tolerances, %, for Nominal Lengths in Feet	
	Up to 100, incl	Over 100 to 2000, incl
Up to 1, incl	5 ^A or 2 ft, whichever is greater	10 ^A
Over 1 to 2, incl	5 ^A or 2 ft, whichever is greater	No tolerances established

^A Expressed to the nearest 1 ft.

Tube Outside Diameter, mm	Tolerances, %, for Nominal Lengths, mm	
	Up to 30 000, incl	Over 30 000 to 600 000, incl
Up to 25, incl	5 ^A or 600 mm, whichever is greater	10 ^A
Over 25 to 50, incl	5 ^A or 600 mm, whichever is greater	No tolerances established

^A Expressed to the nearest 300 mm.

TABLE 5 Coil Schedule of Mill Lengths with Ends

Tube Outside Diameter, in.	Nominal Length, ft	Shortest Permissible Length, % of Nominal Length	Maximum Permissible Weights of Ends, % of Lot Weight
Up to 1, incl	up to 100, incl	70 ^A	10
Over 1, to 2, incl	up to 100, incl	60 ^A	20
Up to 1, incl	over 100 to 2000, incl	50	50 ^B

^A Expressed to the nearest 1 ft.

^B Short pieces shall, at the option of the supplier, be included as follows: up to 10 % of lot weight between 50 ft and one quarter of full length and up to 40 % between one quarter and full length.

Tube Outside Diameter, mm	Nominal Length, mm	Shortest Permissible Length, % of Nominal Length	Maximum Permissible Weights of Ends, % of Lot Weight
Up to 25, incl	up to 30 000, incl	70 ^A	10
Over 25 to 50, incl	up to 30 000, incl	60 ^A	20
Up to 25, incl	over 30 000 to 60 000, incl	50	50 ^B

^A Expressed to the nearest 300 mm.

^B Short pieces shall, at the option of the supplier, be included as follows: up to 10 % of lot weight between 15 m and one quarter of full length and up to 40 % between one quarter and full length.

19.1.1 *Chemical Composition*—Shall be determined as the arithmetic mean of results from at least two replicate determinations for each specified element.

19.1.2 *Tensile, Elongation, and Grain Size*—Shall be reported as the average of results from test specimens and each specimen must conform to specification requirements.

19.1.3 *Other Tests*—At least two specimens shall be prepared for each of the other tests and each must meet test requirements.

19.2 *Retest*:

19.2.1 When test results obtained by the purchaser fail to conform with the product specification requirement(s), the manufacturer or supplier shall have the option to perform a retest.

19.2.2 Retesting shall be as directed in this specification for the initial test except for the number of test specimens which shall be twice that normally required for the test.

19.2.3 Test results for all specimens shall conform to the requirement(s) of this specification in ~~retest and failure~~ retest. Failure to comply shall be cause for lot rejection.

20. Specimen Preparation

20.1 *Chemical Composition*:

20.1.1 Preparation of the analytical specimens for the determination of chemical composition shall be the responsibility of the reporting laboratory.