



Designation: ~~C866-77~~ (Reapproved 2006) Designation: C866 – 11

Standard Test Method for Filtration Rate of Ceramic Whiteware Clays¹

This standard is issued under the fixed designation C866; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers the determination of the rate at which a layer of clay-water paste is formed from a clay-water slip under pressure filtration. The filtration rate is directly related to such whiteware operations as filter pressing, slip casting, and drying of ware in which water permeability through a clay-water paste is the controlling mechanism.

1.2 A straight-line relationship exists between the time of filter pressing and the square of the thickness of the paste layer. The filtration rate is directly related to the filter press pressure and the void fraction of the paste layer, and is inversely related to the square of the clay surface area, the ratio of solids to liquid in the slip, and the viscosity of water at the testing temperature.

1.3

1.3 The values stated in acceptable metric units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:²

C324 Test Method for Free Moisture in Ceramic Whiteware Clays

3. Apparatus

3.1 Balance, 0.001-g sensitivity.

3.2 Blender.

3.3 Filter Press, capable of operation at 345 kPa (50 psi).

3.4 Stop Watch.

3.5 Vernier Calipers, capable of measuring thickness to the nearest 0.1 mm.

4. Procedure

4.1 Weigh 100 g of clay, dried in accordance with Test Method C324, to the nearest 0.1 g and mix with 300 mL of water measured to the nearest 1.0 mL for 10 min in a blender.

4.2 Store the slip in a closed container for at least 24 h to allow the clay and water to reach equilibrium conditions.

4.3 Remix the clay-water slurry for 5 min in the blender.

4.4 Pour the clay-water slurry into the filter press and apply 345 kPa (50 psi) air pressure for 30 min.

4.5 Relieve the pressure from the filter press and then pour the clay-water slurry from the top of the filter cake that has formed. A sharp movement of the wrist is required to remove all of the remaining slip from the filter press.

4.6 Record the temperature of the filtrate.

4.7 Reapply air pressure to the filter press for 10 min to force some of the water from the cake that has formed.

NOTE 1—Some clays have a fast filtration rate and the air may pass through the cake in less than 10 min. In this case, the air pressure should be relieved as soon as the sound of air emitting from the press is detected.

4.8 Remove the filter cake from the press and measure the thickness to the nearest 0.1 mm with the vernier calipers.

¹ This test method is under the jurisdiction of ASTM Committee C21 on Ceramic Whitewares and Related Products and is the direct responsibility of Subcommittee C21.04 on Raw Materials.

Current edition approved Feb. 15, 2006. Published February 2006.

Originally approved in 1977. Last previous edition approved in 1997 as C866-77(1997)^{e1}. DOI: 10.1520/C0866-77R06.

Current edition approved March 1, 2011. Published April 2011. Originally approved in 1977. Last previous edition approved in 2006 as C866-77 (2006). DOI: 10.1520/C0866-11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.