



Designation: C1107/C1107M – 11

Standard Specification for Packaged Dry, Hydraulic-Cement Grout (Nonshrink)¹

This standard is issued under the fixed designation C1107/C1107M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification covers packaged dry, hydraulic cement grout (nonshrink) intended for use under applied load (such as to support a structure, a machine, and the like) where a change in height below initial placement height is to be avoided.

1.2 Grouts covered are composed of hydraulic cement, fine aggregate, and other ingredients. They require only the addition of mixing water for use.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 The following safety hazards caveat pertains only to the test method portion of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

C109/C109M Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in. or [50-mm] Cube Specimens)

C125 Terminology Relating to Concrete and Concrete Aggregates

C138/C138M Test Method for Density (Unit Weight), Yield, and Air Content (Gravimetric) of Concrete

C157/C157M Test Method for Length Change of Hardened Hydraulic-Cement Mortar and Concrete

C185 Test Method for Air Content of Hydraulic Cement Mortar

C305 Practice for Mechanical Mixing of Hydraulic Cement Pastes and Mortars of Plastic Consistency

C702 Practice for Reducing Samples of Aggregate to Testing Size

C827 Test Method for Change in Height at Early Ages of Cylindrical Specimens of Cementitious Mixtures

C939 Test Method for Flow of Grout for Preplaced-Aggregate Concrete (Flow Cone Method)

C1090 Test Method for Measuring Changes in Height of Cylindrical Specimens of Hydraulic-Cement Grout

C1437 Test Method for Flow of Hydraulic Cement Mortar

3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification, refer to Terminology **C125**.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *consistency, flowable, n*—a grout consistency having a flow of 125 to 145 by the flow test in accordance with the applicable provisions of Test Method **C1437**; the flow after 5 drops of the flow table in 3 s.

3.2.2 *consistency, fluid, n*—a grout consistency having a time of efflux of 10 to 30 s when tested by the flow cone procedure of Test Method **C939**.

3.2.3 *consistency, plastic, n*—a grout consistency having a flow of 100 to 125 by the flow test in accordance with the applicable provisions of Test Method **C1437**; the flow after 5 drops of the flow table in 3 s.

4. Ordering Information

4.1 When the purchaser specifies that properties of the packaged, dry grout meet the requirements of this specification, also specify which, if any, of the optional requirements apply.

4.2 When the grout is to be used in contact with stressed tendons or other corrosion-sensitive, load-bearing structural members, the purchaser shall supply this information to the manufacturer and obtain assurances that the material meets relevant chloride, nitrite, nitrate, sulfide, and sulfate

¹ This specification is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.43 on Packaged Dry Combined Materials.

Current edition approved April 1, 2011. Published April 2011. Originally approved in 1991. Last previous edition approved in 2008 as C1107/C1107M-08. DOI: 10.1520/C1107_C1107M-11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard

requirements, and any other material limitations imposed by the applicable codes and standards (See **Note 1**).

4.3 When the grout is to be used in abnormal or aggressive environments, the purchaser shall supply this information to the manufacturer and obtain assurance that the grout has a successful history of performance in the same or similar exposures.

NOTE 1—Since all conditions of use cannot be anticipated, this specification requires nonshrink grout to exhibit no shrinkage when tested in a laboratory-controlled, moist-cured environment, and requires only the reporting of the observed height change, usually shrinkage, when test specimens are subjected to some degree of drying. It is suggested that users consult with manufacturers on specific applications to determine the applicability of specific test results.

5. Materials

5.1 The materials used as ingredients in packaged, dry, grout include hydraulic cement, fine aggregate, and other ingredients.

6. Performance Requirements

6.1 Specimens shall be made from freshly mixed grout and from grout that has been retained in the mixer for the maximum usable working time allowed by the manufacturer. Specimens from both conditions shall meet the requirements prescribed in **Table 1**.

6.2 Specimens shall be prepared using materials and equipment at temperatures representing the maximum and minimum usable temperatures specified by the manufacturer for his product. Specimens from both conditions shall meet the requirements prescribed in **Table 1**, except that the compressive-strength requirements do not have to be met at minimum usable temperature.

6.3 Specimens for testing shall be prepared by combining the use of grout retained in the mixer as in 6.1 with the minimum and maximum as mixed and curing temperatures used in 6.2. Specimens from these combinations of conditions shall meet the requirements of **Table 1**, except that the compressive-strength requirements do not have to be met at minimum usable temperature.

6.4 All test specimens for performance evaluation shall be prepared using the highest water to solids ratio, maximum flow, or most fluid consistency stated on the package.

TABLE 1 Performance Requirements

Compressive Strength, min	MPa	[psi]
1 day ^A	7.0	[1000]
3 day	17.0	[2500]
7 day	24.0	[3500]
28 day	34.0	[5000]
Early Age Height Change		
Max % @ Final Set		+ 4.0
Height Change of Moist Cured Hardened Grout at 1, 3, 14 and 28 Days		
Maximum, %		+ 0.3
Minimum, %		0.0

^A When required, the purchaser must so specify in the purchase contract.

7. Sampling

7.1 Use whole packages of grout selected at random from the lot of grout to be examined.

7.2 Where lesser quantities of grout will serve the purpose, select 3000 g [7 lb] of dry grout from a whole package in accordance with the mechanical-splitter method in Practice **C702**. For high-density grouts, adjust the mass to provide an equivalent volume.

8. Batching

8.1 Grout mixtures shall be produced in the following conditions:

8.1.1 Batch grout mixtures at temperature conditions corresponding to the maximum recommended temperature limit and at a temperature corresponding to the minimum temperature stated by the manufacturer.

8.1.2 For standard temperature testing, maintain the grout mixture and the testing equipment at a temperature of 23 ± 2 °C [73.5 ± 3.5 °F].

8.2 Bring all materials and equipment to be used in preparing test specimens to the specified test temperature, ± 3 °C [± 5 °F] prior to use.

8.2.1 When the controlled-environment test room is too small to accommodate large equipment, immediately prior to use, bring the mixer to the desired testing temperature by filling it with water at the appropriate temperature and agitating it by turning the mixer on. When this water has stabilized at the desired temperature, discard it and start preparing the batch immediately.

8.3 The manufacturer is not prohibited from including, in the package instructions, procedures for adjusting the mixing water temperature to achieve limitations imposed on the grout use temperatures. Use of this technique shall not abrogate the extended mixing time requirement of this specification.

9. Proportioning

9.1 The minimum and maximum amount of water recommended by the manufacturer on the package shall be used to determine conformance with the requirements of this specification. If the manufacturer provides maximum flow (thinnest consistency) information on the package, conduct consistency tests to an accuracy of ± 5 % to determine the amount of water to be added for testing. In either case, express the weight of water so determined as a ratio of water to dry grout material by weight. If both are given, make tests at whichever involves the larger amount of water by ratio of dry grout mixture.

10. Mixing

10.1 Either the mixer described in Practice **C305** or the mortar mixer described in 10.1.2 shall be used for performance qualifications. In the event of a dispute, the mixer described in 10.1.2 shall be used for the referee test.

NOTE 2—The referee test is a test made to settle disagreement as to the conformance to the specified requirements.

10.1.1 *Bench Scale Epicyclic Mixer*—The mortar-mixing apparatus shall be as specified in Practice **C305**. However, the