

Designation: D5989-05 Designation: D5989 - 11

# Standard Specification for Extruded and Monomer Cast Shapes Made from Nylon (PA)<sup>1</sup>

This standard is issued under the fixed designation D5989; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\varepsilon$ ) indicates an editorial change since the last revision or reapproval.

#### INTRODUCTION

This specification is intended to be a means of calling out plastic products used in the fabrication of end items or parts.

### 1. Scope\*

1.1This specification covers requirements and test methods for the material, dimensions, and workmanship, and the properties of extruded and east sheet, plate, rod and tubular bar manufactured from nylon or monomers.

1.2The properties included in this specification are those required for the compositions covered. Requirements necessary to identify particular characteristics important to specialized applications may be described by using the classification system given in Section

- 1.1 This specification covers requirements and test methods for the material, dimensions, and workmanship, and the properties of extruded and cast sheet, plate, rod and tubular bar, excluding pipe and fittings, manufactured from nylon or monomers.
- 1.2 The properties included in this specification are those required for the compositions covered. Section 4 —presents a classification system for defining requirements for particular characteristics important to specialized applications.
  - 1.3 This specification allows for the use of recycled plastics (as defined in Guide <del>D5033</del>D7209).
  - 1.4 The values stated in inch-pound units are regarded as standard. The values in parentheses are for information only.
- 1.5 The following precautionary caveat pertains only to the test method portions of this specification. This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

Note 1—There is no known ISO equivalent to this standard.

Note 2—This specification is intended to replace Federal Standard LP-410A and PS 50.

#### 2. Referenced Documents

2.1 ASTM Standards:<sup>2</sup>

D256 Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics

D638 Test Method for Tensile Properties of Plastics

D790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials

D883 Terminology Relating to Plastics

D3892 Practice for Packaging/Packing of Plastics D5033Guide for Development of ASTM Standards Relating to Recycling and
Use of Recycled Plastics

D6779 Classification System for Polyamide Molding and Extrusion Materials (PA) Classification System for Polyamide Molding and Extrusion Materials (PA)

D7209 Guide for Waste Reduction, Resource Recovery, and Use of Recycled Polymeric Materials and Products

2.2 ANSI Standard:<sup>3</sup>

Z1.4-1993Sampling Procedures and Tables for Inspection by Attributes Z1.9 - 2008 Sampling Procedures for Inspection by Variables

<sup>&</sup>lt;sup>1</sup> This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials. Current edition approved July 15, 2005. Published August 2005. Originally approved in 1998. Last previous edition approved in 2003 as D5989-03. DOI: 10.1520/D5989-05.

Current edition approved April 1, 2011. Published April 2011. Originally approved in 1998. Last previous edition approved in 2005 as D5989 - 05. DOI: 10.1520/D5989-11.

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

2.3 Federal Standard:<sup>4</sup> LP-410A Nylon Stock Shapes

## 3. Terminology

- 3.1 Definitions:
- 3.1.1 *regrind (plastic)*, *n*—a product or scrap such as sprues, runners and edge trim that have been reclaimed by shredding and granulating for use in-house.
- 3.1.2 For definitions of other technical terms pertaining to plastics used in this specification, see Terminology D883 or Guide D5033 or Guide D7209.
  - 3.2 Definitions of Terms Specific to This Standard:
  - 3.2.1 finished product (F), n—product that meets the dimensional criteria of Tables 1-4 of this specification.
  - 3.2.2 monomer-cast nylon, n—nylon polymer prepared by polymerization of epsilon-caprolactam or lauryllactam monomer.
  - 3.2.3 oversize product (O), n—product that meets the designated dimensional criteria of Table 2 and Table 4 only.
  - 3.2.4 plate, n—flat stock greater than  $\frac{3}{8}$  in. (9.5 mm).
  - 3.2.5 recycled-plastic shape, n—a product made from up to 100 % post-consumer material.
- 3.2.6 rod, n—an extruded solid cylindrical shape with a minimum diameter of  $\frac{1}{16}$  in., or cast solid cylindrical shapes with a minimum diameter of 1 in. (25.4 mm).
  - 3.2.7 *sheet*, n—flat stock less than and including  $\frac{3}{8}$  in. thickness.
- 3.2.8 tubular bar, n—extruded annular shapes with minimum inside diameter of  $\frac{3}{8}$  in. (9.5 mm) and minimum wall thickness of  $\frac{1}{16}$  in. (1.6 mm), or cast shapes with minimum inside diameter of  $\frac{1}{2}$  in. (12.7 mm), and minimum wall of  $\frac{1}{4}$  in. (6.4 mm).
- 3.2.9 *unmodified virgin plastic shape*, *n*—a product produced from virgin plastic, as furnished by a manufacturer, with no additives or processing aids.
- 3.2.10 *virgin-plastic shape*, *n*—product that is produced from 100 % plastic resin that has not been subjected to subsequent melt processing.

# Document Preview

#### ASTM D5989-1

TABLE 1 Dimensional Requirements for Extruded Nylon Rod<sup>A</sup>

Size, in. <sup>B</sup>	Length Tolerance, in.	Diameter Tolerance, in.	Roundness TIR, in.	Camber, in./ft	
1/16	+1 -0	+0.003 -0	0.002	21/2 /8	
1/8	+1 -0	+0.003 -0	0.002	21/2 /8	
3/16	+1 -0	+0.003 -0	0.002	21/2 /8	
1/4	+1 -0	+0.003 -0	0.002	21/2 /8	
3/8	+1 -0	+0.003 -0	0.002	21/2 /8	
1/2	+1 -0	+0.003 -0	0.002	21/2 /8	
5/8	+1 -0	+0.003 -0	0.002	21/2 /8	
3/4	+1 -0	+0.003 -0	0.002	21/2 /8	
7/8	+1 -0	+0.003 -0	0.002	21/2 /8	
1	+1 -0	+0.003 -0	0.002	11/4 /8	
11/8	+1 -0	+0.005 -0	0.005	11/4 /8	
11/4	+1 -0	+0.005 -0	0.005	11/4 /8	
13/8	+1 -0	+0.005 -0	0.005	11/4 /8	
11/2	+1 -0	+0.005 -0	0.005	11/4 /8	
<b>1</b> 5⁄8	+1 -0	+0.005 -0	0.005	11/4 /8	
13/4	+1 -0	+0.005 -0	0.005	11/4 /8	
17/8	+1 -0	+0.005 -0	0.005	11/4 /8	
2	+1 -0	+0.005 -0	0.010	11/4 /8	
21/8 -23/4	+1 -0	+0.015 -0	0.030	11/4 /8	
3–5	+1 -0	+0.250 -0	0.060	1/4 /4	
Over 5	+1 -0	+0.250 -0	0.060	1/4 /4	

ABased on dry-as-manufactured condition and proper product storage and nandling.

<sup>&</sup>lt;sup>4</sup> Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401, http://www.access.gpo.gov.

<sup>&</sup>lt;sup>B</sup>To convert inches to millimetres, multiply by 25.40.



TABLE 2 Dimensional Requirements for Monomer Cast Nylon Rod<sup>A</sup>

Size, in. <sup>B</sup>	Length	Diameter Tolerance, in.		Roundnes	ss TIR, in.	Camber, in./ft		
	Tolerance, in.	Finished <sup>C</sup>	Oversize <sup>D</sup>	Finished <sup>C</sup>	Oversize <sup>D</sup>	Finished <sup>C</sup>	Oversize <sup>D</sup>	
1	+1 -0	+0.015 -0		0.015	N/A <sup>E</sup>	1/4 /4	N/A	
<b>1</b> 1/8	+1 -0	+0.015 -0		0.015	N/A	1/4 /4	N/A	
11/4	+1 -0	+0.015 -0		0.015	N/A	1/4 /4	N/A	
1%	+1 -0	+0.015 -0	+0.100 -0	0.015	N/A	1/4 /4	N/A	
11/2	+1 -0	+0.015 -0	+0.100 -0	0.015	N/A	1/4 /4	N/A	
15/8	+1 -0	+0.015 -0	+0.100 -0	0.015	N/A	1/4 /4	N/A	
13/4	+1 -0	+0.015 -0	+0.100 -0	0.015	N/A	1/4 /4	N/A	
17/8	+1 -0	+0.015 -0	+0.100 -0	0.015	N/A	1/4 /4	N/A	
2-23/4	+1 -0	+0.015 -0	+0.125 -0	0.015	N/A	1/4 /4	N/A	
3–5	+1 -0	+0.250 -0	+0.250 -0	0.060	N/A	1/4 /4	N/A	
Over 5	+1 -0	+0.250 -0	+0.500 -0	N/A	N/A	N/A	N/A	

<sup>&</sup>lt;sup>A</sup>Based on dry-as-manufactured condition and proper product storage and handling.

TABLE 3 Dimensional Requirements for Extruded Nylon Sheets and Plates<sup>A</sup> (Squareness Requirement Listed in 11.4)

Size, in. <sup>B</sup>	Width Tolerance, in.	Thickness Tolerances, in. $^{C}$	Length Camber, in./ft	Width Bow, in./ft	
1/16	+0.5 -0	±0.005	3/4 /4	3/16 /2	
3/32	+0.5 -0	±0.005	3/4 /4	3/16 /2	
1/8	+0.5 -0	±0.005	3/4 /4	3/16 /2	
3/16	+0.5 -0	+0.025 -0	3/4 /4	3/16 /2	
1/4	+0.5 -0	+0.025 -0	3/4 /4	3/16 /2	
5/16	+0.5 -0	+0.025 -0	3/4 /4	3/16 /2	
3/8	+0.5 -0	+0.025 -0	3/4 /4	3/16 /2	
<sup>7</sup> / <sub>16</sub>	+0.5 -0	+0.025 -0	3/4 /4	3/16 /2	
1/2	+0.5 -0	+0.025 -0	3/4 /4	3/16 /2	
5/8	+0.5 -0	+0.025 -0	3/4 /4	3/16 /2	
3/4	+0.5 -0	+0.025 -0	3/4 /4	3/16 /2	
7/8	+0.5 -0	+0.025 -0	3/4 /4	3/16 /2	
1	+0.5 -0	+0.025 -0	1/4 /4	1/16 /2	
11/8	+0.5 -0	+0.025 -0	1/4 /4	1/16 /2	
11/4	+0.5 -0	+0.025 -0	1/4 /4	1/16 /2	
13/8	+0.5 -0	+0.025 -0	1/4 /4	1/16 /2	
11/2	+0.5 -0	+0.025 -0	_ 1 1/4 /4	1/16 /2	
15/8	+0.5 -0	+0.025 -0	1/4 /4	1/16 /2	
13/40 g/St	+0.5 -0 s/sist/1	+0.025 -0	203-1/4/40-80	7b-1/16/25bce19	
17/8	+0.5 -0	+0.025 -0	1/4 /4	1/16 /2	
2	+0.5 -0	+0.025 -0	1/4 /4	1/16 /2	
Over 2	+0.5 -0	+0.050 -0	1/4 /4	1/16 /2	

 $<sup>^{</sup>A}\!\text{Based}$  on dry-as-manufactured condition and proper product storage and handling.

TABLE S-PA Requirements for Nylon (Polyamide) Shapes, Dry-as-Manufactured (<0.2 % Moisture)

<sup>&</sup>lt;sup>B</sup>To convert inches to millimetres, multiply by 25.40.

<sup>&</sup>lt;sup>C</sup>Finished product as defined in 3.2.1.

DOversize product as defined in 3.2.3; roundness and camber not applicable.

ENot applicable.

<sup>&</sup>lt;sup>B</sup>To convert inches to millimetres, multiply by 25.40.

 $<sup>^{\</sup>circ}$ Length tolerance in inches for all sizes at 48-in. length is +1.001 -0 and at 144-in. length is +1.001 -0.

TABLE 4 Dimensional Requirements for Monomer Cast Nylon Sheets and Plates<sup>4</sup> (Squareness Requirement Listed in 11.4)

Size, in. <sup>B</sup>	Width Tolerance,	Thickness Tolerances, in.		Length Camber, in./ft		Width Bow, in./ft	
	in.	Finished <sup>C</sup>	Oversize <sup>D</sup>	Finished <sup>C</sup>	Oversize <sup>D</sup>	Finished <sup>C</sup>	Oversize <sup>D</sup>
3/16	+0.5 -0	+0.025 -0		1/4 /4	N/A <sup>E</sup>	1/16 /2	N/A
1/4	+0.5 -0	+0.025 -0		1/4 /4	N/A	1/16 /2	N/A
5/16	+0.5 -0	+0.025 -0		1/4 /4	N/A	1/16 /2	N/A
3/8	+0.5 -0	+0.025 -0	+0.080 -0	1/4 /4	N/A	1/16 /2	N/A
<sup>7</sup> / <sub>16</sub>	+0.5 -0	+0.025 -0	+0.080 -0	1/4 /4	N/A	1/16 /2	N/A
1/2	+0.5 -0	+0.025 -0	+0.080 -0	1/4 /4	N/A	1/16 /2	N/A
5/8	+0.5 -0	+0.025 -0	+0.080 -0	1/4 /4	N/A	1/16 /2	N/A
3/4	+0.5 -0	+0.025 -0	+0.080 -0	1/4 /4	N/A	1/16 /2	N/A
7/8	+0.5 -0	+0.025 -0	+0.080 -0	1/4 /4	N/A	1/16 /2	N/A
1	+0.5 -0	+0.025 -0	+0.100 -0	1/4 /4	N/A	1/16 /2	N/A
11/8	+0.5 -0	+0.025 -0	+0.100 -0	1/4 /4	N/A	1/16 /2	N/A
11/4	+0.5 -0	+0.025 -0	+0.100 -0	1/4 /4	N/A	1/16 /2	N/A
13/8	+0.5 -0	+0.025 -0	+0.100 -0	1/4 /4	N/A	1/16 /2	N/A
11/2	+0.5 -0	+0.025 -0	+0.100 -0	1/4 /4	N/A	1/16 /2	N/A
15/8	+0.5 -0	+0.025 -0	+0.100 -0	1/4 /4	N/A	1/16 /2	N/A
13/4	+0.5 -0	+0.025 -0	+0.100 -0	1/4 /4	N/A	1/16 /2	N/A
17/8	+0.5 -0	+0.025 -0	+0.100 -0	1/4 /4	N/A	1/16 /2	N/A
2-33/4	+0.5 -0	+0.025 -0	+0.200 -0	1/4 /4	N/A	1/16 /2	N/A
Over 33/4	+0.5 -0	+0.025 -0	N/A	1/4 /4	N/A	1/16 /2	N/A

<sup>&</sup>lt;sup>A</sup>Based on dry-as-manufactured condition and proper product storage and handling.

ENot applicable.

Туре	Description	Class	Description	Grade	Applicable Classification System D6779 Callout <sup>A</sup>	Description	Ultimate Tensile Strength, min, psi (MPa)	Tensile Elongation, % at Break, min	Tensile Modulus, min, psi (MPa)	Dimensional Stability, %, max
01	Nylon 66	1	Unfilled	) (1°	//gt.an	General purpose	10 000 (69)	25	350 000 (2400)	0.4
	•			2		Recycled	9000 (62)	15	350 000 (2400)	0.7
				3	PA 0114 <sup>B</sup>	Unmodified virgin	10 000 (69)	25	350 000 (2400)	0.4
		2	MoS <sub>2</sub> filled		PA 0110L01	General purpose	11 000 (76)	15	450 000 (3100)	0.4
				2	ulite	Recycled	9000 (62)	5	350 000 (2400)	0.7
		3	Heat stabilized	1	PA 0124	General purpose	10 000 (69)	25	350 000 (2400)	0.4
		4	Weather resistant	1	PA 0180	General purpose	10 000 (69)	5	350 000 (2400)	0.4
		0	As specified	1	See Table 1	General purpose				
				2	See Table 1	Recycled	•••			
				3	See Table 1	Unmodified virgin	flc-807h-h9	a5hcef9d3	5/astn=d598	89_14-
02	Monomer Cast Nylon 6	1	Unfilled	1		General purpose	10 000 (69)	25	350 000 (2400)	0.4
	-	2	MoS <sub>2</sub> filled, 0.5-1.5 %	1		General purpose	10 000 (69)	15	350 000 (2400)	0.4
		3	Heat stabilized <sup>C</sup>	1		General purpose	10 000 (69)	25	350 000 (2400)	0.4
		4	Internally lubricated	1		General purpose	9000 (62)	25	320 000 (2100)	0.4
		5	Oil-filled	1		General purpose	9000 (62)	25	350 000 (2400)	0.4
		6	Highly plasticized	1		General purpose	8000 (53)	100	275 000 (1845)	0.4
		0	As specified	1	See Table 1	General purpose				
03	Monomer Cast Nylon 612	1	Unfilled	1	•••	General purpose	8000 (53)	40	300 000 (2000)	0.4
04	Nylon 6	1	Unfilled	1		General purpose	10 000 (69)	25	328 000 (2260)	0.4
	-	0	As specified	1	See Table 1	General purpose			′	
05	Nylon 6/12	1	Unfilled	1	PA 0612/0613	General purpose	8000 (53)	20	300 000 (2000)	0.4
00	Other	0		0			***		***	

<sup>&</sup>lt;sup>A</sup> Applicable Classification System D6779 resin type to be specified on purchase order. <sup>B</sup>In accordance with Classification System D6779.

<sup>&</sup>lt;sup>B</sup>To convert inches to millimetres, multiply by 25.40. <sup>C</sup>Finished product as defined in 3.2.1.

<sup>&</sup>lt;sup>D</sup>Oversize product as defined in 3.2.3; roundness and camber not applicable.

<sup>&</sup>lt;sup>c</sup>Heat resistance requirement is 75 % retention of original tensile strength after aging 100 h at 300 ± 3.5°F. After heat aging, use Test Method D638 procedure.