



Designation: D6100 – 11

# Standard Specification for Extruded, Compression Molded and Injection Molded Polyoxymethylene Shapes (POM)<sup>1</sup>

This standard is issued under the fixed designation D6100; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## INTRODUCTION

This specification is intended to be a means of calling out plastic product used in the fabrication of end items or parts.

### 1. Scope\*

1.1 This specification covers requirements and test methods for the material, dimensions, and workmanship, and the properties of extruded, compression molded and injection molded polyoxymethylene (POM) sheet, plate, rod, and tubular bar shapes, excluding pipe and fittings.

1.2 The properties included in this specification are those required for the compositions covered. Section 4 presents a classification system for defining requirements for particular characteristics important to specialized applications.

1.3 This specification allows for the use of recycled plastics.

1.4 The values stated in inch-pound units are to be regarded as the standard in all property and dimensional tables. For reference purposes, SI units are included in Table S-POM and Table 1 only.

1.5 The following precautionary caveat pertains only to the test method portions, Section 11, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no known ISO equivalent to this standard.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.15 on Thermoplastic Materials.

Current edition approved April 1, 2011. Published April 2011. Originally approved in 1997. Last previous edition approved in 2005 as D6100 - 05. DOI: 10.1520/D6100-11.

### 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

D256 Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics

D618 Practice for Conditioning Plastics for Testing

D638 Test Method for Tensile Properties of Plastics

D790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials

D883 Terminology Relating to Plastics

D3892 Practice for Packaging/Packing of Plastics

D6778 Classification System and Basis for Specification for Polyoxymethylene Molding and Extrusion Materials (POM)

D7209 Guide for Waste Reduction, Resource Recovery, and Use of Recycled Polymeric Materials and Products

2.2 *ANSI Standard*:

Z1.9-2008 Sampling Procedures for Inspection by Variables<sup>3</sup>

### 3. Terminology

3.1 *Definitions*:

3.1.1 *regrind (plastic), n*—a product or scrap such as sprues, runners and edge trim that have been reclaimed by shredding and granulating for use in-house.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

\*A Summary of Changes section appears at the end of this standard

3.1.2 For definitions of other technical terms pertaining to plastics used in this specification, see Terminology **D883** or Guide **D7209**.

**iTeh Standards**  
**(<https://standards.itih.ai>)**  
**Document Preview**

[ASTM D6100-11](#)

<https://standards.itih.ai/catalog/standards/sist/a85d520c-5c10-4b15-913e-d1a6f885daaa/astm-d6100-11>

TABLE S-POM Requirements for Polyoxymethylene (POM) Shapes

Type	Description	Class	Description	Grade	Classification System D6778 Resin Callout <sup>A</sup>	Description	Ultimate Tensile Strength min, psi (MPa)	Tensile Elongation % at break, mm	Tensile Modulus min, psi	Dimensional Stability %, max
01	Homopolymer	1	Unfilled	1	POM0111 <sup>B</sup>	General Purpose	9000 (62)	25	350 000	0.4
				2	POM0110B56540 <sup>B</sup>	General Purpose	9000 (62)	15	350 000	0.4
				0	As Specified	Recycle Grade	8000 (55)	25	275 000	0.4
		2	Lubricated	1	POM0110L20A21730 <sup>B</sup>	General purpose	6100 (42)	10	345 000	0.4
				3	POM0110L13 <sup>B</sup>	General Purpose	6800 (47)	10	340 000	0.4
				4	POM0110L20A992 30(46)(2400) <sup>B</sup>	General Purpose	5500 (38)	10	325 000	0.4
5	Lubricated	4	POM0110L12 <sup>B</sup>	General Purpose	5800 (40)	5	375 000	0.4		
		6	POM0131 <sup>B</sup>	General Purpose	9000 (62)	25	350 000	0.4		
		2	POM0132 <sup>B</sup>	General Purpose	9000 (62)	25	350 000	0.4		
02	Copolymer	1	Unfilled	1	POM0211 <sup>B</sup>	General Purpose	8000 (55)	25	350 000	0.4
				2		Recycle Grade	7000 (48)	25	275 000	0.4
				0	As Specified		...	...	...	...
00	Other PolyAc- etals	0	As Specified	1	As Specified	General Purpose	...	...	...	...
				2		Recycle Grade	...	...	...	...

<sup>A</sup> Applicable Classification System D6778 resin type to be specified on purchase order.

<sup>B</sup> In accordance with Classification System D6778.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 centerline porosity, *n*—microvoids which are visibly detectable with the unaided eye using the dye penetration procedure detailed in 7.4.1.

3.2.2 low porosity, *n*—product which either exhibits no white centerline or a white centerline but no dye remains when tested in accordance with section 7.4.1.

3.2.3 plate, *n*—flat stock greater than 1/4 in.

3.2.4 Porosity Level 1, *n*—products containing microvoids with a pore size greater than 50 μm (0.002 in.) in which dye remains either in a broken or continuous line which does not exceed 4 % centerline porosity when tested in accordance with 7.4.1.

3.2.5 recycled plastic shape, *n*—a product made from up to 100 % recycled plastic.

3.2.6 rod, *n*—solid cylindrical shape with a minimum diameter of 1/8 in.

3.2.7 sheet, *n*—flat stock less than and including 1/4 in. (mm) thickness.

3.2.8 tubular bar, *n*—annular shapes with minimum inside diameter of 3/8 in. and minimum wall thickness of 1/16 in.

3.2.9 virgin plastic shape, *n*—product that is produced from 100 % plastic resin that has not been subjected to subsequent melt processing.

4. Classification and Material

4.1 Product shape and size as defined in the applicable purchase order.

4.2 This specification covers product as listed in Table S-POM. Products included in the designations reference Classification System D6778 callouts where applicable.

4.2.1 The type of POM extruded, compression molded or injection molded product is categorized by type, grade and class depending on resin and filler compositions as defined in Table S-POM.

4.3 POM shape products are categorized as General Purpose or Recycle Grade in accordance with the following criteria:

4.3.1 Grade 1—General Purpose:

4.3.1.1 Extruded, compression molded and injection molded product made using only 100 % POM resin. This specification allows for the use of polyoxymethylene plastic materials that are reconstituted, recovered, or reprocessed, or combination thereof, provided that the requirements as stated in this specification are met. It is the responsibility of the supplier and the buyer of reconstituted, recovered, or reprocessed polyoxymethylene plastic materials, or combination thereof, to ensure compliance. (See Guide D7209.)

TABLE A-1 Dimensional Requirements for POM Rod (Grade 1)

Size, in.	Tolerance, in.	Roundness TIR, in.	Camber
1/8 to <1 diameter	+0.003/−0 dia.	0.002	2 1/2 in./8 ft
1 to <2 1/2 diameter	+0.005/−0 dia.	0.005	1 1/4 in./8ft
2 1/2 to 8 diameter	+0.250/−0 dia.	0.050	1 in./8ft
96 length	+1/−0		

4.3.2 Grade 2—Recycle Grade:

4.3.2.1 Extruded, compression molded or injection molded product made using any amount up to 100 % of recycled POM plastic.

4.4 The type class and grade is further differentiated based on dimensional stability (elevated temperature excursion test), Table S-POM and dimensional requirements, Tables A and B.

4.4.1 When the level of centerline porosity needs to be documented it will be designated as either low porosity (LP) or P1 (Porosity Level 1) that is determined using the procedure detailed in 7.4 and will be added to the callout as a suffix (see Example 2 in 4.6.1.2).

4.5 Property Tables: