



SLOVENSKI STANDARD SIST EN ISO 5179:2023

01-julij-2023

Preskus spajkalnosti z omočljivostjo in s kapilarnostjo v ozki reži (ISO 5179:2021)

Investigation of brazeability with spreading and gap-filling test (ISO 5179:2021)

Untersuchung der Hartlötbarkeit anhand der Verteilung und mittels des Spaltfüllverfahrens (ISO 5179:2021)

Étude de l'aptitude au brasage au moyen d'un essai de mouillage et de capillarité (ISO 5179:2021)

Ta slovenski standard je istoveten z: **EN ISO 5179:2023**

ICS:

25.160.50	Trdo in mehko lotanje	Brazing and soldering
-----------	-----------------------	-----------------------

SIST EN ISO 5179:2023

en,fr,de

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 5179

May 2023

ICS 25.160.50

English Version

Investigation of brazeability with spreading and gap-filling
test (ISO 5179:2021)

Étude de l'aptitude au brasage au moyen d'un essai de
mouillage et de capillarité (ISO 5179:2021)

Untersuchung der Hartlötbarkeit anhand der
Verteilung und mittels der Spaltfüllprüfung (ISO
5179:2021)

This European Standard was approved by CEN on 7 May 2023.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/0d155b7c-a68c-45c9-8dee-8a7644bd25f0/sist-en-iso-5179-2023>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Page

European foreword.....	3
------------------------	---

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 5179:2023

<https://standards.iteh.ai/catalog/standards/sist/0d155b7c-a68c-45c9-8dee-8a7644bd25f0/sist-en-iso-5179-2023>

European foreword

The text of ISO 5179:2021 has been prepared by Technical Committee ISO/TC 44 "Welding and allied processes" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 5179:2023 by Technical Committee CEN/TC 121 "Welding and allied processes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2023, and conflicting national standards shall be withdrawn at the latest by November 2023.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

Any feedback and questions on this document should be directed to the users' national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

(standards.iteh.ai) Endorsement notice

The text of ISO 5179:2021 has been approved by CEN as EN ISO 5179:2023 without any modification.

INTERNATIONAL STANDARD

**ISO
5179**

Second edition
2021-03

Investigation of brazeability with spreading and gap-filling test

*Étude de l'aptitude au brasage au moyen d'un essai de mouillage et
de capillarité*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 5179:2023](https://standards.iteh.ai/catalog/standards/sist/0d155b7c-a68c-45c9-8dee-8a7644bd25f0/sist-en-iso-5179-2023)

[https://standards.iteh.ai/catalog/standards/sist/0d155b7c-a68c-45c9-8dee-
8a7644bd25f0/sist-en-iso-5179-2023](https://standards.iteh.ai/catalog/standards/sist/0d155b7c-a68c-45c9-8dee-8a7644bd25f0/sist-en-iso-5179-2023)



Reference number
ISO 5179:2021(E)

© ISO 2021

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 5179:2023

<https://standards.iteh.ai/catalog/standards/sist/0d155b7c-a68c-45c9-8dee-8a7644bd25f0/sist-en-iso-5179-2023>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Description of the test piece	1
4.1 Spreading test piece.....	1
4.2 Gap filling test.....	2
4.2.1 T-joint test piece.....	2
4.2.2 Varying gap test piece.....	2
5 Purpose of the test	3
6 Preparation of test piece	3
7 Brazing cycle	3
8 Examination	4
8.1 Spreading test piece.....	4
8.2 T-joint test piece.....	4
8.3 Varying gap test piece.....	4
9 Micrographic inspection for varying gap test	4
9.1 Varying gap test piece.....	4
10 Results	4
Bibliography	12

SIST EN ISO 5179:2023

<https://standards.iteh.ai/catalog/standards/sist/0d155b7c-a68c-45c9-8dee-8a7644bd25f0/sist-en-iso-5179-2023>

ISO 5179:2021(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 13, *Brazing materials and processes*.

This second edition cancels and replaces the first edition (ISO 5179:1983), which has been technically revised.

The main changes compared to the previous edition are as follows:

- the spreading test has been added;
- the T-joint test has been added.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at <https://www.iso.org/members.html>.

Official interpretations of ISO/TC 44 documents, where they exist, are available from this page: <https://committee.iso.org/sites/tc44/home/interpretation.html>.

Introduction

When designing and making a brazed joint, quite apart from the physical properties of the brazing alloy and the mechanical properties which can be expected from the joint, it is important to know the brazeability as a function of the operating conditions adopted. The determination of wettability has already been the subject of numerous investigations and proposals regarding testing methods. In carrying out these investigations, the most frequently used methods are based on the spreading of a drop, or on the measurement of surface tension, but they in fact only take one element of the problem into account. It is important to know not only the way in which the liquid filler metal wets the surface of the parent material but also how this same liquid filler metal behaves in a given gap between the joint components when diffusion takes place.

In this document, brazeability is defined as a total degree of joinability. The joinability consists of both wettability and fluidity to permit distribution into a joint, i.e. ability to fill a joint gap, although total brazeability includes performance of the physical, and mechanical properties in services.

As the tests to be designated for brazeability, three methods are introduced in this document. The traditional varying gap test is described for the most real ability to fill the gap, but it requires a private sample preparation and special evaluation technique with X-ray device. The T-joint test is newly developed to investigate ability to fill the gap in an easier manner. It can be easily operated at industrial laboratories. Moreover, a simple spreading test is designated for practical convenience.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 5179:2023

<https://standards.iteh.ai/catalog/standards/sist/0d155b7c-a68c-45c9-8dee-8a7644bd25f0/sist-en-iso-5179-2023>