



Designation: D1582 – 98 (Reapproved 2011)

Standard Test Method for Nonvolatile Content of Liquid Phenol, Resorcinol, and Melamine Adhesives¹

This standard is issued under the fixed designation D1582; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of nonvolatile content or total solids of liquid phenol, resorcinol, and melamine adhesives with or without hardener (Note 1) added and containing high-boiling and low-boiling volatile organic solvents or water, or both.

NOTE 1—Some low molecular weight materials in the adhesive may be lost if hardener is not used. When a hardener is used, it must be mixed in accordance with the manufacturer's instructions.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. For specific precautions, see 5.2.

2. Referenced Documents

2.1 ASTM Standards:²

D907 Terminology of Adhesives

3. Terminology

3.1 Definitions—Many of the terms in this test method are defined in Terminology D907.

4. Summary of Test Method

4.1 Without Hardener—A weighed amount of adhesive and quartz sand are oven-dried, cooled in a desiccator, and weighed. The percent nonvolatile content is calculated based on the amount remaining.

¹ This test method is under the jurisdiction of ASTM Committee D14 on Adhesives and is the direct responsibility of Subcommittee D14.30 on Wood Adhesives.

Current edition approved April 1, 2011. Published April 2011. Originally approved in 1958. Last previous edition approved in 2004 as D1582 – 98 (2004). DOI: 10.1520/D1582-98R11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

4.2 With Hardener—A weighed amount of mixed adhesive is oven dried, cooled in a desiccator, and weighed. The percent nonvolatile content is calculated based on the amount remaining.

5. Apparatus

5.1 Petri Dish, 00 by 22 mm or its equivalent.

5.2 Circulating-Air Oven, capable of maintaining temperatures of $70 \pm 1^\circ\text{C}$, $105 \pm 1^\circ\text{C}$, and $150 \pm 1^\circ\text{C}$. (Warning—A safety (explosion-proof) oven should be used when volatile materials are likely to burn or explode.)

5.3 Desiccator, with drying agent and tray.

5.4 Analytical Balance, accurate to 1 mg.

6. Sampling

6.1 Except in special cases, take a composite sample from three or more separate containers chosen at random. Also, take samples from containers which appear to be nonrepresentative and test such samples separately. Place the samples immediately in airtight containers, filled to prevent excessive air space above the adhesive, and take precautions to reduce evaporation or drying to a minimum. Mix the adhesive in the container thoroughly if there is a tendency for the materials to separate.

6.2 Test three specimens of each sample.

7. Procedure

7.1 70°C Drying Temperature Without Hardener:

7.1.1 Place approximately 20 g of the adhesive in a covered weighing bottle.

7.1.2 Place approximately 10 g of fine, oven-dried quartz sand in an open Petri dish, together with a small glass stirring rod, and weigh the dish, rod, and contents to the nearest 1 mg on the analytical balance. Weigh out to the nearest 1 mg approximately 2 g of the adhesive by difference from the weighing bottle, keeping the bottle covered as much as possible. Mix the adhesive and quartz sand intimately by means of the stirring rod and distribute uniformly over the bottom of the dish in as thin a layer as possible. Condition the specimen at $23 \pm 1^\circ\text{C}$ for at least 16 h.

7.1.3 Place the dish with the rod and contents in the oven at $70 \pm 1^\circ\text{C}$ until a constant weight is reached.