



SLOVENSKI STANDARD SIST EN 12814-8:2025

01-februar-2025

Preskušanje zvarjenih spojev plastomernih polizdelkov - 8. del: Zahteve

Testing of welded joints of thermoplastics semi-finished products - Part 8: Requirements

Prüfen von Schweißverbindungen aus thermoplastischen Kunststoffen - Teil 8:
Anforderungen

Essais des assemblages soudés sur produits semi-finis en thermoplastiques - Partie 8 :
Exigences

Ta slovenski standard je istoveten z: **EN 12814-8:2024**

[SIST EN 12814-8:2025](https://standards.iteh.ai/catalog/standards/sist/38a1d904-eb39-4a39-86f0-a661760ed330/sist-en-12814-8-2025)

<https://standards.iteh.ai/catalog/standards/sist/38a1d904-eb39-4a39-86f0-a661760ed330/sist-en-12814-8-2025>

ICS:

25.160.40	Varjeni spoji in vari	Welded joints and welds
83.080.01	Polimerni materiali na splošno	Plastics in general

SIST EN 12814-8:2025

en,fr,de

EUROPEAN STANDARD

EN 12814-8

NORME EUROPÉENNE

EUROPÄISCHE NORM

November 2024

ICS 25.160.40

Supersedes EN 12814-8:2021

English Version

Testing of welded joints of thermoplastics semi-finished products - Part 8: Requirements

Essais des assemblages soudés sur produits semi-finis
en thermoplastiques - Partie 8 : Exigences

Prüfen von Schweißverbindungen aus
thermoplastischen Kunststoffen - Teil 8:
Anforderungen

This European Standard was approved by CEN on 27 October 2024.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and United Kingdom.

[SIST EN 12814-8:2025](https://standards.iteh.ai/)

<https://standards.iteh.ai/catalog/standards/sist/38a1d904-eb39-4a39-86f0-a661760ed330/sist-en-12814-8-2025>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents	Page
European foreword	3
1 Scope	4
2 Normative references	4
3 Terms, definitions, symbols and abbreviations	4
3.1 Terms and definitions	4
3.2 Symbols and abbreviations	4
4 Materials and properties	5
5 Destructive test methods	5
6 Requirements	5
6.1 General	5
6.2 Bend test	5
6.2.1 Bend angle	5
6.2.2 Displacement	13
6.3 Tensile test	19
6.4 Tensile creep test	20
6.5 Peel tests	20
6.6 Macroscopic examination	20
6.7 Low temperature tensile test	20
6.8 Tensile test with waisted test specimen	20

European foreword

This document (EN 12814-8:2024) has been prepared by Technical Committee CEN/TC 249 “Plastics”, the secretariat of which is held by SIS.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2025, and conflicting national standards shall be withdrawn at the latest by May 2025.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 12814-8:2021.

EN 12814-8:2024 includes the following significant technical changes with respect to EN 12814-8:2021:

- bend angle data and ram displacement requirements as well as tensile requirements for PA-U have been added.

Any feedback and questions on this document should be directed to the users’ national standards body. A complete listing of these bodies can be found on the CEN website.

According to the CEN-CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Türkiye and the United Kingdom.

[SIST EN 12814-8:2025](https://standards.iteh.ai/catalog/standards/sist/38a1d904-eb39-4a39-86f0-a661760ed330/sist-en-12814-8-2025)

<https://standards.iteh.ai/catalog/standards/sist/38a1d904-eb39-4a39-86f0-a661760ed330/sist-en-12814-8-2025>

EN 12814-8:2024 (E)

1 Scope

This document provides the requirements for the tests made on welded thermoplastics semi-finished products.

The selection of the appropriate test method(s) is made in accordance with the particular type and application of welded product.

The test results depend on the conditions of manufacture for the test specimen and on the test conditions. They can therefore only be related to the behaviour of the product or can only be used for designing a structure, if the test conditions can be related to the service conditions.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12814-1, *Testing of welded joints of thermoplastics semi-finished products — Part 1: Bend test*

EN 12814-2, *Testing of welded joints of thermoplastics semi-finished products — Part 2: Tensile test*

EN 12814-3, *Testing of welded joints in thermoplastics semi-finished products — Part 3: Tensile creep test*

EN 12814-4, *Testing of welded joints of thermoplastics semi-finished products — Part 4: Peel test*

EN 12814-5, *Testing of welded joints of thermoplastics semi-finished products — Part 5: Macroscopic examination*

EN 12814-6, *Testing of welded joints of thermoplastics semi-finished products — Part 6: Low temperature tensile test*

EN 12814-7, *Testing of welded joints of thermoplastics semi-finished products — Part 7: Tensile test with waisted test specimens*

3 Terms, definitions, symbols and abbreviations

3.1 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp/>
- IEC Electropedia: available at <https://www.electropedia.org/>

3.2 Symbols and abbreviations

For the purposes of this document, the following symbols and abbreviations apply.

HT Heated tool welding

HG Hot gas welding

EX Extrusion welding (continuous)

4 Materials and properties

This document is applicable to the thermoplastic materials listed in Table 1.

In this document, PA-U refers to PA-U 11 180 and PA-U 12 180 only.

Table 1 — Materials and symbols

Symbol	Material
PA-U	Polyamide unplasticised
PE	Polyethylene
PP-B	Polypropylene block copolymer
PP-H	Polypropylene homopolymer
PP-R	Polypropylene random copolymer
PVC-C	Polyvinyl chloride chlorinated
PVC-U	Polyvinyl chloride unplasticised
PVDF	Polyvinylidene fluoride

5 Destructive test methods

The dimensions and the methods for sampling and preparing test specimens, together with the conditions for carrying out destructive tests shall be as given in the standards shown in Table 2.

Table 2 — Destructive test methods for welded joints

Test method	Standard reference
Bend test	EN 12814-1
Tensile test	EN 12814-2
Tensile creep test	EN 12814-3
Peel test	EN 12814-4
Macroscopic examination	EN 12814-5
Low temperature tensile test	EN 12814-6
Tensile test with waisted test specimen	EN 12814-7

6 Requirements

6.1 General


The semi-finished products used for the welded joints shall comply with the relevant standards. The welded joints shall meet the requirements specified hereafter.

6.2 Bend test

6.2.1 Bend angle

The individual measured value of the bend angle shall be greater than or equal to the values given in Figures 1 to 7. For PVC-C, the requirements shall be agreed between the contracting parties.

EN 12814-8:2024 (E)




Key

- 1 bend angle in °
- 2 test specimen thickness in mm
- 3 HT
- 4 EX, HG

Figure 1 — Minimum bend angle for PE

<https://standards.iteh.ai/catalog/standards/sist/38a1d904-eb39-4a39-86f0-a661760ed330/sist-en-12814-8-2025>

**Key**

1 bend angle in °


2 test specimen thickness in mm

3 HT

4 EX, HG

Figure 2 — Minimum bend angle for PP-B and PP-H

EN 12814-8:2024 (E)



Key

- 1 bend angle in °
- 2 test specimen thickness in mm
- 3 HT
- 4 EX, HG

Figure 3 — Minimum bend angle for PP-R