

INTERNATIONAL  
STANDARD

ISO  
23700

First edition  
2021-03

---

---

---

**Wrought magnesium and magnesium  
alloys — Rolled plates and sheets**

**iTeh Standards**  
**(<https://standards.iteh.ai>)**  
**Document Preview**

[ISO 23700:2021](#)

<https://standards.iteh.ai/catalog/standards/iso/697e3d7f-074e-4c2e-a890-32bc3dd59713/iso-23700-2021>



Reference number  
ISO 23700:2021(E)

© ISO 2021

**iTeh Standards**  
**(<https://standards.iteh.ai>)**  
**Document Preview**

[ISO 23700:2021](#)

<https://standards.iteh.ai/catalog/standards/iso/697e3d7f-074e-4c2e-a890-32bc3dd59713/iso-23700-2021>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

## Contents

Page

<b>Foreword</b>	iv
<b>Introduction</b>	v
<b>1 Scope</b>	1
<b>2 Normative references</b>	1
<b>3 Terms and definitions</b>	1
<b>4 Orders or tenders</b>	1
<b>5 Requirements</b>	2
5.1 Designation	2
5.2 Production and manufacturing processes	3
5.3 Quality control	3
5.4 Chemical composition	3
5.5 Dimensional tolerances	5
5.6 Mechanical properties	5
5.7 Surface finish	9
<b>6 Test procedure</b>	9
6.1 Sampling	9
6.1.1 Sampling for chemical analysis	9
6.1.2 Sampling for mechanical testing	9
6.2 Test methods	10
6.2.1 Chemical composition	10
6.2.2 Tensile test	10
6.2.3 Erichsen test	10
6.2.4 Measurement of dimensions	10
6.2.5 Surface finish	10
6.3 Retests	11
6.3.1 Mechanical properties	11
6.3.2 Other properties	11
<b>7 Inspection documents</b>	11
7.1 General	11
7.2 Certificate of conformity	11
7.3 Test report	11
7.4 Specific test report	11
<b>8 Marking</b>	12
<b>9 Packing</b>	12
<b>10 Transportation and storage</b>	12
<b>11 Arbitration tests</b>	12

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 79, *Light metals and their alloys*, Subcommittee SC 5, *Magnesium and alloys of cast or wrought magnesium*.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

<https://standards.iteh.ai/catalog/standards/iso/697e3d7f-074e-4c2e-a890-32bc3dd59713/iso-23700-2021>

## Introduction

This document classifies the commercially available magnesium and magnesium alloy rolled plates and sheets into a number of grades suitable for the application to which they might be put.

iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

[ISO 23700:2021](#)

<https://standards.iteh.ai/catalog/standards/iso/697e3d7f-074e-4c2e-a890-32bc3dd59713/iso-23700-2021>



# Wrought magnesium and magnesium alloys — Rolled plates and sheets

## 1 Scope

This document specifies chemical composition, mechanical properties, dimension and shape tolerance, heat treatment and the technical conditions for inspection and delivery of rolled magnesium and magnesium alloy plates and sheets.

It is applicable to rolled magnesium and magnesium alloy plates and sheets.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3116, *Magnesium and magnesium alloys — Wrought magnesium and magnesium alloys*

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

## 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

### 3.1

#### sheet

product that is rectangular in cross-section with nominal thickness less than 6 mm, but not less than 0,20 mm, and with slit, sheared or sawed edges

### 3.2

#### plate

product that is rectangular in cross-section and with thickness not less than 6 mm with sheared or sawn edges

## 4 Orders or tenders

The order or tender shall define the product required and shall contain the following details:

- a) the type and form of the product:
  - 1) designation of the magnesium or magnesium alloy;
  - 2) form of the product (sheet, plate);
- b) the metallurgical temper (degree of hardness or heat treatment condition) of the material for delivery and, if different, the metallurgical temper for use;

- c) the number of this document, i.e. ISO 23700, the specification number, or, where none exists, the properties agreed between the supplier and the purchaser;
- d) the dimensions and shape of the product (thickness, width, length, diameter of the coil);
- e) the tolerances of the dimensions and form, with reference to the appropriate clause or subclause of this document;
- f) the quantity;
- g) any requirements for certificates of conformity, test and/or analysis;
- h) any special requirements agreed between the supplier and the purchaser (e.g. drawings).

## 5 Requirements

### 5.1 Designation

The following symbols shall be used for temper designation:

- O: annealed;
- H112: strain hardened from working at elevated temperature or from a limited amount of cold work, and for which there are mechanical properties limits;
- H × 4: half hardened (strain hardened to give an ultimate tensile strength approximately midway between that of annealed and H × 8 temper);
- H × 2: quarter hardened (strain hardened to give an ultimate tensile strength approximately midway between that of annealed and H × 4 temper);
- T5: cooled from an elevated temperature shaping process and then artificially aged.

The alloy designation and temper should be as given in [Table 1](#).

<https://standards.iteh.ai/catalog/standards/iso/697e3d7f-074e-4c2e-a890-32bc3dd59713/iso-23700-2021>

**Table 1 — Alloy designation and temper**

Alloy designation	Alloy symbol	Temper	Thickness mm
MAM61	ISO-MgAl6Mn1	H112	1 ≤ t ≤ 5
MAM91	ISO-MgAl9Mn1	H112	1 ≤ t ≤ 5
MAT11	ISO-MgAl1Sn1	O	0.5 ≤ t ≤ 2
MAT61	ISO-MgAl6Sn1	O	0.5 ≤ t ≤ 2
MAZ31a	ISO-MgAl3Zn1(A)	O, H × 4, H × 2	0.5 ≤ t ≤ 25
MAZ31b	ISO-MgAl3Zn1(B)	O, H112	0.4 ≤ t ≤ 70
MAZ40	ISO-MgAl4Zn	H112	40 ≤ t ≤ 70
MAZ41	ISO-MgAl4Zn1	H112	10 ≤ t ≤ 70
MAZX310	ISO-MgAl3Zn1Ca	O	0,5 ≤ t ≤ 1,5
MAZE310	ISO-MgAl3Zn1RE	O	0,5 ≤ t ≤ 1,5
MVWE751	ISO-MgGd7Y5RE1	T5	10 ≤ t ≤ 20
MVW76	ISO-MgGd7Y6	T5	12 ≤ t ≤ 70
MLAZ931	ISO-MgLi9Al3Zn1	O, H112	0,5 ≤ t ≤ 60
MME20	ISO-MgMn2RE	H112	10 ≤ t ≤ 70
MWE43c	ISO-MgY4RE3Zr(C)	T5	12 ≤ t ≤ 70
MWEK711	ISO-MgY7RE1Zr1	T5	10 ≤ t ≤ 20

**Table 1 (continued)**

Alloy designation	Alloy symbol	Temper	Thickness mm
MZE10	ISO-MgZn1RE	O	0,5 ≤ $t$ ≤ 1,5
MZE20	ISO-MgZn2RE	O	0,5 ≤ $t$ ≤ 1,5
MZM21	ISO-MgZn2Mn1	O, H × 4	6 ≤ $t$ ≤ 25
MZK60	ISO-MgZn6Zr0	H112	20 ≤ $t$ ≤ 60
MZK61	ISO-MgZn6Zr1	T5, H112	10 ≤ $t$ ≤ 70

## 5.2 Production and manufacturing processes

Unless otherwise specified in the order, the production and manufacturing processes shall be left to the discretion of the producer. Unless it is explicitly stated otherwise in the order, no obligation shall be placed on the producer to use the same processes for subsequent and similar orders.

## 5.3 Quality control

The supplier shall be responsible for the performances of all inspection and tests required by the relevant International Standard or specification, prior to shipment of the product.

If the purchaser wishes to inspect the product at the supplier's works, he or she shall notify the supplier at the time of placing the order.

## 5.4 Chemical composition

The chemical composition shall conform to the requirements for the appropriate material given in [Table 2](#) or to the requirements specified in ISO 3116.

If the purchaser requires content limits for elements not specified in [Table 2](#) or in ISO 3116, these limits shall be stated in the order document.

[ISO 23700:2021](#)

<https://standards.iteh.ai/catalog/standards/iso/697e3d7f-074e-4c2e-a890-32bc3dd59713/iso-23700-2021>

Table 2 — Chemical composition of rolled magnesium alloy plates and sheets

Alloy group	Material designation	Composition % (mass fraction)																			
		Symbol	Designation	Element	Mg	Al	Zn	Mn	Gd	RE	Li	Zr	Y	Ca	Be	Si	Fe	Cu	Ni	Others each	Others total
MgAlMn	ISO-MgAl6Mn1	MAM61	min. max.	Rem.	5,0	—	0,50	—	—	—	—	—	—	—	—	—	—	—	—	—	
	ISO-MgAl9Mn1	MAM91	min. max.	Rem.	8,0	—	0,50	—	—	—	—	—	—	—	—	—	—	—	—	0,01	0,30
MgAlZn	ISO-MgAl4Zn1	MAZ40	min. max.	Rem.	3,0	0,20	0,15	—	—	—	—	—	—	—	—	—	—	—	—	0,01	0,30
	ISO-MgAl4Zn1	MAZ41	min. max.	Rem.	3,7	0,8	0,30	—	—	—	—	—	—	—	—	—	—	—	—	—	
MgAlZn-Ca	ISO-MgAl3Zn-1Ca	MAZX310	min. max.	Rem.	2,4	0,5	0,15	—	—	—	—	—	0,1	—	—	—	—	—	—	—	
MgAlZn-RE	ISO-MgAl3Zn-1RE	MAZE310	min. max.	Rem.	2,4	0,5	0,15	—	—	—	—	—	0,3	—	0,1	0,005	0,05	0,005	0,05	0,30	
MgLiAl	ISO-MgLi-9Al3Zn1	MLAZ931	min. max.	Rem.	2,5	0,5	—	—	8,5	—	—	—	—	—	—	—	—	—	—	—	
MgMnRE	ISO-MgMn2RE	MME20	min. max.	Rem.	—	3,8	1,5	0,05	—	9,5	—	—	—	—	—	0,05	0,01	0,001	0,02	0,30	
MgZnRE	ISO-MgZn1RE	MZE10	min. max.	Rem.	—	0,20	0,30	2,2	0,35	—	—	—	—	—	—	0,01	0,10	0,05	0,005	0,01	0,30
	ISO-MgZn2RE	MZE20	min. max.	Rem.	—	0,05	1,5	0,05	0,3	—	—	0,1	—	—	—	0,05	0,02	0,02	—	0,01	0,10
MgZnZr	ISO-MgZn6Zr1	MZK61	min. max.	Rem.	—	0,05	6,0	0,10	—	0,30	—	—	—	—	0,01	0,05	0,05	0,005	0,01	0,30	

Key

Rem.: subtract the percentage of all elements except Mg from 100 %.