

---

---

**Rubber, raw — Determination of  
volatile-matter content —**

**Part 1:  
Hot-mill method and oven method**

*Caoutchouc brut — Détermination des matières volatiles —*

*Partie 1: Méthode par mélangeage à chaud et méthode par étuvage*

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

[ISO 248-1:2021](https://standards.iteh.ai/catalog/standards/sist/0309dead-1f8b-4bc8-9617-2b17f82dc189/iso-248-1-2021)

[https://standards.iteh.ai/catalog/standards/sist/0309dead-1f8b-4bc8-9617-  
2b17f82dc189/iso-248-1-2021](https://standards.iteh.ai/catalog/standards/sist/0309dead-1f8b-4bc8-9617-2b17f82dc189/iso-248-1-2021)



**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 248-1:2021](https://standards.iteh.ai/catalog/standards/sist/0309dead-1f8b-4bc8-9617-2b17f82dc189/iso-248-1-2021)

<https://standards.iteh.ai/catalog/standards/sist/0309dead-1f8b-4bc8-9617-2b17f82dc189/iso-248-1-2021>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

	Page
Foreword.....	iv
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>2</b>
4.1 Hot-mill method.....	2
4.2 Oven method.....	2
<b>5 Hot-mill method</b> .....	<b>2</b>
5.1 General.....	2
5.2 Apparatus.....	2
5.3 Procedure.....	2
5.3.1 Hot-mill method, procedure A.....	2
5.3.2 Hot-mill method, procedure B.....	3
5.4 Expression of results.....	3
5.4.1 Hot-mill method, procedure A.....	3
5.4.2 Hot-mill method, procedure B.....	3
<b>6 Oven method</b> .....	<b>4</b>
6.1 General.....	4
6.2 Apparatus.....	4
6.3 Procedure.....	4
6.3.1 Oven method, procedure A.....	4
6.3.2 Oven method, procedure B.....	5
6.4 Expression of results.....	6
6.4.1 Oven method, procedure A.....	6
6.4.2 Oven method, procedure B.....	6
<b>7 Precision</b> .....	<b>7</b>
<b>8 Test report</b> .....	<b>7</b>
<b>Annex A (informative) Selection of appropriate test method</b> .....	<b>8</b>
<b>Annex B (normative) Homogenization</b> .....	<b>9</b>
<b>Annex C (informative) Precision</b> .....	<b>10</b>
<b>Bibliography</b> .....	<b>12</b>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 3, *Raw materials (including latex) for use in the rubber industry*.

This second edition cancels and replaces the first edition (ISO 248-1:2011), which has been technically revised.

The main changes compared to the previous edition are as follows:

- in [6.2.1](#), update of the tolerance temperature of the oven;
- in [6.3.1](#) and [6.3.2](#), update of the procedure: mass of the test sample, drying of the test portion, temperature, requirements on the aluminium tray;
- update of the formulae;
- in [Annex B](#), update of the homogenization procedure for natural rubber;
- in [Annex C](#), addition of the precision data from an ITP conducted in 2020 for natural rubber.

A list of all parts in the ISO 248 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Rubber, raw — Determination of volatile-matter content —

## Part 1: Hot-mill method and oven method

**WARNING** — Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices.

**IMPORTANT** — Certain procedures specified in this document might involve the use or generation of substances, or the generation of waste, that could constitute a local environmental hazard. Reference should be made to appropriate documentation on safe handling and disposal after use.

### 1 Scope

This document specifies two methods for the determination of volatile-matter content in raw rubbers by using a hot mill or an oven.

These methods are applicable to the determination of the volatile-matter content in the “R” group of rubbers listed in ISO 1629. These are rubbers having an unsaturated carbon chain, for example natural rubber and synthetic rubbers derived at least partly from di-olefins. These methods can also be applicable to other raw rubbers, but in these cases it is necessary to demonstrate that the change in mass is due solely to loss of actual volatile matter and not to rubber degradation.

The hot-mill method is not applicable to natural rubber, to synthetic rubbers which are too difficult to handle on a hot mill or to synthetic rubbers in powder or chip form.

The two methods do not necessarily give identical results. Therefore, in the case of dispute, the oven method, procedure A, is the reference method.

**NOTE** The applicability of each test method to various types of rubber is summarized in [Annex A](#).

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1795, *Rubber, raw natural and raw synthetic — Sampling and further preparative procedures*

ISO 2393, *Rubber test mixes — Preparation, mixing and vulcanization — Equipment and procedures*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 1795 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

### 3.1 test portion

quantity of rubber taken from the test sample or laboratory sample for the purpose of a single specific test, for example the amount actually weighted out for a single determination of the volatile-matter content

## 4 Principle

### 4.1 Hot-mill method

A test portion is sheeted out on a heated mill until all volatile matter is driven off. The loss in mass during milling is calculated and expressed as volatile-matter content.

### 4.2 Oven method

A test portion is dried in an oven to constant mass. The loss in mass is calculated and expressed as the volatile-matter content.

## 5 Hot-mill method

### 5.1 General

5.1.1 Two procedures are specified, as follows.

- Hot-mill method, procedure A: a test sample is homogenized using a laboratory mill, and a test portion from the homogenized test sample is dried to constant mass using a hot mill.
- Hot-mill method, procedure B: a test portion is dried to constant mass using a hot mill.

NOTE Procedure B is a simplified method which does not include a homogenization process.

5.1.2 When the sample is flaky or becomes sticky on the hot mill, making weighing difficult or impossible, the oven method shall be used.

5.1.3 The number of test portions shall be agreed between the interested parties.

### 5.2 Apparatus

5.2.1 **Mixing mill**, complying with the requirements of ISO 2393.

5.2.2 **Balance**, capable of weighing to the nearest 0,1 g.

### 5.3 Procedure

#### 5.3.1 Hot-mill method, procedure A

5.3.1.1 Take a test sample of about 250 g from the laboratory sample in accordance with ISO 1795 and homogenize it in accordance with [Annex B](#). Weigh to the nearest 0,1 g before and after homogenization (masses  $m_1$  and  $m_2$ , respectively). Cut the test portions needed for chemical and physical tests from the homogenized test sample, if necessary.

5.3.1.2 Adjust the clearance of the mill rolls to 0,25 mm  $\pm$  0,05 mm, using lead strips as specified in ISO 2393. Maintain the surface temperature of the rolls at 105 °C  $\pm$  5 °C.

**5.3.1.3** Pass a weighed test portion (mass  $m_3$ ), preferably of 100 g or more, taken from the homogenized test sample repeatedly through the mill for 4 min. Do not allow the test portion to band and take care to prevent any loss of material. Weigh the test portion to the nearest 0,1 g. Pass the test portion through the mill for an additional 2 min and reweigh. If the masses at the end of the 4 min and 6 min periods differ by less than 0,1 g, calculate the volatile-matter content.

If not, continue passing the test portion through the mill for 2 min periods until the mass does not decrease by more than 0,1 g between successive weighings (final mass  $m_4$ ). Before each weighing, allow the test portion to cool to room temperature in a desiccator.

### 5.3.2 Hot-mill method, procedure B

**5.3.2.1** Take a test portion of about 250 g from the laboratory sample and weigh to the nearest 0,1 g (mass  $m_5$ ).

**5.3.2.2** Adjust the clearance of the mill roll to  $0,25 \text{ mm} \pm 0,05 \text{ mm}$ , using lead strips as specified in ISO 2393. Maintain the surface temperature of the rolls at  $105 \text{ }^\circ\text{C} \pm 5 \text{ }^\circ\text{C}$ . Pass the test portion repeatedly through the mill for 4 min. Do not allow the test portion to band and take care to prevent any loss of material. Weigh to the nearest 0,1 g, followed by passing through the mill for an additional 2 min and reweigh.

**5.3.2.3** If the difference in mass of the test portion before and after it is passed through the rolls is less than 0,1 g, the test portion is considered to be well dried. If it is not well dried, continue passing the test portion through the rolls for an additional 2 min until the mass difference is less than 0,1 g (final mass  $m_6$ ).

NOTE Cooling in a desiccator before weighing is desirable.

## 5.4 Expression of results

### 5.4.1 Hot-mill method, procedure A

The volatile-matter content  $w_1$  is given, as a percent mass fraction, by [Formula \(1\)](#):

$$w_1 = \left( 1 - \frac{m_2 \times m_4}{m_1 \times m_3} \right) \times 100 \quad (1)$$

where

$m_1$  is the mass, in grams, of the test sample before homogenization;

$m_2$  is the mass, in grams, of the test sample after homogenization;

$m_3$  is the mass, in grams, of the test portion before milling;

$m_4$  is the mass, in grams, of the test portion after milling.

### 5.4.2 Hot-mill method, procedure B

The volatile-matter content  $w_2$  is given, as a percent mass fraction, by [Formula \(2\)](#):

$$w_2 = \frac{m_5 - m_6}{m_5} \times 100 \quad (2)$$

where

$m_5$  is the mass, in grams, of the test portion before milling;

$m_6$  is the mass, in grams, of the test portion after milling.

## 6 Oven method

### 6.1 General

6.1.1 Two procedures are specified, as follows.

- Oven method, procedure A: a test sample is homogenized using a laboratory mill, and a test portion taken from the homogenized test sample is dried in an oven to constant mass. If the sample is in powder form or impossible to weigh before and after homogenization, a test sample shall simply be dried, without carrying out the homogenizing process.
- Oven method, procedure B: a test sample is sheeted out using a laboratory mill, then a test portion taken from the sheeted test sample is dried in an oven to constant mass. If the sample is in powder form or is difficult to pass through the mill, the test portion shall simply be dried, without carrying out the sheeting process. This procedure is only applicable to synthetic rubbers since natural rubber requires homogenization.

6.1.2 The number of test portions shall be agreed between the interested parties.

### 6.2 Apparatus

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

6.2.1 **Oven**, ventilated, preferably air-circulating type, capable of being maintained at  $105\text{ °C} \pm 3\text{ °C}$ .

6.2.2 **Balance**, capable of weighing to the nearest 0,1 mg.

ISO 248-1:2021

<https://standards.iteh.ai/en/standards/sist/0309dead-1f8b-4bc8-9617-2b17f82dc189/iso-248-1-2021>

6.2.3 **Mixing mill**, complying with the requirements of ISO 2393.

### 6.3 Procedure

#### 6.3.1 Oven method, procedure A

##### 6.3.1.1 Natural rubber

6.3.1.1.1 Take a test sample of about 250 g from the laboratory sample in accordance with ISO 1795 and homogenize it in accordance with [Annex B](#). Weigh to the nearest 0,1 g before and after homogenization (masses  $m_7$  and  $m_8$ , respectively). Allow to cool to room temperature before the final weighing. Cut the test pieces for chemical and physical tests from the homogenized test sample, if necessary.

6.3.1.1.2 Take a test portion of about 10 g from the homogenized test sample and weigh it to the nearest 1 mg (mass  $m_9$ ).

6.3.1.1.3 Pass the test portion twice through the mill with the rolls at room temperature and with a mill opening which will produce a sheet of less than 2 mm thickness.

6.3.1.1.4 Dry the test portion in the oven, maintained at  $105\text{ °C} \pm 3\text{ °C}$  at least for 3 ½ h, with the ventilators open and with the air-circulating fan, if fitted, switched on. Arrange the test piece so as to present the largest possible surface area to the hot air. Allow to cool to room temperature in a desiccator and weigh. Repeat the heating for further 30 min periods until the mass does not decrease by more than 1 mg between successive weighings (final mass  $m_{10}$ ).

**6.3.1.1.5** If the sample is in powder form, take a test portion of about 10 g at random and place it on a clean watch-glass or a clean aluminium tray, which has been weighed to the nearest 1 mg (mass  $m_0$ ) to facilitate weighing. Weigh the test portion including the watch-glass/tray to the nearest 1 mg (mass  $m_{11}$ ). Dry the test sample in accordance with [6.3.1.1.4](#) and weigh the tray including dried test portion to the nearest 1 mg (final mass  $m_{12}$ ).

### 6.3.1.2 Synthetic rubber

**6.3.1.2.1** Take a test sample of about 250 g from the laboratory sample in accordance with ISO 1795 and homogenize it in accordance with [Annex B](#). Weigh to the nearest 0,1 g before and after homogenization (masses  $m_7$  and  $m_8$ , respectively). Cut the test portion for chemical and physical tests from the homogenized test sample, if necessary.

**6.3.1.2.2** Take a test portion of about 10 g from the homogenized test sample and weigh it to the nearest 1 mg (mass  $m_9$ ).

**6.3.1.2.3** Pass the test portion twice through the mill with the rolls' temperature set at  $70\text{ °C} \pm 5\text{ °C}$  and with a mill opening which will produce a sheet of less than 2 mm thickness.

**6.3.1.2.4** When sheeting is impossible, take a test portion of about 10 g from the homogenized test sample and cut it by hand into small cubes with edges of 2 mm to 5 mm. Place the cubes on a clean watch-glass or a clean aluminium tray, to facilitate weighing. Weigh to the nearest 1 mg (mass  $m_9$ ).

**6.3.1.2.5** Dry the test portion for 1 h in the oven, maintained at  $105\text{ °C} \pm 3\text{ °C}$ , with the ventilators open and with the air-circulating fan, if fitted, switched on. Arrange the test portion so as to present the largest possible surface area to the hot air. Allow to cool to room temperature in a desiccator and weigh to the nearest 1 mg. Repeat the heating for further 30 min periods until the mass does not decrease by more than 1 mg between successive weighing (final mass  $m_{10}$ ).

**6.3.1.2.6** If it is difficult to weigh the test portion before and after a homogenization process because it sticks to roll surfaces, take a test portion of about 10 g from the laboratory sample and cut it by hand into small cubes with edges of 2 mm to 5 mm. Place the cubes on a clean watch-glass or a clean aluminium tray, which has been weighed to the nearest 1 mg (mass  $m_0$ ), to facilitate weighing. Weigh the test portion including the watch-glass/tray to the nearest 1 mg (mass  $m_{11}$ ). Dry the test sample in accordance with [6.3.1.2.5](#) and weigh to the nearest 1 mg (final mass  $m_{12}$ ).

**6.3.1.2.7** If the sample is in powder form, take a test portion of about 10 g at random and place it on a clean watch-glass or a clean aluminium tray, which has been weighed to the nearest 1 mg (mass  $m_0$ ) to facilitate weighing. Weigh the test portion including the watch-glass/tray to the nearest 1 mg (mass  $m_{11}$ ). Dry the test sample in accordance with [6.3.1.2.5](#) and weigh the tray including dried test portion to the nearest 1 mg (final mass  $m_{12}$ ).

### 6.3.2 Oven method, procedure B

**6.3.2.1** Take a test sample of about 250 g and pass it through the mill with the surface temperature of the rolls adjusted to about  $30\text{ °C}$  and the roll clearance to  $0,25\text{ mm} \pm 0,05\text{ mm}$  to obtain a thin sheet. From the sheeted test sample, take two test portions of about 50 g and weigh each to the nearest 10 mg (mass  $m_{13}$ ). Dry the test portions in accordance with [6.3.1.2.5](#). Remove the test portions from the oven and cool to room temperature in a desiccator. Reweigh to the nearest 10 mg (mass  $m_{14}$ ).

**6.3.2.2** If the sample is in powder form or is impossible to sheet because it sticks to the roll surfaces or because it is flaky, take two test portions of about 10 g directly from the laboratory sample. Cut the test portions by hand into small cubes with edges of 2 mm to 5 mm, if necessary. Place each test portion in a clean aluminium tray of 15 mm depth and 60 mm diameter, or of similar shape, which has been weighed (mass  $m_0$ ), and weigh the tray including test portion to the nearest 1 mg (mass  $m_{15}$ ). Dry the

trays containing the test portions in accordance with [6.3.1.2.5](#). Remove the trays from the oven and allow to cool in a desiccator to room temperature. Reweigh the tray including dried test portion to the nearest 1 mg (mass  $m_{16}$ ).

## 6.4 Expression of results

### 6.4.1 Oven method, procedure A

**6.4.1.1** When the test portion is taken from a homogenized test sample (see [6.3.1.1.1](#), [6.3.1.1.2](#), [6.3.1.1.4](#), [6.3.1.2.1](#), [6.3.1.2.2](#) and [6.3.1.2.5](#)), the volatile-matter content  $w_3$  is given, as a percent mass fraction, by [Formula \(3\)](#):

$$w_3 = \left( 1 - \frac{m_8 \times m_{10}}{m_7 \times m_9} \right) \times 100 \quad (3)$$

where

$m_7$  is the mass, in grams, of the test sample before homogenization;

$m_8$  is the mass, in grams, of the test sample after homogenization;

$m_9$  is the mass, in grams, of the test portion before drying;

$m_{10}$  is the mass, in grams, of the test portion after drying.

**6.4.1.2** When the sample is in powder form or sticky to the roll surface (see [6.3.1.1.5](#), [6.3.1.2.6](#) and [6.3.1.2.7](#)), the volatile-matter content  $w_4$  is given, as a percent mass fraction, by [Formula \(4\)](#):

$$w_4 = \frac{m_{11} - m_{12}}{m_{11} - m_0} \times 100 \quad (4)$$

ISO 248-1:2021  
<https://standards.iteh.ai/catalog/standards/sist/0309dead-1f8b-4bc8-9617-2b17f82dc189/iso-248-1-2021>

where

$m_0$  is the mass, in grams, of the aluminium tray;

$m_{11}$  is the mass, in grams, of the test portion and the aluminium tray before drying;

$m_{12}$  is the mass, in grams, of the test portion and the aluminium tray after drying.

### 6.4.2 Oven method, procedure B

**6.4.2.1** When the test portion is taken from a sheeted test sample (see [6.3.2.1](#)), the volatile-matter content  $w_5$  is given, as a percent mass fraction, by [Formula \(5\)](#):

$$w_5 = \frac{m_{13} - m_{14}}{m_{13}} \times 100 \quad (5)$$

where

$m_{13}$  is the mass, in grams, of the test portion before drying;

$m_{14}$  is the mass, in grams, of the test portion after drying.