



Designation: ~~B228-04~~ Designation: B228 – 11

Standard Specification for Concentric-Lay-Stranded Copper-Clad Steel Conductors¹

This standard is issued under the fixed designation B228; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers bare concentric-lay-stranded conductors made from bare round copper-clad steel wires for general use for electrical purposes.

1.2 For the purpose of this specification, conductors are classified as follows: Grade 40 HS, Grade 30 HS, and Grade 30 EHS.

~~1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are in SI units.~~

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 The following documents of the issue in effect on the date of material purchase form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards*:²

B227 [Specification for Hard-Drawn Copper-Clad Steel Wire](#)

B354 [Terminology Relating to Uninsulated Metallic Electrical Conductors](#)

2.3 *ANSI Standards*:

C 42 [Definitions of Electrical Terms](#)³

2.4 *National Institute of Standards and Technology*:

NBS [Handbook 100—Copper Wire Tables](#)⁴

3. Ordering Information

3.1 Orders for material under this specification shall include the following information:

3.1.1 Quantity of each size and grade;

3.1.2 Conductor size: approximate diameter in fractions of an inch, or number and AWG size of individual wires (Section 7 and Table 1);

3.1.3 Grade (see 1.2 and Table 1);

3.1.4 Direction of lay of outer layer, if other than left-hand (see 6.3);

3.1.5 When physical tests shall be made (see 8.2);

3.1.6 Package size (see 13.1);

3.1.7 Special package marking, if required (Section 12);

3.1.8 Lagging, if required (see 13.2); and

3.1.9 Place of inspection (Section 14).

3.2 In addition, Supplementary Requirements shall apply only when specified by the purchaser in the inquiry, contract, or purchase order for direct procurement by agencies of the U. S. Government (S1, S2, and S3).

¹ This specification is under the jurisdiction of ASTM Committee B01 on Electrical Conductors and is the direct responsibility of Subcommittee B01.06 on Composite Conductors.

Current edition approved April 1, 2004; 2011. Published April 2004; May 2011. Originally approved in 1948. Last previous edition approved in 2002; 2004 as B228 – 024. DOI: 10.1520/B0228-04.10.1520/B0228-11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, <http://www.ansi.org>.

⁴ Available from National Institute of Standards and Technology (NIST), 100 Bureau Dr., Stop 3460, 1070, Gaithersburg, MD 20899-3460; 20899-1070, <http://www.nist.gov>.

TABLE 1 Construction Requirements and Breaking Strength of Concentric-Lay-Stranded Copper-Clad Steel Conductors

NOTE 1—*Metric Equivalents*—For diameter, 1 in. = 25.40 mm (round to four significant figures); for breaking strength, 1 lb = 0.45359 kg (round to four significant figures).

Size Designation		Conductor Diameter, in. ^A	Rated Breaking Strength, min, lb ^B		
Inch ^C	AWG ^D		Grade 40 HS	Grade 30 HS	Grade 30 EHS
<u>7/8</u>	<u>19 No. 5</u>	<u>0.910</u>	<u>50 240</u>	<u>55 570</u>	<u>66 910</u>
<u>7/8</u>	<u>19 No. 5</u>	<u>0.910</u>	<u>48 740</u>	<u>53 910</u>	<u>64 910</u>
<u>13/16</u>	<u>19 No. 6</u>	<u>0.840</u>	<u>41 600</u>	<u>45 830</u>	<u>55 530</u>
<u>13/16</u>	<u>19 No. 6</u>	<u>0.810</u>	<u>40 370</u>	<u>44 470</u>	<u>53 880</u>
<u>23/32</u>	<u>19 No. 7</u>	<u>0.724</u>	<u>34 390</u>	<u>37 740</u>	<u>45 850</u>
<u>23/32</u>	<u>19 No. 7</u>	<u>0.721</u>	<u>33 360</u>	<u>36 610</u>	<u>44 480</u>
<u>21/32</u>	<u>19 No. 8</u>	<u>0.642</u>	<u>28 380</u>	<u>31 040</u>	<u>37 690</u>
<u>21/32</u>	<u>19 No. 8</u>	<u>0.642</u>	<u>27 550</u>	<u>30 140</u>	<u>36 590</u>
<u>9/16</u>	<u>19 No. 9</u>	<u>0.572</u>	<u>23 390</u>	<u>25 500</u>	<u>30 610</u>
<u>9/16</u>	<u>19 No. 9</u>	<u>0.572</u>	<u>22 690</u>	<u>24 730</u>	<u>29 700</u>
<u>5/8</u>	<u>7 No. 4</u>	<u>0.613</u>	<u>22 310</u>	<u>24 780</u>	<u>29 430</u>
<u>5/8</u>	<u>7 No. 4</u>	<u>0.613</u>	<u>21 630</u>	<u>24 040</u>	<u>28 540</u>
<u>9/16</u>	<u>7 No. 5</u>	<u>0.546</u>	<u>18 510</u>	<u>20 470</u>	<u>24 650</u>
<u>9/16</u>	<u>7 No. 5</u>	<u>0.546</u>	<u>17 960</u>	<u>19 860</u>	<u>23 910</u>
<u>1/2</u>	<u>7 No. 6</u>	<u>0.486</u>	<u>15 330</u>	<u>16 890</u>	<u>20 460</u>
<u>1/2</u>	<u>7 No. 6</u>	<u>0.486</u>	<u>14 870</u>	<u>16 390</u>	<u>19 850</u>
<u>7/16</u>	<u>7 No. 7</u>	<u>0.433</u>	<u>12 670</u>	<u>13 910</u>	<u>16 890</u>
<u>7/16</u>	<u>7 No. 7</u>	<u>0.433</u>	<u>12 290</u>	<u>13 490</u>	<u>16 390</u>
<u>3/8</u>	<u>7 No. 8</u>	<u>0.385</u>	<u>10 460</u>	<u>11 440</u>	<u>13 890</u>
<u>3/8</u>	<u>7 No. 8</u>	<u>0.385</u>	<u>10 150</u>	<u>11 100</u>	<u>13 480</u>
<u>11/32</u>	<u>7 No. 9</u>	<u>0.343</u>	<u>8616</u>	<u>9393</u>	<u>11 280</u>
<u>11/32</u>	<u>7 No. 9</u>	<u>0.343</u>	<u>8359</u>	<u>9113</u>	<u>10 940</u>
<u>5/16</u>	<u>7 No. 10</u>	<u>0.306</u>	<u>7124</u>	<u>7758</u>	<u>9 196</u>
<u>5/16</u>	<u>7 No. 10</u>	<u>0.306</u>	<u>6913</u>	<u>7531</u>	<u>8928</u>
...	<u>3 No. 5</u>	<u>0.392</u>	<u>8373</u>	<u>9262</u>	<u>11 860</u>
...	<u>3 No. 5</u>	<u>0.392</u>	<u>8122</u>	<u>8985</u>	<u>10 820</u>
...	<u>3 No. 6</u>	<u>0.349</u>	<u>6934</u>	<u>7639</u>	<u>9754</u>
...	<u>3 No. 6</u>	<u>0.349</u>	<u>6728</u>	<u>7412</u>	<u>8980</u>
...	<u>3 No. 7</u>	<u>0.311</u>	<u>5732</u>	<u>6294</u>	<u>7922</u>
...	<u>3 No. 7</u>	<u>0.311</u>	<u>5559</u>	<u>6102</u>	<u>7413</u>
...	<u>3 No. 8</u>	<u>0.277</u>	<u>4730</u>	<u>5174</u>	<u>6282</u>
...	<u>3 No. 8</u>	<u>0.277</u>	<u>4592</u>	<u>5023</u>	<u>6099</u>
...	<u>3 No. 9</u>	<u>0.247</u>	<u>3898</u>	<u>4250</u>	<u>5129</u>
...	<u>3 No. 9</u>	<u>0.247</u>	<u>3781</u>	<u>4122</u>	<u>4950</u>
...	<u>3 No. 10</u>	<u>0.220</u>	<u>3224</u>	<u>3509</u>	<u>4160</u>
...	<u>3 No. 10</u>	<u>0.220</u>	<u>3127</u>	<u>3407</u>	<u>4039</u>
...	<u>3 No. 12</u>	<u>0.174</u>	<u>1715</u>
...	<u>3 No. 12</u>	<u>0.174</u>	<u>1647</u>	<u>1719</u>	<u>2564</u>

^A Diameter of circumscribing circle.

^B Minimum breaking strength is calculated using the minimum diameter of the individual wire and the minimum tensile strength from B227. Breaking loads of 7-wire and 19-wire conductors are taken as 90 % of the sum of the breaking loads of the individual wires; breaking load of 3-wire conductors is taken as 95 % of the sum of the breaking loads of the individual wires.

^C The designation "Inch" is the approximate diameter in proper fraction of an inch.

^D The designation of "AWG" is a combination of the number of wires each of the American Wire Gage size indicated by "No."

4. Material for Wires

- 4.1 The purchaser shall specify the grade of wire to be used in the conductor.
- 4.2 Before stranding, the copper-clad steel wire shall meet all the requirements of Specification B227.
- 4.3 All wires in the conductor shall be of the same grade and quality.

5. Joints

5.1 Joints or splices may be made in the finished individual copper-clad steel wires composing concentric-lay-stranded conductors, using more than three wires provided that such joints or splices have a protection equivalent to that of the wire itself and that they do not decrease the strength of the finished stranded conductor below the minimum breaking strength shown in Table 1. Such joints or splices shall be not closer than 50 ft (15 m) to any other joint in the same layer in the conductor (Note 1).

NOTE 1—Joints or splices in individual copper-clad steel wires in their finished size are made by electrical butt welding. Two types of joints are used and are described as follows:

(a) *Weld-Annealed Joints*—After butt welding, the wire is annealed for a distance of approximately 5 in. (127 mm) on each side of the weld. The weld is then protected from corrosion with a snug fitting seamless copper sleeve which extends at least 3/8 in. (9.5 mm) on each side of the weld and which is thoroughly sealed to the wire with solder. The wall thickness of the sleeve is at least 10 % of the radius of the wire.