



Designation: A988/A988M-07 **Designation: A988/A988M – 11**

Standard Specification for Hot Isostatically-Pressed Stainless Steel Flanges, Fittings, Valves, and Parts for High Temperature Service¹

This standard is issued under the fixed designation A988/A988M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 This specification covers hot isostatically-pressed, powder metallurgy, stainless steel piping components for use in pressure systems. Included are flanges, fittings, valves, and similar parts made to specified dimensions or to dimensional standards, such as in ASME specification B16.5.

1.2 Several grades of martensitic, austenitic, age hardening, and austenitic-ferritic stainless steels are included in this specification.

1.3 Supplementary requirements are provided for use when additional testing or inspection is desired. These shall apply only when specified individually by the purchaser in the order.

1.4 This specification is expressed in both inch-pound units and in SI units. Unless the order specifies the applicable “M” specification designation (SI units), however, the material shall be furnished to inch-pound units.

1.5 The values stated in either inch-pound units or SI units are to be regarded separately as the standard. Within the text, the SI units are shown in parentheses. The values stated in each system ~~are~~ may not be exact equivalents; therefore, each system ~~must~~ shall be used independently of the other. Combining values from the two systems may result in non-conformance with the ~~specification-standard~~.

1.6 The following safety hazards caveat pertains only to test methods portions 8.1, 8.2, 9.5-9.7, and Section 10 of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

A262 Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels

A275/A275M Practice for Magnetic Particle Examination of Steel Forgings ~~A370 Test Methods and Definitions for Mechanical Testing of Steel Products~~

A745/A745M Practice for Ultrasonic Examination of Austenitic Steel Forgings

A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products

A923 Test Methods for Detecting Detrimental Intermetallic Phase in Duplex Austenitic/Ferritic Stainless Steels

A961/A961M Specification for Common Requirements for Steel Flanges, Forged Fittings, Valves, and Parts for Piping Applications

B311 Test Method for Density of Powder Metallurgy (PM) Materials Containing Less Than Two Percent Porosity

E112 Test Methods for Determining Average Grain Size

E165 Practice for Liquid Penetrant Examination for General Industry

E340 Test Method for Macroetching Metals and Alloys

E606 Practice for Strain-Controlled Fatigue Testing

G48 Test Methods for Pitting and Crevice Corrosion Resistance of Stainless Steels and Related Alloys by Use of Ferric Chloride Solution

2.2 MSS Standard:

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.22 on Steel Forgings and Wrought Fittings for Piping Applications and Bolting Materials for Piping and Special Purpose Applications.

Current edition approved Sept. 1, 2007-2011. Published October 2007-June 2011. Originally approved in 1998. Last previous edition approved in 2005-2007 as A988/A988M – 05.7. DOI: 10.1520/A0988_A0988M-0711.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

SP 25 Standard Marking System for Valves, Fittings, Flanges, and Unions³

2.3 *ASME Specifications and Boiler and Pressure Vessel Codes:*

B16.5 Dimensional Standards for Steel Pipe Flanges and Flanged Fittings⁴

2.4 *ASME Specification IX Welding Qualifications:*

SFA-5.4 Specification for Corrosion-Resisting Chromium and Chromium-Nickel Steel Covered Welding Electrodes⁴

SFA-5.9 Specification for Corrosion-Resisting Chromium and Chromium-Nickel Steel Welding Rods and Bare Electrodes⁴

SFA-5.11 Specification for Nickel and Nickel-Alloy Covered Welding Electrodes⁴

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *can, n*—the container used to encapsulate the powder during the pressure consolidation process; it is partially or fully removed from the final part.

3.1.2 *compact, n*—the consolidated powder from one can. It may be used to make one or more parts.

3.1.3 *consolidation, n*—the bonding of adjacent powder particles in a compact under pressure by heating to a temperature below the melting point of the powder.

3.1.4 *fill stem, n*—the part of the compact used to fill the can. It is not usually integral to the part produced.

3.1.5 *hot isostatic pressing, n*—a process for simultaneously heating and forming a compact in which the powder is contained in a sealed formable enclosure usually made from metal and the so-contained powder is subjected to equal pressure from all directions at a temperature high enough to permit plastic deformation and consolidation of the powder particles to take place.

3.1.6 *lot, n*—a number of parts made from a single powder blend following the same manufacturing practice.

3.1.7 *part, n*—a single item coming from a compact, either prior to or after machining.

3.1.8 *powder blend, n*—a homogeneous mixture of powder from one or more heats of the same grade.

3.1.9 *rough part, n*—the part prior to final machining.

4. Ordering Information

4.1 It is the responsibility of the purchaser to specify in the purchase order all requirements that are necessary for material ordered under this specification. Such requirements may include, but are not limited to, the following:

4.1.1 Quantity (weight or number of parts),

4.1.2 Name of material or UNS number,

4.1.3 ASTM designation and year of issue,

4.1.4 Dimensions (tolerances and surface finishes should be included),

4.1.5 Microstructure examination if required (5.1.4),

4.1.6 Inspection (15.1),

4.1.7 Whether rough part or finished machined part (8.2.2),

4.1.8 Supplementary requirements, if any,

4.1.9 Additional requirements (See 7.2 and 17.1), and

4.1.10 Requirement, if any, that the manufacturer shall submit drawings for approval showing the shape of the rough part before machining and the exact location of test specimen material (See 9.3).

TABLE 1 Chemical Requirements

Composition, % ^A												
UNS Designation	Grade	Carbon	Manganese	Phosphorus	Sulfur	Silicon	Nickel	Chromium	Molybdenum	Columbium plus Tantalum	Tantalum	Titanium
Martensitic Stainless Steels												
S41000	13 chromium	0.15	1.00	0.040	0.030	1.00		11.5–13.5
S41026	13 chromium 0.5 molybdenum	0.15	1.00	0.020	0.020	1.00	1.00–2.00	11.5–13.5	0.40–0.60	Other Elements Cu 0.50		
S41500	13 chromium, 4 nickel	0.05	0.50–1.00	0.030	0.030	0.60	3.5–5.5	11.5–14.0	0.50–1.00
S42390	12 chromium, 1.0 molybdenum, modified with vanadium	0.18–0.25	1.00	0.030	0.030	1.00	0.30–0.80	11.5–12.5	0.80–1.20	Other Elements N 0.03–0.08 V 0.25–0.35 Cb 0.08–0.15		
Austenitic Stainless Steels												
S30400 ^B	18 chromium, 8 nickel	0.08	2.00	0.045	0.030	1.00	8.0–11.0	18.0–20.0

³ Available from Manufacturers Standardization Society of the Valve and Fittings Industry (MSS), 127 Park St., NE, Vienna, VA 22180-4602, <http://www.mss-hq.com>.

⁴ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Three Park Ave., New York, NY 10016-5990, <http://www.asme.org>.