



**SLOVENSKI STANDARD**  
**oSIST prEN ISO 877-1:2024**  
**01-september-2024**

**Nadomešča:**  
**SIST EN ISO 877-1:2012**

---

**Polimerni materiali - Metode izpostavitve vremenskim vplivom - 1. del: Splošna navodila (ISO/DIS 877-1:2024)**

Plastics - Methods of exposure to solar radiation - Part 1: General guidance (ISO/DIS 877-1:2024)

Kunststoffe - Freibewitterung - Teil 1: Allgemeine Anleitung (ISO/DIS 877-1:2024)

Plastiques - Méthodes d'exposition au rayonnement solaire - Partie 1: Lignes directrices générales (ISO/DIS 877-1:2024)

**Ta slovenski standard je istoveten z: prEN ISO 877-1**

<https://standards.iteh.ai/catalog/standards/sist/8b70e40c-54d7-4d59-a593-c7098b0dfce6/osist-pr-en-iso-877-1-2024>

**ICS:**

83.080.01	Polimerni materiali na splošno	Plastics in general
-----------	--------------------------------	---------------------

**oSIST prEN ISO 877-1:2024**

**en,fr,de**





# DRAFT International Standard

## ISO/DIS 877-1

### Plastics — Methods of exposure to solar radiation —

#### Part 1: General guidance

*Plastiques — Méthodes d'exposition au rayonnement solaire —  
Partie 1: Lignes directrices générales*

ICS: 83.080.01

ISO/TC 61/SC 6

Secretariat: **DIN**

Voting begins on:  
**2024-07-08**

Voting terminates on:  
**2024-09-30**

<https://standards.iteh.ai/catalog/standards/sist/8b70e40c-54d7-4d59-a593-c7098b0dfec6/osist-pren-iso-877-1-2024>

This document is circulated as received from the committee secretariat.

**ISO/CEN PARALLEL PROCESSING**

Reference number  
ISO/DIS 877-1:2024(en)

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENTS AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

© ISO 2024

## ISO/DIS 877-1:2024(en)

# iTeh Standards (<https://standards.iteh.ai>) Document Preview

[oSIST prEN ISO 877-1:2024](https://standards.iteh.ai/catalog/standards/sist/8b70e40c-54d7-4d59-a593-c7098b0dfec6/osist-pren-iso-877-1-2024)

<https://standards.iteh.ai/catalog/standards/sist/8b70e40c-54d7-4d59-a593-c7098b0dfec6/osist-pren-iso-877-1-2024>



### **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

## ISO/DIS 877-1:2024(en)

## Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>2</b>
<b>4 Principle</b> .....	<b>2</b>
<b>5 Apparatus</b> .....	<b>3</b>
5.1 General requirements.....	3
5.2 Apparatus for measurement of climatic factors.....	3
5.2.1 Apparatus for measurement of radiant exposure.....	3
5.2.2 Other climate-measuring instruments.....	4
<b>6 Test specimens</b> .....	<b>4</b>
6.1 Form, shape and preparation.....	4
6.2 Number of test specimens.....	5
6.3 Conditioning and storage.....	6
<b>7 Conditions of exposure of the test specimens</b> .....	<b>6</b>
7.1 Classes of climate.....	6
7.2 Types of exposure used for specimens.....	6
<b>8 Exposure stages</b> .....	<b>7</b>
8.1 General considerations.....	7
8.2 Duration of exposure.....	7
8.3 Solar radiant exposure.....	7
8.3.1 Importance.....	7
8.3.2 Instrumental measurement of solar radiant exposure.....	7
<b>9 Procedure</b> .....	<b>8</b>
9.1 Mounting of test specimens.....	8
9.2 Mounting of reference materials.....	8
9.3 Climatic observations.....	8
9.4 Exposure of test specimens.....	9
9.5 Determination of changes in properties, if required.....	9
<b>10 Expression of results</b> .....	<b>9</b>
10.1 Determination of changes in properties.....	9
10.2 Levels (values) of exposure stages.....	9
10.3 Climatic conditions.....	9
<b>11 Test report</b> .....	<b>10</b>
<b>Annex A (informative) Classification of climates</b> .....	<b>12</b>
<b>Bibliography</b> .....	<b>14</b>

## ISO/DIS 877-1:2024(en)

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

ISO draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). ISO takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, ISO had not received notice of (a) patent(s) which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at [www.iso.org/patents](http://www.iso.org/patents). ISO shall not be held responsible for identifying any or all such patent rights.+

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see: [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 6, *Ageing, chemical and environmental resistance*.

This second edition cancels and replaces the first edition (ISO 877-1:2009), which has been technically revised.

The main changes are as follows:

- addition of new term and [definition 3.1](#) "natural weathering";
- addition of a requirement for the area beneath and in the vicinity of racks in [5.1](#);
- addition of new NOTE 2 in 9.2 referring to ISO/TR 19032;
- addition of information to be included in the test report ([Clause 11](#)).

A list of all parts in the ISO 877 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

## ISO/DIS 877-1:2024(en)

### Introduction

Outdoor-exposure tests of the type specified in the three parts of this International Standard are needed to evaluate the performance of plastics when exposed to solar radiation. The results of such tests should be regarded only as an indication of the effect of exposure to direct weathering (ISO/DIS 877-2:2024, method A) or to indirect weathering using glass-filtered solar radiation (ISO/DIS 877-2:2024, method B) or to intensified solar radiation (ISO 877-3) by the methods described. Results from tests conducted in accordance with any of the parts of this International Standard will show some variability when comparing results from repeat exposures conducted at the same location at a different time. This is much more important for materials that show significant change after a year or less of exposure. In general, results from repeat exposures at the same location are necessary to determine the range of performance of a material subjected to exposure to solar radiation as specified in this International Standard. Since the type of climate can have a significant effect on the rate and type of degradation, results from exposures conducted in different types of climate are necessary to fully characterize the outdoor durability of a material. For solar-concentrating exposures conducted in accordance with ISO 877-3, exposure duration is defined in terms of the total solar UV radiant exposure. This reduces the effect of annual and seasonal variations in solar ultraviolet radiation.

Fresnel-reflecting concentrators of the type described in ISO 877-3, are utilized to intensify natural solar radiation, in an attempt to accelerate outdoor-exposure testing of plastics materials.

A system of classifying and characterizing climates in different parts of the world is given in [Annex A](#).

The test method chosen is usually that designed to expose the material to the most severe conditions associated with any particular climate. It should, therefore, be borne in mind that the severity of exposure in actual use is, in most cases, likely to be less than that specified in this International Standard, and allowance should be made accordingly when interpreting the results. For example, vertical exposure at 90° from the horizontal is considerably less severe in its effects on plastics than near-horizontal exposure, particularly in tropical regions, where the sun is most powerful at high zenith angles.

Polar-facing surfaces are much less likely to be degraded than equator-facing surfaces because they are less exposed to solar radiation. However, the fact that they may remain wet for longer periods may be of significance for materials affected by moisture or for materials that are susceptible to microbial growth.

[oSIST prEN ISO 877-1:2024](#)

<https://standards.iteh.ai/catalog/standards/sist/8b70e40c-54d7-4d59-a593-c7098b0dfec6/osist-pren-iso-877-1-2024>





# Plastics — Methods of exposure to solar radiation —

## Part 1: General guidance

### 1 Scope

This document provides information and general guidance on the selection and use of the methods of exposure to solar radiation described in detail in subsequent parts of ISO 877. These methods of exposure to solar radiation are applicable to plastics materials of all kinds as well as to products and portions of products.

It also specifies methods for determining radiant exposure.

It does not include direct weathering using black-box test fixtures, which simulate higher end-use temperatures in some applications.

NOTE ASTM G7 [\[1\]](#) and ASTM D4141 [\[2\]](#) describe black-box exposure tests.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 472, *Plastics — Vocabulary*

ISO/DIS 877-2:2024, *Plastics — Methods of exposure to solar radiation — Part 2: Direct weathering and exposure behind window glass*

ISO 877-3, *Plastics — Methods of exposure to solar radiation — Part 3: Intensified weathering using concentrated solar radiation*

ISO 2818, *Plastics — Preparation of test specimens by machining*

ISO 4582, *Plastics — Determination of changes in colour and variations in properties after exposure to glass-filtered solar radiation, natural weathering or laboratory radiation sources*

ISO 4892-1, *Plastics — Methods of exposure to laboratory light sources — Part 1: General guidance and requirements*

ISO 9370:2017, *Plastics — Instrumental determination of radiant exposure in weathering tests — General guidance and basic test method*

ASTM G179, *Standard Specification for Metal Black Panel and White Panel Temperature Devices for Natural Weathering Tests*

ASTM G183, *Standard Practice for Field Use of Pyranometers, Pyrhemometers and UV Radiometers*

## ISO/DIS 877-1:2024(en)

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 472, ISO 4892-1, and ISO 9370 and the following apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

#### 3.1

##### **natural weathering**

outdoor exposure of materials to unconcentrated sunlight, the purpose of which is to assess the effects of environmental factors on various functional and decorative parameters of interest

### 4 Principle

Specimens or, if required, sheets or other shapes from which specimens can be cut, are exposed to natural solar radiation (ISO/DIS 877-2:2024, method A), or to window-glass-filtered solar radiation (ISO/DIS 877-2:2024, method B) or to intensified solar radiation using a Fresnel-reflecting concentrator (ISO 877-3). After the prescribed exposure period, the specimens are removed from exposure and, if a characterization is required, tested for changes in optical, mechanical or other properties of interest. The exposure stage may be a given period of time or may be expressed in terms of a given total radiant exposure or UV radiant exposure. The latter is preferred whenever the main objective of the exposure is to determine resistance to solar radiation, since it minimizes the effect of variations in spectral irradiance with climate, location and time.

NOTE 1 Exposures with the same total or UV radiant exposure in different climates, locations and periods can still result in different rate and type of degradation.

Instrumental means of measuring irradiance, and means for integration to give the radiant exposure over a period of time, are preferred.

NOTE 2 Physical standard materials that change in colour, or another property, upon exposure to solar radiation have been used to determine radiant exposures. Determinations of radiant exposure using these procedures are less reliable indicators than determination of radiant exposure by actual measurement of solar radiation.

When comparing the results of exposure using ISO/DIS 877-2:2024, method A or B, with ISO 877-3, differences in specimen temperatures, ultraviolet radiant exposure levels and moisture deposition should be taken into account. Additionally, when comparing ISO/DIS 877-2:2024, method B, to ISO 877-3, the glass or other transparent material used as the filter must be identical. Comparison of results from ISO 877-3 to those from ISO/DIS 877-2:2024, method A or B, must be based on equal radiant exposure levels.

The climatic conditions during the test may be monitored and reported with the other conditions of exposure.

It is recommended that a similar material of known behaviour be exposed simultaneously with the experimental material as a control.

Unless otherwise specified, test pieces for the determination of change in colour and change in mechanical properties are exposed in a mechanically unstressed state.

ISO/DIS 877-2:2024, method B, excludes the effects of wind, dew and rain. The devices used for ISO 877-3 are typically equipped to provide moisture in the form of water spray.

Exposures in hot and wet and in hot and dry climates are often used to benchmark the outdoor durability of materials such as plastics. Information on climate classification can be found in [Annex A](#).

NOTE 3 More detailed information about the effects of different climates and different exposure parameters on the variability of results from outdoor exposures can be found in ASTM G141 [3].