This document is not an ASTM standard and is intended only to provide the user of an ASTM standard an indication of what changes have been made to the previous version. Because it may not be technically possible to adequately depict all changes accurately, ASTM recommends that users consult prior editions as appropriate. In all cases only the current version of the standard as published by ASTM is to be considered the official document.

INTERNATIONAL

Designation:A491–10 Designation: A491 – 11

# Standard Specification for Aluminum-Coated Steel Chain-Link Fence Fabric<sup>1</sup>

This standard is issued under the fixed designation A491; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

# 1. Scope

1.1 This specification covers aluminum-coated steel chain-link fence fabric, aluminum-coated before weaving.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

# 2. Referenced Documents

# 2.1 ASTM Standards:<sup>2</sup>

A370 Test Methods and Definitions for Mechanical Testing of Steel Products

A700 Practices for Packaging, Marking, and Loading Methods for Steel Products for Shipment

A817 Specification for Metallic-Coated Steel Wire for Chain-Link Fence Fabric and Marcelled Tension Wire

2.2 Federal Standard:<sup>3</sup>

Fed. Std. No. 123 Marking for Shipment, Civil Agencies

2.3 Military Standards:<sup>3</sup>

MIL-STD-129 Marking for Shipment and Storage

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

# 3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *chain link fence fabric*—a fencing material made from steel wire helically wound and interwoven in such a manner as to provide a continuous mesh without knots or ties except in the form of knuckling or of twisting the ends of the wires to form the selvage of the fabric.

3.1.2 *diamond count*—the number of diamond openings from one edge of the fabric to the other. The diamond count of a given fabric shall begin at the first completed diamond at one edge and continue to the unfinished  $(\frac{1}{2})$  or full opening at the other edge.

3.1.3 *knuckling*—a term used to describe the type of selvage obtained by interlocking adjacent pairs of wire ends and then bending the wire ends back into a loop. The loop shall be closed or nearly closed to a measurement less than the diameter of the wire.

3.1.4 *twisting*—a term used to describe the type of selvage obtained by twisting adjacent pairs of wire ends together in a close helix of  $1\frac{1}{2}$  machine turns, which is equivalent to 3 full twists, and cutting the wire ends at an angle. The wire ends beyond the twist shall be at least  $\frac{1}{4}$  in. (6.4 mm) long. This type of selvage is not used on fabric with a mesh size of less than 2 in. (50.8 mm).

# 4. Ordering Information

4.1 Orders for chain-link fence fabric purchased to this specification shall include the following information:

- 4.1.1 Quantity (Section 14),
- 4.1.2 Size of mesh (Section 7),
- 4.1.3 Size of wire (Section 8),
- 4.1.4 Height of fabric (Section 9),
- 4.1.5 Diamond count, if specified (Section 6),
- 4.1.6 Type of selvage (Section 10),

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

<sup>&</sup>lt;sup>1</sup> This specification is under the jurisdiction of ASTM Committee F14 on Fences and is the direct responsibility of Subcommittee F14.40 on Chain Link Fence and Wire Accessories.

Current edition approved JulyJune 1, 2010:2011. Published July 2010. June 2011. Originally approved in 1963. Last previous edition approved in 20072010 as A491 - 107. DOI: 10.1520/A0491-101.

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>&</sup>lt;sup>3</sup> Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

4.1.7 Certification if required (Section 17), and

4.1.8 ASTM designation and year of issue.

4.2 All rolls of fencing accepted by the purchaser shall be billed on the basis of the original footage of the rolls before sampling, unless changed by contractual arrangement.

🦻 A491 – 11

NOTE 1—A typical ordering description is as follows: 25 rolls, 50 ft each, chain-link fence fabric, aluminum-coated, 2 in. mesh. 0.148 in. wire, 60 in. high, knuckled both selvages, to ASTM A491–XX.

### 5. Materials

5.1 The wire from which the fabric is woven shall conform to all requirements of Specification A817 for Type I coating.

#### 6. Weave

6.1 The wire shall be woven throughout in the form of approximately uniform square mesh, having parallel sides and horizontal and vertical diagonals of approximately uniform dimensions. The top and bottom of the fabric shall be knuckled or twisted as specified in Section 10.

6.2 Typical diamond count for each standard height is shown in Table 1. Other diamond counts are permissible provided that they are consistent within a lot. The purchaser has the option to specify the diamond count (4.1.5).

# 7. Size of Mesh

7.1 The size of mesh shall be as indicated in Table 2 (see Fig. 1).

7.2 The permissible variation from the specified size of mesh shall be  $\pm \frac{1}{8}$  in. ( $\pm 3.2$  mm) for all mesh sizes over 1 in. (25 mm), and  $\pm \frac{1}{16}$  in. ( $\pm 1.6$  mm) for all mesh sizes 1 in. (25.4 mm) and under.

7.3 The size of mesh shall be determined by measuring the minimum clear distance between the wires forming the parallel sides of the mesh, and determined as the average of two readings taken at right angles to each other.

#### 8. Size of Wire

8.1 Chain-link fabric shall be fabricated from wire diameters as listed in Specification A817, with a permissible variation from the specified diameter of the coated wire of  $\pm 0.005$  in. ( $\pm 0.13$  mm).

#### 9. Height of Fabric

9.1 Chain-link fabric shall be furnished in the standard heights shown in Table 2. Custom order fabric is available in heights to and including 20 ft. (6.56 m). The height of fabric shall be the overall dimension from ends of twists or knuckles. The permissible variation from the specified height shall be  $\pm 1$  in. ( $\pm 25$  mm) for standard selvage on fabric with mesh sizes 1 in. (25 mm) and over and  $\pm \frac{1}{2}$  in. ( $\pm 13$  mm) for all fabric with mesh sizes less than 1 in. (25 mm).

10. Selvages://standards.iteh.ai/catalog/standards/sist/17db994c-74bf-492f-abaa-458aedf96bc1/astm-a491-11

10.1 Unless otherwise specified by the purchaser, fabrics with 2- or 2<sup>1</sup>/<sub>8</sub>-in. (50- or 54-mm) mesh, in heights 60 in. (1520 mm) and under shall be knuckled at both selvages. Fabric 72 in. (1830 mm) high and over shall be knuckled at one selvage and twisted at the other.

10.2 The selvages of fabrics with meshes of less than 2 in. (50 mm) shall be knuckled.

#### TABLE 1 Typical Diamond Count<sup>A</sup>

Note 1—Other diamond counts are permitted (see 6.2). Note 2— For fabric heights over 144 in., see Section 9.

Nominal Diameter Coated Wire, in.	Size of Mesh, in.	Height of Fence Fabric, in.									
		36	42	48	60	72	84	96	108	120	144
0.192	2	101/2	<b>12</b> ½	131⁄2	171/2	201/2	241/2	271/2	31½	341/2	<b>41</b> ½
0.148	2	101/2	<b>12</b> ½	131/2	171/2	201/2	241/2	271/2	311/2	341/2	411/2
<del>-0.148</del>	<del>13/4</del>	<del>20</del> —	<del>23 ½</del>	27—	<del>33</del> —	<del>39 ½</del>	45—	<del>53</del> —	<del>61</del> —	67—	<del>79</del> —
0.148	13⁄4	<b>11</b> ½	131/2	151/2	191/2	231/2	271/2	<u>31½</u>	351/2	391/2	411/2
<del>-0.148</del>	11/4			23	29	35	41	46	52	56	70
0.148	11⁄4	17	21	23	29	35	41	46	52	56	70
0.148	1	20	23	27	33	39	45	53	61	67	79
0.135	2	101/2	121/2	131/2	171/2	201/2	241/2	271/2	311/2	341/2	411/2
0.120	2	101/2	121/2	141/2	171/2	201/2	241/2				
<del>- 0.120</del>	<del>13/4</del>	<del></del>	<del></del>	<del></del>	<del></del>	<del></del>	<del></del>	<del>31½</del>	<del>35½</del>	<del>39½</del>	<del>47½</del>
0.120	13/4	<b>11</b> ½	131/2	151/2	191/2	231/2	271/2	<u>31½</u>	351/2	391/2	471/2
-0.120	<del>11/4</del>			23	29	35	41	46	52	<del>58</del>	70
0.120	11/4	17	21	23	29	35	41	46	52	58	70
0.120	1	20	23	27	33	39	45	53	61	67	79
0.113	21/8	91/2	111/2	131/2	<b>16</b> ½	191/2					

<sup>A</sup>See Appendix X1 for metric equivalents.

#### TABLE 2 Sizes of Wire and Mesh<sup>A</sup>


Specified Diameter of Coated Wire, in.	Size, Coated Wire Gage	Size of Mesh, in. <sup>B</sup>	Height of Fence Fabric, in.
0.192	6	2	36, 42, 48, 60, 72, 84, 96, 108, 120, 144
0.148	9	2	36, 42, 48, 60, 72, 84, 96, 108, 120, 144
0.148	<u>9</u>	13⁄4	36, 42, 48, 60, 72, 84, 96, 108, 120, 144
<del>0.148<sup>C</sup></del>	_ <del>9</del>	$\frac{13/4}{11/4}$	,, 48, 60, 72, 84, 96, 108, 120, 144
<u>0.148</u> <sup>C</sup>	9	11⁄4	36, 42, 48, 60, 72, 84, 96, 108, 120, 144
0.148	9	1	36, 42, 48, 60, 72, 84, 96, 108, 120, 144
0.148	_9	$\frac{1/2}{2}$	36, 42, 48, 60, 72, 84, 96, 108, 120, 144
0.135	10	2	36, 42, 48, 60, 72, 84, 96, 108, 120, 144
0.120	11	2	36, 42, 48, 60, 72, 84
<del>0.120</del>	<del>11</del>	<del>13/4</del>	<del></del>
0.120	<u>11</u>	<u>13/4</u>	36, 42, 48, 60, 72, 84, 96, 108, 120, 144
0.120 <sup>C</sup>	-11	<del>11/4</del>	<del>,, 48, 60, 72, 84, 96, 108, 120, 144</del>
<u>0.120<sup>C</sup></u>	<u>11</u> 11	$\frac{11/4}{1}$	36, 42, 48, 60, 72, 84, 96, 108, 120, 144
0.120	11	-	36, 42, 48, 60, 72, 84, 96, 108, 120, 144
0.120	11	5/8 <sup>D</sup>	36, 42, 48, 60, 72, 84, 96, 108, 120, 144
0.120	11	1/2 <sup>D</sup>	36, 42, 48, 60, 72, 84, 96, 108, 120, 144
0.120	11	3/8 <sup>D</sup>	36, 42, 48, 60, 72, 84, 96, 108, 120, 144
0.113	111/2	21/8	36, 42, 48, 60, 72

<sup>A</sup>See Appendix X1 for metric equivalents.

<sup>B</sup>See Fig. 1 for mesh dimensions for 5% in., 1/2 in., and 3% in. fence fabric.

<sup>C</sup>This mesh size and smaller is recommended for swimming pools.

<sup>D</sup>These sizes are designed for security purposes.



NOTE 2-Caution: Twisted selvages for fence fabric under 72 in. (1830 mm) in height are not recommended because of consumer safety considerations.

# 11. Weight of Aluminum Coating

11.1 The weight of aluminum coating on the wire in the fabric shall be as specified in Specification A817, for the wire diameter used (see Table 3).

#### 12. Breaking Strength

12.1 Wire constituting the fabric shall meet the minimum breaking strength listed in the Breaking Strength Table of

TABLE 3 Minimum Weight of Aluminum Coating for Type I

Specified Diameter of Coated Wire, in. (mm)	Minimum Weight of Coating, oz/ft <sup>2</sup> (g/m <sup>2</sup> ) of uncoated wire surface
0.192 (4.88)	0.40 (122)
0.148 (3.76)	0.40 (122)
0.135 (3.43)	0.40 (122)
0.120 (3.05)	0.35 (107)
0.113 (2.87)	0.30 (92)