

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Determination of certain substances in electrotechnical products –
Part 11: Tris(2-chloroethyl) phosphate (TCEP) in plastics by gas
chromatography-mass spectrometry (GC-MS) and liquid chromatography-mass
spectrometry (LC-MS)**

Document Preview

Détermination de certaines substances dans les produits électrotechniques –
Partie 11: Phosphate de tris(2-chloroéthyle) (TCEP) dans les plastiques par
chromatographie en phase gazeuse-spectrométrie de masse (GC-MS) et
chromatographie en phase liquide-spectrométrie de masse (LC-MS)





THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2023 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de l'IEC ou du Comité national de l'IEC du pays du demandeur. Si vous avez des questions sur le copyright de l'IEC ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de l'IEC de votre pays de résidence.

IEC Secretariat
3, rue de Varembé
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee, ...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

<https://standards.iteh.ai/catalog/standards/iso/7433a1c5-351f-48b3-81c6-936d435d464b/iec-62321-11-2023>

A propos de l'IEC

La Commission Electrotechnique Internationale (IEC) est la première organisation mondiale qui élabore et publie des Normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications IEC

Le contenu technique des publications IEC est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

Recherche de publications IEC -

webstore.iec.ch/advsearchform

La recherche avancée permet de trouver des publications IEC en utilisant différents critères (numéro de référence, texte, comité d'études, ...). Elle donne aussi des informations sur les projets et les publications remplacées ou retirées.

IEC Just Published - webstore.iec.ch/justpublished

Restez informé sur les nouvelles publications IEC. Just Published détaille les nouvelles publications parues. Disponible en ligne et une fois par mois par email.

Service Clients - webstore.iec.ch/csc

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions contactez-nous: sales@iec.ch.

IEC Products & Services Portal - products.iec.ch

IEC Products & Services Portal - products.iec.ch

Discover our powerful search engine and read freely all the publications previews. With a subscription you will always have access to up to date content tailored to your needs.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 300 terminological entries in English and French, with equivalent terms in 19 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

Découvrez notre puissant moteur de recherche et consultez gratuitement tous les aperçus des publications. Avec un abonnement, vous aurez toujours accès à un contenu à jour adapté à vos besoins.

Electropedia - www.electropedia.org

Le premier dictionnaire d'électrotechnologie en ligne au monde, avec plus de 22 300 articles terminologiques en anglais et en français, ainsi que les termes équivalents dans 19 langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International (IEV) en ligne.

INTERNATIONAL STANDARD

NORME INTERNATIONALE

**Determination of certain substances in electrotechnical products –
Part 11: Tris(2-chloroethyl) phosphate (TCEP) in plastics by gas
chromatography-mass spectrometry (GC-MS) and liquid chromatography-mass
spectrometry (LC-MS)**

Document Preview

Détermination de certaines substances dans les produits électrotechniques –

Partie 11: Phosphate de tris(2-chloroéthyle) (TCEP) dans les plastiques par

<https://www.iec.ch/standard/62321-11-01/62321-11-01-2023-11-2023>

chromatographie en phase gazeuse-spectrométrie de masse (GC-MS) et chromatographie en phase liquide-spectrométrie de masse (LC-MS)

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

CONTENTS

FOREWORD	4
INTRODUCTION	6
1 Scope	7
2 Normative references	7
3 Terms, definitions and abbreviated terms	7
3.1 Terms and definitions	7
3.2 Abbreviated terms	8
4 Principle	9
5 Reagents and materials	9
6 Apparatus	10
6.1 GC-MS method	10
6.2 LC-MS method	11
7 Sampling	11
8 Procedure	11
8.1 General instructions for the analysis	11
8.2 Sample preparation	11
8.2.1 General	11
8.2.2 GC-MS method	12
8.2.3 LC-MS method	13
8.3 Instrumental parameters	14
8.3.1 GC-MS method	14
8.3.2 LC-MS method	15
8.4 Calibrants	16
8.5 Calibration	17
8.5.1 General	17
8.5.2 TCEP and surrogate (100 µg/ml) stock solution	17
8.5.3 Internal standard solution (100 µg/ml of anthracene-d ₁₀)	17
8.5.4 Standard solutions	17
9 Calculation of TCEP concentration	19
10 Precision	21
10.1 GC-MS method	21
10.2 LC-MS method	21
11 Quality assurance and control	22
11.1 General	22
11.2 GC-MS method	22
11.2.1 Performance	22
11.2.2 Method detection limit and reporting limit	23
11.3 LC-MS method	24
11.3.1 Performance	24
11.3.2 Method detection limit and reporting limit	25
12 Test report	25
Annex A (informative) Tris(2-chloroethyl) phosphate (TCEP) in plastics by gas chromatography-mass spectrometry using a pyrolyser/thermal desorption accessory (Py/TD-GC-MS)	26
A.1 Principle	26

A.2	Reagents and materials	27
A.3	Apparatus	27
A.4	Sampling	28
A.5	Procedure	28
A.5.1	General instructions for the analysis	28
A.5.2	Sample preparation	28
A.5.3	Instrumental parameters	29
A.5.4	Calibration	30
A.6	Calculation of TCEP concentration	31
A.6.1	General	31
A.6.2	Determination of RF of DEHP	31
A.6.3	Calculation	32
Annex B (informative)	Examples of chromatograms and mass spectrum by GC-MS	33
Annex C (informative)	Examples of chromatograms and mass spectrum by LC-MS	34
Annex D (informative)	Examples of chromatograms and mass spectrum by Py-TD-GC-MS	35
Bibliography	36	
Figure B.1 – Gas chromatogram of TCEP, TCEP-d ₁₂ , and anthracene-d ₁₀	33	
Figure B.2 – Mass spectrum of TCEP by GC-MS	33	
Figure B.3 – Mass spectrum of TCEP-d ₁₂ by GC-MS	33	
Figure C.1 – Liquid chromatogram of TCEP and TCEP-d ₁₂	34	
Figure C.2 – Mass spectrum of TCEP by LC-MS	34	
Figure C.3 – Mass spectrum of TCEP-d ₁₂ by LC-MS	34	
Figure D.1 – Total ion current chromatogram of TCEP by Py-TD-GC-MS	35	
Figure D.2 – Mass spectrum of TCEP by Py-TD-GC-MS	35	
Table 1 – Measurement condition of GC-MS	14	
Table 2 – Reference masses for the quantification of TCEP	15	
Table 3 – Measurement condition of LC-MS	16	
Table 4 – Calibration standard solution of TCEP with internal standard – Estimated TCEP sample solution concentration 0,1 µg/ml and higher	18	
Table 5 – Calibration standard solution of TCEP with internal standard – Estimated TCEP sample solution concentration lower than 0,1 µg/ml	18	
Table 6 – IIS 11 repeatability and reproducibility (GC-MS)	21	
Table 7 – IIS 11 repeatability and reproducibility (LC-MS)	22	
Table A.1 – Measurement conditions of Py/TD-GC-MS	29	

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**DETERMINATION OF CERTAIN SUBSTANCES
IN ELECTROTECHNICAL PRODUCTS –****Part 11: Tris(2-chloroethyl) phosphate (TCEP) in plastics by gas
chromatography-mass spectrometry (GC-MS) and liquid
chromatography-mass spectrometry (LC-MS)****FOREWORD**

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) IEC draws attention to the possibility that the implementation of this document may involve the use of (a) patent(s). IEC takes no position concerning the evidence, validity or applicability of any claimed patent rights in respect thereof. As of the date of publication of this document, IEC had not received notice of (a) patent(s), which may be required to implement this document. However, implementers are cautioned that this may not represent the latest information, which may be obtained from the patent database available at <https://patents.iec.ch>. IEC shall not be held responsible for identifying any or all such patent rights.

IEC 62321-11 has been prepared by IEC technical committee 111: Environmental standardization for electrical and electronic products and systems, in collaboration with ISO subcommittee SC 5: Physical-chemical properties of ISO technical committee 61: Plastics. It is an International Standard.

It is published as a double logo standard.

The text of this International Standard is based on the following documents:

Draft	Report on voting
111/723/FDIS	111/735A/RVD

Full information on the voting for its approval can be found in the report on voting indicated in the above table.

The language used for the development of this International Standard is English.

This document was drafted in accordance with ISO/IEC Directives, Part 2, and developed in accordance with ISO/IEC Directives, Part 1 and ISO/IEC Directives, IEC Supplement, available at www.iec.ch/members_experts/refdocs. The main document types developed by IEC are described in greater detail at www.iec.ch/publications.

A list of all parts in the IEC 62321 series, published under the general title *Determination of certain substances in electrotechnical products*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under webstore.iec.ch in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn, or
- revised.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[IEC 62321-11:2023](https://standards.iteh.ai/catalog/standards/iso/7433a1c5-351f-48b3-81c6-936d435d464b/iec-62321-11-2023)

<https://standards.iteh.ai/catalog/standards/iso/7433a1c5-351f-48b3-81c6-936d435d464b/iec-62321-11-2023>

INTRODUCTION

The widespread use of electrotechnical products has drawn increased attention to their impact on the environment. In many countries, this has resulted in the adoption of regulations affecting wastes, substances, and energy use of electrotechnical products.

The use of certain substances (e.g. lead (Pb), cadmium (Cd), and polybrominated diphenyl ethers (PBDEs)) in electrotechnical products is a source of concern in current and proposed regional legislation.

The purpose of the IEC 62321 series is therefore to provide test methods that will allow the electrotechnical industry to determine the levels of certain substances of concern in electrotechnical products on a consistent global basis.

This first edition of IEC 62321-11 introduces a new subject covering tris(2-chloroethyl) phosphate (TCEP) in the IEC 62321 series.

TCEP is a halogenated phosphorus-based flame retardant that is disclosable as a substance of very high concern (SVHC) as it is classified as toxic to reproduction category 2 (R60) and was included in the candidate list for authorization on 13 January 2010, following ECHA's decision ED/68/2009 [1]¹ and in regulation (EC) No 1907/2006 ANNEX XVI [2].

TCEP is used as a flame retardant in plastics such as polyester and polyurethane foam and as a plasticizer in polyvinyl chloride. Additionally, TCEP is used as an alternative for brominated flame retardants that have been restricted. No applicable testing standard exists for TCEP analysis in plastics. <https://standards.iteh.ai>

As a result, analysis criteria have been established by an IEC TC 111 and ISO/TC 61/SC 5 joint working group for the joint development of an IEC and ISO double logo International Standard, to provide a test method that will allow the industry to determine the concentrations of TCEP in plastics.

IEC 62321-11:2023

<https://standards.iteh.ai/std/iso/7432-1-5-2516491-2-81-6-036142514641/> IEC 62321-11:2023

WARNING – Persons using this document should be familiar with normal laboratory practice. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any national regulatory conditions.

¹ Numbers in square brackets refer to the Bibliography.

DETERMINATION OF CERTAIN SUBSTANCES IN ELECTROTECHNICAL PRODUCTS –

Part 11: Tris(2-chloroethyl) phosphate (TCEP) in plastics by gas chromatography-mass spectrometry (GC-MS) and liquid chromatography-mass spectrometry (LC-MS)

1 Scope

This part of IEC 62321 specifies two different techniques for the determination of tris(2-chloroethyl) phosphate (TCEP) in plastics, the GC-MS or LC-MS method, both of which are applicable to quantitative analysis.

These two techniques are applicable to use with polyurethane, polyvinylchloride, and polyethylene materials containing TCEP between 200 mg/kg to 2 000 mg/kg.

These test methods do not apply to plastic materials having a processing temperature higher than 230 °C.

GC-MS using a pyrolyser/thermal desorption accessory (Py/TD-GC-MS) technique is described in Annex A and can be used for the screening of TCEP in plastics.

NOTE TCEP starts thermal decomposition at approximately 230 °C. Polymer types that have a processing temperature into shapes of plastics (e.g. pellets, moulded parts or sheets) not exceeding the decomposition temperature can contain TCEP.

2 Normative references

IEC 62321-11:2023

<https://standards.iteh.ai/standard/62321-11-2023>
The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 62321-1:2013, *Determination of certain substances in electrotechnical products – Part 1: Introduction and overview*

IEC 62321-2:2021, *Determination of certain substances in electrotechnical products – Part 2: Disassembly, disjointment and mechanical sample preparation*

3 Terms, definitions and abbreviated terms

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- IEC Electropedia: available at <https://www.electropedia.org>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1.1 **screening**

analytical procedure to determine the presence or absence of substances in the representative part or section of a product, relative to the value or values chosen as the criterion for presence, absence, or further testing

Note 1 to entry: If the screening method produces values that are not conclusive, then additional analysis or other follow-up actions can be necessary to make a final presence or absence decision.

3.1.2 **plastic**

material that contains as an essential ingredient a high polymer and which, at some stage in its processing into finished products, can be shaped by flow

Note 1 to entry: Elastomeric materials, which are also shaped by flow, are not considered to be plastics.

Note 2 to entry: In some countries, particularly the United Kingdom, the term "plastics" is used as the singular form as well as the plural form.

[SOURCE: ISO 472:2013 [3], 2.702]

3.1.3 **polymer**

substance composed of molecules characterized by the multiple repetition of one or more species of atoms or groups of atoms (constitutional units) linked to each other in amounts sufficient to provide a set of properties that do not vary markedly with the addition or removal of one or a few of the constitutional units

[SOURCE: ISO 1382:2020 [4], 3.369]

3.1.4 **blank**

test that follows the same procedures and conditions as the sample test without a sample, which enables quantification of the contamination in the test

<https://standards.iteh.ai/catalog/standards/iso/7433a1c5-351f-48b3-81c6-936d435d464b/iec-62321-11-2023>

3.2 Abbreviated terms

ACN	acetonitrile
API-ES	atmospheric pressure ionization-electrostatic
BSA	N,O-bis(trimethylsilyl)acetamide
BSTFA	N,O-bis(trimethylsilyl)trifluoroacetamide
CCC	continuing calibration check standard
D	dilution factor
DEHP	di-(2-ethylhexyl) phthalate
DMDCS	dimethyldichlorosilane
EI	electron ionization
GC-MS	gas chromatography-mass spectrometry
HPLC	high-performance liquid chromatography
ID	internal diameter
IIS	international interlaboratory study
IS	internal standard
LC-MS	liquid chromatography-mass spectrometry
LOD	limit of detection
MDL	method detection limit

MS	mass spectrometry
PBB	polybrominated biphenyl
PBDE	polybrominated diphenyl ether
PE	Polyethylene
PS	polystyrene
PTFE	polytetrafluoroethylene
PUR	Polyurethane
PVC	Polyvinyl chloride
Py/TD-GC-MS	gas chromatography-mass spectrometry using a pyrolyser/thermal desorption accessory
QC	quality control
RF	response factor
RRF	relative response factor
RSD	relative standard deviation
SIM	single (or "selected") ion monitoring
TCEP	tris(2-chloroethyl) phosphate
TD	thermal desorption
THF	tetrahydrofuran
TICS	tentatively identified compounds

4 Principle

<https://standards.iteh.ai>

The samples are dissolved in THF and the matrix polymer is separated by precipitation with methanol, TCEP is determined qualitatively and quantitatively using GC-MS or LC-MS.

<https://standards.iteh.ai/catalog/standards/iso/7433a1c5-351f-48b3-81c6-936d435d464b/iec-62321-11-2023>

Use chemicals of analytical grade, unless otherwise indicated.

- TCEP (tris(2-chloroethyl) phosphate): CAS No. 115-96-8 (purity of greater than a mass fraction of 98 %);
- THF (GC grade or higher, higher than 99,9 %);
- n-Hexane (GC grade or higher, higher than 98,5 %);
- methanol (GC grade or higher, higher than 99,9 %);
- mixed solvent (THF mixed with methanol, the volume ratio of THF/methanol is 1/4);
- helium (purity of greater than a volume fraction of 99,999 %);
- calibrants; reference materials of TCEP (purity of greater than a mass fraction of 98 %);
- surrogate and internal standards:
 - surrogate standard is used to monitor analytes recovery according to 8.2.2.1 and 8.2.3.1, for example TCEP-d₁₂;
 - internal standard is used to correct injection errors, according to 8.2.2.1 and 8.2.3.1, for example anthracene-d₁₀.

The standards are acceptable when using a quadrupole-type mass spectrometer. A high-resolution mass spectrometer will require the use of other suitable standard substances having a mass and elution time similar to that of the analyte.

6 Apparatus

6.1 GC-MS method

The following items shall be used for the analysis:

- a) analytical balance capable of measuring accurately to 0,000 1 g;
- b) cryogenic grinding mill with liquid N₂ cooling;
- c) ultrasonic bath;
- d) 1 ml, 5 ml, 10 ml, 50 ml, and 100 ml volumetric flasks;
- e) Soxhlet extractors:
 - 30 ml Soxhlet extractors;
 - 250 ml round-bottomed flask;
 - ground-in stopper NS 29/32;
 - Dimroth condenser NS 29/32;
 - boiling stones (e.g. glass pearls or Raschig rings);
- f) 30 ml cellulose extraction thimble with ID 22 mm, height 80 mm;
- g) glass wool for extraction thimble;
- h) heating jackets for 250 ml round-bottomed flask;
- i) glass funnels;
- j) aluminium foil;
- k) cork rings;
- l) 0,45 µm PTFE syringe filter;
- m) microlitre syringe or automatic pipettes;
- n) Pasteur pipettes;
- o) 2 ml sample vials and a screw cap with a PTFE gasket or, depending on the analytical system, a comparable sample receptacle;
- p) mini-shaker known as vortexer or vortex mixer;
- q) deactivated injector liner for GC-MS;
- r) gas chromatograph-mass spectrometer, split/splitless inlet, and a programmable temperature-controlled oven. The mass spectrometer shall be able to perform selected ion monitoring (SIM) and total ion current ("full scan"). The ionization box shall be treated for chemical stability and controlled at 230 °C. The kinetic energy of 70 eV shall be applied in electron ionization (EI) mode;
- s) capillary column;
A liquid phase of 100 % dimethyl polysiloxane or 5 % diphenyl, 95 % dimethyl polysiloxane has been found suitable. The preferred column dimension length is 30 m, internal diameter is 0,25 mm, and the film thickness is 0,25 µm;
- t) 50 ml amber vial;
- u) vacuum rotary evaporator;
- v) auto-sampler.

The use of an auto-sampler is recommended to ensure repeatability.

6.2 LC-MS method

Items a) to p) in 6.1 and the following items shall be used for the analysis:

- a) high-performance liquid chromatography (HPLC) system equipped with a mass spectrometer detector;
The use of an auto-sampler is recommended to ensure repeatability.
- b) pump;
- c) column oven;
- d) stationary phase: C₁₈, 150 mm × 2,1 mm, 5 µm or equivalent film thickness.

7 Sampling

Manual cutting or cryogenic grinding or milling with liquid nitrogen cooling is recommended to be performed in accordance with IEC 62321-2:2021.

The sample shall be ground as small as 500 µm in diameter. Cryogenic grinding with liquid N₂ cooling is strongly recommended. Reference polymer materials shall also be ground in the same way.

If the grinder cannot be used, the sample shall be cut to around 2 mm × 2 mm.

NOTE For a composite plastic that is made from more than one material, but cannot be separated mechanically, the concentration of TCEP can be determined for the composite material, as it cannot be confirmed which of the constituent plastics is the source of the TCEP.

8 Procedure

Document Preview

8.1 General instructions for the analysis

The validation of the instrumentation should include testing of potential cross-contaminations between sequential samples. Additional blanks or an inverted sequence of testing will help to identify cross-contamination.

In order to reduce blank values, ensure the cleanliness of all glass equipment and deactivate glass wool (see 6.1 g)) by subjecting it to 450 °C for at least 30 min. To avoid the decomposition of TCEP by UV light during extraction and analysis, glass equipment made from brown or amber glass shall be used.

If the amount of TCEP in the sample is considerably above the 0,1 % range, it will be necessary to carry out the analysis using an adjusted sample size or by repeating the analysis using an extract that has been appropriately diluted prior to internal standard addition.

After analysis of test samples with high analyte concentration, blank samples shall be analysed, until the background level is decreased to lower than 30 mg/kg. In order to reduce blank values, ensure the cleanliness of all tools used in sample preparation.

A blank polymer material or blank sample cup is used for blank-sample analysis.

8.2 Sample preparation

8.2.1 General

The sample preparation requires clean glassware (e.g. single-use items) to avoid cross-contamination. The extraction method is chosen by the solubility of the sample polymer in THF.

8.2.2 GC-MS method

8.2.2.1 Stock solution

The following stock solution shall be prepared:

- a) surrogate standard to monitor analyte recovery (e.g. TCEP-d₁₂): 1 000 µg/ml in a solvent;

NOTE 1 The solvent is THF or n-hexane, which is decided by the extraction method.

- b) internal standard to correct for injection error (e.g. anthracene-d₁₀): 10 µg/ml or 100 µg/ml in a solvent.

NOTE 2 The solvent is methanol or n-hexane, which is decided by the extraction method.

8.2.2.2 Extraction by sonication for soluble polymer

For a soluble polymer sample like PUR or PVC, the following procedure shall be applied:

- a) Weigh 200 mg ± 10 mg of the sample and transfer it into a 50 ml vial (6.1 t)). Record the weight to the nearest 0,1 mg. Other sample amounts may be used for samples with potentially very low or very high TCEP concentrations but the maximum sample amount is 500 mg. Transfer 10 ml of THF and 10 µl of surrogate standard (8.2.2.1 a)) to the 50 ml vial (6.1 t)).

- b) Tightly cap the sample 50 ml vial (6.1 t)). A small piece of adhesive tape may be used to prevent the cap from loosening due to vibration.

- c) Place the 50 ml vial (6.1 t)) in an ultrasonic bath (6.1 c)) at 60 °C and sonicate for 60 min.

- d) Allow the 50 ml vial (6.1 t)) to cool to ambient temperature, (20 ± 5) °C.

- e) Add 40 ml of methanol (Clause 5 d)) dropwise into the 50 ml vial (6.1 t)) and mix well to precipitate the sample matrix. The resulting extracted solution should stand at room temperature for 30 min.

- f) Filter the solution through a 0,45 µm PTFE membrane filter.

- g) Transfer 1 ml of the filtrate into a 2 ml vial (6.1 o)) and add 10 µl of internal standard (8.2.2.1 b)) into the 2 ml vial (6.1 o)).

- h) Cap the 2 ml vial (6.1 o)) with a PTFE-coated seal and stir well.

8.2.2.3 Soxhlet extraction for insoluble polymer

The following steps shall be applied for samples other than PUR and PVC:

- a) To clean the Soxhlet extractors (6.1 e)), a 2 h pre-extraction is carried out with 100 ml of n-hexane (Clause 5 c)). The washing solvent is discarded after cleaning.

- b) Transfer 200 mg ± 10 mg of the sample into cellulose extraction thimbles (6.1 f)) for Soxhlet extraction. Record the mass to the nearest 0,1 mg. Other sample amounts may be used for samples with potentially very low or very high TCEP concentrations but the maximum sample amount is 500 mg.

- c) Allow the sample to be transferred through a funnel (6.1 i)) into the extraction thimble (6.1 f)). In order to ensure a quantitative transfer, the funnel (6.1 i)) should be rinsed with approximately 10 ml of n-hexane (Clause 5 c)).

- d) 10 µl of surrogate standard (8.2.2.1 a)) is added.

- e) Cover the thimble (6.1 f)) with glass wool (6.1 g)) to prevent the sample from floating.

- f) 100 ml of n-hexane (Clause 5 c)) is used for extraction under reflux. Allow the sample to be extracted for at least 6 h with 6 cycles/h to 8 cycles/h. Cover the flask with aluminium foil during extraction. The evaporation temperature is recommended to be controlled under 68 °C.

- g) After 6 h of reflux, concentrate the extract to less than 40 ml using a vacuum rotary evaporator (6.1 u)), or a similar process.