



Designation: D3988 – 05 (Reapproved 2011)

## Standard Test Method for Vanadium in Paint Driers by EDTA Method<sup>1</sup>

This standard is issued under the fixed designation D3988; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This test method covers the titrimetric determination of vanadium in liquid vanadium driers and utilizes the disodium salt of ethylenediaminetetraacetic acid dihydrate (EDTA).

1.2 This test method is limited to the determination of the vanadium content of a liquid vanadium drier that does not contain other drier elements. This test method is not applicable to drier blends.

1.3 All cations that can be titrated with EDTA in alkaline media interfere and must not be present in the sample.

1.4 This test method has been tested for concentrations of 3 and 4 % vanadium, but there is no reason to believe that it is not suitable for higher or lower vanadium concentrations provided specimen size is adjusted proportionately.

1.5 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.6 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[D600 Specification for Liquid Paint Driers](#)

[D1193 Specification for Reagent Water](#)

[E180 Practice for Determining the Precision of ASTM Methods for Analysis and Testing of Industrial and Specialty Chemicals \(Withdrawn 2009\)](#)<sup>3</sup>

[E300 Practice for Sampling Industrial Chemicals](#)

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.21 on Chemical Analysis of Paints and Paint Materials.

Current edition approved June 1, 2011. Published June 2011. Originally approved in 1981. Last previous edition approved in 2005 as D3988 – 05. DOI: 10.1520/D3988-05R11.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

### 3. Summary of Test Method

3.1 The amount of vanadium drier used in oxidizing-type coatings significantly affects their drying properties. The vanadium drier is acidified and heated to make the vanadium available for chelation with EDTA. It is then chelated, the pH adjusted, and the excess titrated with zinc chloride solution, using Eriochrome Black T as the indicator.

### 4. Significance and Use

4.1 This test method may be used to confirm the stated content of a pure liquid vanadium drier manufactured for use by the coatings industry.

### 5. Apparatus

5.1 *Centrifuge*, capable of developing 1000 to 2000 g.

### 6. Reagents

6.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.<sup>4</sup> Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

6.2 *Purity of Water*—Unless otherwise indicated, reference to water shall be understood to mean reagent water conforming to Type II of Specification [D1193](#).

6.3 *Ammonium Hydroxide (sp gr 0.90)*—Concentrated ammonium hydroxide (NH<sub>4</sub>OH).

6.4 *Ascorbic Acid*.

6.5 *Buffer Solution*—Add 350 mL of concentrated NH<sub>4</sub>OH to 54 g of ammonium chloride and dilute to 1 L with water.

6.6 *Eriochrome Black T Indicator*—Mix and grind thoroughly in a mortar a mixture of 0.2 g of Eriochrome Black T

<sup>4</sup> *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.