



SLOVENSKI STANDARD
oSIST prEN ISO 16834:2024
01-april-2024

Dodajni in pomožni materiali za varjenje - Žične elektrode, žice, palice in čisti vari za oblačno varjenje visokotrnostnih jekel v zaščitnem plinu - Razvrstitev (ISO/DIS 16834:2024)

Welding consumables - Wire electrodes, wires, rods and deposits for gas shielded arc welding of high strength steels - Classification (ISO/DIS 16834:2024)

Schweißzusätze - Drahtelektroden, Drähte, Stäbe und Schweißgut zum Schutzgasschweißen von hochfesten Stählen - Einteilung (ISO/DIS 16834:2024)

Produits consommables pour le soudage - Fils-électrodes, fils, baguettes et dépôts pour le soudage à l'arc sous flux gazeux des aciers à haute résistance - Classification (ISO/DIS 16834:2024)

<https://standards.iteh.ai/> <https://standards.iteh.ai/standards/osist-pr-en-iso-16834-2024>
Ta slovenski standard je istoveten z: prEN ISO 16834

ICS:

25.160.20 Potrošni material pri varjenju Welding consumables

oSIST prEN ISO 16834:2024

en,fr,de



DRAFT International Standard

ISO/DIS 16834

Welding consumables — Wire electrodes, wires, rods and deposits for gas shielded arc welding of high strength steels — Classification

*Produits consommables pour le soudage — Fils-électrodes, fils,
baguettes et dépôts pour le soudage à l'arc sous flux gazeux des
aciers à haute résistance — Classification*

ICS: 25.160.20

ISO/TC 44/SC 3

Secretariat: ANSI

Voting begins on:
2024-02-28

Voting terminates on:
2024-05-22

Standards
(<https://standards.iteh.ai>)
Document Preview

[oSIST prEN ISO 16834:2024](https://standards.iteh.ai/catalog/standards/sist/0579ca2e-0de6-46e3-8adc-ea532c95ecc0/osist-pren-iso-16834-2024)

<https://standards.iteh.ai/catalog/standards/sist/0579ca2e-0de6-46e3-8adc-ea532c95ecc0/osist-pren-iso-16834-2024>

This document is circulated as received from the committee secretariat.

ISO/CEN PARALLEL PROCESSING

Reference number
ISO/DIS 16834:2024(en)

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENTS AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

© ISO 2024

ISO/DIS 16834:2024(en)

iTeh Standards (<https://standards.iteh.ai>) Document Preview

[oSIST prEN ISO 16834:2024](https://standards.iteh.ai/catalog/standards/sist/0579ca2e-0de6-46e3-8adc-ea532c95ecc0/osist-pren-iso-16834-2024)

<https://standards.iteh.ai/catalog/standards/sist/0579ca2e-0de6-46e3-8adc-ea532c95ecc0/osist-pren-iso-16834-2024>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

© ISO 2024 – All rights reserved

ISO/DIS 16834:2024(en)

Contents

	Page
Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Classification	2
4.1 General.....	2
4.2 Classification systems.....	2
5 Symbols and requirements	3
5.1 Symbols for the product/process.....	3
5.2 Symbols for strength and elongation properties of all-weld metal.....	3
5.3 Symbol for impact properties of all-weld metal.....	3
5.3.1 Classification by yield strength and 47 J impact energy - A.....	3
5.3.2 Classification by tensile strength and 27 J impact energy - B.....	3
5.4 Symbol for shielding gas.....	4
5.5 Symbol for the chemical composition of wire electrodes, wires and rods.....	4
5.6 Symbol for condition of post-weld heat treatment.....	5
5.6.1 Classification by yield strength and 47 J impact energy - A.....	5
5.6.2 Classification by tensile strength and 27 J impact energy - B.....	5
6 Mechanical tests	10
7 Preheating and interpass temperatures	10
8 Welding conditions and pass sequence	10
8.1 Post-weld heat-treated condition.....	11
8.1.1 Classification by yield strength and 47 J impact energy - A.....	11
8.1.2 Classification by tensile strength and 27 J impact energy - B.....	11
9 Chemical analysis	11
10 Rounding procedure	12
11 Retest	12
12 Technical delivery conditions	12
13 Examples of designation	12
13.1 Example 1 - Classification by yield strength and 47 J impact energy - A.....	12
13.2 Example 2 - Classification by tensile strength and 27 J impact energy - B.....	13
13.3 Example 3 - Classification by yield strength and 47 J impact energy - A.....	13
13.4 Example 4 - Classification by tensile strength and 27 J impact energy - B.....	13
13.5 Example 5 - Classification by yield strength and 47 J impact energy - A.....	14
13.6 Example 6 - Classification by tensile strength and 27 J impact energy - B.....	14
Annex A (informative) Description of composition designations for electrodes in the classification system based upon tensile strength and average impact energy of 27 J - B	16
Bibliography	17

ISO/DIS 16834:2024(en)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*.

This third edition cancels and replaces the second edition (ISO 16834:2012), which has been technically revised.

The main changes are as follows:

— to be added after DIS ballot

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html. Official interpretations of ISO/TC 44 documents, where they exist, are available from this page: <https://committee.iso.org/sites/tc44/home/interpretation.html>.

ISO/DIS 16834:2024(en)

Introduction

This document recognizes that there are two somewhat different approaches in the global market to classifying a given wire electrode, wire, rod or deposit, and allows for either or both to be used to suit a particular market need. Application of either type of classification designation (or of both where suitable) identifies a product as classified in accordance with this document.

The classification in accordance with system A was originally based on EN 12534:1999.^[1] The classification in accordance with system B is mainly based upon standards used around the Pacific Rim. Future revisions will aim to merge the two systems into a single classification system.

This document provides a classification for the designation of wire electrodes, wires, rods and deposits in terms of their chemical composition and, where required, in terms of the yield strength, tensile strength and elongation of the all-weld metal. The ratio of yield to tensile strength of weld metal is generally higher than that of the parent metal. Users should note that matching weld metal yield strength to parent metal yield strength does not necessarily ensure that the weld metal tensile strength matches that of the parent material. Thus, where the application requires matching tensile strength, selection of the consumable should be made by reference to column 3 of [Table 1A](#) or [1B](#), as appropriate.

iTeh Standards (<https://standards.iteh.ai>) Document Preview

[oSIST prEN ISO 16834:2024](https://standards.iteh.ai/catalog/standards/sist/0579ca2e-0de6-46e3-8adc-ea532c95ecc0/osist-pren-iso-16834-2024)

<https://standards.iteh.ai/catalog/standards/sist/0579ca2e-0de6-46e3-8adc-ea532c95ecc0/osist-pren-iso-16834-2024>

Welding consumables — Wire electrodes, wires, rods and deposits for gas shielded arc welding of high strength steels — Classification

1 Scope

This document specifies requirements for classification of wire electrodes, wires, rods and all-weld metal deposits in the as-welded condition and in the post-weld heat-treated (PWHT) condition for gas shielded metal arc welding and tungsten inert-gas welding of high-strength steels with a minimum yield strength greater than 500 MPa, or a minimum tensile strength greater than 570 MPa. One wire electrode can be tested and classified with different shielding gases.

This document is a combined specification providing for classification utilizing a system based upon the yield strength and the average impact energy of 47 J of all-weld metal, or utilizing a system based upon the tensile strength and the average impact energy of 27 J of all-weld metal.

- a) Clauses, subclauses and tables which carry the suffix letter “A” are applicable only to wire electrodes, wires, rods and deposits classified according to the system based upon the yield strength and the average impact energy of 47 J of all-weld metal under this document.
- b) Clauses, subclauses and tables which carry the suffix letter “B” are applicable only to wire electrodes, wires, rods and deposits classified according to the system based upon the tensile strength and the average impact energy of 27 J of all-weld metal under this document.
- c) Clauses, subclauses and tables which do not have either the suffix letter “A” or the suffix letter “B” are applicable to all wire electrodes, wires, rods and deposits classified under this document.

[Annex A](#) gives information on the description designations for electrodes in the classification system based upon tensile strength and average impact energy of 27 J – B.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 544, *Welding consumables — Technical delivery conditions for filler materials and fluxes — Type of product, dimensions, tolerances and markings*

ISO 13916, *Welding — Guidance on the measurement of preheating temperature, interpass temperature and preheat maintenance temperature*

ISO 14175:2008, *Welding consumables — Gases and gas mixtures for fusion welding and allied processes*

ISO 14344, *Welding consumables — Procurement of filler materials and fluxes*

ISO 15792-1:2020, *Welding consumables — Test methods — Part 1: Test methods for all-weld metal test specimens in steel, nickel and nickel alloys*

ISO 80000-1:2022, *Quantities and units — Part 1: General*

ISO/DIS 16834:2024(en)

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Classification

4.1 General

Classification designations are based upon two approaches to indicate the tensile properties and the impact properties of the all-weld metal obtained with a given wire electrode, wire or rod. The two designation approaches include additional designators for some other classification requirements, but not all, as is clear from the following clauses. In most cases, a given commercial product can be classified according to the classification requirements in both systems. Then either or both classification designations can be used for the product.

A wire electrode, wire or rod shall be classified in accordance with its chemical composition in [Table 4](#). A weld deposit shall be classified with additional symbols in accordance with the mechanical properties of its all-weld metal, using a shielding gas from a specific group.

Since these are not equivalent, each system shall be used independently of the other, yet both may be used. Differences in welding parameters and PWHT conditions can result in significant differences in the strength and toughness of the weld metal.

4.2 Classification systems

Each classification system, A and B, is split into parts as given in [Table 1](#).

Table 1 — Parts of the classification systems, A and B

Part of classification designation	Classification system	
	A Classification by yield strength and 47 J impact energy	B Classification by tensile strength and 27 J impact energy
1	symbol indicating the product/process to be identified	
2	symbol indicating the strength and elongation of all-weld metal (see Table 2)	symbol indicating the strength and elongation of the all-weld metal in either the as-welded or post-weld heat-treated condition (see Table 2)
3	symbol indicating the impact properties of all-weld metal (see Table 3);	symbol indicating the impact properties of all-weld metal in the same condition as specified for the tensile strength (see Table 3). The letter "U" after this designator indicates that the deposit meets an average optional requirement of 47 J at the designated Charpy test temperature.
4	symbol indicating the shielding gas used (see 5.4)	
5	symbol indicating the chemical composition of the wire electrode, wire or rod used (see Table 4);	
6	symbol indicating the post-weld heat treatment in case this is applied (see 5.6.1 or 5.6.2).	