



**SLOVENSKI STANDARD**  
**oSIST prEN ISO 7965-1:2023**  
**01-julij-2023**

---

**Embalaza - Preskus s prostim padom - 1. del: Papirnate vreče (ISO/DIS 7965-1:2023)**

Packaging - Drop test - Part 1: Paper sacks (ISO/DIS 7965-1:2023)

Packmittel - Stoßprüfung im freien Fall für Säcke - Teil 1: Papiersäcke (ISO/DIS 7965-1:2023)

Emballages - Essai de chute - Partie 1: Sacs en papier (ISO/DIS 7965-1:2023)

**Ta slovenski standard je istoveten z: prEN ISO 7965-1**

---

**ICS:**

55.080

Vreče. Vrečke

Sacks. Bags

**oSIST prEN ISO 7965-1:2023**

**en,fr,de**



# DRAFT INTERNATIONAL STANDARD

## ISO/DIS 7965-1

ISO/TC 122/SC 3

Secretariat: **BSI**

Voting begins on:  
**2023-05-09**

Voting terminates on:  
**2023-08-01**

---

---

## Packaging — Drop test —

### Part 1: Paper sacks

ICS: 55.080

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

[oSIST prEN ISO 7965-1:2023](https://standards.iteh.ai/catalog/standards/sist/73792095-b8ec-4da8-a001-4076483d61d5/osist-pren-iso-7965-1-2023)

<https://standards.iteh.ai/catalog/standards/sist/73792095-b8ec-4da8-a001-4076483d61d5/osist-pren-iso-7965-1-2023>

This document is circulated as received from the committee secretariat.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

**ISO/CEN PARALLEL PROCESSING**



Reference number  
ISO/DIS 7965-1:2023(E)

© ISO 2023

# iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 7965-1:2023](https://standards.iteh.ai/catalog/standards/sist/73792095-b8ec-4da8-a001-4076483d61d5/osist-pren-iso-7965-1-2023)

<https://standards.iteh.ai/catalog/standards/sist/73792095-b8ec-4da8-a001-4076483d61d5/osist-pren-iso-7965-1-2023>



## **COPYRIGHT PROTECTED DOCUMENT**

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

Foreword.....	iv
<b>1 Scope.....</b>	<b>1</b>
<b>2 Normative references.....</b>	<b>1</b>
<b>3 Terms and definitions.....</b>	<b>1</b>
<b>4 Principle.....</b>	<b>1</b>
<b>5 Apparatus.....</b>	<b>1</b>
5.1 General.....	1
5.2 Ensuring correct drop height.....	1
5.3 Lifting arrangement.....	2
5.4 Placing the sack.....	2
5.5 Release mechanism.....	2
5.6 Impact surface.....	2
<b>6 Sampling.....</b>	<b>2</b>
<b>7 Test conditions.....</b>	<b>2</b>
7.1 General.....	2
7.2 Conditioning for testing of paper sacks.....	3
7.3 Testing in non-laboratory situations.....	3
<b>8 Procedure.....</b>	<b>3</b>
8.1 General.....	3
8.2 Filling.....	3
8.3 Dropping.....	3
8.3.1 General.....	3
8.3.2 Dropping procedure.....	3
8.4 Sack breakage.....	4
<b>9 Test methods.....</b>	<b>4</b>
9.1 General.....	4
9.2 Progressive drop height method.....	4
9.2.1 General.....	4
9.2.2 Flat progressive height drop test.....	4
9.2.3 Butt drop test.....	5
9.3 Constant drop height method.....	5
9.3.1 General.....	5
9.3.2 Flat constant height drop test.....	5
9.3.3 Butt constant height drop test.....	6
<b>10 Test report.....</b>	<b>6</b>
<b>Annex A (informative) Example of apparatus for drop testing.....</b>	<b>7</b>
<b>Annex B (informative) Identification of surfaces of filled sacks for testing.....</b>	<b>8</b>
<b>Bibliography.....</b>	<b>9</b>

## ISO/DIS 7965-1:2023(E)

### Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 122, *Packaging*, Subcommittee SC 3, *Performance requirements and tests for means of packaging, packages and unit loads (as required by ISO/TC 122)*.

This second edition cancels and replaces the first edition (ISO 7965-1:1984), which has been technically revised.

The main changes are as follows:

- General editorial changes have been made to the document in line with ISO/IEC Directives Part 2,
- Normative reference to ISO 6599-1 has been added to [Clause 2](#), replacing the reference to ISO 2233.
- Two additional sub-clauses have been added to [Clause 5](#) to include information on ensuring correct drop height and placement of the sack, respectively,
- A new sub-clause has been added to [Clause 7](#) for information on testing in non-laboratory situations,
- The limit height method has been deleted from [Clause 9](#), keeping only the progressive- and constant drop height methods, respectively,
- The principle of testing for the constant drop method in [9.3](#) has been changed to exclude the side constant height drop test,
- Annex C has been deleted and [Clause 10](#) has been added to outline the information that the test report shall include.

A list of all parts in the ISO 7965 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Packaging — Drop test —

## Part 1: Paper sacks

### 1 Scope

This document specifies a method of vertical impact testing on a filled paper sack by dropping. It is performed either as a single test to investigate the effects of vertical impact or as part of a sequence of tests designed to measure the ability of a sack to withstand a distribution system that includes a vertical impact hazard.

This document specifies the testing procedure and how the results of tests are presented. It is based on ISO 2248 but is specifically related to paper sacks.

### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6599-1, *Packaging — Sacks — Conditioning for testing — Part 1: Paper sacks*

ISO 7023, *Packaging — Sacks — Method of sampling empty sacks for testing*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 6590-1 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

### 4 Principle

The filled sack is raised above a rigid plane surface and released to strike this surface after a free fall, with the height of drop and the position of the package being set in advance.

### 5 Apparatus

#### 5.1 General

This standard stipulates that an appropriate drop test apparatus shall be used to ensure that a drop can be performed according to the described procedure. An example of apparatus necessary for drop testing is provided in [Annex A](#).

#### 5.2 Ensuring correct drop height

Means to ensure the correct drop height in accordance with the selected testing method.

## ISO/DIS 7965-1:2023(E)

### 5.3 Lifting arrangement

Lifting arrangement which will not damage the sack during either lifting or release.

### 5.4 Placing the sack

Means of placing the sack prior to release in its predetermined position. The difference in performance of a sack suspended from the top or supported underneath in a butt drop can be significant, and so it is a requirement of this document that the method of placing the sack before dropping is included in the test report.

### 5.5 Release mechanism

To release the sack in such a way that its fall is not obstructed by any part of the apparatus before striking the impact surface (see 5.6).

### 5.6 Impact surface

Impact surface horizontal and flat, massive enough to be immovable and rigid enough to be non-deformable under test conditions.

Ensure that the surface is clean and free from any objects, particles or contamination that could affect the testing procedure.

A plastic film may be used on the impact surface under the sack in order not to damage the sack while moving it.

In normal circumstances the impact surface provided should be:

- a) one piece, with a mass at least 50 times that of the heaviest sack to be tested;
- b) flat, such that no two points on its surface differ in level by more than 2 mm;
- c) rigid, such that it will not be deformed by more than 0,1 mm when an area of 100 mm<sup>2</sup> is loaded statically with 10 kg anywhere on the surface;
- d) sufficiently large to ensure that the sack falls entirely upon the surface.

## 6 Sampling

For assessing an average quality of a consignment, sampling shall be carried out in accordance with the procedure in ISO 7023.

## 7 Test conditions

### 7.1 General

Since paper is a hygroscopic material, it will change some of its mechanical properties, like paper strength (tensile energy absorption), with the moisture content of the paper. This will vary according to the ambient atmospheric conditions and the temperature of the filling content. Hence it is very important to register and record the conditions in which the drop test is performed continuously throughout the test; the ambient temperature and relative humidity (RH) as well as the temperature of the filling content.



## 7.2 Conditioning for testing of paper sacks

Separate tests can only be directly compared if all conditions are the same in the respective test. For direct comparisons, it is essential that the sack is conditioned in a laboratory according to the requirements of ISO 6599-1.

## 7.3 Testing in non-laboratory situations

In a situation where a laboratory is not available, the methodology in this document can still be followed. In this case, the temperature and the humidity shall be recorded and reported.

# 8 Procedure

## 8.1 General

Prior to the test, it shall be ensured that:

- a) the empty sacks are properly inspected, cured and ready to be used. Further the empty sack shall be conditioned in accordance with the procedure in ISO 6599-1,
- b) the apparatus is in accordance with [Clause 4](#) of this document and in good condition,
- c) the ambient temperature and relative humidity are recorded and registered.

## 8.2 Filling

Fill the sacks with the intended commodity or, if this is not possible, with similar material, taking into account the type and size of granules, angle of repose etc., to give the same degree of filling. The mass of filling material shall be within  $\pm 0,5$  % of that of the nominal mass of the intended contents of the sack.

The temperature of the filling goods shall preferably be ambient temperature, but if that is not possible the temperature shall be registered and recorded for every sack in the test.

Position the sack on the trap door of the apparatus before the drop.

## 8.3 Dropping

### 8.3.1 General

Place the filled sack centrally on the platform which is then raised to a height that is within  $\pm 2$  % of the predetermined drop height as defined by the distance between the lowest point of the sack at the time of release and the nearest point of the impact surface.

The sack shall be released from its predetermined position within the following tolerances immediately prior to release

- a) for flat, butt or side drop tests: there shall be no variation of more than  $2^\circ$  between the impacting surface of the sack, and the horizontal surface;
- b) for edge or corner drop tests: the angle between a prescribed surface of the sack and the horizontal surface shall be  $45 \pm 5^\circ$ ;

### 8.3.2 Dropping procedure

Drops can be performed on all sides of the sack. The definition of the sack sides is described in [Annex B](#).

Each sack side needs to be tested separately.

## ISO/DIS 7965-1:2023(E)

### 8.3.2.1 Flat dropping

Drop the sack only on the face side (1) or only the back side (3), until it breaks.

### 8.3.2.2 Butt dropping

Drop the sack only on the bottom (5) or only top side (6), until it breaks.

### 8.3.2.3 Side, edge and corner dropping

For side dropping drop the sack only on the right side (2) or only the left side (4), until it breaks.

If edge and corner test will be performed, drop the sack on any corner or any edge until it breaks.

These types of tests are relatively seldom performed and will not be further described in this document.

## 8.4 Sack breakage

A sack shall be considered broken when either of the following conditions occur:

- a) content spillage occurs through a visible failure on the sack; or
- b) the contents are exposed due to breakage of the paper plies; or
- c) contents are withheld only by the plastic film or another non-paper film if such is used.

## 9 Test methods

### 9.1 General

There are two methods described in this document.

- a) **Progressive drop height**, where the height is incrementally increased to add energy and stress for every drop making this method more challenging and preferred when very high demands are put on the sacks.
- b) **Constant drop height**, where the sacks are dropped from a selected constant height. This is an easier method, with a more simple apparatus and is better at simulating a supply chain where sacks tend to be exposed to a number of similar drops and handlings.

Either of these methods can be used for any application. However, it is important to clearly state in the test report which method is used.

### 9.2 Progressive drop height method

#### 9.2.1 General

This method shall be performed from a drop height which is incrementally increased for each drop where the face and/or the back of the sack is dropped against the surface and may be used for flat or butt drop testing.

#### 9.2.2 Flat progressive height drop test

The flat drop test is where the face and/or the back of the sack is dropped against the surface.

The drop height,  $h$ , is given by the [formula \(1\)](#)

$$h = h_0 + [(n-1) \times \Delta h] \quad (1)$$