

---

---

## Metallic powders — Determination of particle size by dry sieving

*Poudres métalliques — Détermination de la granulométrie par  
tamisage à sec*

iTeh Standards  
(<https://standards.iteh.ai>)  
Document Preview

ISO 4497:2020

<https://standards.iteh.ai/catalog/standards/iso/e37e4c78-c249-491c-b39c-5c97864ad02f/iso-4497-2020>



**iTeh Standards**  
**(<https://standards.itih.ai>)**  
**Document Preview**

ISO 4497:2020

<https://standards.itih.ai/catalog/standards/iso/e37e4c78-c249-491c-b39c-5c97864ad02f/iso-4497-2020>



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2020

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
CP 401 • Ch. de Blandonnet 8  
CH-1214 Vernier, Geneva  
Phone: +41 22 749 01 11  
Fax: +41 22 749 09 47  
Email: [copyright@iso.org](mailto:copyright@iso.org)  
Website: [www.iso.org](http://www.iso.org)

Published in Switzerland

# Contents

Page

<b>Foreword</b> .....	<b>iv</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Normative references</b> .....	<b>1</b>
<b>3 Terms and definitions</b> .....	<b>1</b>
<b>4 Principle</b> .....	<b>1</b>
<b>5 Test equipment</b> .....	<b>1</b>
<b>6 Preparation of test portion</b> .....	<b>2</b>
6.1 General.....	2
6.2 Mass of test portion .....	2
<b>7 Procedure</b> .....	<b>2</b>
7.1 General.....	2
7.2 Sieving time .....	2
7.3 Measurement.....	3
<b>8 Expression of results</b> .....	<b>3</b>
<b>9 Precision</b> .....	<b>3</b>
<b>10 Test report</b> .....	<b>6</b>
<b>Bibliography</b> .....	<b>7</b>

iTeh Standards  
(<https://standards.itih.ai>)  
Document Preview

ISO 4497:2020

<https://standards.itih.ai/catalog/standards/iso/e37e4c78-c249-491c-b39c-5c97864ad02f/iso-4497-2020>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see [www.iso.org/directives](http://www.iso.org/directives)).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see [www.iso.org/patents](http://www.iso.org/patents)).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see [www.iso.org/iso/foreword.html](http://www.iso.org/iso/foreword.html).

This document was prepared by Technical Committee ISO/TC 119, *Powder metallurgy*, Subcommittee SC 2, *Sampling and testing methods for powders (including powders for hardmetals)*, in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/SS M11, *Powder metallurgy*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This second edition cancels and replaces the first edition (ISO 4497:1983), which has been technically revised. The main changes compared to the previous edition is as follows:

- inclusion of a precision statement.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at [www.iso.org/members.html](http://www.iso.org/members.html).

# Metallic powders — Determination of particle size by dry sieving

## 1 Scope

This document specifies a method of determining the particle size distribution of metallic powders by dry sieving into size fractions.

The method is applicable to dry, unlubricated metallic powders, but not applicable to powders in which the morphology differs markedly from being equiaxial, for example flake-type powders.

The method is not applicable to metallic powders having a particle size wholly or mostly under 45 µm.

## 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 565, *Test sieves — Metal wire cloth, perforated metal plate and electroformed sheet — Nominal sizes of openings*

ISO 2591-1, *Test sieving — Part 1: Methods using test sieves of woven wire cloth and perforated metal plate*

ISO 3310-1, *Test sieves — Technical requirements and testing — Part 1: Test sieves of metal wire cloth*

## 3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

## 4 Principle

The metallic powder are separated into particle size fractions by shaking through a set of wire cloth test sieves. The test sieves shall be stacked in consecutive order of size of aperture openings.

The fractions retained on each sieve and the fraction passing the finest sieve are weighed.

## 5 Test equipment

### 5.1 Calibrated cloth sieves.

A calibrated series of non-magnetic wire cloth sieves, having different nominal aperture sizes shall be used. Each sieve cloth shall be mounted in a non-magnetic metal frame having a nominal diameter of 200 mm and a nominal depth within the range 25 mm to 50 mm.

NOTE ISO 3310-1 specifies a nominal depth of 50 mm or 25 mm.

The test sieve frames and spacers, if used, shall nest seamlessly with one another, and the set shall be completed with a lid on top and a collecting pan below the bottom sieve.

The calibration of sieves shall be carried out according to ISO 3310-1.

The aperture size of the test sieves shall be chosen from the principal size (R 20/3) sieves of ISO 565. If this is not appropriate the principal sizes can be partly or totally replaced from one of the intermediate sizes (R 40/3 or R 20). The aperture sizes of the test sieves shall be chosen so as to determine adequately the particle size distribution of the sample (see [Clause 8](#)).

If mechanical sieving machine is used, see [7.1](#).

**5.2 Balance**, capable of weighing at least 100 g to an accuracy of  $\pm 0,05$  g shall be used.

**5.3 A soft brush**, shall be used.

## 6 Preparation of test portion

### 6.1 General

In general, the powder shall be tested in the as-received condition. If necessary, the powder may be dried. However, if the powder is susceptible to oxidation, the drying shall take place in vacuum or an inert gas.

### 6.2 Mass of test portion

The test portion shall have a mass of approximately 100 g for powders having an apparent density greater than  $1,50 \text{ g/cm}^3$ . If the apparent density of the powder is  $1,50 \text{ g/cm}^3$  or less, the mass of the test portion shall be approximately 50 g.

## 7 Procedure

ISO 4497:2020

<https://standards.iteh.ai/catalog/standards/iso/e37e4c78-c249-491c-b39c-5c97864ad02f/iso-4497-2020>

### 7.1 General

The series of test sieves selected shall be assembled complete with lid and collecting pan in consecutive order of size of apertures, with the sieve having the largest aperture on top. The test portion shall be placed on the top sieve and this shall be closed by a lid.

The sieving shall be performed either by hand or by means of a mechanical sieving machine.

**NOTE 1** As different types of sieving machines are known to give different results when using the same sieves and the same powder, it is generally possible to establish a correlation between different machines for a particular powder.

A partial set or sieves of different frame diameter may be selected, if agreed between the supplier and the purchaser.

For other than 200 mm size of frame diameter, mass of test portion should be adapted to the sieve area. The minimum mass of the test portion should be 10 g.

**NOTE 2** The precision statement in [Clause 9](#) is based on 200 mm sieve frame diameter and 100 g test portions. The precision statement is not valid for sieve frame diameters other than 200 mm or test portion mass other than 100 g.

### 7.2 Sieving time

The sieving process shall be continued either until the end point of the sieving is reached or for a time to be agreed between the supplier and the purchaser. The end point is reached when the quantity passing