



SLOVENSKI STANDARD
oSIST prEN ISO 1833-4:2023
01-junij-2023

Nadomešča:
SIST EN ISO 1833-4:2017

Tekstilije - Kvantitativna kemična analiza - 4. del: Mešanica nekaterih proteinskih vlaken z nekaterimi drugimi vlakni (metoda z uporabo hipoklorita) (ISO/DIS 1833-4:2023)

Textiles - Quantitative chemical analysis - Part 4: Mixtures of certain protein fibres with certain other fibres (method using hypochlorite) (ISO/DIS 1833-4:2023)

Textilien - Quantitative chemische Analysen - Teil 4: Mischungen aus bestimmten Proteinfasern mit bestimmten anderen Fasern (Hypochlorit-Verfahren) (ISO/DIS 1833-4:2023)

<https://standards.iteh.ai/catalog/standards/sist/885a6a3b-bc11-4019-9c7c-ef5ebbab35e8/osist-pr-en-iso-1833-4-2023>

Textiles - Analyse chimique quantitative - Partie 4: Mélanges de certaines fibres protéiniques avec certaines autres fibres (méthode à l'hypochlorite) (ISO/DIS 1833-4:2023)

Ta slovenski standard je istoveten z: prEN ISO 1833-4

ICS:

59.060.20	Umetna vlakna	Man-made fibres
71.040.40	Kemijska analiza	Chemical analysis

oSIST prEN ISO 1833-4:2023 **en,fr,de**

DRAFT INTERNATIONAL STANDARD

ISO/DIS 1833-4

ISO/TC 38

Secretariat: SAC

Voting begins on:
2023-04-13Voting terminates on:
2023-07-06

Textiles — Quantitative chemical analysis —

Part 4: Mixtures of certain protein fibres with certain other fibres (method using hypochlorite)

*Textiles — Analyse chimique quantitative —**Partie 4: Mélanges de certaines fibres protéiniques avec certaines autres fibres (méthode à l'hypochlorite)*

ICS: 59.060.01

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN ISO 1833-4:2023](https://standards.iteh.ai/catalog/standards/sist/885a6a3b-bc11-4019-9c7c-cf5ebbab35e8/osist-pren-iso-1833-4-2023)<https://standards.iteh.ai/catalog/standards/sist/885a6a3b-bc11-4019-9c7c-cf5ebbab35e8/osist-pren-iso-1833-4-2023>

This document is circulated as received from the committee secretariat.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 1833-4:2023(E)

© ISO 2023

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 1833-4:2023](https://standards.iteh.ai/catalog/standards/sist/885a6a3b-bc11-4019-9c7c-ef5ebbab35e8/osist-pren-iso-1833-4-2023)

<https://standards.iteh.ai/catalog/standards/sist/885a6a3b-bc11-4019-9c7c-ef5ebbab35e8/osist-pren-iso-1833-4-2023>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2023

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Principle.....	1
5 Reagents.....	1
6 Apparatus.....	2
7 Test procedure.....	2
8 Calculation and expression of results.....	3
9 Precision.....	3

iTeh STANDARD PREVIEW (standards.iteh.ai)

[oSIST prEN ISO 1833-4:2023](https://standards.iteh.ai/catalog/standards/sist/885a6a3b-bc11-4019-9c7c-ef5ebbab35e8/osist-pren-iso-1833-4-2023)

<https://standards.iteh.ai/catalog/standards/sist/885a6a3b-bc11-4019-9c7c-ef5ebbab35e8/osist-pren-iso-1833-4-2023>

ISO/DIS 1833-4:2023(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 38, *Textiles*.

This third edition cancels and replaces the second edition (ISO 1833-4:2017), which has been technically revised.

The main changes compared to the previous edition are as follows:

- in [5.1.1](#), the instruction for the preparation of the sodium hypochlorite solution has been detailed.

A list of all parts in the ISO 1833 series can be found on the ISO website.

Textiles — Quantitative chemical analysis —

Part 4:

Mixtures of certain protein fibres with certain other fibres (method using hypochlorite)

1 Scope

This document specifies a method, using hypochlorite, to determine the mass percentage of protein fibre, after removal of non-fibrous matter, in textiles made of mixtures of certain non-protein fibres and certain protein fibres, as follows:

— wool, other animal-hair (such as cashmere, mohair), silk, protein,

with

— cotton, cupro, viscose, modal, acrylic, chlorofibres, polyamide, polyester, polypropylene, glass, elastane, elastomultiester, elastolefin, melamine and polypropylene/polyamide bicomponent.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1833-1, *Textiles — Quantitative chemical analysis — Part 1: General principles of testing*

3 Terms and definitions

No terms and definitions are listed in this document.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Principle

The protein fibre is dissolved out from a known dry mass of the mixture with alkaline hypochlorite. The residue is collected, washed, dried and weighed; its mass, corrected if necessary, is expressed as a percentage of the dry mass of the mixture. The percentage of protein fibre is found by the difference.

5 Reagents

Use the reagents described in ISO 1833-1 together with those given in [5.1](#), [5.2](#) and [5.3](#).