



Designation: ~~C1400-01 (Reapproved 2007)~~ Designation: C1400 – 11

Standard Guide for Reduction of Efflorescence Potential in New Masonry Walls¹

This standard is issued under the fixed designation C1400; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This guide covers methods for reducing efflorescence potential in new masonry walls.

~~1.2 The values stated in inch-pound units are to be regarded as the standard. The SI units given in parentheses are for information only.~~

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C43 Terminology of Structural Clay Products

C67 Test Methods for Sampling and Testing Brick and Structural Clay Tile

C270 Specification for Mortar for Unit Masonry

C1180 Terminology of Mortar and Grout for Unit Masonry

C1209 Terminology of Concrete Masonry Units and Related Units

C1232 Terminology of Masonry

3. Terminology

3.1 *Definitions:*

3.1.1 Terminology defined in Terminologies C43, C1180, C1209, and C1232 shall apply in this guide.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *cryptoflorescence, n*—a crystalline deposit of water-soluble compounds in the pores of masonry

3.2.2 *efflorescence, n*—a crystalline deposit, usually white, of water-soluble compounds on the surface of masonry.

3.2.2.1 *Discussion*—The color of stains produced by acid-soluble vanadium compounds in clay masonry is usually yellow or green. The color of stains produced by acid-soluble manganese compounds is usually brown or gray.

4. Significance and Use

4.1 This guide provides information that, if implemented, will reduce efflorescence potential in new masonry walls. However, its implementation will not always completely prevent efflorescence.

4.2 This guide may be augmented by related information contained in the appendixes of Specification C270, the additional material listed at the end of this specification, and other publications.

5. Principles of Efflorescence

5.1 Efflorescence is directly related to the quantity of water-soluble compounds within, or exposed to, the wall; and to the quantity of water exposed to these compounds. Since neither water nor water-soluble compounds can be completely eliminated

¹ This guide is under the jurisdiction of ASTM Committee C15 on Manufactured Masonry Units and is the direct responsibility of Subcommittee C15.05 on Masonry Assemblies.

~~Current edition approved Dec. 1, 2007. Published January 2008. Originally approved in 1998. Last previous edition approved in 2001 as C1400-01. DOI: 10.1520/C1400-01R07.~~

Current edition approved June 1, 2011. Published June 2011. Originally approved in 1998. Last previous edition approved in 2007 as C1400-01 (2007). DOI: 10.1520/C1400-11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.