

ISO/TC 120/SC 2

Secretariat: BIS

Voting begins on:
2021-01-28

Voting terminates on:
2021-03-25

Leather — Leather for dress gloves — Specification

AMENDMENT 1: Colour fastness to to- and-fro rubbing

Cuir — Cuir pour gants de cérémonie — Spécifications

iTeh **STANDARD PREVIEW**
(standards.iteh.ai)

ISO 14930:2012/FDAmd 1

<https://standards.iteh.ai/catalog/standards/sist/ec78e4a7-e78c-4534-a93c-5c6f2973ce28/iso-14930-2012-fdamd-1>

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.



Reference number
ISO 14930:2012/FDAM 1:2021(E)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 14930:2012/FDAmd 1](https://standards.iteh.ai/catalog/standards/sist/ec78e4a7-e78c-4534-a93c-5c6f2973ce28/iso-14930-2012-fdamd-1)
<https://standards.iteh.ai/catalog/standards/sist/ec78e4a7-e78c-4534-a93c-5c6f2973ce28/iso-14930-2012-fdamd-1>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2021

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 120, *Leather*, Subcommittee SC 2, *Tanned leather*.

<https://standards.iteh.ai/catalog/standards/sist/ec78e4a7-e78c-4534-a93c-fs-d7973-m384-sl49d-2011-fd-amd-1>

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 14930:2012/FDAmd 1

<https://standards.iteh.ai/catalog/standards/sist/ec78e4a7-e78c-4534-a93c-5c6f2973ce28/iso-14930-2012-fdamd-1>

Leather — Leather for dress gloves — Specification

AMENDMENT 1: Colour fastness to to-and-fro rubbing

Clause 4

Replace the existing Table 1 with the following:

Table 1 — Requirements for leather for dress gloves

Characteristics	Requirements	Test method
pH of aqueous extract ΔpH of aqueous extract	≥ 3,5 If the pH value is below 4, ΔpH shall be ≤ 0,7.	ISO 4045
Shrinkage temperature	≥ 90 °C	ISO 3380
Colour fastness to to-and-fro rubbing	a) For aniline, nubuck or suede: — dry felt 20 cycles ≥ 3 grey scale — wet felt 10 cycles ≥ 3 grey scale — felt wetted with artificial perspiration solution ^a 10 cycles ≥ 3 grey scale b) Other finishing: — dry felt 50 cycles ≥ 3 grey scale — wet felt 20 cycles ≥ 3 grey scale — felt wetted with artificial perspiration solution ^a 20 cycles ≥ 3 grey scale	ISO 11640
Tear load	≥ 15,0 N	ISO 3377-1
Colour fastness to light	Aniline ≥ 3 blue scale Nubuck ≥ 3 blue scale Suede ≥ 3 blue scale Other finishing ≥ 4 blue scale	ISO 105-B02
Elongation at 2 N/mm ² , in per cent	≥ 20 %	ISO 3376

^a Alkaline artificial perspiration solution is defined in ISO 11641.