



SLOVENSKI STANDARD
oSIST prEN ISO 16811:2024
01-marec-2024

Neporušitvene preiskave - Ultrazvočne preiskave - Občutljivost in območje nastavitve (ISO/DIS 16811:2024)

Non-destructive testing - Ultrasonic testing - Sensitivity and range setting (ISO/DIS 16811:2024)

Zerstörungsfreie Prüfung - Ultraschallprüfung - Empfindlichkeits- und Entfernungseinstellung (ISO/DIS 16811:2024)

Essais non destructifs - Contrôle par ultrasons - Réglage de la sensibilité et de la base de temps (ISO/DIS 16811:2024)

Ta slovenski standard je istoveten z: prEN ISO 16811

oSIST prEN ISO 16811:2024

ICS:

19.100 Neporušitveno preskušanje Non-destructive testing

oSIST prEN ISO 16811:2024

en,fr,de

DRAFT INTERNATIONAL STANDARD

ISO/DIS 16811

ISO/TC 135/SC 3

Secretariat: DIN

Voting begins on:
2024-01-18Voting terminates on:
2024-04-11

Non-destructive testing — Ultrasonic testing — Sensitivity and range setting

Essais non destructifs — Contrôle par ultrasons — Réglage de la sensibilité et de la base de temps

ICS: 19.100

iTeh Standards (<https://standards.iteh.ai>) Document Preview

[oSIST prEN ISO 16811:2024](https://standards.iteh.ai/catalog/standards/sist/f56e9b73-1cbd-4e26-97ff-a4cabc44ccc7/osist-pren-iso-16811-2024)<https://standards.iteh.ai/catalog/standards/sist/f56e9b73-1cbd-4e26-97ff-a4cabc44ccc7/osist-pren-iso-16811-2024>

This document is circulated as received from the committee secretariat.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

ISO/CEN PARALLEL PROCESSING



Reference number
ISO/DIS 16811:2024(E)

© ISO 2024

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[oSIST prEN ISO 16811:2024](https://standards.iteh.ai/catalog/standards/sist/f56e9b73-1cbd-4e26-97ff-a4cabc44ccc7/osist-pren-iso-16811-2024)

<https://standards.iteh.ai/catalog/standards/sist/f56e9b73-1cbd-4e26-97ff-a4cabc44ccc7/osist-pren-iso-16811-2024>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2024

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	v
Introduction.....	vi
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Quantities and symbols.....	1
5 Qualification of personnel.....	3
6 Test equipment.....	3
6.1 Instrument.....	3
6.2 Probes.....	3
6.2.1 Probe selection.....	3
6.2.2 Frequency and dimensions of transducer.....	4
6.2.3 Dead zone.....	4
6.2.4 Damping.....	4
6.2.5 Focusing probes.....	4
6.3 Coupling media.....	4
6.4 Calibration blocks.....	5
6.5 Reference blocks.....	5
6.6 Specific test blocks.....	6
7 Categories of test objects.....	6
8 Test objects, reference blocks and reference reflectors.....	6
9 Probes.....	9
9.1 General.....	9
9.2 Longitudinally curved probes.....	10
9.2.1 Convex scanning surface.....	10
9.2.2 Concave scanning surface.....	10
9.3 Transversely curved probes.....	10
9.3.1 Convex scanning surface.....	10
9.3.2 Concave scanning surface.....	11
10 Determination of probe index and beam angle.....	11
10.1 General.....	11
10.2 Flat angle-beam probes.....	11
10.2.1 Calibration block technique.....	11
10.2.2 Reference block technique.....	12
10.3 Angle-beam probes curved longitudinally.....	12
10.3.1 Mechanical determination.....	12
10.3.2 Reference block technique.....	13
10.4 Angle-beam probes curved transversely.....	13
10.4.1 Mechanical determination.....	13
10.4.2 Reference block technique.....	14
10.5 Probes curved in two directions.....	16
10.6 Probes for use on materials other than non-alloy steel.....	16
11 Time base setting.....	16
11.1 General.....	16
11.2 Reference blocks and reference reflectors.....	17
11.3 Straight-beam probes.....	17
11.3.1 Single-reflector technique.....	17
11.3.2 Multiple-reflector technique.....	17
11.4 Angle-beam probes.....	18
11.4.1 Radius technique.....	18

ISO/DIS 16811:2023(E)

11.4.2	Straight-beam probe technique	18
11.4.3	Reference block technique.....	18
11.4.4	Contoured probes.....	18
11.5	Alternative range settings for angle-beam probes.....	18
11.5.1	Flat surfaces.....	18
11.5.2	Curved surfaces.....	19
12	Sensitivity setting and echo height evaluation	20
12.1	General.....	20
12.2	Angle of impingement.....	21
12.3	Distance-amplitude curve (DAC) technique.....	21
12.3.1	Reference blocks.....	21
12.3.2	Preparation of a distance-amplitude curve.....	22
12.3.3	Evaluation of signals using a distance-amplitude curve.....	23
12.3.4	Evaluation of signals using a reference height.....	23
12.4	Distance-gain-size (DGS) technique.....	24
12.4.1	General.....	24
12.4.2	Reference blocks.....	26
12.4.3	Use of DGS diagrams.....	27
12.4.4	Restrictions on use of the DGS technique due to geometry.....	29
12.5	Transfer correction	29
12.5.1	General.....	29
12.5.2	Fixed path length technique.....	30
12.5.3	Comparative technique.....	30
12.5.4	Compensation for local variations in transfer correction.....	31
Annex A	(normative) Determination of sound path distance and impingement angle in category 2 test objects.....	32
Annex B	(informative) General DGS diagram.....	37
Annex C	(informative) Determination of contact transfer correction factors.....	39
Bibliography	42

oSIST prEN ISO 16811:2024

<https://standards.iteh.ai/catalog/standards/sist/f56e9b73-1cbd-4e26-97ff-a4cabc44ccc7/osist-pren-iso-16811-2024>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT), see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 135, *Non-destructive testing*, Subcommittee SC 3, *Ultrasonic testing*.

This second edition cancels and replaces the first edition (ISO 16811:2012), which has been technically revised.

The main changes are as follows:

- normative references have been updated;
- [Annex A](#) and [Annex B](#) have been moved to the main text;
- the whole document has been editorially revised.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

ISO/DIS 16811:2023(E)

Introduction

The following documents are linked:

ISO 16810, *Non-destructive testing — Ultrasonic testing — General principles*

ISO 16811, *Non-destructive testing — Ultrasonic testing — Sensitivity and range setting*

ISO 16823, *Non-destructive testing — Ultrasonic testing — Transmission technique*

ISO 16826, *Non-destructive testing — Ultrasonic testing — Testing for discontinuities perpendicular to the surface*

ISO 16827, *Non-destructive testing — Ultrasonic testing — Characterization and sizing of discontinuities*

ISO 16828, *Non-destructive testing — Ultrasonic testing — Time-of-flight diffraction technique as a method for detection and sizing of discontinuities*

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[oSIST prEN ISO 16811:2024](https://standards.iteh.ai/catalog/standards/sist/f56e9b73-1cbd-4e26-97ff-a4cabc44ccc7/osist-pren-iso-16811-2024)

<https://standards.iteh.ai/catalog/standards/sist/f56e9b73-1cbd-4e26-97ff-a4cabc44ccc7/osist-pren-iso-16811-2024>

Non-destructive testing — Ultrasonic testing — Sensitivity and range setting

1 Scope

This document specifies the general rules for setting the time-base range and sensitivity (i.e. gain adjustment) of a manually operated ultrasonic instrument with A-scan display in order that reproducible measurements may be made of the location and echo height of a reflector.

It is applicable to contact techniques employing a single probe with either a single transducer or dual transducers, but excludes the immersion technique and techniques employing more than one probe.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2400, *Non-destructive testing — Ultrasonic testing — Specification for calibration block No. 1*

ISO 5577, *Non-destructive testing — Ultrasonic testing — Vocabulary*

ISO 7963, *Non-destructive testing — Ultrasonic testing — Specification for calibration block No. 2*

ISO 22232-1, *Non-destructive testing — Characterization and verification of ultrasonic test equipment — Part 1: Instruments*

ISO 22232-2, *Non-destructive testing — Characterization and verification of ultrasonic test equipment — Part 2: Probes*

ISO 22232-3, *Non-destructive testing — Characterization and verification of ultrasonic test equipment — Part 3: Combined equipment*

3 Terms and definitions

For the purpose of this document, the terms and definitions given in ISO 5577 apply.

ISO and IEC maintain terminology databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <https://www.electropedia.org/>

4 Quantities and symbols

A full list of the quantities and symbols used throughout this document is given in [Table 1](#).

Table 1 — Quantities and symbols

Symbol	Quantity	Unit
A	Normalized distance in DGS diagram	
A'	Probe coordinate	mm
a	Projected sound path length	mm
a'	Reduced projected sound path length	mm
α	Beam angle in steel	°
α_r	Beam angle in a non-alloy steel reference block or wedge	°
α_d	Incident angle (beam angle in delay block)	°
α_t	Beam angle in test object	°
β	Angle of impingement	°
c_r	Sound velocity in reference block	m/s
c_t	Velocity of transverse waves in test object	m/s
c_d	Velocity of longitudinal waves in delay block or wedge	m/s
D_{obj}	Outer diameter of test object or curvature of scanning surface	mm
d	Wall thickness	mm
D_{eff}	Effective transducer size	mm
D_{SSH}	Diameter of spherical-shaped reflector	mm
D_{DSR}	Diameter of disc-shaped reflector	mm
D_{ps}	Diameter of probe shoe	mm
D_{SDH}	Diameter of side-drilled hole	mm
e_1 to e_7	Reference block dimensions	mm
g	Depth of contour on probe face	mm
G	Normalized diameter of disc-shaped reflector in DGS-Diagram	
λ	Wavelength	mm
ΔH_u	Difference between the echo height from a reference reflector and the echo height from a discontinuity	dB
l_{ps}	Length of probe shoe in direction of curvature	mm
l_d	Length of delay path	mm
Δl_{ps}	Length of contoured probe face	mm
N_{eff}	Effective near field length	mm
P_r	Reference point at s_{max}	
P_j	Reference point at s_j	
q	Coordinate of reflector	mm
s	Sound path length (single trip)	mm
s_d	Equivalent sound path distance in the delay block	
s_j	Sound path length of reference reflector	mm
s_{max}	Maximum sound path length	mm
s_u	Sound path length associated with evaluated signal	mm
s_v	Acoustic equivalent to delay path in test object	mm
t	Depth coordinate of reflector	mm
V	Gain in DGS diagram	dB
V_j	Basic gain	dB
V_r	Recording gain	dB
V_t	Gain for determining ΔV_t	dB
V_u	Indication gain	dB

Table 1 (continued)

Symbol	Quantity	Unit
ΔV	Gain difference	dB
ΔV_{\sim}	Correction for ΔV_t	dB
ΔV_k	Gain correction for cylindrical reflector surface	dB
ΔV_s	Gain difference associated with sound path length	dB
ΔV_t	Transfer correction (average)	dB
$V_{t,r}$	Gain for back wall echo on reference block	dB
$V_{t,t}$	Gain for back wall echo on test object	dB
ΔV_u	Difference between indication gain and recording gain	dB
w_{ps}	Width of probe shoe in direction of curvature	mm
Δw_{ps}	Width of contouring of the probe face	mm
x	Distance between probe index point and front edge of probe, for an uncountoured probe	mm
Δx	Probe index shift	mm

5 Qualification of personnel

- a) The testing shall be performed by personnel qualified in accordance with ISO 9712.
- b) The requirements for qualification of test personnel shall be specified in the product standards and/or other applicable documents.

6 Test equipment

6.1 Instrument

The ultrasonic instrument shall fulfil the requirements of ISO 22232-1.

6.2 Probes

The probe(s) shall fulfil the requirements of ISO 22232-2.

6.2.1 Probe selection

The choice of the probe depends on the purpose of the testing and the requirements of the referencing standard or specification. It depends on:

- the material thickness, shape and surface condition of the test object;
- the type and metallurgical condition of the material to be tested;
- the type, position and orientation of imperfections to be detected and assessed.

The probe parameters listed in [6.2.2](#), [6.2.3](#) and [6.2.4](#) shall be considered in relation to the characteristics of the test object stated above.

ISO/DIS 16811:2023(E)

6.2.2 Frequency and dimensions of transducer

The frequency and dimensions of a transducer determine the shape of the sound beam (near field and beam divergence).

- a) The selection shall assure that the characteristics of the beam are the optimum for the testing by a compromise between the following:
- 1) the near field length which shall remain, whenever possible, smaller than the thickness of the test object.
- NOTE It is possible to detect imperfections in the near field, but their characterization is less accurate and less reproducible as in the far field.
- 2) the beam width, which shall be sufficiently small within the test volume furthest from the probe to maintain an adequate detection level;
 - 3) the beam divergence, which shall be sufficiently large to detect planar imperfections that are unfavourably orientated.
- b) Apart from the above considerations the selection of frequency shall take into account the sound attenuation in the material and the reflectivity of imperfections.

The higher the frequency, the greater the test resolution, but the sound waves are more attenuated (or the spurious signals due to the structure are greater) than with lower frequencies.

The choice of frequency thus represents a compromise between these two factors.

Most ultrasonic tests are performed at frequencies between 1 MHz and 10 MHz.

6.2.3 Dead zone

The choice of the probe shall take into account the dead zone in relation to the test volume.

6.2.4 Damping

The probe selection shall also include consideration of the damping which influences the resolution as well as the frequency spectrum.

6.2.5 Focusing probes

Focusing probes are mainly used for the detection of small imperfections and for sizing reflectors. Their sound fields should be described by focal distance, focal zone and focal diameter.

Their advantages in relation to unfocused single-transducer probes are an increased lateral resolution and a higher signal-to-noise ratio than with non-focussing probes.

- a) Their sound beams shall be described by the focal distance, the focal zones and the focal diameters.
- b) The sensitivity setting shall be carried out by using reference reflectors.

6.3 Coupling media

a) Different coupling media can be used, but their type shall be compatible with the materials to be tested. Examples are:

- water, possibly containing an agent, e.g. wetting, anti-freeze, corrosion inhibitor;
- contact paste;
- oil;

- grease;
 - cellulosic paste containing water
- b) The characteristics of the coupling medium shall remain constant throughout the verification, the setting operations and the testing.
- c) It shall be suitable for the temperature range in which it will be used.
- d) If the constancy of the characteristics cannot be guaranteed between setting and testing, a transfer correction may be applied.

One method for determining the necessary correction is described in [12.5](#).

- e) After testing is completed, the coupling medium shall be removed if its presence will adversely affect subsequent operations or use of the test object.

6.4 Calibration blocks

The calibration blocks which shall be used are specified in ISO 2400 and ISO 7963.

The stability of test equipment and setting can be verified by using the blocks given in ISO 2400 and ISO 7963.

6.5 Reference blocks

- a) When amplitudes of echoes from the test object are compared with echoes from a reference block, certain requirements relating to the material, surface condition, geometry and temperature of the block shall be observed.
- b) Where possible, the reference blocks shall be made from a material with acoustic properties which are within a specified range with respect to the material to be tested and shall have a surface condition comparable to that of the test object.
- c) If these characteristics are not the same, a transfer correction shall be applied.

A method for determining the necessary correction is described in [12.5](#).

- d) The geometrical conditions of the reference blocks and the test object shall be considered.

For further details, see [Clause 8](#).

- e) The geometry of the reference blocks, its dimensions, and the position of any reflectors, shall be indicated on a case by case basis in the specific standards and specifications.
- f) The position and number of reflectors shall relate to the scanning of the entire test volume.
- g) The most commonly used reflectors are:
- 1) large planar reflectors, compared to the beam width, perpendicular to the beam axis (e.g. back wall);
 - 2) flat-bottomed holes;
 - 3) side-drilled holes;
 - 4) grooves or notches of various cross-sections
- h) When reference blocks are used for immersion testing the influence of water in the holes shall be considered or the ends of the holes shall be plugged.
- i) The consequences of temperature differences between test object, probes, and reference blocks shall be considered and compared to the requirements for the accuracy of the test.

ISO/DIS 16811:2023(E)

- j) If necessary the reference blocks shall be maintained within the specified temperature range during the testing.

6.6 Specific test blocks











In certain cases, specific blocks, e.g. with identified natural imperfections, can be used to finalize the test technique and to check the stability of the test sensitivity.

7 Categories of test objects

The requirements for range and sensitivity setting will depend on the geometrical form of the test object.

Five categories of test objects are defined in [Table 2](#).

Table 2 — Categories of test objects

Category	Feature	Section in x -direction	Section in y -direction
1	Plane parallel surfaces (e.g. plate/sheet)		
2	Parallel, uniaxially curved surfaces (e.g. tubes)		
3	Parallel surfaces curved in more than one direction (e.g. dished ends)		
4	Solid material of circular cross section (e.g. rods and bars)		
5	Complex shapes (e.g. nozzles, sockets)		

8 Test objects, reference blocks and reference reflectors

Requirements for geometrical features of test objects, reference blocks and reference reflectors in general are contained in [Table 3](#).